



DPC: 17 / 30370705 DC

BSI Group Headquarters

389 Chiswick High Road London W4 4AL

Tel: +44 (0)20 8996 9000

Fax: +44 (0)20 8996 7400

www.bsigroup.com

Date: 29 November 2017

Origin: European

Latest date for receipt of comments: 19 January 2018

Project No. 2009/01617

Responsible committee: ACE/12 Aerospace fasteners and fastening systems

Interested committees:

Title: Draft BS EN 3685 Aerospace series - Bolts in heat resisting steel FE-PA2601 (A286) - Classification: 1 100 MPa/650 °C - Technical specification

Please notify the secretary if you are aware of any keywords that might assist in classifying or identifying the standard or if the content of this standard

- i) has any issues related to 3rd party IPR, patent or copyright
- ii) affects other national standard(s)
- iii) requires additional national guidance or information

**WARNING: THIS IS A DRAFT AND MUST NOT BE REGARDED OR USED AS A BRITISH STANDARD.
THIS DRAFT IS NOT CURRENT BEYOND 19 January 2018**

This draft is issued to allow comments from interested parties; all comments will be given consideration prior to publication. No acknowledgement will normally be sent. **See overleaf for information on the submission of comments.**

No copying is allowed, in any form, without prior written permission from BSI except as permitted under the Copyright, Designs and Patent Act 1988 or for circulation within a nominating organization for briefing purposes. Electronic circulation is limited to dissemination by e-mail within such an organization by committee members.

Further copies of this draft may be purchased from BSI Shop <http://shop.bsigroup.com> or from BSI Customer Services, Tel: +44(0) 20 8996 9001 or email cservices@bsigroup.com. British, International and foreign standards are also available from BSI Customer Services.

Information on the co-operating organizations represented on the committees referenced above may be obtained from <http://standardsdevelopment.bsigroup.com>

Introduction

This draft standard is based on European discussions in which the UK has taken an active part. Your comments on this draft are welcome and will assist in the preparation of the consequent British Standard. Comment is particularly welcome on national, legislative or similar deviations that may be necessary.

Even if this draft standard is not approved by the UK, if it receives the necessary support in Europe, the UK will be obliged to publish the official English Language text unchanged as a British Standard and to withdraw any conflicting standard.

UK Vote

Please indicate whether you consider the UK should submit a negative (with reasons) or positive vote on this draft.

Submission of Comments

- The guidance given below is intended to ensure that all comments receive efficient and appropriate attention by the responsible BSI committee. **Annotated drafts are not acceptable and will be rejected.**
- All comments must be submitted, preferably electronically, to the Responsible Committee Secretary at the address given on the front cover. Comments should be compatible with version 6.0 or version 97 of Microsoft Word for Windows, if possible; otherwise comments in ASCII text format are acceptable. **Any comments not submitted electronically should still adhere to these format requirements.**
- All comments submitted should be presented as given in the example below. Further information on submitting comments and how to obtain a blank electronic version of a comment form are available from the BSI website at:
<http://drafts.bsigroup.com/>

Template for comments and secretariat observations

Date: xx/xx/20xx	Document: ISO/DIS xxxx
------------------	-------------------------------

1	2	(3)	4	5	(6)	(7)
MB	Clause No./ Subclause No./Annex (e.g. 3.1)	Paragraph/ Figure/ Table/Note	Type of comment	Comment (justification for change) by the MB	Proposed change by the MB	Secretariat observations on each comment submitted
	3.1	Definition 1	ed	Definition is ambiguous and needs clarifying.	Amend to read '...so that the mains connector to which no connection...'	
	6.4	Paragraph 2	te	The use of the UV photometer as an alternative cannot be supported as serious problems have been encountered in its use in the UK.	Delete reference to UV photometer.	

Aerospace series — Bolts in heat resisting steel FE-PA2601 (A286) — Classification: 1 100 MPa/650 °C — Technical specification

*Luft- und Raumfahrt — Schrauben aus hochwarmfestem Stahl FE-PA2601 (A286) — Klasse: 1 100 MPa/650 °C —
Technische Lieferbedingungen*

*Série aéronautique — Vis en acier résistant à chaud FE-PA2601 (A286) — Classification : 1 100 MPa/650 °C —
Spécification technique*

ICS:

Descriptors:

Document type: **Error! Reference source not found.**
Document subtype: **Error! Reference source not found.**
Document stage: **Error! Reference source not found.**
Document language: **Error! Reference source not found.**

C:\Users\fouried\AppData\Local\Temp\Temp1_ASD-STAN-
D3_N0369_NDB_prEN_3685_P3.zip\EN_3685_2017(E).doc **Error! Reference source not found.**

Contents		Page
Foreword		3
1	Scope	4
2	Normative references	4
3	Terms and definitions	5
4	Certification and quality assurance	6
5	Technical requirements and test method	8

Foreword

This document (EN 3685:2017) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by *month year of DOP*, and conflicting national standards shall be withdrawn at the latest by *month year of DOW*.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This standard specifies the technical, qualification and quality assurance requirements for bolts in material FE-PA2601 (A286) of tensile strength class 1 100 MPa at room temperature, maximum test temperature of material 650 °C.

Primarily for aerospace applications it is applicable to such bolts when referenced on the product standard or definition document.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2859-1, *Sampling procedures for inspection by attributes — Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection*.

ISO 3452, *Non-destructive testing — Penetrant inspection — General principles*.

ISO 4288, *Geometrical Product Specifications (GPS) — Surface texture: Profile method — Rules and procedures for the assessment of surface texture*.

ISO 6508-1, *Metallic materials — Rockwell hardness test — Part 1: Test method (scales A, B, C, D, E, F, G, H, K, N, T)*.

ISO 7961, *Aerospace — Bolts — Test methods*.

EN 2002-8, *Aerospace series — Metallic materials — Test methods — Part 8: Micrographic determination of grain size*. ¹⁾

EN 3041, *Aerospace series — Propulsion standard parts — Manufacturing process change procedure for qualified parts*. ²⁾

EN 3761, *Aerospace series — Heat resisting alloy FE-PA2601 — Softened and cold worked — Bar for forged fasteners — $D \leq 50 \text{ mm}$ — $1\ 100 \text{ MPa} \leq R_m \leq 1\ 300 \text{ MPa}$* . ¹⁾

TR 3040-1, *Aerospace series — Quality Assurance — EN aerospace products — Part 1: List of approved manufacturers*. ³⁾

TR 3775, *Aerospace series — Bolts and pins — Materials*. ⁴⁾

ASTM E 112-96, *Standard Test Methods for Determining Average Grain Size*. ⁵⁾

1) Published as ASD-STAN Prestandard at the date of publication of this standard.

2) In preparation at the date of publication this standard.

3) Published as ASD-STAN Technical Report at the date of publication of this standard.

4) Published as ASD-STAN Technical Report at the date of publication of this standard.

5) Published by: American Society for Testing and Materials (ASTM), 1916 Race street, Philadelphia, PA 19103-1187, USA.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

production batch

quantity of finished parts fabricated by the same process from a single material cast (single heat of alloy), having the same basic part number and diameter, heat treated together to the same specified condition and produced as one continuous run

3.2

inspection lot

quantity of parts from a single production batch of the same part number which completely defines the parts

3.3 Surface discontinuities

3.3.1

crack

rupture in the material which may extend in any direction and which may be intercrystalline or transcrystalline in character

3.3.2

seam

longitudinal surface defect in the form of an unwelded open fold in the material

3.3.3

lap

surface defect caused by folding over metal fins or sharp corners and then rolling or forging them into the surface

3.3.4

inclusion

non-metallic particles originating from the material making process. They may exist as discrete particles or strings of particles extending longitudinally.

3.4

test temperature

ambient temperature, unless otherwise specified

3.5

simple random sampling

the taking of n items from a population of N items in such a way that all possible combinations of n items have the same probability of being chosen

3.6

critical defect

a defect that according to judgement and experience, is likely to result in hazardous or unsafe conditions for individuals using, maintaining, or depending upon the considered product, or that is likely to prevent performance of the function of a major end item

3.7

major defect

a defect other than critical, that is likely to result in a failure or to reduce materially the usability of the considered product for its intended purpose

Error! Reference source not found.

3.8

minor defect

a defect that is not likely to reduce materially the usability of the considered product for its intended purpose, or that is a departure from established specification having little bearing on the effective use or operation of this product

3.9

sampling plan

a plan according to which one or more samples are taken in order to obtain information and possibly to reach a decision

3.10

limiting quality (LQ₁₀)

in a sampling plan, a quality limit which corresponds to a specified and relatively low probability of acceptance in this case 10 % probability of acceptance. It is the limiting lot quality characteristic that a lot of this if quality would occur.

3.11

acceptance quality limit (AQL)

a quality limit which in a sampling plan corresponds to a specified but relatively high probability of acceptance

It is the maximum per cent defective (or the maximum number of defects per hundred units) that, for purposes of sampling inspection, can be considered satisfactory as a process average.

3.12

finished bolt

a bolt ready for use, inclusive of any possible treatments and/or surface coatings, as specified in the dimensional standard or definition document

4 Certification and quality assurance

4.1 Qualification

4.1.1 Purpose

The purpose of qualification tests is to ensure that the bolt design and bolt manufacturing conditions allow the bolt to comply with the requirements of this standard.

4.1.2 Conditions

The qualification tests summarized in Table 3 shall be performed on each type and diameter of bolt. Proposed changes in manufacturing source or procedure shall be subject to the requirements of EN 3041.

25 bolts selected from a single inspection lot by simple random sampling shall be subjected to the qualification tests.

The number of bolts to be subjected to each test as well as the method(s) to be used are specified in Table 1.

The tests to be applied to each bolt are shown in Table 4.

The test programme may possibly be reduced, this decision will be based on the comparison of results obtained from parts of similar design, size and manufacturing conditions.

All or part of these tests may also be performed for production acceptance, when a reinforced inspection seems to be necessary, or to survey bolts that have not proved satisfactory in use.