



DPC: 22/30439528 DC

BSI Group Headquarters

389 Chiswick High Road London W4 4AL

Tel: +44 (0)20 8996 9000

Fax: +44 (0)20 8996 7400

www.bsigroup.com

Date: 15 February 2022

Origin: International

Latest date for receipt of comments: 10 April 2022

Project No. 2021/01581

Responsible committee: PRI/22 Testing and analysis of rubber

Interested committees:

Title: Draft BS ISO 6502-3 Rubber - Measurement of vulcanization characteristics using curemeters. Part 3: Rotorless curemeter.

Please notify the secretary if you are aware of any keywords that might assist in classifying or identifying the standard or if the content of this standard

- i) has any issues related to 3rd party IPR, patent or copyright
- ii) affects other national standard(s)
- iii) requires additional national guidance or information

WARNING: THIS IS A DRAFT AND MUST NOT BE REGARDED OR USED AS A BRITISH STANDARD. THIS DRAFT IS NOT CURRENT BEYOND 10 April 2022

This draft is issued to allow comments from interested parties; all comments will be given consideration prior to publication. No acknowledgement will normally be sent. **See overleaf for information on the submission of comments.**

No copying is allowed, in any form, without prior written permission from BSI except as permitted under the Copyright, Designs and Patent Act 1988 or for circulation within a nominating organization for briefing purposes. Electronic circulation is limited to dissemination by e-mail within such an organization by committee members.

Further copies of this draft may be purchased from BSI Shop <http://shop.bsigroup.com> or from BSI Customer Services, Tel: +44(0) 20 8996 9001 or email cservices@bsigroup.com. British, International and foreign standards are also available from BSI Customer Services.

Information on the co-operating organizations represented on the committees referenced above may be obtained from <https://standardsdevelopment.bsigroup.com/>.

Responsible Committee Secretary: Ms Ellena Cullum (BSI)

Direct tel:

E-mail: ellena.cullum@bsigroup.com

Full document details: 22/30439528 DC

Introduction

This draft standard is based on national and international discussions. Your comments on this draft are invited and will assist in the preparation of the consequent standard.

For international standards, comments will be reviewed by the relevant UK national committee before sending the consensus UK vote and comments to the international committee, which will then decide appropriate action. If the international standard is approved, it is usual for the text to be published as a British Standard.

For national standards, comments will be reviewed by the relevant UK national committee and the resulting standards published as a British Standard.

UK Vote

Please indicate whether you consider the UK should submit a negative (with supporting technical reasons) or positive vote on this draft. Please indicate if you are aware of any reason why this draft standard should not be published as a British Standard.

Submission of Comments

- **Annotated drafts are not acceptable and will be rejected.**
- All comments should be submitted online at <https://standardsdevelopment.bsigroup.com/>. You will need to register in order to comment.

Template for comments and secretariat observations

Date: xx/xx/20xx	Document: ISO/DIS xxxx
------------------	------------------------

1	2	(3)	4	5	(6)	7
MB	Clause No./ Subclause No./Annex (e.g. 3.1)	Paragraph/ Figure/Table/Note	Type of comment	Comment (justification for change) by the MB	Proposed change by the MB	Secretariat observations on each comment submitted
	3.1	Definition 1	ed	Definition is ambiguous and needs clarifying.	Amend to read '...so that the mains connector to which no connection...'	
	6.4	Paragraph 2	te	The use of the UV photometer as an alternative cannot be supported as serious problems have been encountered in its use in the UK.	Delete reference to UV photometer.	

DRAFT INTERNATIONAL STANDARD

ISO/DIS 6502-3

ISO/TC 45/SC 2

Secretariat: JISC

Voting begins on:
2022-02-15

Voting terminates on:
2022-05-10

Rubber — Measurement of vulcanization characteristics using curemeters —

Part 3: Rotorless curemeter

*Caoutchouc — Mesure des caractéristiques de vulcanisation à l'aide de rhéomètres —
Partie 3: Rhéomètre sans rotor*

ICS: 83.060

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.



Reference number
ISO/DIS 6502-3:2022(E)

AVA Documents
Document Sharing Hub
© ISO 2022



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	2
5.1 General.....	2
5.2 Dies.....	6
5.2.1 Seal plate.....	7
5.2.2 Seal.....	7
5.3 Die closure.....	7
5.4 Oscillation system.....	8
5.5 Torque-measuring system.....	8
5.6 Protective films.....	8
5.7 Heating and temperature control.....	8
6 Calibration	9
7 Test piece	9
8 Vulcanization temperature	9
9 Conditioning	9
10 Procedure	9
10.1 Preparation for test.....	9
10.2 Loading the curemeter.....	10
11 Expression of results	10
11.1 General.....	10
11.2 Torque values.....	10
11.3 Scorch time.....	10
11.4 Time to a percentage of full cure.....	10
11.5 Cure rate index.....	11
12 Precision	11
13 Test report	11
Annex A (normative) Calibration schedule	12
Annex B (informative) Practical examples of calibration for the various curemeters	14
Annex C (informative) Precision	17
Bibliography	20

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This second edition cancels and replaces the first edition (ISO 6502-3:2018), which has been technically revised.

The main changes compared to the previous edition are as follows:

- The die closing force requirement has been changed ([5.3](#) and Table A.1).

A list of all parts in the ISO 6502 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Rubber — Measurement of vulcanization characteristics using curemeters —

Part 3: Rotorless curemeter

WARNING 1 — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to determine applicability of any other restrictions.

WARNING 2 — Certain procedures specified in this document might involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope

This document specifies a method for determining selected vulcanization characteristics of a rubber compound by means of a rotorless curemeter. The introduction to the use of curemeters is given in ISO 6502-1.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6502-1:2018, *Rubber — Measurement of vulcanization characteristics using curemeters — Part 1: Introduction*

ISO 18899:2013, *Rubber — Guide to the calibration of test equipment*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6502-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Principle

A test piece of rubber is placed in a heated cavity formed by two dies, one of which is oscillated at a given frequency and amplitude. This action exerts a shear strain on the test piece and a shear torque which depends on the stiffness (shear modulus) of the rubber. The torque that increases as vulcanization proceeds is measured by a torque sensor incorporated in the other die member. The torque is recorded autographically as a function of time.

The stiffness of the rubber test piece increases as vulcanization proceeds. The curve is complete when the recorded torque rises either to an equilibrium value or to a maximum value (see ISO 6502-1). If the torque continues to increase, vulcanization is considered to be complete after a given time. The time required to obtain a vulcanization curve is a function of the test temperature and the characteristics of the rubber compound.

The vulcanization characteristics are obtained from the recorded curve of torque as a function of time, in accordance with ISO 6502-1.

5 Apparatus

5.1 General

A rotorless curemeter consists of two dies that are heated and closed or almost closed, under a specified force, to form a test cavity that contains a test piece. One of the dies oscillates, and reaction torque on the stationary die, which is opposite to the moving die, can be measured at specified conditions of temperature, frequency and amplitude.

There are two types of assembly surrounding the test cavity formed by the upper and lower dies, one is unsealed or open type, and the other is sealed type. In the case of a sealed type die system, the die cavity is surrounded by seal plates and seal rings, and is completely closed. In the unsealed type the cavity is not completely closed.

Two kinds of cavity shape formed by the dies are used, namely, a biconical shape and a flat plate shape.

Three types of curemeter with different combination of sealing type and die cavity shape are available:

- a) biconical die cavity with unsealed system,
- b) biconical die cavity with sealed system, or
- c) flat plate die cavity (with sealed system).

The general arrangements for rotorless curemeters are shown in [Figure 1](#), [Figure 2](#) and [Figure 3](#), including typical machine dimensions.

Curemeters with different design might result in different torque responses and cure time (see ISO 6502-1:2018, A.2).