



DPC: 23 / 30446890 DC

BSI Group Headquarters

389 Chiswick High Road London W4 4AL

Tel: +44 (0)20 8996 9000

Fax: +44 (0)20 8996 7400

www.bsigroup.com

Date: 14 February 2023

Origin: International

Latest date for receipt of comments: 5 April 2023

Project No. 2021/03051

Responsible committee: CPL/35 Primary cells

Interested committees:

Title: BS EN 60086-4 Primary batteries

Part 4: Safety of lithium batteries

Please notify the secretary if you are aware of any keywords that might assist in classifying or identifying the standard or if the content of this standard

- i) has any issues related to 3rd party IPR, patent or copyright
- ii) affects other national standard(s)
- iii) requires additional national guidance or information

**WARNING: THIS IS A DRAFT AND MUST NOT BE REGARDED OR USED AS A BRITISH STANDARD.
THIS DRAFT IS NOT CURRENT BEYOND 5 April 2023**

This draft is issued to allow comments from interested parties; all comments will be given consideration prior to publication. No acknowledgement will normally be sent. **See overleaf for information on the submission of comments.**

No copying is allowed, in any form, without prior written permission from BSI except as permitted under the Copyright, Designs and Patent Act 1988 or for circulation within a nominating organization for briefing purposes. Electronic circulation is limited to dissemination by e-mail within such an organization by committee members.

Further copies of this draft may be purchased from BSI Shop <http://shop.bsigroup.com> or from BSI Customer Services, Tel: +44(0) 20 8996 9001 or email cservices@bsigroup.com. British, International and foreign standards are also available from BSI Customer Services.

Information on the co-operating organizations represented on the committees referenced above may be obtained from <http://standardsdevelopment.bsigroup.com>

Responsible Committee Secretary: Ms Nicola Young (BSI)

Direct tel:

E-mail: nicola.young@bsigroup.com

Introduction

This draft standard is based on national and international discussions. Your comments on this draft are invited and will assist in the preparation of the consequent standard.

For international standards, comments will be reviewed by the relevant UK national committee before sending the consensus UK vote and comments to the international committee, which will then decide appropriate action. If the international standard is approved, it is usual for the text to be published as a British Standard.

For national standards, comments will be reviewed by the relevant UK national committee and the resulting standards published as a British Standard.

UK Vote

Please indicate whether you consider the UK should submit a negative (with supporting technical reasons) or positive vote on this draft. Please indicate if you are aware of any reason why this draft standard should not be published as a British Standard.

Submission of Comments

- **Annotated drafts are not acceptable and will be rejected.**
- All comments should be submitted online at <https://standardsdevelopment.bsigroup.com/>. You will need to register in order to comment.

Template for comments and secretariat observations

Date: xx/xx/20xx	Document: ISO/DIS xxxx
------------------	------------------------

1	2	(3)	4	5	(6)	7
MB	Clause No./ Subclause No./Annex (e.g. 3.1)	Paragraph/Figure/ Table/Note	Type of comment	Commend (justification for change) by the MB	Proposed change by the MB	Secretariat observations on each comment submitted
	3.1	Definition 1	ed	Definition is ambiguous and needs clarifying.	Amend to read '...so that the mains connector to which no connection...'	
	6.4	Paragraph 2	te	The use of the UV photometer as an alternative cannot be supported as serious problems have been encountered in its use in the UK.	Delete reference to UV photometer.	



35/1516/CD

COMMITTEE DRAFT (CD)

PROJECT NUMBER:

IEC 60086-4 ED6

DATE OF CIRCULATION:

2023-02-10

CLOSING DATE FOR COMMENTS:

2023-05-05

SUPERSEDES DOCUMENTS:

35/1477/RR

IEC TC 35 : PRIMARY CELLS AND BATTERIES

SECRETARIAT:

Japan

SECRETARY:

Mr Takao Uyama

OF INTEREST TO THE FOLLOWING COMMITTEES:

SC 3C,TC 21,SC 21A,TC 61,TC 108

PROPOSED HORIZONTAL STANDARD:

☐

Other TC/SCs are requested to indicate their interest, if any, in this CD to the secretary.

FUNCTIONS CONCERNED:

☐ EMC

☐ ENVIRONMENT

☐ QUALITY ASSURANCE

☒ SAFETY

This document is still under study and subject to change. It should not be used for reference purposes.

Recipients of this document are invited to submit, with their comments, notification of

- any relevant patent rights of which they are aware and to provide supporting documentation,
- any local regulations or technical reasons that may exist and should be considered should this proposal proceed, recognizing that failure to address such requirements could result in the need for new or existing "in some countries" clauses. See AC/22/2007.

TITLE:

Primary batteries - Part 4: Safety of lithium batteries

NOTE FROM TC/SC OFFICERS:

Copyright © 2023 International Electrotechnical Commission, IEC. All rights reserved. It is permitted to download this electronic file, to make a copy and to print out the content for the sole purpose of preparing National Committee positions. You may not copy or "mirror" the file or printed version of the document, or any part of it, for any other purpose without permission in writing from IEC.

CONTENTS

1		
2	CONTENTS	2
3	FOREWORD	2
4	INTRODUCTION	4
5	1 Scope	5
6	2 Normative references	5
7	3 Terms and definitions	5
8	4 Requirements for safety	8
9	4.1 Design	8
10	4.2 Quality plan	9
11	5 Type testing and sampling	9
12	5.1 Validity of Testing	9
13	5.2 Test samples	9
14	6 Testing and requirements	10
15	6.1 General	10
16	6.1.1 Test application matrix	10
17	6.1.2 Cautionary notice	10
18	6.1.3 Ambient temperature	10
19	6.1.4 Parameter measurement tolerances	11
20	6.1.5 PredischARGE	11
21	6.1.6 Additional cells	11
22	6.2 Evaluation of test criteria	11
23	6.2.1 Short-circuit	11
24	6.2.2 Excessive temperature rise	11
25	6.2.3 Leakage	11
26	6.2.4 Venting	12
27	6.2.5 Fire	12
28	6.2.6 Rupture	12
29	6.2.7 Explosion	12
30	6.3 Tests and requirements – Overview	12
31	6.4 Tests for intended use	13
32	6.4.1 Test A: Altitude	13
33	6.4.2 Test B: Thermal cycling	13
34	6.4.3 Test C: Vibration	14
35	6.4.4 Test D: Shock	15
36	6.5 Tests for reasonably foreseeable misuse	16
37	6.5.1 General	16
38	6.5.2 Test E: External short-circuit	16
39	6.5.3 Test F: Impact	16
40	6.5.4 Test G: Crush	17
41	6.5.5 Test H: Forced discharge	18
42	6.5.6 Test I: Abnormal charging	18
43	6.5.7 Test J: Free fall	19
44	6.5.8 Test K: Thermal abuse	19
45	6.5.9 Test L: Incorrect installation	20
46	6.5.10 Test M: Overdischarge	20

47	6.6	Information to be given in the relevant specification	22
48	6.7	Evaluation and report.....	22
49	7	Information for safety	22
50	7.1	Safety precautions during design of equipment	22
51	7.1.1	General	22
52	7.1.2	Charge protection	23
53	7.1.3	Parallel connection	23
54	7.2	Precautions during handling of batteries	23
55	7.3	Packaging	26
56	7.4	Handling of battery cartons	26
57	7.5	Transport	26
58	7.5.1	General	26
59	7.5.2	Air transport.....	26
60	7.5.3	Sea transport.....	26
61	7.5.4	Land transport	26
62	7.6	Display and storage	26
63	7.7	Disposal.....	27
64	8	Instructions for use	27
65	9	Marking and packaging.....	28
66	9.1	General.....	28
67	9.2	Marking of smaller batteries	28
68	9.3	Additional requirements for swallowable batteries	28
69	9.4	Safety pictograms	29
70	Annex A (informative)	Guidelines for the achievement of safety of lithium batteries	30
71	Annex B (informative)	Guidelines for designers of equipment using lithium batteries	31
72	Annex C (informative)	Additional information on display and storage	34
73	Annex D (informative)	Safety pictograms	35
74	D.1	General.....	35
75	D.2	Pictograms.....	35
76	D.3	Instruction for use	36
77	Annex E (normative)	Child resistant packaging of coin cells	37
78	E.1	General.....	37
79	E.2	Applicability	37
80	E.3	Packaging tests	37
81	E.3.1	General	37
82	E.3.2	Test items.....	37
83	E.3.3	Test procedure	39
84	E.3.4	Criteria	40
85	Annex F (informative)	Use of the KEEP OUT OF REACH OF CHILDREN safety sign	41
86	F.1	General.....	41
87	F.2	Safety sign.....	41
88	F.3	Best practices for marking the packaging	41
89	F.4	Best practices for marking the cell	41
90	Annex G (informative)	Ingestion test	42
91	G.1	General.....	42
92	G.2	Test: Ingestion	42
93	G.3	Assessment	44

94	Annex H (normative) Measures against misuse of batteries that are not specified in	
95	Part 2 of this Standard	46
96	H.1 Background	46
97	H.2 Additional measures for the prevention of confusion of primary batteries	
98	presenting a particular risk with secondary batteries	46
99	H.2.1 Identification of primary (non-rechargeable) batteries presenting a	
100	particular risk.	46
101	H.2.2 Requirements for the marking of primary batteries presenting a	
102	particular risk.	47
103	H.2.3 Information responsibility of manufacturers and distributors	47
104	Bibliography	48
105		
106	Figure 1 – Thermal cycling procedure	14
107	Figure 2 – Example of a test set-up for the impact test.....	17
108	Figure 3 – Examples of a test set-up for the crush test.....	18
109	Figure 4 – Axes for free fall.....	19
110	Figure 5 – Circuit diagram for incorrect installation	20
111	Figure 6 – Circuit diagram for overdischarge.....	21
112	Figure 7 – Examples of wiring for charge protection	23
113	Figure 8 – Ingestion gauge	24
114	Figure 9 – Example for warning against swallowing, particularly coin cell batteries	24
115	Figure E.1 – Bending test	38
116	Figure E.2 – Torsion test.....	38
117	Figure E.3 – Tearing test	39
118	Figure E.4 – Pushing test.....	39
119	a) Round hole b) Slit c) Arc in primary protective seal	40
120	Figure E.5 – Maximum packaging opening	40
121	Figure F.1 – Recommended safety signs for use on coin cells	41
122	Figure G.1 – Filter paper test	43
123		
124	Table 1 – Number of test samples.....	9
125	Table 2 – Test application matrix	10
126	Table 3 – Mass loss limits	12
127	Table 4 – Tests and requirements	13
128	Table 5 – Vibration profile (sinusoidal)	15
129	Table 6 – Shock parameters	15
130	Table 7 – Resistive load for overdischarge.....	21
131	Table 8 – Parameters to be specified	22
132	Table 9 – Marking requirements.....	29
133	Table 10 – Additional marking and packaging requirements for swallowable batteries.....	29
134	Table A.1 – Battery design guidelines	30
135	Table B.1 – Equipment design guidelines (1 of 3)	31
136	Table D.1 – Safety pictograms (1 of 2)	35
137	Table E.1 – Test procedure.....	39
138	Table G.1 – Amount of saline solution and target consumed capacity	42

INTERNATIONAL ELECTROTECHNICAL COMMISSION

PRIMARY BATTERIES –

Part 4: Safety of lithium batteries

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60086-4 has been prepared by technical committee 35: Primary cells and batteries.

This sixth edition cancels and replaces the fifth edition published in 2019. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) Added definitions for leakage and venting, in addition to the test criteria;
- b) Revised overdischarge test;
- c) Revised marking requirements;
- d) Revised criteria for the child resistant packaging test;
- e) Addition of a new Annex with a filter paper test for coin cells;

f) Addition of a new Annex with Additional measures against misuse of batteries that are not specified in Part 2 of this Standard;

g) Integration of the contents of Interpretation Sheet 1 (IEC 60086-4:2019/ISH1:2020).

The text of this standard is based on the following documents:

FDIS	Report on voting
35/xxxx/FDIS	35/xxxx/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

NOTE The following print types are used:

– instructions/warnings for consumers: *in italic type*.

A list of all parts in the IEC 60086 series, under the general title *Primary batteries*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

215

INTRODUCTION

216 The concept of safety is closely related to safeguarding the integrity of people and property.
217 This document specifies tests and requirements for lithium batteries and has been prepared in
218 accordance with ISO/IEC guidelines, taking into account all relevant national and international
219 standards which apply.

220 Lithium batteries are different from conventional primary batteries using aqueous electrolyte
221 in that they contain flammable materials.

222 Consequently, it is important to carefully consider safety during design, production,
223 distribution, use, and disposal of lithium batteries. Based on such special characteristics,
224 lithium batteries for consumer applications were initially small in size and had low power
225 output. There were also lithium batteries with high power output which were used for special
226 industrial and military applications and were characterized as being “technician replaceable”.
227 The first edition of this document was drafted to accommodate this situation.

228 However, from around the end of the 1980s, lithium batteries with high power output started to
229 be widely used in the consumer replacement market, mainly as a power source in camera
230 applications. Since the demand for such lithium batteries with high power output significantly
231 increased, various manufacturers started to produce these types of lithium batteries. As a
232 consequence of this situation, the safety aspects for lithium batteries with high power output
233 were included in the second edition of this document.

234 Primary lithium batteries both for consumer and industrial applications are well-established
235 safe and reliable products in the market, which is at least partly due to the existence of safety
236 standards such as this document and, for transport, IEC 62281. The fourth edition of this
237 document therefore reflects only minor changes which became necessary in order to keep it
238 harmonized with IEC 62281 and to continuously improve the user information about safety
239 related matters.

240 Guidelines addressing safety issues during the design of lithium batteries are provided in
241 Annex A. Annex B provides guidelines addressing safety issues during the design of
242 equipment where lithium batteries are installed. Both Annex A and B reflect experience with
243 lithium batteries used in camera applications and are based on [23]¹.

244 Safety is freedom from unacceptable risk. There can be no absolute safety: some risk will
245 remain. Therefore a product, process or service can only be relatively safe. Safety is achieved
246 by reducing risk to a tolerable level determined by the search for an optimal balance between
247 the ideal of absolute safety and the demands to be met by a product, process or service, and
248 factors such as benefit to the user, suitability for purpose, cost effectiveness, and conventions
249 of the society concerned.

250 As safety will pose different problems, it is impossible to provide a set of precise provisions
251 and recommendations that will apply in every case. However, this document, when followed
252 on a judicious “use when applicable” basis, will provide reasonably consistent standards for
253 safety.

254

¹ Numbers in square brackets refer to the bibliography.

PRIMARY BATTERIES –

Part 4: Safety of lithium batteries

1 Scope

This part of IEC 60086 specifies tests and requirements for primary lithium batteries to ensure their safe operation under intended use and reasonably foreseeable misuse.

NOTE Primary lithium batteries that are standardized in IEC 60086-2 are expected to meet all applicable requirements herein. It is understood that consideration of this part of IEC 60086 might also be given to measuring and/or ensuring the safety of non-standardized primary lithium batteries. In either case, no claim or warranty is made that compliance or non-compliance with this standard will fulfil or not fulfil any of the user's particular purposes or needs.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60086-1, *Primary batteries – Part 1: General*

IEC 60086-2, *Primary batteries – Part 2: Physical and electrical specifications*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

NOTE Certain definitions taken from IEC 60050-482, IEC 60086-1, and ISO/IEC Guide 51 are repeated below for convenience.

3.1 battery

one or more cells electrically connected and fitted in a case, with terminals, markings and protective devices etc., as necessary for use

[SOURCE: IEC 60050-482:2004, 482-01-04, modified ("fitted with devices necessary for use, for example case" replaced by "electrically connected and fitted in a case", addition of "etc., as necessary for use")]

3.2**cell**

basic functional unit, consisting of an assembly of electrodes, electrolyte, container, terminals and usually separators, that is a source of electric energy obtained by direct conversion of chemical energy

[SOURCE: IEC 60050-482:2004, 482-01-01]

3.3**coin** <cell or battery>**lithium button** <cell or battery>

small round cell or battery where the overall height is less than the diameter, containing non-aqueous electrolyte.

Note 1 to entry: The nominal voltage of lithium batteries is typically greater than 2 V.

[SOURCE: IEC 60050-482:2004 482-02-40, modified (terms modified, NOTE "In practice terms, the term coin is used exclusively for non-aqueous lithium cells." replaced with a different note)]

3.4**component cell**

cell contained in a battery

3.5**cylindrical** <cell or battery>

round cell or battery in which the overall height is equal to or greater than the diameter

[SOURCE: IEC 60050-482:2004, 482-02-39, modified ("cell with a cylindrical shape" replaced by "round cell or battery")]

3.6**depth of discharge****DOD**

percentage of rated capacity discharged from a battery

3.7**fully discharged**

state of a cell or battery at 100 % depth of discharge

3.8**harm**

injury or damage to the health of people, or damage to property or the environment

[SOURCE: ISO/IEC Guide 51:2014, 3.1]

3.9**hazard**

potential source of harm

[SOURCE: ISO/IEC Guide 51:2014, 3.2]

3.10**intended use**

use in accordance with information provided with a product or system, or, in the absence of such information, by generally understood patterns of usage

[SOURCE: ISO/IEC Guide 51:2014, 3.6]

3.11**large battery**

battery with a gross mass of more than 12 kg

3.12**large cell**

cell with a gross mass of more than 500 g

3.12.1**leakage**

unplanned escape of electrolyte, gas or other material from a cell or battery

Note 1 to entry: Leakage in this sense should not be confused with the test evaluation criteria for leakage specified in Clause 6 of this document.

3.13**lithium cell**

cell containing a non-aqueous electrolyte and a negative electrode of lithium or containing lithium

[SOURCE: IEC 60050-482:2004 482-01-06, modified (removal of NOTE)]

3.14**nominal voltage**

suitable approximate value of the voltage used to designate or identify a cell, a battery or an electrochemical system

[SOURCE: IEC 60050-482:2004, 482-03-31]

3.15**open circuit voltage**

OCV, U_{OC} , off-load voltage

voltage across the terminals of a cell or battery when no external current is flowing

[SOURCE: IEC 60050-482:2004, 482-03-32, modified (alternative terms “OCV, U_{OC} , off-load voltage” added, “across the terminals” added, “when the discharge current is zero” replaced with “when no external current is flowing”)]

3.16**prismatic** <cell or battery>

qualifies a cell or a battery having the shape of a parallelepiped whose faces are rectangular

[SOURCE: IEC 60050-482:2004, 482-02-38]

3.17**protective devices**

devices such as fuses, diodes or other electric or electronic current limiters designed to interrupt the current flow, block the current flow in one direction or limit the current flow in an electrical circuit

3.18**rated capacity**

capacity value of a cell or battery determined under specified conditions and declared by the manufacturer

[SOURCE: IEC 60050-482:2004, 482-03-15, modified (“cell or” added)]

3.19**reasonably foreseeable misuse**

use of a product, process or system in a way not intended by the supplier, but which may result from readily predictable human behaviour

[SOURCE: ISO/IEC Guide 51:2014, 3.7, modified (removal of NOTES)]

3.20**risk**

combination of the probability of occurrence of harm and the severity of that harm

[SOURCE: ISO/IEC Guide 51:2014, 3.9, modified (removal of NOTE)]

3.21**safety**

freedom from risk which is not tolerable

[SOURCE: ISO/IEC Guide 51:2014, 3.14]

3.22**undischarged**

state of a primary cell or battery at 0 % depth of discharge

3.23**venting**

release of excessive internal pressure from a cell or battery in a manner intended by design

Note 1 to entry: Venting in this sense should not be confused with the test evaluation criteria for leakage specified in Clause 6 of this document.

4 Requirements for safety**4.1 Design**

Lithium batteries are categorized by their chemical composition (anode, cathode, electrolyte), internal construction (bobbin, spiral) and are available in cylindrical, coin and prismatic configurations. It is necessary to consider all relevant safety aspects at the battery design stage, recognizing the fact that they can differ considerably, depending on the specific lithium system, power capability and battery configuration.

The following design concepts for safety are common to all lithium batteries:

- a) Abnormal temperature rise above the critical value defined by the manufacturer shall be prevented by design.
- b) Temperature increases in the battery shall be controlled by a design which limits current flow.
- c) Lithium cells and batteries shall be designed to relieve excessive internal pressure or to preclude a violent rupture under conditions of transport, intended use and reasonably foreseeable misuse.

If, in particular cases, this design concept cannot be implemented, alternatively, the organisational requirements described in Annex H shall apply.

See Annex A for guidelines for the achievement of safety of lithium batteries.

4.2 Quality plan

The manufacturer shall prepare and implement a quality plan defining the procedures for the inspection of materials, components, cells and batteries during the course of manufacture, to be applied to the total process of producing a specific type of battery. Manufacturers should understand their process capabilities and should institute the necessary process controls as they relate to product safety.

5 Type testing and sampling

5.1 Validity of Testing

Lithium cells or batteries shall be subjected to the tests, as required in this standard. Testing remains valid until a design change or requirement revision has been made. Retesting is required when:

- a) a battery specification changes by more than 0,1 g or 20 % mass, whichever is greater, for the cathode, anode or electrolyte;
- b) a battery specification change would lead to a failure of any of the tests;
- c) there is an addition of new tests or requirements; or
- d) there is a requirement change that would lead to a failure of any of the tests.

5.2 Test samples

Samples should be drawn from production lots in accordance with accepted statistical methods. The number of test samples is given in Table 1. The same test cells and batteries are used for tests A to E in sequence. New test cells and batteries are required for each of tests F to M.

Table 1 – Number of test samples

Tests	Discharge state		Cells and single cell batteries ^a	Multi-cell batteries
Tests A to E	Undischarged		10	4
	Fully discharged		10	4
Test F or G	Undischarged		5	5 component cells
	Fully discharged		5	5 component cells
Test H	Fully discharged		10	10 component cells
Tests I to K	Undischarged		5	5
Test L	Undischarged		20 ^b	n/a
Test M	50 % predischarged	CR	10 ^c	n/a
	Fully discharged	CR	10 ^d	n/a
	50 % predischarged	FR	20 ^e	n/a
	Fully discharged	FR	20 ^f	n/a
^a Single cell batteries containing one tested component cell do not require re-testing unless the change could result in a failure of any of the tests.				
^b Four batteries connected in series with one of the four batteries reversed (5 sets).				
^c Two CR-type batteries connected in series, one of which is 50 % predischarged (5 sets). Undischarged cells shall be sampled from the same production lot.				
^d Two CR-type batteries connected in series, one of which is fully discharged (5 sets). Undischarged cells shall be sampled from the same production lot.				

^e	Four FR-type batteries connected in series, one of which is 50 % predischarged (5 sets). Undischarged cells shall be sampled from the same production lot.
^f	Four FR-type batteries connected in series, one of which is fully discharged (5 sets). Undischarged cells shall be sampled from the same production lot.
Key: n/a: not applicable	

6 Testing and requirements

6.1 General

6.1.1 Test application matrix

Applicability of test methods to test cells and batteries is shown in Table 2.

Table 2 – Test application matrix

Form	Applicable tests												
	A	B	C	D	E	F	G	H	I	J	K	L	M
s	x	x	x	x	x	x ^a	x ^a	x	x	x	x	x ^b	x ^c
m	x	x	x	x	x	x ^{a, d}	x ^{a, d}	x ^d	x	x	x	n/a	n/a
Test description:								Key:					
Intended use tests A: Altitude B: Thermal cycling C: Vibration D: Shock			Reasonably foreseeable misuse tests E: External short-circuit F: Impact G: Crush H: Forced discharge I: Abnormal charging J: Free fall K: Thermal abuse L: Incorrect installation M: Overdischarge					Form s: cell or single cell battery m: multi cell battery					
								Applicability x: applicable n/a: not applicable					
^a Only one test shall be applied, test F or test G.													
^b Only applicable to CR17345, CR15H270, FR14505, FR10G445 and similar type batteries of a spiral construction that could be installed incorrectly and charged.													
^c Only applicable to CR17345, CR15H270, FR14505, FR10G445 and similar type batteries of a spiral construction that could be overdischarged.													
^d Test applies to the component cells.													

6.1.2 Cautionary notice

WARNING: These tests call for the use of procedures which can result in injury if adequate precautions are not taken.

It has been assumed in the drafting of these tests that their execution is undertaken by appropriately qualified and experienced technicians using adequate protection.

6.1.3 Ambient temperature

Unless otherwise specified, the tests shall be carried out at an ambient temperature of 20 °C ± 5 °C.

6.1.4 Parameter measurement tolerances

The overall accuracy of controlled or measured values, relative to the specified or actual parameters, shall be within the following tolerances:

- a) $\pm 1 \%$ for voltage;
- b) $\pm 1 \%$ for current;
- c) $\pm 2 \text{ }^{\circ}\text{C}$ for temperature;
- d) $\pm 0,1 \%$ for time;
- e) $\pm 1 \%$ for dimensions;
- f) $\pm 1 \%$ for capacity.

These tolerances comprise the combined accuracy of the measuring instruments, the measurement techniques used, and all other sources of error in the test procedure.

6.1.5 PredischARGE

Where a test requires predischARGE, the test cells or batteries shall be discharged to the respective depth of discharge on a resistive load with which the rated capacity is obtained or at a current specified by the manufacturer.

6.1.6 Additional cells

Where additional cells are required to perform a test, they shall be of the same type and, preferably, from the same production lot as the test cell.

6.2 Evaluation of test criteria**6.2.1 Short-circuit**

A short-circuit is considered to have occurred during a test if the open-circuit voltage of the cell or battery immediately after the test is less than 90 % of its voltage prior to the test. This requirement is not applicable to test cells and batteries in fully discharged states.

6.2.2 Excessive temperature rise

An excessive temperature rise is considered to have occurred during a test if the external case temperature of the test cell or battery rises above 170 $^{\circ}\text{C}$.

6.2.3 Leakage

Leakage is considered to have occurred during a test if there is visible escape of electrolyte or other material from the test cell or battery, or the loss of material (except battery casing, handling devices or labels) from the test cell or battery such that the mass loss exceeds the limits in Table 3.

In order to quantify mass loss $\Delta m / m$, the following equation is provided:

$$\Delta m / m = \frac{m_1 - m_2}{m_1} \times 100 \%$$

where

m_1 is the mass before a test;

m_2 is the mass after that test.