



DPC: 24/30461104 DC

BSI Group Headquarters

389 Chiswick High Road London W4 4AL

Tel: +44 (0)20 8996 9000

Fax: +44 (0)20 8996 7400

www.bsigroup.com

Date: 14 March 2024

Origin: European

Latest date for receipt of comments: 07 May 2024

Project No. 2022/01824

Responsible committee: STI/10 Test methods for paints

Interested committees:

Title: Draft BS EN ISO 7012-3 Paints and varnishes - Determination of preservatives in water-dilutable coating materials. Part 3: Determination of in-can isothiazolinones with LC-UV and LC-MS.

Please notify the secretary if you are aware of any keywords that might assist in classifying or identifying the standard or if the content of this standard

- i) has any issues related to 3rd party IPR, patent or copyright
- ii) affects other national standard(s)
- iii) requires additional national guidance or information

WARNING: THIS IS A DRAFT AND MUST NOT BE REGARDED OR USED AS A BRITISH STANDARD. THIS DRAFT IS NOT CURRENT BEYOND 07 May 2024

This draft is issued to allow comments from interested parties; all comments will be given consideration prior to publication. No acknowledgement will normally be sent. **See overleaf for information on the submission of comments.**

No copying is allowed, in any form, without prior written permission from BSI except as permitted under the Copyright, Designs and Patent Act 1988 or for circulation within a nominating organization for briefing purposes. Electronic circulation is limited to dissemination by e-mail within such an organization by committee members.

Further copies of this draft may be purchased from BSI Shop <http://shop.bsigroup.com> or from BSI Customer Services, Tel: +44(0) 20 8996 9001 or email cservices@bsigroup.com. British, International and foreign standards are also available from BSI Customer Services.

Information on the co-operating organizations represented on the committees referenced above may be obtained from <https://standardsdevelopment.bsigroup.com/>.

Responsible Committee Secretary: Ms Katherine Imbert (BSI)
Direct tel: 0208 996 6450
E-mail: katherine.imbert@bsigroup.com

Full document details: 24/30461104 DC

Introduction

This draft standard is based on national and international discussions. Your comments on this draft are invited and will assist in the preparation of the consequent standard.

For international standards, comments will be reviewed by the relevant UK national committee before sending the consensus UK vote and comments to the international committee, which will then decide appropriate action. If the international standard is approved, it is usual for the text to be published as a British Standard.

For national standards, comments will be reviewed by the relevant UK national committee and the resulting standards published as a British Standard.

UK Vote

Please indicate whether you consider the UK should submit a negative (with supporting technical reasons) or positive vote on this draft. Please indicate if you are aware of any reason why this draft standard should not be published as a British Standard.

Submission of Comments

- **Annotated drafts are not acceptable and will be rejected.**
- All comments should be submitted online at <https://standardsdevelopment.bsigroup.com/>. You will need to register in order to comment.

Template for comments and secretariat observations

Date: xx/xx/20xx	Document: ISO/DIS xxxx
------------------	------------------------

1	2	(3)	4	5	(6)	7
MB	Clause No./ Subclause No./Annex (e.g. 3.1)	Paragraph/ Figure/Table/Note	Type of comment	Comment (justification for change) by the MB	Proposed change by the MB	Secretariat observations on each comment submitted
	3.1	Definition 1	ed	Definition is ambiguous and needs clarifying.	Amend to read '...so that the mains connector to which no connection...'	
	6.4	Paragraph 2	te	The use of the UV photometer as an alternative cannot be supported as serious problems have been encountered in its use in the UK.	Delete reference to UV photometer.	



DRAFT International Standard

ISO/DIS 7012-3

Paints and varnishes — Determination of preservatives in water-dilutable coating materials —

Part 3: Determination of in-can isothiazolinones with LC-UV and LC- MS

ICS: 87.040

ISO/TC 35/SC 16

Secretariat: **DIN**

Voting begins on:
2024-03-14

Voting terminates on:
2024-06-06

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING

Reference number
ISO/DIS 7012-3:2024(en)

Full document details: 24/30461104 DC

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENTS AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

© ISO 2024

 **Documents**
Document Sharing Hub



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

© ISO 2024 – All rights reserved

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	2
5.1 Equipment for extraction and sample preparation	2
5.2 LC-UV/VIS system	3
5.3 LC-MS/MS or LC-MS system	3
6 Reagents and materials	3
7 Sampling	5
8 Procedure	5
8.1 LC-UV/VIS method	5
8.1.1 Extraction of LC-UV/VIS	5
8.1.2 Operation conditions of LC-UV/VIS	6
8.1.3 Blank	6
8.1.4 Interferences of LC-UV/VIS	6
8.1.5 Calibration of LC-UV/VIS	6
8.1.6 Determination by LC-UV/VIS	7
8.2 LC-MS method	7
8.2.1 Extraction of LC-MS	7
8.2.2 Further dilution	7
8.2.3 Filtration	7
8.2.4 Operation conditions of LC-MS	7
8.2.5 Blank	8
8.2.6 Interferences of LC-MS	8
8.2.7 Calibration of LC-MS	8
8.2.8 Determination by LC-MS	9
9 Calculation	9
10 Precision	9
10.1 General	9
10.2 Repeatability limit r	10
10.3 Reproducibility limit R	10
11 Test report	10
Annex A (informative) Example of LC conditions	12
Annex B (informative) Example of multiple reaction monitoring LC-MS/MS conditions	15
Annex C (informative) Calculation of preservative content with standard addition for LC-MS method	18
Annex D (informative) Mechanical method for homogenization and extraction	20
Annex E (informative) Results of the interlaboratory test	21
Bibliography	22

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 16, *Chemical analysis*.

Paints and varnishes — Determination of preservatives in water-dilutable coating materials —

Part 3:

Determination of in-can isothiazolinones with LC-UV and LC-MS

1 Scope

This document specifies the apparatus and the analytical method for determining the content of in-can isothiazolinone preservatives in water-dilutable coating materials or related products.

NOTE 1 The document is also applicable for polymer dispersions.

NOTE 2 The document is in general applicable for OIT and DCOIT. However, the standard was not validated for these compounds in the round robin test. There are national standards covering these compounds.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1513, *Paints and varnishes — Examination and preparation of test samples*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 4618, *Paints and varnishes — Vocabulary*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

ISO 7012-1, *Paints and varnishes — Determination of preservatives in water-dilutable coating materials — Part 1: Determination of in-can free formaldehyde*

ISO 7012-2, *Paints and varnishes — Determination of preservatives in water-dilutable coating materials — Part 2: Determination of in-can total formaldehyde*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1**ready for use**

state of a product when it is mixed in accordance with the manufacturer's instructions in the correct proportions and thinned if required using the correct thinners so that it is ready for application by the approved method

[SOURCE: ISO 11890-2:2020, term 3.7]

3.2**water-thinnable coating material****water-dilutable coating material****water-reducible coating material****water-based coating material****water-borne coating material**

DEPRECATED: water paint

coating material whose viscosity is reduced by the addition of water

[SOURCE: ISO 4618:2023, term 3.272]

3.3**detection limit of instrument**

three times the standard deviation of the result obtained in the blank test using a specific instrument

[SOURCE: ISO 8124-5: 2015, term 3.5]

3.4**in-can preservative**

biocide used to prevent growth of microorganisms during storage of a stock solution of a coating material or water-based coating material

[SOURCE: ISO 4618:2023, term 3.141]

4 Principle

The sample is extracted with suitable dilution solvent using an appropriate homogenization such as ultrasonic water bath. The extract is purified by centrifugation, after which the isothiazolinones are identified and quantified by liquid chromatography (LC) in combination with UV/VIS detection or different mass spectrometry detectors. This includes liquid chromatography-tandem mass spectrometry (LC-MS/MS) and liquid chromatography-single quad mass spectrometry (LC-MS).

For the purposes of this document, LC also designates high-performance liquid chromatography (HPLC) or ultra-performance liquid chromatography (e.g., UPLC or UHPLC).

Atmospheric pressure chemical ionisation (APCI) and electrospray ionisation (ESI) have been found suitable. Other ionization techniques and mass analysers with sufficient performance can also be used.

NOTE The difference of the results is expected to be smaller than the reproducibility limits of the methods for a standard water-borne coating sample. In the round robin test according to [Annex E](#), the determination by the LC-UV method and the LC-MS or LC-MS/MS method turned out to deliver comparable results within the reproducibility limits of the methods, validating the above statement.

5 Apparatus**5.1 Equipment for extraction and sample preparation**

5.1.1 High speed centrifuge, with an acceleration at a suitable speed (typically 50 000 ×g).

5.1.2 Ultrasonic water bath, with a frequency from 35 kHz to 45 kHz.

5.1.3 Analytical balance, capable of weighing to an accuracy of 0.1mg.

5.1.4 One-mark volumetric flask, of 10 ml, 25 ml, 50 ml and 100 ml nominal capacity.

5.1.5 Pipettes, suitable single-volume pipettes, graduated pipettes and Pasteur pipettes.

5.1.6 Centrifuge tubes, with a suitable snap /screw cap.

5.1.7 Glass autosampler vials, with a suitable snap /screw pre-slit cap, 2 ml.

5.1.8 Syringe, minimum volume 2 ml.

5.1.9 Filtration membrane, about 0.22 µm pore size.

5.2 LC-UV/VIS system

5.2.1 LC system, equipped with a sample injection system, a solvent pumping system capable of mixing solvents, a sample compartment capable of maintaining required temperature and a temperature-controlled column compartment, a degassing system and data processing software. An LC system that is capable of performing at the flows, pressures, controlled temperatures, sample volumes and other requirements of the document shall be used.

5.2.2 Analytical column, reverse phase C18 particle columns were used to develop this test method. Any column that achieves adequate resolution may be used. The retention times and order of elution may change depending on the column used and need to be monitored.

5.2.3 UV/VIS detector, a UV/VIS detector or optionally a diode array detector (DAD).

5.3 LC-MS/MS or LC-MS system

5.3.1 LC system, equipped with a sample injection system, a solvent pumping system capable of mixing solvents, a sample compartment capable of maintaining required temperature and a temperature-controlled column compartment, a degassing system and data processing software. An LC system that is capable of performing at the flows, pressures, controlled temperatures, sample volumes, and other requirements of the document shall be used.

5.3.2 Analytical column, reverse phase C18 particle columns were used to develop this test method. Any column that achieves adequate resolution may be used. The retention times and order of elution may change depending on the column used and need to be monitored.

5.3.3 MS/MS or MS-system, equipped with APCI or ESI. Other ionization techniques and mass analysers with sufficient performance can also be used.

6 Reagents and materials

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of grade 1 in accordance with ISO 3696. Solvents shall be of a suitable quality for LC-UV/VIS and LC-MS, i.e. LC-MS grade for LC-MS analysis.

6.1 Reference substances: MIT(CAS no.: 2682-20-4), CMIT(CAS no.: 26172-55-4), BIT(CAS no.: 2634-33-5).

6.2 Methanol (CAS no. : 67-56-1).