



DPC: 25/30502044 DC

BSI Group Headquarters

389 Chiswick High Road London W4 4AL

Tel: +44 (0)20 8996 9000

Fax: +44 (0)20 8996 7400

www.bsigroup.com

Date: 03 April 2025

Origin: European

Latest date for receipt of comments: 27 May 2025

Project No. 2024/02953

Responsible committee: FSH/18 Fixed fire fighting systems

Interested committees:

Title: Draft BS EN 1568-3 BS Fire extinguishing media - Foam concentrates. Part 3: Specification for low expansion foam concentrates for surface application to water-immiscible liquids.

Please notify the secretary if you are aware of any keywords that might assist in classifying or identifying the standard or if the content of this standard

- i) has any issues related to 3rd party IPR, patent or copyright
- ii) affects other national standard(s)
- iii) requires additional national guidance or information

WARNING: THIS IS A DRAFT AND MUST NOT BE REGARDED OR USED AS A BRITISH STANDARD. THIS DRAFT IS NOT CURRENT BEYOND 27 May 2025

This draft is issued to allow comments from interested parties; all comments will be given consideration prior to publication. No acknowledgement will normally be sent. **See overleaf for information on the submission of comments.**

No copying is allowed, in any form, without prior written permission from BSI except as permitted under the Copyright, Designs and Patent Act 1988 or for circulation within a nominating organization for briefing purposes. Electronic circulation is limited to dissemination by e-mail within such an organization by committee members.

Further copies of this draft may be purchased from BSI Shop <http://shop.bsigroup.com> or from BSI Customer Services, Tel: +44(0) 20 8996 9001 or email cservices@bsigroup.com. British, International and foreign standards are also available from BSI Customer Services.

Information on the co-operating organizations represented on the committees referenced above may be obtained from <https://standardsdevelopment.bsigroup.com/>.

Responsible Committee Secretary: Mrs Susan Revell (BSI)
Direct tel: 020 8996 7195
E-mail: susan.revell@bsigroup.com

Full document details: 25/30502044 DC

Introduction

This draft standard is based on national and international discussions. Your comments on this draft are invited and will assist in the preparation of the consequent standard.

For international standards, comments will be reviewed by the relevant UK national committee before sending the consensus UK vote and comments to the international committee, which will then decide appropriate action. If the international standard is approved, it is usual for the text to be published as a British Standard.

For national standards, comments will be reviewed by the relevant UK national committee and the resulting standards published as a British Standard.

UK Vote

Please indicate whether you consider the UK should submit a negative (with supporting technical reasons) or positive vote on this draft. Please indicate if you are aware of any reason why this draft standard should not be published as a British Standard.

Submission of Comments

- **Annotated drafts are not acceptable and will be rejected.**
- All comments should be submitted online at <https://standardsdevelopment.bsigroup.com/>. You will need to register in order to comment.

Template for comments and secretariat observations

Date: xx/xx/20xx	Document: ISO/DIS xxxx
------------------	------------------------

1	2	(3)	4	5	(6)	7
MB	Clause No./ Subclause No./Annex (e.g. 3.1)	Paragraph/ Figure/Table/Note	Type of comment	Comment (justification for change) by the MB	Proposed change by the MB	Secretariat observations on each comment submitted
	3.1	Definition 1	ed	Definition is ambiguous and needs clarifying.	Amend to read '...so that the mains connector to which no connection...'	
	6.4	Paragraph 2	te	The use of the UV photometer as an alternative cannot be supported as serious problems have been encountered in its use in the UK.	Delete reference to UV photometer.	

English Version

Fire extinguishing media - Foam concentrates - Part 3: Specification for low expansion foam concentrates for surface application to water-immiscible liquids

Agents extincteurs - Émulseurs - Partie 3 :
Spécifications pour les émulseurs bas foisonnement
destinés à une application à la surface de liquides
n'ayant pas d'affinité pour l'eau

Feuerlöschmittel - Schaummittel - Teil 3:
Anforderungen an Schaummittel zur Erzeugung von
Schwerschaum zum Aufgeben auf mit Wasser nicht
mischbare Flüssigkeiten

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 191.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword.....	7
Introduction	8
1 Scope	9
2 Normative references	9
3 Terms and definitions	10
4 Sediment in the foam concentrate	12
4.1 Sediment before ageing	12
4.2 Sediment after ageing	12
5 Freezing point.....	12
6 Viscosity of the foam concentrate	12
6.1 Test temperatures	12
6.2 Newtonian foam concentrates.....	12
6.3 Pseudo-plastic foam concentrates	12
7 pH of the foam concentrate	12
8 Surface tension of the foam solution.....	13
9 Stability/separation test of foam concentrate.....	13
10 Determination of expansion and drainage time	13
10.1 Before temperature conditioning	13
10.2 After temperature conditioning	13
11 Test fire performance.....	14
12 Occupational health and ecotoxicological information	15
13 Annual foam quality check	15
13.1 General.....	15
13.2 Principles	15
13.3 Types of analysis	16
14 Expansion performance comparison test	17
15 Technical information sheet	17
16 Container marking.....	17
Annex A (informative) Grades of foam concentrate and performance.....	19
A.1 Grades.....	19
A.2 Typical performance.....	19
Annex B (normative) Sampling of foam concentrates	21
Annex C (normative) Determination of percentage sediment.....	22
C.1 Sampling.....	22
C.2 Apparatus.....	22
C.3 Procedure.....	22

Annex D (normative) Freezing point determination	23
D.1 General	23
D.2 Apparatus	23
D.3 Procedure	23
D.4 Example of a temperature against time curve for evaluation	24
Annex E (normative) Determination of Viscosity for pseudo-plastic foam concentrates	25
E.1 Pseudo-plastic foam concentrates.....	25
E.2 Viscosity determination	25
E.2.1 Apparatus	25
E.2.2 Viscosity measurement	25
E.2.3 Results	26
Annex F (normative) Temperature conditioning of foam concentrates.....	27
F.1 General	27
F.2 Low temperature conditioning.....	27
F.2.1 Apparatus	27
F.2.2 Procedure	27
F.3 High temperature conditioning.....	27
F.3.1 Apparatus	27
F.3.2 Procedure	27
F.4 Division into top and bottom half-samples	28
F.4.1 Apparatus	28
F.4.1.1 Top half-sample container(s).....	28
F.4.1.2 Divider device	28
F.4.2 Procedure	29
Annex G (normative) Determination of surface tension	30
G.1 Solution of foam concentrate	30
G.2 Procedure — Surface tension.....	30
Annex H (normative) Stability/Separation test of foam concentrate	31
H.1 General	31
H.2 Apparatus	31
H.3 Procedure	31
Annex I (normative) Determination of expansion and drainage time	32
I.1 Apparatus	32
I.2 Temperature conditions	32
I.3 Procedure	32
I.4 Simulated fresh and sea water.....	33

Annex J (normative) Determination of test fire performance	38
J.1 General.....	38
J.2 General conditions.....	38
J.2.1 Test series and criteria for success	38
J.2.1.1 Foam concentrates not compatible with sea water	38
J.2.1.2 Foam concentrates compatible with sea water.....	38
J.2.2 Temperatures and wind speed	38
J.2.3 Records	39
J.2.4 Foam solution.....	39
J.2.5 Fuel.....	40
J.3 Gentle application fire test	40
J.3.1 Apparatus.....	40
J.3.2 Test procedure.....	41
J.4 Forceful application fire test.....	42
J.4.1 Apparatus.....	42
J.4.2 Procedure.....	42
Annex K (normative) Occupational health and ecotoxicological testing.....	44
Annex L (informative) Description of a radiation measurement method.....	45
L.1 Evaluation	45
L.2 General arrangement of test	45
L.3 Technical data for radiometers	46
L.4 Procedure.....	47
Annex M (informative) Small-scale fire test.....	49
M.1 Apparatus.....	49
M.2 Test procedure.....	50
M.2.1 Test conditions.....	50
M.2.2 Set-up.....	50
M.2.3 Fire test.....	50
Annex N (informative) Annual foam quality check.....	59
N.1 Visual examination.....	59
N.1.1 Object of the test.....	59
N.1.2 Test procedure	59
N.2 Density	59
N.2.1 Object of the test.....	59
N.2.2 Test procedure	59
N.3 pH-value	59

N.3.1	Object of the test	59
N.3.2	Apparatus	60
N.3.3	Test execution.....	60
N.4	Sediment	61
N.4.1	Object of the test	61
N.4.2	Test procedure	61
N.5	Viscosity	61
N.5.1	Object of the test	61
N.5.2	Test procedure	61
N.6	Refractive index	61
N.6.1	Object of the test	61
N.6.2	Apparatus	61
N.6.3	Test execution.....	62
N.7	25 %-drainage time and expansion ratio	62
N.7.1	Object of the test	62
N.7.2	Test procedure	62
N.8	Resistance to isopropanol	62
N.8.1	Object of the test	62
N.8.2	Test procedure	62
N.8.3	Test requirements.....	62
Annex O (normative)	Determination of foam expansion sensitivity	63
O.1	General	63
O.2	General conditions	63
O.2.1	Test series and evaluation.....	63
O.2.2	Temperatures	64
O.2.3	Records.....	64
O.2.4	Foam solution.....	64
O.2.5	Fuel	64
O.3	Apparatus	64
O.3.1	Circular fire tray.....	64
O.3.2	Foam making equipment	65
O.3.2.1	Supply of pressurised air	65
O.3.2.2	Supply of foam solution	65
O.3.2.3	Foam nozzle with mixing chamber.....	65
O.4	Test procedure	65
O.5	Test report	65

0.6 Figures..... 66

Annex P (informative) Example for a technical information sheet..... 74

Annex Q (informative) A-Deviations 77

Bibliography..... 79

European foreword

This document (prEN 1568-3:2025) has been prepared by Technical Committee CEN/TC 191 “Fixed firefighting systems”, the secretariat of which is held by BSI.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 1568-3:2018.

This document includes the following significant technical changes with respect to EN 1568-3:2018:

- Determination of solid deposits for synthetic foams and protein foams clarified;
- Aqueous film formation evaluation removed;
- Optional annual foam quality check introduced;
- Temperature and wind speed measurements for performance fire test clarified;
- Stainless steel as optional material for small-scale fire test fire tray introduced;
- Foam expansion performance test introduced;
- Some test procedures clarified.

This document is Part 3 of EN 1568 which has the general title Fire extinguishing media — Foam concentrates. The other parts are:

- *Part 1: Specification for medium expansion foam concentrates for surface application to water-immiscible liquids;*
- *Part 2: Specification for high expansion foam concentrates for surface application to water-immiscible liquids;*
- *Part 4: Specification for low expansion foam concentrates for surface application to water-miscible liquids.*

This European Standard is one of a series of standards specifying requirements for fire extinguishing media in common use. This series includes the following standards:

- EN ISO 5923, *Equipment for fire protection and fire fighting — Fire extinguishing media — Carbon dioxide*;
- EN 27201-1, *Fire protection — Fire extinguishing media — Halogenated hydrocarbons — Part 1: Specifications for halon 1211 and halon 1301* (ISO 7201-1);
- EN 27201-2, *Fire protection — Fire extinguishing media — Halogenated hydrocarbons — Part 2: Code of practice for safe handling and transfer procedures* (ISO 7201-2);
- EN 615, *Fire protection — Fire extinguishing media — Specifications for powders (other than class D powders)*.

Introduction

As fire fighting foams are chemical agents or chemical preparations, Commission Directive 2000/60/CE and Regulations (EC) No 1272/2008 (CLP) and No 1907/2006 (REACH) apply and should be taken into account.

Classes of fire are defined in EN 2 as follows:

- Class A: fires involving solid materials, usually of an organic nature, in which combustion normally takes place with the formation of glowing embers;
- Class B: fires involving liquids or liquefiable solids;
- Class C: fires involving gases;
- Class D: fires involving metals;
- Class F: fires involving cooking media (vegetable or animal oils and fats) in cooking appliances.

Fire-fighting foams are widely used to control and extinguish Class B fires and to inhibit re-ignition. These foams can also be used for prevention of ignition of flammable liquids and, in certain conditions, to extinguish Class A fires.

Foams can be used in combination with other extinguishing media, particularly gaseous media and powders, which are the subject of other European Standards (see European foreword).

These specifications have been designed to ensure that fire extinguishing media have the minimum useful fire fighting capability. The user should ensure that the foam concentrates are used accurately at the concentration recommended by the manufacturer. Fire performances indicated by this standard cannot replicate practical fire situations.

Foam concentrates of different types and manufacture should not be mixed.

It should be noted that some combinations of extinguishing powder and foam can lead to unacceptable loss of efficiency, caused by unfavourable interaction of the chosen media when applied simultaneously or successively to the fire.

It is extremely important that the foam concentrate after dilution with water to the recommended concentration should not in normal usage present a significant toxic hazard to life in relation to the environment. The current version of Commission Directive 2000/60/CE, Regulations (EC) No 1272/2008 (CLP) and No 1907/2006 (REACH) apply when considering the testing of ecotoxicological properties and safety in the work environment.

A special quality characteristic is the type test conducted by an independent testing laboratory accredited to EN ISO/IEC 17025.

1 Scope

This document specifies requirements for chemical and physical properties, and minimum performance requirements of low expansion foams suitable for surface application to water-immiscible liquids. Requirements are also given for marking.

WARNING — Any type approval according to this document is invalidated by any change in composition of the approved product.

NOTE Some concentrates conforming to this document can also conform to other parts and therefore can also be suitable for application as medium and/or high expansion foams, and for application at low expansion to water-miscible liquids.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13565 (all parts), *Fixed firefighting systems — Foam systems*

EN ISO 2811-1, *Paints and varnishes - Determination of density - Part 1: Pycnometer method (ISO 2811-1)*

EN ISO 3104, *Petroleum products - Transparent and opaque liquids - Determination of kinematic viscosity and calculation of dynamic viscosity (ISO 3104)*

EN ISO 3219-2:2021, *Rheology - Part 2: General principles of rotational and oscillatory rheometry (ISO 3219-2:2021)*

EN ISO 3675, *Crude petroleum and liquid petroleum products - Laboratory determination of density - Hydrometer method (ISO 3675)*

EN ISO 3696, *Water for analytical laboratory use - Specification and test methods (ISO 3696)*

EN ISO 11348-2, *Water quality - Determination of the inhibitory effect of water samples on the light emission of *Vibrio fischeri* (Luminescent bacteria test) - Part 2: Method using liquid-dried bacteria (ISO 11348-2)*

EN ISO 23753-1, *Soil quality - Determination of dehydrogenases activity in soils - Part 1: Method using triphenyltetrazolium chloride (TTC) (ISO 23753-1)*

ISO 304, *Surface active agents — Determination of surface tension by drawing up liquid films*

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

OECD 201, *Test No. 201: Freshwater Alga and Cyanobacteria, Growth Inhibition Test*

OECD 202, *Test No. 202: Daphnia sp. Acute Immobilisation Test*

OECD 203, *Test No. 203: Fish, Acute Toxicity Test*

OECD 301, *Test No. 301: Ready Biodegradability*

OECD 404, *Test No. 404: Acute Dermal Irritation/Corrosion*

OECD 405, *Test No. 405: Acute Eye Irritation/Corrosion*

OECD 420, *Test No. 420: Acute Oral Toxicity - Fixed Dose Procedure*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/> ;
- ISO Online browsing platform: available at <http://www.iso.org/obp> .

3.1
25 %/50 % drainage time
time taken for 25 %/50 % of the volume of the original foam solution to drain out of the generated foam

3.2
expansion (E)
expansion value
expansion ratio
ratio of the volume of foam to the volume of the foam solution from which it was made

3.3
low expansion foam
foam which has an expansion ratio less than 20

3.4
medium expansion foam
foam which has an expansion ratio greater than or equal to 20 but less than 200

3.5
high expansion foam
foam which has an expansion ratio greater than or equal to 200

3.6
fire-fighting foam
aggregate of air filled bubbles formed from a foam solution used for fire-fighting

3.7
foam concentrate
liquid which is diluted with water to produce foam solution

Note 1 to entry: Annex A gives information on grades of foam concentrate.

3.8
foam solution
homogeneous mixture of foam concentrate and water in the proportions as specified by the foam concentrate manufacturer

3.9**premix**

foam solution prepared in a batch process by introducing a measured amount of foam concentrate into a given amount of water in a storage

3.10**sediment**

insoluble particles in the foam concentrate

3.11**Newtonian foam concentrate**

foam concentrate which has a viscosity which is independent of the shear rate

3.12**pseudo-plastic foam concentrate**

foam concentrate which has a viscosity which decreases with increasing shear rate

3.13**surface tension**

tension within the interface between a liquid and air

3.14**freezing point**

temperature at which the first ingredient of a mixture starts to solidify or freeze

3.15**designation****identifying name**

name that corresponds to a chemical formulation and a specific production process

Note 1 to entry: It guarantees consistency of the characteristics, performance and conditions of use of the foam concentrate.

3.16**demineralized water**

water conforming to EN ISO 3696 (Grade 3), or having a surface tension greater than $70 \text{ mN}\cdot\text{m}^{-1}$ and a conductivity of $\leq 5 \mu\text{S}\cdot\text{cm}^{-1}$

Note 1 to entry: Surface tension tested in accordance with Clause G.2.

3.17**gentle application**

application (of foam from the test nozzle) indirectly to the surface of the fuel via a backboard

Note 1 to entry: This definition of gentle application relates to the fire test procedures used in EN 1568-3 and EN 1568-4. In practice fire-fighting systems foam can also be applied gently by fixed foam pourers or by indirect application via a tank wall or other surface.

3.18**forceful application**

application (of foam from the test nozzle) directly onto the surface of the fuel

3.19

qualified personnel

designated individual, suitably trained, competent through knowledge and practical experience and with the necessary instruction to enable the tests and examinations to be carried out

4 Sediment in the foam concentrate

4.1 Sediment before ageing

Any sediment in the foam concentrate sampled in accordance with Annex B, but not aged in accordance with Clause C.1, shall be dispersible through a 180 µm sieve, and the percentage volume of sediment shall be not more than 0,25 % when tested in accordance with Annex C.

4.2 Sediment after ageing

Any sediment in the foam concentrate sampled in accordance with Annex B, and aged in accordance with Clause C.1, shall be dispersible through a 180 µm sieve and the percentage volume of sediment shall be not more than 1,0 % when tested in accordance with Annex C.

5 Freezing point

The freezing point of the foam concentrate sampled in accordance with Annex B shall be determined in accordance with Annex D.

6 Viscosity of the foam concentrate

6.1 Test temperatures

The viscosity of the foam concentrate shall be measured from 20 °C, to and including the lowest temperature for use claimed by the manufacturer in steps of 10 °C. Use a fresh sample for each temperature.

6.2 Newtonian foam concentrates

The viscosity of the foam concentrate shall be determined in accordance with EN ISO 3104. If the viscosity is $> 200 \text{ mm}^2 \text{ s}^{-1}$, the container shall be marked in accordance with Clause 15 k).

6.3 Pseudo-plastic foam concentrates

The viscosity of the foam concentrate shall be determined in accordance with Annex E. If the viscosity at the lowest temperature for use is greater than or equal to 120 mPa·s at 375 s^{-1} , the container shall be marked in accordance with Clause 15 l).

7 pH of the foam concentrate

The pH of the foam concentrate sampled in accordance with Annex B shall be not less than 6,0 and not more than 9,5 at $(20 \pm 1) \text{ °C}$.

8 Surface tension of the foam solution

The surface tension (determined in accordance with Clause G.2) of the foam solutions prepared using top and bottom half-samples (see Clause F.4) of the foam concentrate sampled in accordance with Annex B and conditioned in accordance with Annex F shall be not less than 0,95 times and not more than 1,05 times the surface tension of the foam solution prepared using the sampled foam concentrate.

9 Stability/separation test of foam concentrate

The foam concentrate shall not separate, stratify or precipitate as indicated by two or more distinct layers when tested in accordance with Annex H.

The amount of solid deposits of the aged sample determined according to Annex C at 20 °C in synthetic foams shall not increase from the fresh sample.

The amount of solid deposits of the aged sample determined according to Annex C at 20 °C in protein foams shall not increase by more than 4 times the amount obtained from the fresh sample, and shall not exceed a volume fraction of 1 % in total.

10 Determination of expansion and drainage time

10.1 Before temperature conditioning

The foam produced from the foam solution prepared from the foam concentrate sampled in accordance with Annex B, at the supplier's recommended concentration with simulated fresh water in accordance with Clause I.4 shall be tested in accordance with Annex I and give an expansion according to 3.3. If appropriate, a further sample for the same concentration made with the simulated sea water in accordance with Clause I.4 shall also be tested.

10.2 After temperature conditioning

The foams produced from the solutions prepared with simulated fresh water by using top and bottom half-samples (see Clause F.4) of foam concentrate, sampled in accordance with Annex B, at the supplier's recommended concentration, when tested in accordance with Annex I, shall have the following:

- a) expansions which do not differ from each other or from the value obtained according to 10.1 using simulated fresh water (i.e. before temperature conditioning) by more than 20 % of the value obtained according to 10.1 using simulated fresh water; and
- b) 25 % drainage times which do not differ from each other or from the value obtained according to 10.1 using simulated fresh water (i.e. before temperature conditioning) by more than 20 % of the value obtained according to 10.1 using simulated fresh water.

If appropriate, the tests shall be repeated using top and bottom half-samples (see Clause F.4) of foam concentrate, sampled in accordance with Annex B, at the supplier's recommended concentration, using foam solutions prepared with the simulated sea water in accordance with Clause I.4. These foam solutions shall have the following:

- c) expansions which do not differ from each other or from the value obtained according to 10.1 using the simulated sea water (i.e. before temperature conditioning) by more than 20 % of the value obtained according to 10.1 using the simulated sea water in accordance with Clause I.4; and

- d) 25 % drainage times which do not differ from each other or from the value obtained according to 10.1 using the simulated sea water (i.e. before temperature conditioning) by more than 20 % of the value obtained according to 10.1 using the simulated sea water in accordance with Clause I.4.

NOTE Expansion is dependent on the foam concentrate and the equipment used to make the foam.

11 Test fire performance

The foam produced from the foam solutions, prepared using the foam concentrate, sampled in accordance with Annex B at the supplier's recommended concentration with simulated fresh water and if appropriate at the same concentration with the simulated sea water in accordance with Clause I.4, shall have an extinguishing performance class and burn-back resistance level as specified in Table 1 when tested in accordance with Clause J.2 and Clause J.3 and/or Clause J.4 as appropriate.

NOTE 1 The values obtained with sea water can differ from those obtained with simulated fresh water.

NOTE 2 Annex M describes a small scale fire test which can be suitable for quality control purposes.

NOTE 3 The lack of homogeneity of the premix can influence the firefighting performance of the foam generated from it.

Table 1 — Maximum extinction times and minimum burn-back times

Times in minutes.

Extinguishing performance class	Burn-back resistance level	Gentle application test		Forceful application test	
		(see J.3)		(see J.4)	
		Extinction time not more than	25 % burn-back time not less than	Extinction time not more than	25 % burn-back time not less than
I+	A			1,5	10
	B		15	1,5	
	C		10	1,5	
	D		5	1,5	
I	A			3	10
	B		15	3	
	C		10	3	
	D		5	3	
II	A			4	10
	B		15	4	
	C		10	4	
	D		5	4	

Times in minutes.

Extinguishing performance class	Burn-back resistance level	Gentle application test		Forceful application test
		(see J.3)		(see J.4)
III	B	5	15	
	C	5	10	
	D	5	5	
NOTE 1 There is no burn-back resistance level A for class III.				
NOTE 2 Typical extinguishing performance classes and burn-back resistance levels for different types of foam concentrate are given in Annex A.				

12 Occupational health and ecotoxicological information

The manufacturer shall provide information as specified in Annex K.

If the toxicological/ecotoxicological data were generated by application of mathematical methodologies in accordance with Annex K the corresponding report shall be added to the report confirming conformity with this document.

If the toxicological/ecotoxicological data were generated by an independent third party the data may be added to the report confirming conformity to this document either as a report or as a reference to the report-ID given by the third party.

If the data for the ecotoxicological report was generated by a third party, this data may be added to the test report or may added as a reference. If the data for the ecotoxicological report was generated by mathematical means (or as a reference) it shall be added to the test report.

13 Annual foam quality check

13.1 General

Firefighting foam concentrates are recommended to be checked annually for their quality, indicating their functionality. The test program described in 13.2 is considered to be a collection of analytical methods which in its entirety is suitable to detect degradation or a declining function of a foam concentrate.

The outcome of the annual foam quality check described in 13.2 is intended to be used to qualify or disqualify a foam concentrate for its further usability. Therefore, the quality of testing and evaluation of test data is a special quality characteristic of the body executing the foam quality check.

13.2 Principles

13.2.1 The sample of the foam concentrate(s) shall be collected in such a way, that the sample is representative of the stored volume.

13.2.2 A full declaration of the foam product's identity, hazards associated with it [see section 2 of the most recent material safety data sheet (MSDS)], as well as information on PFAS content, proportioning rate, age, storage condition and possible contaminations shall be given.

13.2.3 For foam concentrates which can be used as low, medium and high expansion foam the desired testing expansion shall be specified as well as the water quality (simulated fresh or sea water) to be used.

13.2.4 Packing and labelling of foam concentrate samples is subject to European regulation on packaging and labelling of chemical mixtures (Regulation (EC) No 1272/2008, CLP, e.g. Article 35).

13.2.5 The equipment for testing shall be calibrated and maintained in full function.

13.2.6 The foam concentrate sample should be processed as it was received. If stratification, sedimentation or other inhomogeneities are visible, that sample shall not be homogenised prior to testing. Instead, the sample may be considered as a fail.

13.2.7 A comprehensive test report with all tested results should be provided. The report may include evaluation of the obtained results and further recommendations. If this is the case, this shall be indicated as an evaluation of the data based on the experience and knowledge of the body executing the foam quality test.

13.2.8 The test data shall be compared with the technical data of the respective foam concentrate given by the manufacturer.

13.3 Types of analysis

Table 2 indicates the type of analysis that should be run for a given type of foam concentrate. Annex N gives test descriptions and requirements.

Table 2 — Types of analysis

	AR	non-AR	medium expansion application	high expansion application
Visual examination	X	X	X	X
Density at (20 ± 1) °C	X	X	X	X
pH-value at (20 ± 1) °C	X	X	X	X
Sediment at (20 ± 1) °C	X	X	X	X
Viscosity at (20 ± 1) °C	X	X	X	X
Refractive index at (20 ± 1) °C	X	X	X	X
25 %-drainage, low expansion foam	X	X	—	—
25 %-drainage, medium expansion foam	—	—	X	—
25 %-drainage, high expansion foam	—	—	—	X
expansion, low expansion foam	X	X	—	—

	AR	non-AR	medium expansion application	high expansion application
expansion, medium expansion foam	—	—	X	—
expansion, high expansion foam	—	—	—	X
Resistance to isopropanol	X	—	—	—

14 Expansion performance comparison test

The extinguishing performance of foams is influenced by the foam expansion ratio.

For foams of the type F3 and/or F3-AR (fire extinguishing performance class I and class II) fire extinguishing tests shall be performed according to Annex O, Table O.1 a) and b), to determine the degree of the performance impact caused by changing the expansion ratio.

Foams that are claimed by the manufacturer to be suitable for use in fixed firefighting systems according to EN 13565 shall additionally be tested according to Annex O, Table O.1 c).

The records of the tests (O.2.3) and the test results should be made available to the end user according to O.5.

15 Technical information sheet

The manufacturer should provide information for the foam concentrate. An example of the type of information provided in a manufacturers' technical information sheet is given in Annex P.

16 Container marking

Markings on shipping containers should be permanent and legible. The following information shall be marked on the packaging or transport container:

- a) the designation (identifying name) of the concentrate;
- b) the words “low expansion fire-fighting foam concentrate” and the number and publication date of this document (i.e. EN 1568-3:2025);

NOTE 1 For low expansion concentrates which also conform to other parts of EN 1568 additional markings can be used as given in those parts.

- c) ((DELETED))
- d) recommended usage concentration (most commonly 1 %, 3 % or 6 %);
- e) recommended maximum storage temperature, lowest temperature for use and freezing point;
- f) if the manufacturer advises that the foam concentrate is adversely affected by low temperature storage according to Annex F the words 'Do not freeze';
- g) the nominal quantity in the container;

- h) the supplier's name and address;
- i) the batch number and the date of manufacture;
- j) the words “Not suitable for use with sea water” or “Suitable for use with sea water” as appropriate;
- k) if the foam concentrate is Newtonian and the viscosity at the lowest temperature for use is more than $200 \text{ mm}^2 \text{ s}^{-1}$ when measured in accordance with EN ISO 3104 the words “This concentrate can require special proportioning equipment”;
- l) if the foam concentrate is pseudo-plastic and the viscosity at the lowest temperature for use is greater than or equal to $120 \text{ mPa}\cdot\text{s}$ at 375 s^{-1} the words “Pseudo-plastic foam concentrate. This concentrate can require special proportioning equipment”; and
- m) the lowest extinguishing performance class and the lowest burn-back resistance level obtained with all fuels in simulated fresh water and sea water.

NOTE 2 The marking of shipping containers shipped to laboratories for testing are exempt from this requirement.

Annex A (informative)

Grades of foam concentrate and performance

A.1 Grades

Foam concentrates are graded as follows:

- a) protein foam concentrates (P): these are liquids derived from hydrolysed protein materials;
- b) fluoroprotein foam concentrates (FP): these are protein concentrates with added fluorinated surface active agents;
- c) synthetic foam concentrates (S): these are based upon mixtures of hydrocarbon surface-active agents and do not contain fluoro organic compounds;
- d) alcohol resistant foam concentrates (AR): these can be suitable for use on hydrocarbon fuels, and additionally are resistant to breakdown when applied to the surface of water-miscible liquid fuels. Some alcohol resistant foam concentrates can precipitate a polymeric membrane on the surface of alcohol;
- e) aqueous film-forming foam concentrates (AFFF): these are based on mixtures of hydrocarbon surfactants and fluorinated surface active agents and have the ability to form an aqueous film on the surface of some hydrocarbon fuels;
- f) film-forming fluoroprotein foam concentrates (FFFP): these are fluoroprotein foam concentrates which have the ability to form an aqueous film on the surface of some hydrocarbon fuels;
- g) fluorine free foam concentrates (F3): these foam concentrates are dedicated to meet fire performance ratings and are targeting applications similar to AFFF and/or -AR-foams without using fluoroorganic compounds. These foam concentrates are based upon mixtures of hydrocarbon surface-active agents and non-fluorine containing stabilizers.

NOTE Fluorine free foams are currently not considered to provide an aqueous film.

A.2 Typical performance

The correlation between performance and grade of concentrate is not perfect. The values given in Table A.1 are therefore only typical and particular foam of a given grade can have performance better or worse than that shown.

Table A.1 — Typical performance for various grades of foam concentrate

Grade	Extinguishing performance class	25 % Burn-back resistance level	Film formation	Application type
AFFF (not AR)	I	A to C	Yes	Forceful
AFFF (AR)	I	A or B	Yes	Forceful
FFFP (not AR)	I	B	Yes	Forceful
FFFP (AR)	I	A or B	Yes	Forceful
FP (not AR)	II	A or B	No	Forceful
FP (AR)	II	A or B	No	Forceful
P (not AR)	III	B	No	Gentle
P (AR)	III	B	No	Gentle
S (not AR)	III	C	No	Gentle
S (AR)	III	C	No	Gentle
F3 (not AR)	I or II	A to C	No	Forceful
F3 (AR)	I or II	A to C	No	Forceful

Annex B (normative)

Sampling of foam concentrates

The samples for testing shall be delivered by the supplier in completely filled sealable containers. The samples for testing shall be taken and delivered by the supplier using a method which provides a representative sample of the foam concentrate to be tested.

NOTE Nominal 20-l containers are convenient.

Annex C (normative)

Determination of percentage sediment

C.1 Sampling

NOTE See Clause 4.

Use a sample prepared in accordance with Annex B. Place approximately 1 l of the sample in a suitable container of nominal capacity sufficient to provide an ullage of 5 % to 10 % of the container volume. Seal the container. Ensure that any sediment is dispersed evenly by agitating the sample container.

Take two samples, testing one immediately at a temperature of $(20 \pm 5) ^\circ\text{C}$, the other after ageing for (24 ± 2) h at $(60 \pm 2) ^\circ\text{C}$ in a completely filled container without access to air.

C.2 Apparatus

C.2.1 Graduated centrifuge tubes.

NOTE The centrifuge tubes described in ISO 3734 are suitable.

C.2.2 Centrifuge, operating at $(6\,000 \pm 600) \text{ m s}^{-2}$.

NOTE The centrifuge described in ISO 3734 is suitable.

C.2.3 180 μm sieve conforming to ISO 3310-1.

C.2.4 Plastic wash bottle.

C.3 Procedure

C.3.1 Centrifuge each sample of the concentrate for 10 min. Determine the volume of the sediment and report it as a percentage of the volume of the centrifuged sample.

C.3.2 Wash the contents of the centrifuge tube onto the sieve and check whether the sediment can be dispersed through the sieve by the jet from the plastic wash bottle.

Annex D (normative)

Freezing point determination

D.1 General

NOTE See Clause 5.

This test is derived from the test procedure EN ISO 5764 "Freezing Point of Milk".

D.2 Apparatus

D.2.1 Cooling bath capable of attaining temperatures below minus 30 °C;

D.2.2 250 ml vessel (double-neck flask or beaker) with stirrer;

D.2.3 Temperature measuring device, capable of electronic data read-out and accuracy of $\pm 0,5$ K;

NOTE Examples for a suitable device would be a Pt100 or a thermocouple type K class 1.

D.2.4 XY-recorder for plotting a curve of temperature against time.

D.3 Procedure

D.3.1 Fill (200 ± 10) ml sample into the 250 ml vessel;

D.3.2 Insert the stirrer and the temperature measuring device into the vessel in such a way that the temperature measuring device does not touch the stirrer, and is completely covered by liquid;

D.3.3 Insert the vessel into the cooling bath;

D.3.4 Start the stirrer, and adjust the speed so that the entire volume of liquid is slightly agitated, but no air is drawn into the liquid;

D.3.5 Set the cooling bath temperature to $(5 \text{ to } 10)$ °C below the expected freezing point of the liquid;

D.3.6 Note the temperature, and plot a graph of temperature against time;

D.3.7 The temperature curve will drop until a certain point, then it will rise for a period before dropping again;

D.3.8 The freezing point of the liquid is the highest point of this part of the graph, before the curve starts to drop again.