

Specification for Flux and Electrode Combinations for Submerged Arc and Electroslag Joining and Surfacing of Stainless Steel and Nickel Alloys



Documents

Document Sharing Hub

AWS A5.39/A5.39M:2020
An American National Standard

Approved by the
American National Standards Institute
February 24, 2020

Specification for Flux and Electrode Combinations for Submerged Arc and Electroslag Joining and Surfacing of Stainless Steel and Nickel Alloys

1st Edition

Prepared by the
American Welding Society (AWS) A5 Committee on Filler Metals and Allied Materials

Under the Direction of the
AWS Technical Activities Committee

Approved by the
AWS Board of Directors

Abstract

This specification prescribes the requirements for the classification of flux-electrode combinations used with submerged arc or electroslag joining or surfacing using stainless steel and nickel alloys. Electrode classification is per AWS A5.9/A5.9M for solid and stranded stainless steel electrodes, A5.14/A5.14M for solid and stranded nickel-alloy electrodes, A5.22/A5.22M for cored stainless steel electrodes and A5.34/A5.34M for cored nickel-alloy electrodes. Flux-electrode joining classification is based on the mechanical properties and the composition of weld metal produced with the flux and a specific electrode. Flux-electrode surfacing classification is based on the composition of the weld metal produced with the flux and a specific electrode. The form and usability of the flux are also included. A guide is appended to the specification as a source of information concerning the classification system employed and the intended use of submerged arc and electroslag fluxes and electrodes.

This specification makes use of both US Customary Units and the International System of Units (SI). Since these are not equivalent, each system must be used independently of the other.



ISBN Print: 978-1-64322-121-2

ISBN PDF: 978-1-64322-122-9

© 2020 by American Welding Society

All rights reserved

Printed in the United States of America

Photocopy Rights. No portion of this standard may be reproduced, stored in a retrieval system, or transmitted in any form, including mechanical, photocopying, recording, or otherwise, without the prior written permission of the copyright owner.

Authorization to photocopy items for internal, personal, or educational classroom use only or the internal, personal, or educational classroom use only of specific clients is granted by the American Welding Society provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, tel: (978) 750-8400; Internet: <www.copyright.com>.

Statement on the Use of American Welding Society Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society (AWS) are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute (ANSI). When AWS American National Standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guarantee or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is neither undertaking to render professional or other services for or on behalf of any person or entity, nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. It is assumed that the use of this standard and its provisions is entrusted to appropriately qualified and competent personnel.

This standard may be superseded by new editions. This standard may also be corrected through publication of amendments or errata or supplemented by publication of addenda. Information on the latest editions of AWS standards including amendments, errata, and addenda is posted on the AWS web page (www.aws.org). Users should ensure that they have the latest edition, amendments, errata, and addenda.

Publication of this standard does not authorize infringement of any patent or trade name. Users of this standard accept any and all liabilities for infringement of any patent or trade name items. AWS disclaims liability for the infringement of any patent or product trade name resulting from the use of this standard.

AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

Official interpretations of any of the technical requirements of this standard may only be obtained by sending a request, in writing, to the appropriate technical committee. Such requests should be addressed to the American Welding Society, Attention: Managing Director, Standards Development, 8669 NW 36 St, # 130, Miami, FL 33166 (see Annex B). With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. These opinions are offered solely as a convenience to users of this standard, and they do not constitute professional advice. Such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS A5 Committee on Filler Metals and Allied Materials. It must be reviewed every five years, and if not revised, it must be either reaffirmed or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are requested and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS A5 Committee on Filler Metals and Allied Materials and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS A5 Committee on Filler Metals and Allied Materials to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166.

This page is intentionally blank.

Personnel

AWS A5 Committee on Filler Metals and Allied Materials

T. Melfi, Chair	<i>The Lincoln Electric Company</i>
R. V. Decker, Vice Chair	<i>Weldstar</i>
M. F. Sinfield, 2nd Vice Chair	<i>Naval Surface Warfare Center</i>
R. K. Gupta, Secretary	<i>American Welding Society</i>
T. Anderson	<i>ITW-Miller Electric Manufacturing Company</i>
A. Boulianne	<i>CWB Group</i>
J. C. Bundy	<i>Hobart Brothers LLC</i>
J. L. Caron	<i>Haynes International, Incorporated</i>
G. L. Chouinard	<i>Stoody Company (a division of ESAB)</i>
T. J. Eckardt	<i>Ashland</i>
D. M. Fedor	<i>The Lincoln Electric Company</i>
J. G. Feldstein	<i>Foster Wheeler North America</i>
D. A. Fink	<i>The Lincoln Electric Company</i>
R. J. Fox	<i>Hobart Brothers LLC</i>
G. L. Franke	<i>Consultant</i>
R. D. Fuchs	<i>Voestalpine Bohler Welding USA, Inc.</i>
S. D. Kiser	<i>Consultant</i>
P. J. Konkol	<i>Concurrent Technologies Corporation</i>
D. J. Kotecki	<i>Damian Kotecki Welding Consultants</i>
L. G. Kvidahl	<i>Ingalls Shipbuilding</i>
J. S. Lee	<i>Chevron</i>
C. McEvoy	<i>Consultant</i>
M. T. Merlo	<i>Select-Arc, Incorporated</i>
B. Mosier	<i>Polymet Corporation</i>
T. C. Myers	<i>Westec</i>
B. A. Pletcher	<i>Bechtel Global Corporation</i>
K. C. Pruden	<i>BP Americas</i>
K. Roossinck	<i>Ingalls Shipbuilding</i>
K. Sampath	<i>Chart Industries</i>
J. D. Schaefer	<i>Aqua-Chem, Incorporated</i>
F. A. Schweighardt	<i>Airgas</i>
W. S. Severance	<i>Severance Engineering LLC</i>
D. Singh	<i>BHGE</i>
R. C. Sutherlin	<i>Richard Sutherlin PE Consulting LLC</i>
H. D. Wehr	<i>Arcos Industries</i>
J. Zhang	<i>Ohmstede, Limited</i>

Advisors to AWS A5 Committee on Filler Metals and Allied Materials

D. R. Bajek	<i>Chicago Bridge and Iron</i>
M. R. Brinkman	<i>Welding Consultants LLC</i>
K. P. Campion	<i>Central Wire Industries</i>
J. DeVito	<i>Consultant</i>
W.D. England	<i>ITW Welding North America</i>
S. E. Ferree	<i>Consultant</i>
O. Henderson	<i>Trinity Industries Incorporated</i>
S. Imaoka	<i>Kobe Steel Limited</i>
S. J. Knostman	<i>Hobart Brothers LLC</i>
J. R. Logan	<i>BMX Technologies, Incorporated</i>

AWS A5B Subcommittee on Carbon and Low Alloy Steel Electrodes and Fluxes for Submerged Arc Welding

T. Melfi, Chair	<i>The Lincoln Electric Company</i>
R. K. Gupta, Secretary	<i>American Welding Society</i>
H. Beck	<i>Harbert's Products Incorporated</i>
R. J. Fox	<i>Hobart Brothers LLC</i>
R. D. Fuchs	<i>Voestalpine Bohler Welding USA Inc</i>
B. D. Gaal	<i>Select-Arc, Incorporated</i>
D. J. Kotecki	<i>Damian Kotecki Welding Consultants</i>
M. T. Merlo	<i>Select-Arc Incorporated</i>
D. W. Meyer	<i>ESAB Welding & Cutting Products</i>
J. Procaro	<i>The Lincoln Electric Company</i>
A. K. Singh	<i>Welspun Pipes Incorporated</i>
R. D. Strugar	<i>Bechtel Plant Machinery Incorporated</i>
R. A. Swain	<i>Euroweld, Limited</i>

Advisors to the A5B Subcommittee on Carbon and Low Alloy Steel Electrodes and Fluxes for Submerged Arc Welding

S. Imaoka	<i>Kobe Steel Limited</i>
-----------	---------------------------

AWS A5D Subcommittee on Stainless Steel Filler Metals

D. J. Kotecki, Chair	<i>Damian Kotecki Welding Consultants</i>
F. B. Lake, Vice Chair	<i>Stoody Company (a division of ESAB)</i>
R. K. Gupta, Secretary	<i>American Welding Society</i>
R. V. Decker	<i>Weldstar</i>
M. Denault	<i>Sandvik Materials Technology</i>
T. J. Eckardt	<i>Ashland</i>
J. G. Feldstein	<i>Foster Wheeler North America</i>
R. D. Fuchs	<i>Voestalpine Bohler Welding USA Inc.</i>
M. James	<i>The Lincoln Electric Company</i>
S. J. Knostman	<i>Hobart Brothers LLC</i>
W. P. Koegel	<i>R-V Industries, Inc.</i>
M. T. Merlo	<i>Select-Arc, Inc.</i>
S. J. Merrick	<i>The Lincoln Electric Company</i>
R. A. Swain	<i>Euroweld, Limited</i>
H. D. Wehr	<i>Arcos Industries, LLC</i>
J. M. Zawodny	<i>Voestalpine Bohler Welding USA, Inc.</i>

Advisors to the AWS A5D Subcommittee on Stainless Steel Filler Metals

A. Boulianne	<i>CWB Group</i>
K. K. Gupta	<i>Westinghouse Electric Corp</i>
S. Imaoka	<i>Kobe Steel Ltd</i>
S. R. Jana	<i>Mailam India, Limited</i>
B. L. Kahut	<i>Select-Arc, Inc.</i>
R. G. Miller	<i>UT-Battelle</i>
J. S. Ogborn	<i>The Lincoln Electric Company</i>
J. P. Roberts	<i>Ingalls Shipbuilding</i>
S. M. Williams	<i>Arcos Industries LLC</i>
M. Yamakami	<i>Kobelco Welding of America Inc.</i>

AWS A5E Subcommittee on Nickel and Nickel-Alloy Filler Metals

R. D. Fuchs, Chair	<i>Voestalpine Bohler Welding USA Inc</i>
T. Melfi Co-Chair	<i>Lincoln Electric</i>
S. D. Kiser, Vice Chair	<i>Consultant</i>
R. K. Gupta, Secretary	<i>American Welding Society</i>
M. E. Barrett	<i>Lincoln Electric</i>
J. L. Caron	<i>Haynes International Incorporated</i>
G. S. Clark	<i>OUTOKUMPU VDM USA LLC</i>
M. Denault	<i>Sandvik Materials Technology</i>
R. D. Gollihue	<i>Special Metals Corporation</i>
D. D. Kiilunen	<i>Cor-Met Incorporated</i>
D. J. Kotecki	<i>Damian Kotecki Welding Consultants</i>
F. B. Lake	<i>Stoody Company (a division of ESAB)</i>
J. S. Lee	<i>Chevron</i>
J. R. Logan	<i>BMX Technologies, Incorporated</i>
B. A. Pletcher	<i>Bechtel Global Corporation</i>
R. A. Swain	<i>Euroweld, Limited</i>
H. D. Wehr	<i>Arcos Industries LLC</i>
M. Yamakami	<i>Kobelco Welding of America, Incorporated</i>

Advisors to the AWS A5E Subcommittee on Nickel and Nickel-Alloy Filler Metals

J. J. DeLoach, Jr.	<i>Naval Surface Warfare Center</i>
S. Imaoka	<i>Kobe Steel Limited</i>
S. R. Jana	<i>Mailam India, Limited</i>
W. E. Layo	<i>Midalloy</i>

This page is intentionally blank.

Foreword

This foreword is not part of this standard, but is included for informational purposes only.

This document is the first edition of the A5.39/A5.39M specification. It makes use of both US Customary Units and the International System of Units (SI). The measurements are not exact equivalents; therefore each system must be used independently of the other without combining values in any way.

In selecting rational metric units, AWS A1.1, *Metric Practice Guide for the Welding Industry*, and ISO 544, *Welding Consumables—Technical Delivery Condition for Filler Materials and Fluxes—Type of Products, Dimensions, Tolerances and Markings*, are used where suitable.

NOTE: The user's attention is called to the possibility that compliance with this standard may require use of an invention covered by patent rights.

By publication of this standard, no position is taken with respect to the validity of any such claim(s) or of any patent rights in connection therewith. If a patent holder has filed a statement of willingness to grant a license under these rights on reasonable and nondiscriminatory terms and conditions to applicants desiring to obtain such a license, then details may be obtained from the standards developer.

Comments and suggestions for the improvement of this standard are welcome. They should be sent to the Secretary, AWS A5 Committee on Filler Metals and Allied Materials, American Welding Society, 8669 NW 36 St # 130, Miami, FL 33166.

The welding terms used in this specification shall be interpreted in accordance with the definitions given in the latest edition of AWS A3.0M/A3.0, *Standard Welding Terms and Definitions including Terms for Adhesive Bonding, Brazing, Soldering, Thermal Cutting, and Thermal Spraying*, unless specifically defined in this standard.

This page is intentionally blank.

Table of Contents

	Page No.
Personnel	v
Foreword	ix
List of Tables	xiii
List of Figures	xiii
1. Scope	1
2. Normative References	2
3. Definitions	3
4. Classification	4
5. Acceptance	4
6. Certification	4
7. Rounding Procedure	5
8. Summary of Tests	5
8.1 Electrodes	5
8.2 Fluxes	5
9. Retest	5
10. Weld Test Assemblies	5
10.1 Requirements for Classification of Flux-Electrode Combinations for Joining Designations	5
10.2 Weld Pad for Joining Designations	6
10.3 Groove Welds for Joining Designations	6
11. Chemical Analysis for Joining Designations	6
12. Radiographic Test for Joining Designations	7
13. Tension Test for Joining Designations	7
14. Impact Test for Joining Designations	7
15. Bend Test for Joining Designations	8
16. Method of Manufacture	8
17. Flux Requirements	8
17.1 Form and Particle Size	8
17.2 Usability	9
17.3 Packaging	9
17.4 Marking of Packages	9
Annex A (Normative): Rules for Sample Preparation and Testing for Flux-Electrode Combinations Classified with Cladding Designations per A5.39/A5.39M	25
A1. Cladding Classification of Flux-Electrode Combinations	25
A2. Tests for Classification of Flux-Electrode Combinations for Cladding Designations	25

A2.1 Requirements for Classification 25

A2.2 Preparation of Weld Pad for Cladding Designations.....25

A3. Chemical Analysis for Cladding Designations 26

A4. Radiographic Test for Cladding Designations.....26

A5. Bend Test for Cladding Designations 27

Annex B (Informative): Guide to AWS Specification for Flux and Electrode Combinations for Submerged
Arc and Electroslag Joining and Surfacing of Stainless Steel and Nickel Alloys 31

Annex C (Informative): Requesting an Official Interpretation on an AWS Standard 39

AWS Filler Metal Specifications by Material and Welding Process 41

AWS Filler Metal Specifications and Related Documents.....43

List of Tables

Table	Page No.
1. A5.39 Tension Test Requirements	10
1M. A5.39M Tension Test Requirements	10
2. Charpy Impact Toughness Requirements.	11
3. Chemical Composition Requirements for Weld Metal	12
4. Tests Required for Joining Classifications.	15
5. Face Bend Specimen Thickness for Alloys with Minimum Elongation less than 20%.	15
6. Welding Parameters for Weld Test Assemblies	16
7. Base Metals for Test Assemblies	17
8. Preheat and Interpass Temperatures and Postweld Heat Treatment Conditions	18
A1. Tests Required for Cladding Classifications	28

List of Figures

Figure	Page No.
1. A5.39 Joining Classification System for US Customary Units	19
1M. A5.39M Joining Classification System for the International System of Units (SI).	20
2. Weld Pad for Chemical Analysis and Bend Testing of Weld Metal.	21
3. Groove Weld Test Assembly for Tension, Impact and Radiographic Tests	22
4. Longitudinal Face-Bend Test Specimen	23
5. Radiographic Standards for Rounded Indications	24
A1. A5.39 Cladding Classification System	28
A2. Weld Pad for Bend, Chemical Composition, and Radiographic Tests for CLAD1 Designator.	29
A3. Weld Pad for Bend, Chemical Composition, and Radiographic Tests for CLAD2 Designator.	29

This page is intentionally blank.

Specification for Flux and Electrode Combinations for Submerged Arc and Electroslag Joining and Surfacing of Stainless Steel and Nickel Alloys

1. Scope

1.1 This specification prescribes requirements for the classification of flux-electrode combinations using submerged arc or electroslag welding. Flux-electrode joining classifications include requirements for soundness, mechanical properties and weld metal composition. Flux-electrode cladding classifications include requirements for soundness and weld metal composition. Electrode classification is per AWS A5.9/A5.9M for solid and stranded stainless steel electrodes, A5.14/A5.14M for solid and stranded nickel-alloy electrodes, A5.22/A5.22M for cored stainless steel electrodes and A5.34/A5.34M for cored nickel-alloy electrodes.

1.2 This specification makes use of both US Customary Units and the International System of Units (SI). The measurements are not exact equivalents; therefore, each system must be used independently of the other without combining in any way when referring to weld metal properties. The specification with the designation A5.39 uses US Customary Units. The specification with the designation A5.39M uses SI units. The latter are shown within brackets [] or in appropriate columns in tables and figures. Standard dimensions based on either system may be used for the sizing of electrodes or packaging or both under specification A5.39 or A5.39M.

1.3 Safety and health issues and concerns are beyond the scope of this standard; some safety and health information is provided, but such issues are not fully addressed herein. Some safety and health information can be found in the nonmandatory annex, Clauses B5 and B10.

Safety and Health information is available from the following sources:

American Welding Society:

- (1) ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*
- (2) AWS Safety and Health Fact Sheets
- (3) Other safety and health information on AWS website

Material or Equipment Manufacturers:

- (1) Safety Data Sheets supplied by material manufacturers
- (2) Operating Manuals supplied by equipment manufacturers

Applicable federal and state regulations:

Work performed in accordance with this standard may involve the use of materials that have been deemed hazardous and may involve operations or equipment that may cause injury or death. This standard does not purport to address all safety and health risks that may be encountered. The user of this standard should establish an appropriate safety program to address such risks as well as to meet applicable regulatory requirements. ANSI Z49.1 should be considered when developing the safety program.

2. Normative References

The documents listed below are referenced within this publication and are mandatory to the extent specified herein. For undated references, the latest edition of the referenced standard shall apply. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply.

2.1 The following AWS standards are referenced in the mandatory clauses of this document:

AWS A3.0M/A3.0, *Standard Welding Terms and Definitions Including Terms for Adhesive Bonding, Brazing, Soldering, Thermal Cutting and Thermal Spraying*.

AWS A4.2M, *Standard Procedures for Calibrating Magnetic Instruments to Measure the Delta Ferrite Content of Austenitic and Duplex Ferritic-Austenitic Stainless Steel Weld Metal*

AWS A5.01M/A5.01, *Welding Consumables—Procurement of Filler Metals and Fluxes*

AWS A5.02/A5.02M, *Specification for Filler Metal Standard Sizes, Packaging, and Physical Attributes*

AWS A5.9/A5.9M:2012, *Welding Consumables—Wire Electrodes, Strip Electrodes, Wires and Rods for Arc Welding of Stainless and Heat Resisting Steels—Classification*

AWS A5.14/A5.14M, *Specification for Nickel and Nickel-Alloy Bare Welding Electrodes and Rods*

AWS A5.22/A5.22M, *Specification for Stainless Steel Flux Cored and Metal Cored Welding Electrodes and Rods*

AWS A5.34/A5.34M, *Specification for Nickel-Alloy Electrodes for Flux Cored Arc and Metal Cored Arc Welding*

AWS B4.0, *Standard Methods for Mechanical Testing of Welds*

2.2 The following ANSI standard is referenced in the mandatory clauses of this document:

ANSI Z49.1, *Safety in Welding, Cutting, and Allied Processes*

2.3 The following ASTM International standards are referenced in the mandatory clauses of this document:

ASTM A36/A36M, *Standard Specification for Carbon Structural Steel*

ASTM A131/A131M, *Standard Specification for Structural Steel for Ships*

ASTM A240/A240M, *Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications*

ASTM A285/A285M, *Standard Specification for Pressure Vessel Plates, Carbon Steel, Low- and Intermediate-Tensile Strength*

ASTM A515/A515M, *Standard Specification for Pressure Vessel Plates, Carbon Steel, for Intermediate- and Higher-Temperature Service*

ASTM A560, *Standard Specification for Castings, Chromium-Nickel Alloy*

ASTM B127, *Standard Specification for Nickel-Copper Alloy (UNS N04400) Plate, Sheet, and Strip*

ASTM B160, *Standard Specification for Nickel Rod and Bar*

ASTM B162, *Standard Specification for Nickel Plate, Sheet, and Strip*

ASTM B164, *Standard Specification for Nickel-Copper Alloy Rod, Bar, and Wire*

ASTM B166, *Standard Specification for Nickel-Chromium-Iron Alloys (UNS N06600, N06601, N06603, N06690, N06693, N06025, N06045, and N06696), Nickel-Chromium-Cobalt-Molybdenum Alloy (UNS N06617), and Nickel-Iron-Chromium-Tungsten Alloy (UNS N06674) Rod, Bar, and Wire*

ASTM B167, *Standard Specification for Nickel-Chromium-Iron Alloys (UNS N06600, N06601, N06603, N06690, N06693, N06025, N06045, and N06696), Nickel-Chromium-Cobalt-Molybdenum Alloy (UNS N06617), and Nickel-Iron-Chromium-Tungsten Alloy (UNS N06674) Seamless Pipe and Tube*

ASTM B168, *Standard Specification for Nickel-Chromium-Iron Alloys (UNS N06600, N06601, N06603, N06690, N06693, N06025, N06045, and N06696), Nickel-Chromium-Cobalt-Molybdenum Alloy (UNS N06617), and Nickel-Iron-Chromium-Tungsten Alloy (UNS N06674) Plate, Sheet, and Strip*

ASTM B333, *Standard Specification for Nickel-Molybdenum Alloy Plate, Sheet, and Strip*

ASTM B435, *Standard Specification for UNS N06002, UNS N06230, UNS N12160, and UNS R30556 Plate, Sheet, and Strip*

ASTM B443, *Standard Specification for Nickel-Chromium-Molybdenum-Columbium Alloy (UNS N06625) and Nickel-Chromium-Molybdenum-Silicon Alloy (UNS N06219) Plate, Sheet, and Strip*

ASTM B446, *Standard Specification for Nickel-Chromium-Molybdenum-Columbium Alloy (UNS N06625), Nickel-Chromium-Molybdenum-Silicon Alloy (UNS N06219), and Nickel-Chromium-Molybdenum-Tungsten Alloy (UNS N06650) Rod and Bar*

ASTM B575, *Standard Specification for Low-Carbon Nickel-Chromium-Molybdenum, Low-Carbon Nickel-Chromium-Molybdenum-Copper, Low-Carbon Nickel-Chromium-Molybdenum-Tantalum, Low-Carbon Nickel-Chromium-Molybdenum-Tungsten, and Low-Carbon Nickel-Molybdenum-Chromium Alloy Plate, Sheet, and Strip*

ASTM B582, *Standard Specification for Nickel-Chromium-Iron-Molybdenum-Copper Alloy Plate, Sheet, and Strip*

ASTM E23, *Standard Test Methods for Notched Bar Impact Testing of Metallic Materials*

ASTM E29, *Standard Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications*

ASTM E76, *Standard Test Methods for Chemical Analysis of Nickel-Copper Alloys*

ASTM E353, *Standard Test Methods for Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys*

ASTM E354, *Standard Test Methods for Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys*

ASTM E1019, *Standard Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Various Combustion and Inert Gas Fusion Techniques*

ASTM E1032, *Standard Test Method for Radiographic Examination of Weldments*

ASTM E1473, *Standard Test Methods for Chemical Analysis of Nickel, Cobalt, and High-Temperature Alloys*

ASTM E2033, *Standard Practice for Computed Radiology (Photostimulable Luminescence Method)*

ASTM E2698, *Standard Practice for Radiological Examination Using Digital Detector Arrays*

2.4 The following ISO standard is referenced in the mandatory clauses of this document.

ISO 80000-1, *Quantities and units-Part 1 General*

3. Definitions

The welding terms used in this specification shall be interpreted in accordance with the definitions given in the latest edition of AWS A3.0M/A3.0 with further detail as described in this standard.

4. Classification

4.1 The submerged arc and electroslag flux-electrode combinations covered by the A5.39 specification utilize a classification system based upon US Customary Units and are classified according to the following:

(1) For joining designations, classification requires mechanical properties of the weld metal obtained from a groove weld made with a combination of a particular flux and a particular classification of electrode, as specified in Tables 1 and 2.