

Designations and Chemical Composition Limits for Aluminum Alloys in the Form of Castings and Ingot



1525 Wilson Boulevard, Arlington, VA 22209
www.aluminum.org

Revised: November 2009

Supersedes: February 2008

Use of the Information

The Aluminum Association has used its best efforts in compiling the information contained in this publication. Although the Association believes that its compilation procedures are reliable, it does not warrant, either expressly or impliedly, the accuracy or completeness of this information. The Aluminum Association assumes no responsibility or liability for the use of the information herein.

All Aluminum Association published standards, data, specifications and other material are reviewed at least every five years and revised, reaffirmed or withdrawn. Users are advised to contact The Aluminum Association to ascertain whether the information in this publication has been superseded in the interim between publication and proposed use.

FOREWORD

Listed herein are designations and chemical composition limits for aluminum alloys in the form of castings or ingot registered with The Aluminum Association. This list is maintained by the Technical Committee on Product Standards of The Aluminum Association. The numerical designations of these compositions were assigned in conformance with the system adopted by The Aluminum Association in 1954 and approved by the American Standards Association (now American National Standards Institute Incorporated) as an American Standard in 1957 (see American National Standard Alloy and Temper Designation Systems for Aluminum ANSI H35.1). Additions may be made as required, and alloys will be deleted when no longer in commercial use. In considering requests for additions, the following criteria apply:

1. The aluminum or aluminum alloy shall be offered for sale currently and shall have been sold within the 12 months immediately preceding the date of the registration request, in both cases in commercial quantities ^{a-d}. Such sales shall have been made to external users/customers (i.e., internal use and/or transfer of an alloy within a company does not meet the stated criteria).

- a. The alloy has undergone bona fide mill production and is NOT a "laboratory" scale volume.
- b. The alloy is cast and fabricated in standard production facilities and is NOT a one-time production.
- c. There is an expected and ongoing commercial demand and/or need for the alloy.
- d. The alloy shall be purchased and sold in a standard business context, which indicates that the alloy is actually "sold" and not "given away" for uses such as promotional evaluations.

2. The complete chemical composition limits shall be disclosed and judged to be reasonable and technically correct by the Technical Committee on Product Standards.
3. The composition shall be significantly different from that of any aluminum or aluminum alloy for which a numerical designation for castings and ingot has already been assigned.
4. Any request for the registration of Ingot composition limits shall be accompanied with a request for registration of casting composition limits of the same designation, with the exception of rotor and aluminizing ingot for which only ingot composition limits are required.
5. Ingot designated xxx.1 has chemical composition limits identical to those assigned to the casting (xxx.0) except grain refining elements and except for the following provisions:

Maximum Iron Percentage:

For All Forms of Castings

Up thru 0.15
Over 0.15 thru 0.25
Over 0.25 thru 0.6
Over 0.6 thru 1.0
Over 1.0

For Ingot, Fe Shall be At Least

0.03 less than castings
0.05 less than castings
0.10 less than castings
0.2 less than castings
0.3 less than castings

Minimum Magnesium Percentage^e:

For All Forms of Castings

Less than 0.50
0.50 and greater

For Ingot

0.05 more than castings
0.1 more than castings

Maximum Zinc Percentage:

For Die Castings

Over 0.25 thru 0.6
Over 0.6

For Ingot

0.10 less than castings
0.1 less than castings

^e. Applicable only if magnesium is an alloying element (i.e. has a registered minimum and maximum percentage).

6. Ingot designated xxx.2 has chemical composition limits which differ from, but fall within, those prescribed for xxx.1 ingot.
7. The product (Sand, Permanent Mold, Die, Investment Casting, or any variation of these processes) shall be shown at the time of registration. Other products may pertain even when not listed.
8. Composition limits changes:
 - 8.1 No changes in composition limits are allowed after the registration is final.
 - 8.2 Composition limit change proposals for experimental ("X") aluminum or aluminum alloys, including the net of changes made sequentially, shall be restricted to the extent allowed by the alloy modification rules of ANSI H35.1. No changes shall be permitted if they affect the validity of any registered alloy or alloy modification. If the composition limit changes are beyond those for a modification, then the changed composition will be given a new experimental designation. The former experimental alloy can continue as such or be deactivated at the discretion of the registrant. Composition limit changes are subject to review for 30 days by the Technical Committee on Product Standards of The Aluminum Association. However, the registrant has the final authority to change the composition, as desired, provided the change complies with the above rules. Changes proposed by those other than the registrant are acceptable only with the written approval of the registrant.
 - 8.3 A composition shall not be designated as experimental (with prefix "X") for more than five years. During the period that an alloy is designated as experimental, the registrant shall confirm to the Technical Committee on Product Standards at intervals not exceeding two years the reason(s) experimental designation is still required.

Some of the registered alloys may be the subject of patent or patent applications, and their listing herein is not to be construed in any way as the granting of a license under such patent rights.

CHEMICAL COMPOSITION LIMITS^{1,2}

Only composition limits which are identical to those listed herein or are registered with The Aluminum Association should be designated as "AA" alloys.

REGISTERED ALLOYS IN THE FORM OF xxx.0 CASTINGS, xxx.1 INGOT AND xxx.2 INGOT.

DESIGNATION		DATE REGISTERED	PRO- DUCTS ⁵	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Sn	OTHERS ³¹		ALUMINUM
AA No.	FORMER													Each	Total ³	
100.1*		1970-06-30	Ingot	0.15	0.6-0.8	0.10	— ²⁰	—	— ²⁰	—	0.05	— ²⁰	—	²⁰ 0.03	0.10	99.00 ^d
130.1*		1970-06-30	Ingot	— ¹⁹	— ¹⁹	0.10	— ²⁰	—	— ²⁰	—	0.05	— ²⁰	—	²⁰ 0.03	0.10	99.30 ^d
150.1*		1970-06-30	Ingot	— ²¹	— ²¹	0.05	— ²⁰	—	— ²⁰	—	0.05	— ²⁰	—	²⁰ 0.03	0.10	99.50 ^d
160.1		1976-01-28	Ingot	0.10 ²¹	0.25 ²¹	—	— ²⁰	—	— ²⁰	—	0.05	— ²⁰	—	²⁰ 0.03	0.10	99.60 ^d
170.1*		1970-06-30	Ingot	— ²²	— ²²	—	— ²⁰	—	— ²⁰	—	0.05	— ²⁰	—	²⁰ 0.03	0.10	99.70 ^d
201.0		1968-04-17	S	0.10	0.15	4.0-5.2	0.20-0.50	0.15-0.55	—	—	—	0.15-0.35	—	⁷ 0.05	0.10	Remainder
201.2		1968-04-17	Ingot	0.10	0.10	4.0-5.2	0.20-0.50	0.20-0.55	—	—	—	0.15-0.35	—	⁷ 0.05	0.10	Remainder
A201.0		1970-10-09	S	0.05	0.10	4.0-5.0	0.20-0.40	0.15-0.35	—	—	—	0.15-0.35	—	⁷ 0.03	0.10	Remainder
A201.1	A201.2	1970-10-09	Ingot	0.05	0.07	4.0-5.0	0.20-0.40	0.20-0.35	—	—	—	0.15-0.35	—	⁷ 0.03	0.10	Remainder
B201.0		1984-09-21	S	0.05	0.05	4.5-5.0	0.20-0.50	0.25-0.35	—	—	—	0.15-0.35	—	³⁰ 0.05	0.15	Remainder
203.0	Hiduminium 350	1972-12-02	S	0.30	0.50	4.5-5.5	0.20-0.30	0.10	—	1.3-1.7	0.10	0.15-0.25	—	²³ 0.05	0.20	Remainder
203.2	Hiduminium 350	1972-12-02	Ingot	0.20	0.35	4.8-5.2	0.20-0.30	0.10	—	1.3-1.7	0.10	0.15-0.25	—	²³ 0.05	0.20	Remainder
204.0	A-U5GT	1974-10-01	S&P	0.20	0.35	4.2-5.0	0.10	0.15-0.35	—	0.05	0.10	0.15-0.30	0.05	— 0.05	0.15	Remainder
204.2	A-U5GT	1974-10-01	Ingot	0.15	0.10-0.20	4.2-4.9	0.05	0.20-0.35	—	0.03	0.05	0.15-0.25	0.05	— 0.05	0.15	Remainder
206.0		1976-04-23	S&P	0.10	0.15	4.2-5.0	0.20-0.50	0.15-0.35	—	0.05	0.10	0.15-0.30	0.05	— 0.05	0.15	Remainder
206.2		1976-04-23	Ingot	0.10	0.10	4.2-5.0	0.20-0.50	0.20-0.35	—	0.03	0.05	0.15-0.25	0.05	— 0.05	0.15	Remainder
A206.0		1976-04-23	S&P	0.05	0.10	4.2-5.0	0.20-0.50	0.15-0.35	—	0.05	0.10	0.15-0.30	0.05	— 0.05	0.15	Remainder
A206.2		1976-04-23	Ingot	0.05	0.07	4.2-5.0	0.20-0.50	0.20-0.35	—	0.03	0.05	0.15-0.25	0.05	— 0.05	0.15	Remainder
B206.0		2003-07-07	S&P	0.05	0.10	4.2-5.0	0.20-0.50	0.15-0.35	—	0.05	0.10	0.10	0.05	— 0.05	0.15	Remainder
B206.2		2003-07-07	Ingot	0.05	0.07	4.2-5.0	0.20-0.50	0.20-0.35	—	0.03	0.05	0.05	0.05	— 0.05	0.15	Remainder
240.0	A240.0, A140		S	0.50	0.50	7.0-9.0	0.30-0.7	5.5-6.5	—	0.30-0.7	0.10	0.20	—	— 0.05	0.15	Remainder
240.1	A240.1, A140		Ingot	0.50	0.40	7.0-9.0	0.30-0.7	5.6-6.5	—	0.30-0.7	0.10	0.20	—	— 0.05	0.15	Remainder
242.0	142		S&P	0.7	1.0	3.5-4.5	0.35	1.2-1.8	0.25	1.7-2.3	0.35	0.25	—	— 0.05	0.15	Remainder
242.1	142		Ingot	0.7	0.8	3.5-4.5	0.35	1.3-1.8	0.25	1.7-2.3	0.35	0.25	—	— 0.05	0.15	Remainder
242.2	142		Ingot	0.6	0.6	3.5-4.5	0.10	1.3-1.8	—	1.7-2.3	0.10	0.20	—	— 0.05	0.15	Remainder
A242.0	A142		S	0.6	0.8	3.7-4.5	0.10	1.2-1.7	0.15-0.25	1.8-2.3	0.10	0.07-0.20	—	— 0.05	0.15	Remainder
A242.1	A142		Ingot	0.6	0.6	3.7-4.5	0.10	1.3-1.7	0.15-0.25	1.8-2.3	0.10	0.07-0.20	—	— 0.05	0.15	Remainder
A242.2	A142		Ingot	0.35	0.6	3.7-4.5	0.10	1.3-1.7	0.15-0.25	1.8-2.3	0.10	0.07-0.20	—	— 0.05	0.15	Remainder

See footnotes on pages 10-11

CHEMICAL COMPOSITION LIMITS^{1,2} (continued)

Only composition limits which are identical to those listed herein or are registered with The Aluminum Association should be designated as "AA" alloys.

REGISTERED ALLOYS IN THE FORM OF xxx.0 CASTINGS, xxx.1 INGOT AND xxx.2 INGOT.

DESIGNATION		DATE	PRO- DUCTS ⁵	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Sn	OTHERS ³¹		ALUMINUM	
AA No.	FORMER													REGISTERED	Each		Total ³
295.0	195		S	0.7-1.5	1.0	4.0-5.0	0.35	0.03	—	—	0.35	0.25	—	—	0.05	0.15	Remainder
295.1	195		Ingot	0.7-1.5	0.8	4.0-5.0	0.35	0.03	—	—	0.35	0.25	—	—	0.05	0.15	Remainder
295.2	195		Ingot	0.7-1.2	0.8	4.0-5.0	0.30	0.03	—	—	0.30	0.20	—	—	0.05	0.15	Remainder
296.0	B295.0, B195		P	2.0-3.0	1.2	4.0-5.0	0.35	0.05	—	0.35	0.50	0.25	—	—	—	0.35	Remainder
296.1	B295.1, B195		Ingot	2.0-3.0	0.9	4.0-5.0	0.35	0.05	—	0.35	0.50	0.25	—	—	—	0.35	Remainder
296.2	B295.2, B195		Ingot	2.0-3.0	0.8	4.0-5.0	0.30	0.03	—	—	0.30	0.20	—	—	0.05	0.15	Remainder
301.0		1994-08-02		9.5-10.5	0.8-1.5	3.0-3.5	0.50-0.8	0.25-0.50	—	1.0-1.5	0.05	0.20	—	—	0.03	0.10	Remainder
301.1 ³³		1994-08-02	Ingot ³²	9.5-10.5	0.8-1.2	3.0-3.5	0.50-0.8	0.30-0.50	—	1.0-1.5	0.05	0.20	—	—	0.03	0.10	Remainder
302.0		1994-08-02		9.5-10.5	0.25	2.8-3.2	—	0.7-1.2	—	1.0-1.5	0.05	0.20	—	—	0.03	0.10	Remainder
302.1 ³³		1994-08-02	Ingot ³²	9.5-10.5	0.20	2.8-3.2	—	0.8-1.2	—	1.0-1.5	0.05	0.20	—	—	0.03	0.10	Remainder
303.0		1994-08-02		9.5-10.5	0.8-1.5	0.20	0.50-0.8	0.45-0.7	—	—	0.05	0.20	—	—	0.03	0.10	Remainder
303.1 ³³		1994-08-02	Ingot ³²	9.5-10.5	0.8-1.2	0.20	0.50-0.8	0.50-0.7	—	—	0.05	0.20	—	—	0.03	0.10	Remainder
308.0	A108		S&P	5.0-6.0	1.0	4.0-5.0	0.50	0.10	—	—	1.0	0.25	—	—	—	0.50	Remainder
308.1 ³³	A108		Ingot	5.0-6.0	0.8	4.0-5.0	0.50	0.10	—	—	1.0	0.25	—	—	—	0.50	Remainder
308.2 ³³	A108		Ingot	5.0-6.0	0.8	4.0-5.0	0.30	0.10	—	—	0.50	0.20	—	—	—	0.50	Remainder
318.0		1991-01-29	S&P	5.5-6.5	1.0	3.0-4.0	0.50	0.10-0.6	—	0.35	1.0	0.25	—	—	—	0.50	Remainder
318.1 ³³		1991-01-29	Ingot	5.5-6.5	0.8	3.0-4.0	0.50	0.15-0.6	—	0.35	0.9	0.25	—	—	—	0.50	Remainder
319.0	319, All Cast		S&P	5.5-6.5	1.0	3.0-4.0	0.50	0.10	—	0.35	1.0	0.25	—	—	—	0.50	Remainder
319.1 ³³	319, All Cast		Ingot	5.5-6.5	0.8	3.0-4.0	0.50	0.10	—	0.35	1.0	0.25	—	—	—	0.50	Remainder
319.2 ³³	319, All Cast		Ingot	5.5-6.5	0.6	3.0-4.0	0.10	0.10	—	0.10	0.10	0.20	—	—	—	0.20	Remainder
A319.0		1970-08-28	S&P	5.5-6.5	1.0	3.0-4.0	0.50	0.10	—	0.35	3.0	0.25	—	—	—	0.50	Remainder
A319.1 ³³		1970-08-28	Ingot	5.5-6.5	0.8	3.0-4.0	0.50	0.10	—	0.35	3.0	0.25	—	—	—	0.50	Remainder
B319.0	SAE 329	1981-10-30	S&P	5.5-6.5	1.2	3.0-4.0	0.8	0.10-0.50	—	0.50	1.0	0.25	—	—	—	0.50	Remainder
B319.1 ³³		1981-10-30	Ingot	5.5-6.5	0.9	3.0-4.0	0.8	0.15-0.50	—	0.50	1.0	0.25	—	—	—	0.50	Remainder
320.0		1982-04-08	S&P	5.0-8.0	1.2	2.0-4.0	0.8	0.05-0.6	—	0.35	3.0	0.25	—	—	—	0.50	Remainder
320.1 ³³		1982-04-08	Ingot	5.0-8.0	0.9	2.0-4.0	0.8	0.10-0.6	—	0.35	3.0	0.25	—	—	—	0.50	Remainder
328.0	Red X-8	2003-07-09 ³⁸	S	7.5-8.5	1.0	1.0-2.0	0.20-0.6	0.20-0.6	0.35	0.25	1.5	0.25	—	—	—	0.50	Remainder
328.1 ³³	Red X-8	2003-07-09 ³⁸	Ingot	7.5-8.5	0.8	1.0-2.0	0.20-0.6	0.25-0.6	0.35	0.25	1.5	0.25	—	—	—	0.50	Remainder
332.0	F332.0, F132		P	8.5-10.5	1.2	2.0-4.0	0.50	0.50-1.5	—	0.50	1.0	0.25	—	—	—	0.50	Remainder
332.1 ³³	F332.1, F132		Ingot	8.5-10.5	0.9	2.0-4.0	0.50	0.6-1.5	—	0.50	1.0	0.25	—	—	—	0.50	Remainder
332.2 ³³	F332.2, F132		Ingot	8.5-10.0	0.6	2.0-4.0	0.10	0.9-1.3	—	0.10	0.10	0.20	—	—	—	0.30	Remainder

See footnotes on pages 10-11