
Standard Specification for Mineral Filler for Asphalt Mixtures

AASHTO Designation: M 17-11 (2023)

Technically Revised: 2011

Reviewed but Not Updated: 2023

Editorially Revised: 2023

Technical Subcommittee: 2c, Asphalt–Aggregate Mixtures

ASTM Designation: D242/D242M-19



**American Association of State Highway and Transportation Officials
555 12th Street NW, Suite 1000
Washington, D.C. 20004**

Standard Specification for

Mineral Filler for Asphalt Mixtures

AASHTO Designation: M 17-11 (2023)

AASHTO

Technically Revised: 2011

Reviewed but Not Updated: 2023

Editorially Revised: 2023

Technical Subcommittee: 2c, Asphalt–Aggregate Mixtures

ASTM Designation: D242/D242M-19

AASHTO M 17-11 (2019) is identical to ASTM D242/D242M-19, except for the following provisions:

1. All references to the ASTM standards contained in ASTM D242/D242M-19, listed in the following table, shall be replaced with the corresponding AASHTO standard:

<i>Referenced Standards</i>	
ASTM	AASHTO
C183/C183M	R 71
D546	T 37
D4318	T 90

2. Add a new Section 5.3 after Section 5.2 that contains the following:
Fly ash used as a mineral filler shall have a maximum loss on ignition of 12 percent.
3. Add a new Section 6.5 after Section 6.4 that contains the following:
Determine the loss on ignition of fly ash according to ASTM C311/C311M.