
Standard Practice for Ultrathin Bonded Wearing Course Design

AASHTO Designation: PP 100-20¹

**Technical Subcommittee: 5b, Bridge and
Pavement Preservation**

Release: Group 1 (April)



**American Association of State Highway and Transportation Officials
555 12th Street NW, Suite 1000
Washington, DC 20004**

Ultrathin Bonded Wearing Course Design

AASHTO Designation: PP 100-20¹



Technical Subcommittee: 5b, Bridge and
Pavement Preservation

Release: Group 1 (April)

1. SCOPE

- 1.1. This standard practice for ultrathin bonded wearing course includes a mix design evaluation for the asphalt surface mixture, usually $\frac{1}{2}$ to 1 in. (12.5 to 25.4 mm) thick, to determine the proportions of polymer-modified emulsified asphalt that is used as the tack coat, PG binder, mineral aggregate, mineral filler, and additives to produce an ultrathin bonded wearing course job-mix formula.

2. REFERENCED STANDARDS

- 2.1. *AASHTO Standards:*
- [M 295](#), Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
 - [M 303](#), Lime for Asphalt Mixtures
 - [M 316](#), Polymer-Modified Emulsified Asphalt
 - [M 320](#), Performance-Graded Asphalt Binder
 - [M 332](#), Performance-Graded Asphalt Binder Using Multiple Stress Creep Recovery (MSCR) Test
 - [MP 44](#), Materials for Ultrathin Bonded Wearing Course
 - [R 30](#), Mixture Conditioning of Hot Mix Asphalt (HMA)
 - [T 59](#), Emulsified Asphalts
 - [T 209](#), Theoretical Maximum Specific Gravity (G_{mm}) and Density of Asphalt Mixtures
 - [T 269](#), Percent Air Voids in Compacted Dense and Open Asphalt Mixtures
 - [T 283](#), Resistance of Compacted Asphalt Mixtures to Moisture-Induced Damage
 - [T 305](#), Determination of Draindown Characteristics in Uncompacted Asphalt Mixtures
 - [T 312](#), Preparing and Determining the Density of Asphalt Mixture Specimens by Means of the Superpave Gyratory Compactor

3. SIGNIFICANCE AND USE

- 3.1. The procedure described in this standard practice is used to produce an ultrathin bonded wearing course. The materials used in the design of ultrathin bonded wearing course can be found in [MP 44](#).