
Standard Method of Test for Determining Water-Soluble Sulfate Ion Content in Soil

AASHTO Designation: T 290-95 (2024)

Technically Revised: 1995

Reviewed but Not Updated: 2024

Editorially Revised: 2021

Technical Subcommittee: 1a, Soil and Unbound Recycled Materials



**American Association of State Highway and Transportation Officials
555 12th Street NW, Suite 1000
Washington, DC 20004**

Standard Method of Test for

Determining Water-Soluble Sulfate Ion Content in Soil

AASHTO Designation: T 290-95 (2024)



Technically Revised: 1995

Reviewed but Not Updated: 2024

Editorially Revised: 2021

Technical Subcommittee: 1a, Soil and Unbound Recycled Materials

1.

SCOPE

1.1. This test method covers the determination of the water-soluble sulfate ion content in soil. This standard is divided into two parts. The first part specifies the procedure for sampling and preparing the sample to size for testing. The second part delineates two test procedures (Methods A or B) for the determination of the sulfate ion content in soils. The selection of the method is dependent on the concentration of sulfate ion and the accuracy desired. Two methods are given as follows:

	Section
Method A: (Gravimetric Method)	(1 to 7) and (8 to 16)
Method B: (Turbidimetric Method)	(1 to 7) and (17 to 26)

1.2. Method A is a primary measure of sulfate ion. Method B is less time-consuming, but often more liable to interference than Method A. It is particularly useful in the lower sulfate range and can be used as a screening test. This method is directly applicable over the range of 10 to 100 mg/kg.

1.3. The values stated in SI units are to be regarded as the standard.

1.4. *The quality of the results produced by this standard is dependent on the competence of the personnel performing the procedure and the capability, calibration, and maintenance of the equipment used. Agencies that meet the criteria of R 18 are generally considered capable of competent and objective testing/sampling/inspection/etc. Users of this standard are cautioned that compliance with R 18 alone does not completely assure reliable results. Reliable results depend on many factors; following the suggestions of R 18 or some similar acceptable guideline provides a means of evaluating and controlling some of those factors.*

2.

REFERENCED DOCUMENTS

- 2.1. AASHTO Standards:
- M 231, Weighing Devices Used in the Testing of Materials
 - R 18, Establishing and Implementing a Quality Management System for Construction Materials Testing Laboratories
 - R 90, Sampling Aggregate Products



2.2.

ASTM Standards:

- D859, Standard Test Method for Silica in Water
- D1129, Standard Terminology Relating to Water
- D1193, Standard Specification for Reagent Water
- E11, Standard Specification for Woven Wire Test Sieve Cloth and Test Sieves
- E29, Standard Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E60, Standard Practice for Analysis of Metals, Ores, and Related Materials by Spectrophotometry
- E275, Standard Practice for Describing and Measuring Performance of Ultraviolet and Visible Spectrophotometers

3. TERMINOLOGY

- 3.1. For definitions of terms used in these methods, refer to ASTM D1129.

PART I—INITIAL PREPARATION OF TEST SAMPLES

4. SCOPE

- 4.1. This method covers the dry preparation of soil and soil-aggregate samples, as received from the field, for use in determining the sulfate ion content in soils.
- 4.2. The following applies to all specified limits in this standard: For the purpose of determining conformance with these specifications, an observed value or calculated value shall be rounded off “to the nearest unit” in the last right-hand place of figures used in expressing the limiting value, in accordance with ASTM E29.

5. APPARATUS

- 5.1. The balance shall have sufficient capacity, be readable to 0.1 percent of the sample mass or better, and conform to the requirements of M 231.
- 5.2. *Drying Apparatus*—Any suitable device capable of drying samples at a temperature not exceeding 60°C (140°F).
- 5.3. *Sieves*—A series of sieves of the following sizes: 6.3 mm ($\frac{1}{4}$ in.), 4.75 mm (No. 4), 2.00 mm (No. 10), and a pan. The sieve shall conform to E11, Wire-Cloth Sieves for Testing Purposes (Note 1).
Note 1—The sieve sizes that have an opening size of 6.3 mm ($\frac{1}{4}$ in.) or larger shall conform to the requirements specified in E11, excluding Column No. 7. This exclusion permits the use of heavier screens in nonstandard frames that are larger than the 203.2-mm (8-in.) round frames.
- 5.4. *Pulverizing Apparatus*—Either a mortar and rubber-covered pestle or any device suitable for breaking up the aggregations of soil particles without reducing the size of the individual grains (Note 2).
Note 2—Other types of apparatus are satisfactory if the aggregations of soil particles are broken up without reducing the size of the individual grains.