



Association of Textile, Apparel & Materials Professionals

AATCC takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this test method. Users of this test method are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This test method is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reaffirmed or withdrawn. Your comments are invited either for revision of this test method or for additional procedures and should be addressed to the AATCC Technical Center. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing, you should make your views known to Diana A. Wyman, Technical Director, at the address shown below.

This test method is copyrighted by AATCC, PO Box 12215, Research Triangle Park, NC 27709 USA. Individual reprints (single or multiple copies) of this method may be obtained by contacting AATCC at the above address or tel: 919-549-3526; fax: 919-549-8933, or e-mail: orders@aatcc.org.

AATCC License Agreement: This test method is copyrighted by the American Association of Textile Chemists and Colorists (AATCC), PO Box 12215, 1 Davis Drive, Research Triangle Park, NC USA. All rights reserved.

AATCC grants you a license as follows: The right to download one electronic file of this AATCC test method for temporary storage on one computer for purposes of viewing, and/or printing one copy of the AATCC test method for individual use. Neither the electronic file nor the hard copy print may be reproduced in any way. In addition, the electronic file may not be distributed elsewhere over computer networks or otherwise. The hard copy print may only be distributed to other employees for their internal use within your organization.

This test method is not for resale.

Antibacterial Activity Assessment of Textile Materials: Parallel Streak Method

Developed in 1976 by AATCC Committee RA31; reaffirmed 1977, 1982, 1998; editorially revised 1980, 1982, 1983, 1986, 2010; revised 1987, 1988 (with title change), 1993, 2011; editorially revised and reaffirmed 2004.

Foreword

The Parallel Streak Method has filled a need for a relatively quick and easily executed qualitative method to determine antibacterial activity of diffusible antimicrobial agents on treated textile materials.

AATCC Method 100, Antibacterial Finishes on Textile Materials, Assessment of, is a quantitative procedure which is adequately sensitive but is cumbersome and time consuming for routine quality control and screening tests. Therefore, when the intent is to demonstrate bacteriostatic activity by the diffusion of the antibacterial agent through agar, AATCC Method 147 fulfills this need. In the Parallel Streak Method, the agar surface is inoculated making it easier to distinguish between the test organism and contaminant organisms which may be present on the unsterilized specimen. The Parallel Streak Method has proven effective over a number of years of use in providing evidence of antibacterial activity against both Gram positive and Gram negative bacteria.

1. Purpose and Scope

1.1 The objective is to detect bacteriostatic activity on textile materials. The results of using this procedure have been demonstrated by Committee RA31 to be reproducible by various laboratories working with materials containing residual amounts of antibacterial agents (as determined by chemical assay) after multiple standard washings. The method is useful for obtaining a rough estimate of activity in that the growth of the inoculum organism decreases from one end of each streak to the other and from one streak to the next resulting in increasing degrees of sensitivity. The size of the zone of inhibition and the narrowing of the streaks caused by the presence of the antibacterial agent permit an estimate of the residual antibacterial activity after multiple washings.

2. Principle

2.1 Specimens of the test material, in-

cluding corresponding untreated controls of the same material, are placed in intimate contact with the agar surface which has been previously streaked with an inoculum of a test bacterium. After incubation, a clear area of interrupted growth underneath and along the sides of the test material indicates antibacterial activity of the specimen. A standard strain of bacteria is used which is specific to the requirements of the material under test. If no other bacterial species is specified, *Staphylococcus aureus* may be used as a representative Gram positive organism. Other recommended strains are listed below in Section 6.

3. Terminology

3.1 **activity**, n.—of an antibacterial agent, a measure of effectiveness of the agent.

3.2 **antibacterial agent**, n.—in textiles, any chemical which kills bacteria (bactericide) or interferes with the multiplication, growth or activity of bacteria (bacteriostat).

3.3 **zone of inhibition**, n.—clear area of no growth of a microorganism, cultured onto the surface of an agar growth medium, in proximity to the borders of a specimen placed in direct contact with this agar surface.

NOTE: A zone of inhibition occurs as a result of the diffusion of an antimicrobial agent from the specimen.

4. Safety Precautions

NOTE: These safety precautions are for information purposes only. The precautions are ancillary to the testing procedures and are not intended to be all inclusive. It is the user's responsibility to use safe and proper techniques in handling materials in this test method. Manufacturers MUST be consulted for specific details such as material safety data sheets and other manufacturer's recommendations. All OSHA standards and rules must also be consulted and followed.

4.1 This test should be performed only by trained personnel. The U.S. Department of Health and Human services publication *Biosafety in Microbiological and Biomedical Laboratories* should be consulted (see 12.1).

4.2 CAUTION: Some of the bacteria used in this test are pathogenic; i.e., capable of infecting humans and producing disease. Therefore, every necessary and

reasonable precaution must be taken to eliminate this risk to the laboratory personnel and to personnel in the associated environment. Wear protective clothing and respiratory protection that prevents penetration by the bacteria.

4.3 Good laboratory practices should be followed. Wear safety glasses in all laboratory areas.

4.4 All chemicals should be handled with care.

4.5 An eyewash/safety shower should be located nearby for emergency use.

4.6 Sterilize all contaminated samples and test materials prior to disposal.

4.7 Exposure to chemicals used in this procedure must be controlled at or below levels set by government authorities (e.g., Occupational Safety and Health Administrations [OSHA] permissible exposure limits [PEL] as found in 29 CFR 1910.1000; see web site: www.osha.gov for latest version). In addition, the American Conference of Governmental Industrial Hygienists (ACGIH) Threshold Limit Values (TLVs) comprised of time weighted averages (TLV-TWA), short term exposure limits (TLV-STEL) and ceiling limits (TLV-C) are recommended as a general guide for air contaminant exposure which should be met (see 12.2).

5. Uses and Limitations

5.1 The method is not suitable for materials which tend to encapsulate and prevent the diffusion of the antibacterial agent or contain antibacterial-neutralizing substances.

6. Test Organisms

6.1 Test bacteria:

6.1.1 *Staphylococcus aureus*, ATCC 6538, CIP 4.83, DSM 799, NBRC 13276, NCIMB 9518 or equivalent strain (see 12.3).

6.1.2 *Klebsiella pneumoniae*, ATCC 4352, CIP 104216, DSM 789, NBRC 13277, NCIMB 10341 or equivalent strain (see 12.3).

6.1.3 Other suitable species can also be used depending on the intended end-use of the test sample.

6.2 Maintain test organisms according to good laboratory practice standard (see 12.4).

6.3 Whenever possible, test the activity of the culture to be used against a standard control specimen (a positive control) with known antibacterial activity.