Association of Textile, Apparel & Materials Professionals

AATCC takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this test method. Users of this test method are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This test method is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reaffirmed or withdrawn. Your comments are invited either for revision of this test method or for additional procedures and should be addressed to the AATCC Technical Center. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing, you should make your views known to Diana A. Wyman, Technical Director, at the address shown below.

This test method is copyrighted by AATCC, PO Box 12215, Research Triangle Park, NC 27709 USA. Individual reprints (single or multiple copies) of this method may be obtained by contacting AATCC at the above address or tel: 919-549-3526; fax: 919-549-8933, or e-mail: orders@aatcc.org.

AATCC License Agreement: This test method is copyrighted by the American Association of Textile Chemists and Colorists (AATCC), PO Box 12215, 1 Davis Drive, Research Triangle Park, NC USA. All rights reserved.

AATCC grants you a license as follows: The right to download one electronic file of this AATCC test method for temporary storage on one computer for purposes of viewing, and/or printing one copy of the AATCC test method for individual use. Neither the electronic file nor the hard copy print may be reproduced in any way. In addition, the electronic file may not be distributed elsewhere over computer networks or otherwise. The hard copy print may only be distributed to other employees for their internal use within your organization.

This test method is not for resale.

Documents
Document Sharing Hub

Copyright The American Association of Textile Chemists and Colorists
Provided by IHS Markit under license with AATCC
No reproduction or networking permitted without license from IHS
Full document details: AATCC 199 2018

Licensee=Hong Kong Polytechnic University/9976803100, User=ERIKSSON, Anna Pernil
Not for Resale, 02/28/2020 02:13:32 MST

Test Method for Drying Time of Textiles: Moisture Analyzer

Developed in 2011 by AATCC Committee RA63; reaffirmed 2018; revised 2012, 2013; editorially revised 2017, 2019.

Foreword

Historically, the textile industry has utilized many different test procedures for determining the drying characteristics of textile fabrics, whether those characteristics are drying rate, time or some other drying parameter. Within the last decade, the industry has developed new technologies that have resulted in an improvement in these characteristics, as one of many attributes associated with the use of the term "moisture management." Many interested groups (textile manufacturers, chemical suppliers, retailers, as well as independent testing laboratories) participated in the effort to develop and publish standard test methods to measure the drying characteristics of fabrics. Unofficial techniques for determining the drying properties of textile fabrics were published in the 2008 AATCC/ASTM International's *Moisture Management Technical Supplement: Applicable to Apparel, Linens and Soft Goods*. This test method formalizes an additional technique that has been used by several companies.

1. Purpose and Scope

1.1 This test method is intended to evaluate the drying time of knit, woven or nonwoven fabrics at an elevated temperature using a gravimetric moisture analyzer. By performing the test at nonstandard textile testing conditions, it is possible to simulate drying at body temperature or to perform testing at temperatures that simulate conditions of use.

2. Principle

2.1 Water is applied to the test specimen and then dried at a pre-selected temperature (37° ± 2°C [99 ± 4°F]); if an alternative temperature is used it should be reported, in an automated moisture analyzer. The time required for a test specimen to reach a designated endpoint is measured and recorded as the drying time.

3. Terminology

3.1 **drying rate,** n.—the change in volume per unit time of a liquid that evaporates from a textile.

NOTE: Drying rate is dependent upon textile construction, fiber content, apparel construction, finishes, the atmosphere in which the test is performed, and the volume challenge of the liquid.

3.2 **drying time,** n.—the time it takes for a specified amount of liquid to evaporate from a textile under controlled testing conditions.

NOTE: In this test method the amount of water is determined in a preparatory step so that the specimen is wet-out to a given level. The testing conditions are controlled by the analyzer.

3.3 **endpoint,** n.—the point of termination of a drying test that is either to the original dry weight of a specimen or some other agreed value such as dry weight +4.0% moisture content.

3.4 **moisture retention,** adj.—*for this test method*, the percent moisture retention of the specimen after being submerged in deionized water for 1 min, and hanging vertically for 5 min in a controlled environment (see 9.3.2 and formula 1).

3.5 **test side,** n.—the side, either the face or back of a specimen, which is uppermost when placed on the moisture balance analyzer support platform; the side onto which the test volume of water is applied.

3.6 **weight loss,** n.—the difference between the saturated weight of a specimen and the weight after drying.

3.7 **wet pick-up,** n.—*in textile processing*, the amount of liquid, and material carried by the liquid, applied to a textile.

4. Safety Precautions

NOTE: These safety precautions are for information purposes only. The precautions are ancillary to the testing procedures and are not intended to be all inclusive. It is the users' responsibility to use safe and proper techniques in handling materials in this test method. Manufacturers MUST be consulted for specific details such as material safety data sheets and other manufacturers' recommendations. All OSHA standards and rules must also be consulted and followed.

4.1 Good laboratory practices should be followed. Wear safety glasses in all laboratory areas.

5. Uses and Limitations

5.1 The drying of a fabric may be influenced by fiber content, fabric construction (e.g., thickness or raised surface, such as fleece), mechanical or chemical processing or a combination of these aspects.

5.2 Other factors that may influence drying include the temperature and humidity conditions of the test and the amount of liquid to be dried. This test method is performed in non-standard textile testing conditions. Since this test can be performed at various temperature settings of the moisture analyzer, test temperatures can be selected to simulate the temperature of a human body at rest, during exercise, or when exposed to outdoor temperatures.

5.3 This method is based on the application of a controlled amount of water to test specimens, measurement of the drying rate of that application, and calculation of the moisture retention based on that application.

5.4 This method is limited to fabrics with at least one side that exhibits an absorbency time within 30 ± 2 s (see AATCC TM79, Test Method for Absorbency of Textiles). It is not applicable to fabrics that exhibit an absorbency of more than 30 s, as in such fabrics water would begin evaporating from the surface of the fabric as the temperature is being raised, thereby skewing the results.

5.5 One possible use of this method is to compare the moisture retention characteristics of untreated versus treated fabrics, or to compare the moisture retention characteristics of a textile material with or without an additive.

5.6 The results obtained by this test are not a measure of comfort which is beyond the scope of this method.

5.7 The relationship between drying time measured by this test and absorbency has not been defined. Although TM79 is used in the preparatory steps to determine which side of a fabric should be used in testing, this test does not measure absorbency.

6. Apparatus and Materials

6.1 Moisture analyzer with a ceramic heating element and accurate to at least 0.001 g (see 14.1).

6.2 Deionized water.

6.3 Vertical specimen stand. The stand should have a horizontal hanger of suitable size to hang the specimen using binder clips. (see Fig. 2).

6.4 Tweezers.

6.5 400 mL beaker.

6.6 Wire screen—standard 0.25 × 0.25 in. mesh (see 14.2).

6.7 Specimen support platform (see

Copyright The American Association of Textile Chemists and Colorists
Provided by IHS Markit under license with AATCC
No reproduction or networking permitted without license from IHS
Full document details: AATCC 199 2018
Copyright © 2019 American Association of Textile Chemists and Colorists
Licensee=Hong Kong Polytechnic University/9970803100, User=ERIKSSON, Anna Pernil
Not for Resale, 02/28/2020 02:13:32 MST
Documents
Document Viewing Hub