Association of Textile, Apparel & Materials Professionals

AATCC takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this test method. Users of this test method are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This test method is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reaffirmed or withdrawn. Your comments are invited either for revision of this test method or for additional procedures and should be addressed to the AATCC Technical Center. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing, you should make your views known to Diana A. Wyman, Technical Director, at the address shown below.

This test method is copyrighted by AATCC, PO Box 12215, Research Triangle Park, NC 27709 USA. Individual reprints (single or multiple copies) of this method may be obtained by contacting AATCC at the above address or tel: 919-549-3526; fax: 919-549-8933, or e-mail: orders@aatcc.org.

AATCC License Agreement: This test method is copyrighted by the American Association of Textile Chemists and Colorists (AATCC), PO Box 12215, 1 Davis Drive, Research Triangle Park, NC USA. All rights reserved.

AATCC grants you a license as follows: The right to download one electronic file of this AATCC test method for temporary storage on one computer for purposes of viewing, and/or printing one copy of the AATCC test method for individual use. Neither the electronic file nor the hard copy print may be reproduced in any way. In addition, the electronic file may not be distributed elsewhere over computer networks or otherwise. The hard copy print may only be distributed to other employees for their internal use within your organization.

This test method is not for resale.

Documents
Document Sharing Hub

Copyright The American Association of Textile Chemists and Colorists
Provided by IHS Markit under license with AATCC
No reproduction or networking permitted without license from IHS
Full document details: AATCC 84 2018

Licensee=Hong Kong Polytechnic University/9976803100, User=ERIKSSON, Anna Pernil
Not for Resale, 03/03/2020 11:44:35 MST

Test Method for Electrical Resistance of Yarns

Developed in 1955 by AATCC Committee RA32; reaffirmed 1960, 1969, 1973, 1977, 1989, 2005, 2011, 2018; editorially revised 1974, 1984, 1985, 1997, 2008, 2019; revised 1982, 2000 (with title change); editorially revised and reaffirmed 1987, 1995.

1. Purpose and Scope

1.1 The purpose of this method is to determine the electrical resistance of any textile yarns containing natural or man-made fibers. The tendency of a textile yarn to accumulate electrical charges may depend upon the electrical resistance of the yarn. Due to the mechanism of conductance, this method is not applicable to yarns containing randomly situated stainless steel or other highly conductive fibers (refer to AATCC TM76, Test Method for Electrical Surface Resistivity of Fabrics).

2. Principle

2.1 Specimens of yarn are conditioned at specified relative humidity and temperature. The electrical resistance of the yarn held between two electrodes is measured by the use of an electrical resistance meter.

3. Terminology

3.1 **electrical resistance,** n.—the physical property of a material which is a measure of the ability of electrons to flow through it when a voltage is applied across two points on the material (resistance [in ohms] equal voltage [in volts] divided by current flow [in amperes]).

NOTE: This test method measures the electrical resistance of a material between two electrodes, and the results are expressed as resistance per unit of length per yarn strand, ohms per 10 mm.

4. Safety Precautions

NOTE: These safety precautions are for information purposes only. The precautions are ancillary to the testing procedures and are not intended to be all inclusive. It is the user's responsibility to use safe and proper techniques in handling materials in this test method. Manufacturers MUST be consulted for specific details such as material safety data sheets and other manufacturer's recommendations. All OSHA standard and rules must also be consulted and followed.

4.1 Good laboratory practices should be followed. Wear safety glasses in all laboratory areas.

4.2 The safety recommendations provided by the manufacturer of the radioactive bar should be followed.

4.3 The radioactive bar emits alpha radiation which is externally harmless to the human body. The radioactive isotope polonium 210 is toxic and precaution should be exercised to prevent ingestion or inhalation of the solid material. Do not take the radioactive bar apart or touch the radioactive strip under the grid. If the strip is touched or handled, wash hands thoroughly at once. Return the device to the manufacturer when it loses its effectiveness as a static eliminator or for disposal if use is to be discontinued. ***Do not discard as scrap***.

5. Apparatus and Materials

5.1 Electrical resistance meter equipped with either fixed position parallel plate electrodes or with separate variable position parallel plate electrodes (see 11.1). The concentric ring electrode system recommended for fabrics in AATCC TM76 is not suitable for use in testing yarns.

5.2 Conditioning and test chamber (see 11.2).

5.3 Standard resistors.

5.4 Radioactive bar.

6. Test Specimens

6.1 The length of the test specimens depends on whether or not the electrodes used are in fixed or variable position. If the electrode system used provides for variable distances between the parallel plates, run a preliminary test to determine what distance between the plates provides the greatest sensitivity for resistance measurements for the meter being used.

6.2 To determine the uniformity of resistance along a single end of yarn, make measurements on at least 10 specimens of single strands.

6.3 For predicting the properties of woven or knitted fabrics to be made from yarn tested by this method, measurements should be made on multiple strands.

6.4 Prepare a minimum of three test specimens for each test, with parallel strands having the same tension, evenly spaced, with no overlap or touching along their length. When a limited supply of yarn is available, each specimen should contain 10 strands. If an adequate supply of yarn is available, prepare larger specimens by winding 50-100 turns on a skein winder, then fastening the strands with adhesive tape to prepare lengths suitable for the electrode system used. The number of strands in the specimen must be the same for each test specimen for reproducible results. The resistance may also be dependent on the cross-section of the yarn bundle; thus, similarly manufactured fibers may yield yarns with different resistance, due to different numbers of filaments in the yarn bundle or different numbers of plies.

7. Procedure

7.1 Calibrate the electrical resistance meter according to the manufacturer's recommendations.

7.2 Condition the test specimens in a suitable testing chamber or conditioning room at the pre-selected relative humidity and temperature at which the electrical resistance of the yarn is to be measured.

7.2.1 For yarns which require antistatic treatments or whose electrostatic propensity is critical, measurements at 20% RH will be most meaningful. For special requirements other relative humidities may be used. For example, preconditioning at 21 ± 2°C (70 ± 5°F) is required for antistatic sheeting, film and textiles for use in hospital operating rooms (see 11.2.1). If it is necessary to measure electrical resistance under a broad range of conditions, additional tests may be run at 65% RH and at 24°C (75°F) or other relevant conditions (see 11.3).

7.2.2 Condition the specimens at 24°C and at the predetermined relative humidity for a minimum of 4 h or until equilibrium is attained. A sufficient indication of equilibrium is no significant change of resistance on further conditioning. A significant change may be considered ± 5% of the logarithm of the resistance (Log R).

7.3 Remove static charges from the surface of the yarn by passing a radioactive bar over both sides of the specimen.

7.4 Place the yarn test specimen in firm contact with the electrodes with the direction of the yarn perpendicular to the adjacent edges of the electrodes. Apply sufficient tension to hold the strands straight.

7.5 Measure the electrical resistance of the specimen according to the operating instructions and procedures for the particular resistance meter being used.

7.6 Allow the current to pass through the sample for a minimum period of 1 min and until a constant reading is obtained. The time to reach a constant read-

Copyright The American Association of Textile Chemists and Colorists
Provided by IHS Markit under license with AATCC
No reproduction or networking permitted without license from IHS
Full document details: AATCC 84 2018
Copyright © 2019 American Association of Textile Chemists and Colorists
Licensee=Hong Kong Polytechnic University/9970803100, User=ERIKSSON, Anna Pernil
Not for Resale, 03/03/2020 11:44:35 MST
IHS Markit Documents Standards Sourcing Hub