

Standard Specification for Cold Weather Concreting (306.1-90)

Reported by ACI Committee 306

Nicholas J. Carino, Chairman*

Fred Anderson*
Peter Antonich
George R. U. Burg
Oleh B. Ciuk
Douglas J. Haavik*
Gilbert Haddad
Jules Houde

David A. Hunt
Robert A. Kelsey
Albert W. Knott
Charles J. Korhonen
William Perenchio*
John M. Scanlon

Michael Shydrowski
Bruce A. Suprenant
J. Derle Thorpe
Valery Tokar
Lewis H. Tuthill*
Harold B. Wenzel
Arthur T. Winters

This Standard Specification gives requirements for cold weather concreting. It includes cold weather requirements for preparations prior to placement of concrete, and protection of concrete.

Keywords: accelerating admixtures; cold weather; compressive strength; construction; curing; formwork; freezing; heating; insulation; maturity; protection; temperature.

FOREWORD

F1. This foreword is included for explanatory purposes only; it does not form a part of the Standard Specification ACI 306.1.

F2. Standard Specifications ACI 306.1 is a Reference Standard which the Architect/Engineer may cite in the Project Specifications for any building project, together with supplementary requirements for the specific project.

F3. Each technical section of Standard Specification ACI 306.1 is written in the Three-Part Section Format of the Construction Specifications Institute, as adapted by ACI and modified to ACI requirements. The language is generally imperative and terse.

F4. Checklists do not form a part of Standard Specification ACI 306.1. Checklists are to assist the Architect/Engineer in properly choosing and specifying any necessary requirements for the Project Specifications.

PREFACE TO SPECIFICATION CHECKLIST

P1. Standard Specification ACI 306.1 is intended to be used by reference or incorporation in its entirety in the Project Specifications. Individual sections, articles, or paragraphs shall not be copied into the Project Specifications, since taking them out of context may change their meaning.

P2. If sections or parts of Standard Specification ACI 306.1 are edited into project specifications or any other document, they shall not be referred to as ACI Standards, since the Standard Specification has been altered.

P3. Building codes set minimum requirements necessary to protect the public. This Standard Specification may stipulate requirements more restrictive than the minimum. Adjustments to the needs of a particular project shall be made by the Architect/Engineer by reviewing each of the items in the Specification Checklist and then including the Architect/Engineer's decision on each item as a mandatory requirement in the Project Specifications.

P4. These mandatory requirements designate the specific qualities, procedures, materials, and performance criteria for which alternatives are permitted or for which provisions were not made in the Standard Specification. Exceptions to the Standard Specification shall be made in the Project Specifications, if required.

P5. A statement such as the following will serve to make Standard Specification ACI 306.1 a part of the Project Specifications.

Work on _____ shall conform to all requirements of ACI 306.1, Standard Specification for Cold Weather Concreting, published by the American Concrete Institute, Detroit, Michigan, except as modified by the requirements of these Contract Documents.

P6. The Standard Specification Checklist identifies Architect/Engineer choices and alternatives. The checklist identifies the sections, parts, and articles of the Standard Specification and the action required by the Architect/Engineer.

*Task force for revision.

Supersedes ACI 306.1-87. Revised by the Expedited Standardization Procedure, effective July 1, 1990. In 1990, the format was revised. The Foreword, Preface, and Specification Checklist were revised. Reference Standards were updated and the sections on Materials and Execution were rewritten and renumbered.

Copyright © 2002, American Concrete Institute. All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process or by any electronic or mechanical device, printed or written or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

SPECIFICATION CHECKLIST

M. MANDATORY REQUIREMENTS

Section/Part/Article of
ACI 306.1

Notes to the Architect/Engineer

1.4 Reference standards

Review applicability of the cited references and take exception if required

3.1 Preparation before concreting

If the temperature of massive embedments, such as heavy steel guide rails or channels and steel grate frames or ducts, is lower than 32 F, concrete cast around them will be damaged by freezing. Identify in the Contract Documents massive embedments which must be at a temperature above freezing prior to placement of concrete.

A frozen subgrade can lead to freezing of newly-placed concrete or foundation settlement upon subsequent thawing of the subgrade. Specify in the Contract Documents the depth to which frozen subgrade should be thawed prior to placement of concrete. Specify procedure to verify that subgrade has been thawed to specified depth.

3.2.2 Protection temperature

Specify the frequency for recording the temperature but do not use a frequency lower than twice per 24-hr period.

3.4.5 Protection for structural safety

Indicate in the Contract Documents the concrete strength required for each structural member before form removal or continued construction, or both.

O. OPTIONAL REQUIREMENTS

Section/Part/Article of
ACI 306.1

Notes to the Architect/Engineer

1.5.1 Detailed procedures

Indicate in the Contract Documents whether submittal, review, and acceptance of procedure is required. Designate degree of detail required in any submittal procedure.

3.3 Curing concrete

Strength gain may not continue after removal of the protection because of rapid drying in regions where there are periods of cold, dry, windy weather. Therefore, under these conditions, consideration should be given to extending the protection period in order to facilitate moist curing.

3.2.2 Protection temperature

Specify the minimum protection temperature if different than Column 2 of Table 3.2.1.

3.4.4 Protection against freezing

- 1 Any changes in the concrete mix proportions for reducing the duration of the protection period to prevent early freezing should be submitted for review or acceptance.
- 1 For certain structures, the protection period may be reduced if, after 24 hr of protection, the compressive strength of the in-place concrete is at least 500 psi. The requirements for these structures are that they do not require early strengths, will undergo little or no freezing and thawing during construction and in service, and have not been exposed to an external supply of moisture during the protection period.
- 1 The minimum protection temperature specified in Table 3.2.1 may be reduced provided that the protection period is extended until the compressive strength of the in-place concrete is at least 500 psi.
- 1 Note that a compressive strength of 500 psi is only adequate to protect the concrete against damage from one cycle of freezing and thawing.
- 1 The specified minimum protection periods are based on the assumption that additional curing will be specified and provided, as needed, prior to putting the structure into service. Longer protection periods may be specified to assure that desired properties are developed prior to removal of protection.

S. SUBMITTALS

Section/Part/Article of
ACI 306.1

Notes to the Architect/Engineer

1.5 Submittal of procedures

If required, indicate to whom submittals will be sent.

1.5.1 Detailed procedures

Minimum procedures for placement, curing and protection of the concrete may follow the recommendations in ACI 306R, "Cold Weather Concreting." The details should include, but not be limited to, the following:

- 1 Procedures for protecting the subgrade from frost and the accumulation of ice or snow on reinforcement or forms prior to placement.
- 1 Methods for temperature protection during placement.
- 1 Types of covering, insulation, housing, or heating to be provided.
- Curing methods to be used during and following the protection period.
- 1 Use of strength accelerating admixtures.
- 1 Methods for verification of in-place strength.
- Procedures for measuring and recording concrete temperatures.
- 1 Procedures for preventing drying during dry, windy conditions.

Require detailed procedures for those items of concern for the Work.

