

3678—1990 Hot-rolled steel plates, floorplates and
slabs
(In Update Services 15, 30, 51, 55) A4 12pp D
Specifies requirements for the production and supply of hot-
rolled structural steel plates, floorplates and slabs rolled on
a reversing mill for carbon and carbon-manganese mechani-
cally tested steels, fully killed analysis only steels and low
alloy (weathering) mechanically tested.
Committee BD/23. Supersedes AS 1204—1980, AS 1205—1980 and
AS 1227—1980 (in part). Draft for comment DR 87234. Publication date
1990-01-26. ISBN 0 7262 5970 5.

WITHDRAWN
TAS MARCH 1990
S/S BY A.S. 3679-1990

DR 87235
DR 87234

AS 1204—1980
UDC 669.14.018.29:621.791

Australian Standard 1204—1980

Amat 1 870706

For near BS equil see
BS 4360:1986

STRUCTURAL STEELS ORDINARY WELDABLE GRADES



STANDARDS ASSOCIATION OF AUSTRALIA
Incorporated by Royal Charter

AVA Documents
Document Sharing Hub

THE FOLLOWING INDUSTRIAL AND GOVERNMENTAL ORGANIZATIONS AND SAA technical committees were officially represented on the committee entrusted with the preparation of this standard:

Australian Institute of Steel Construction Ltd
Bureau of Steel Manufacturers of Australia
Confederation of Australian Industry
Department of Public Works, N.S.W.
National Association of Australian State Road Authorities
Railways of Australia Committee
Steel Reinforcement Promotion Group
University of New South Wales
University of Sydney
SAA Committee on Concrete Structures
SAA Committee on Prestressed Concrete
SAA Committee on Testing of Metals

This standard, prepared by Committee BD/23, Structural Steel, was approved on behalf of the Council of the Standards Association of Australia on 10 October 1980, and was published on 1 December 1980.

To keep abreast of progress in industry, Australian standards are subject to continuous review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that their standards are up-to-date. Full details of all SAA publications will be found in the Annual List of Australian Standards; these details are supplemented by listings in the SAA monthly journal 'The Australian Standard'. Information on the Annual List and 'The Australian Standard' may be obtained from any sales office of the Association, where details are also available of the current status of individual standards. Suggestions for improvements to published standards, addressed to the head office of the Association, are welcomed.

This standard was issued in draft form for public review as DR 79170.

AUSTRALIAN STANDARD

STRUCTURAL STEELS— ORDINARY WELDABLE GRADES

AS 1204—1980

First published	1972
Second edition	1980

PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA,
STANDARDS HOUSE, 80 ARTHUR STREET, NORTH SYDNEY, N.S.W.

PREFACE

This standard was prepared by the Association's Committee on Structural Steel to supersede both AS 1204—1972 and AS 1405—1973. The number of grades of steel covered has been reduced to include only those which are readily available. The product range has been extended to cover strip and floorplate, and tensile test requirements of some grades have been increased to take full advantage of the known properties of the steel. Weldable structural steels with enhanced weather-resistance properties are specified in AS 1205.

The grade designation used in the standard is a number which is the minimum yield stress in megapascals (MPa) rounded to 50 MPa, for the majority of the material involved. Where low-temperature impact properties are specified, an L suffix is introduced followed by 0 or 15, depending on the temperature at which the Charpy V-notch tests are to be carried out, i.e. at 0°C or -15°C, as appropriate.

The fact that low temperatures are used for impact tests does not necessarily imply that the relevant steels are guaranteed to be completely satisfactory for use at those temperatures, although in general they can be regarded as progressive improvements in the order shown over steels for which low-temperature impact tests are not prescribed.

The mechanical tests for universal sections are carried out on test pieces taken from the flange. AS 1227, which lays down general requirements for structural steel, defines the location of the test piece. Tapered-flange beams and channel sections will continue to be tested in the web, as this is the only

location from which a parallel-sided test piece can be obtained.

Hollow sections are not included in this standard; these are specified in AS 1163 and AS 1450.

The bend test is not included in the mechanical test requirements but a table giving recommended minimum bending radii for fabrication is given in Appendix B for guidance.

Any heat treatment or hot-forming operation must be controlled to avoid prolonged soaking times or excessively high temperatures which may have adverse effects on any type of steel since many of the grades covered have their properties developed by the use of grain refining and controlled temperatures during rolling.

This standard may require reference to the following Australian standards:

AS 1000	The International System of Units (SI) and Its Application
AS 1155	Metric Units for Use in the Construction Industry
AS 1227	General Requirements for the Supply of Hot-rolled Steel Plates, Sections, Piling and Bars for Structural Purposes
AS 1391	Methods for Tensile Testing of Metals
AS 1544	Methods for Impact Tests on Metals Part 2—Charpy V-notch
AS 1554	SAA Structural Steel Welding Code Part 1—Welding of Steel Structures
AS 1365	Tolerances for Flat-rolled Steel Products (Amendment 1)

CONTENTS

	Page
SPECIFICATION	
1 Scope	3
2 Designation	3
3 Grades and Product Forms	3
4 General Requirements	3
5 Chemical Composition	3
6 Mechanical Tests	3
7 Mechanical Test Requirements	4
8 Retests	4
9 Identification	5
APPENDICES	
A Purchasing Guidelines	7
B Cold Bending and Hot Forming of Plate During Fabrication	8

©Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1980

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard
for
STRUCTURAL STEELS—ORDINARY WELDABLE GRADES

1 SCOPE. This standard specifies requirements for the production and supply of hot-rolled carbon and carbon-manganese steel as—

- (a) plate,
- (b) floorplate,
- (c) strip,
- (d) structural sections,
- (e) piling bar, and
- (f) bar (flat, round, hexagonal and square),

for general structural and engineering purposes. The steels are suitable for welding, and grade 200 is suitable for cold forming and flanging. The standard does not cover bars in L15 grades.

NOTE: Guidelines to purchasers on requirements that should be specified by the purchaser and those that should or may be agreed to at the time of enquiry and/or order are given in Appendix A.

2 DESIGNATION. The grade designation shall be based on the yield strength of the steel (see Clause 7.1) and impact strength requirement (see Clause 7.2).

3 GRADES AND PRODUCT FORMS. The grade of steel shall be suitable for the required product form, and in accordance with Table 1.

4 GENERAL REQUIREMENTS. Steel shall comply with AS 1227.

4.1 See Amendment 1
5 CHEMICAL COMPOSITION.

5.1 Ladle Analysis. The ladle analysis of the steel shall conform to the limits given in Table 2 for the appropriate grade.

5.2 Product Analysis. When the steel is subjected to a product analysis, the analysis shall conform to the limits given in Table 2 for the appropriate grade.

5.3 Residual Elements. Elements not shown for the appropriate grade in Table 2 shall not be inten-

tionally added to the steel, other than for the purpose of finishing the heat.

All reasonable precautions shall be taken to prevent the addition of such elements during manufacture, and the quantities present shall not be detrimental to the intended use of the steel.

Percentages of residual elements up to the following amounts shall be considered as incidental:

Copper	0.35 percent max.
Nickel	0.35 percent max.
Chromium	0.30 percent max.
Molybdenum	0.10 percent max.

6 MECHANICAL TESTS.

6.1 Frequency of Testing. Test samples shall be taken to represent finished steel of the same product form treated in the same manner and from the same ladle as follows:

- (a) One sample for up to 50 t.
- (b) Two samples for over 50 t and up to 100 t.
- (c) Three samples for over 100 t and up to 150 t.
- (d) Four samples for over 150 t.

6.2 Tensile Test. One tensile test shall be made on a test piece prepared from a test sample taken in accordance with Clause 6.1. The position and preparation of the test piece and the method of test shall be in accordance with Clauses 9 to 13 of AS 1227.

If the quantity includes steel of more than one thickness, a further tensile test shall be made for each variation in thickness, above or below the thickness of the first test piece selected, as follows:

- (a) For material 50 mm thick and less, 5 mm variation.
- (b) For material greater than 50 mm thick, 25 mm variation.

TABLE 1
GRADES AND PRODUCT FORMS

Grade	Plate and strip	Floorplate	Sections	Bars	Piling bar
200	X	X	—	—	—
250	X	X	X	X	X
250L0	X	—	X	X	—
250L15	X	—	X	—	—
350	X	—	X	X	—
350L0	X	—	X	X	—
350L15	X	—	X	—	—

NOTES:

1. A dash (—) denotes the grades not covered by this standard for the product forms indicated.
2. X denotes the grades covered by this standard for the product forms indicated.
3. L indicates guaranteed low-temperature impact properties.
4. Grade 200 applies only to plate, strip and floorplate up to 12 mm thick.

COPYRIGHT