

STANDARDS AUSTRALIA

RECONFIRMATION

OF

AS 1334.10—1994

Methods of testing conveyor and elevator belting
Method 10: Determination of ignitability and flame propagation
characteristics of conveyor belting

RECONFIRMATION NOTICE

Technical Committee RU-002 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 08 December 2018.

The following are represented on Technical Committee RU-002:

Australasian Institute of Mining and Metallurgy
Australasian Plastics and Rubber Institute
Australian Chamber of Commerce and Industry
Australian Industry Group
Bureau of Steel Manufacturers of Australia
Engineers Australia
NSW Department of Planning and Environment
SafeWork NSW
University of Newcastle

NOTES

Methods of testing conveyor and elevator belting

Method 10: Determination of ignitability and flame propagation characteristics of conveyor belting

PREFACE

This Standard was prepared by the Standards Australia Committee on Conveyor and Elevator Belting under the direction of the Multitechnics Standards Policy Board to supersede AS 1334.10—1982.

The Standard eliminates the discrepancy between the temperature and flame size specified in the previous edition.

CONTENTS

	<i>Page</i>
1 SCOPE	1
2 PRINCIPLE	1
3 APPLICATION TO FIRE HAZARD ASSESSMENT	2
4 REAGENT	2
5 APPARATUS	2
6 TEST PIECES	2
7 PROCEDURE	2
8 REPORT	3
9 REFERENCES IN OTHER AUSTRALIAN STANDARDS	3
10 COMMERCIAL LITERATURE	3

METHOD

1 SCOPE This Standard sets out a method for determining the ignitability and flame propagation characteristics of a horizontally oriented specimen of conveyor belting.

2 PRINCIPLE The end of a horizontally oriented specimen of belting is subjected to a flame from a specified gas burner for a given period and the duration of flame after removal of the burner is measured. After the disappearance of flame, a current of air is passed over the specimen and the duration of the afterglow is measured.