

STANDARDS AUSTRALIA

Amendment No. 1
to
AS 4046.5—2002
Methods of testing roof tiles
Part 5: Determination of permeability

CORRECTION

The 2002 edition of AS 4046.5 is amended as follows; the amendment(s) should be inserted in the appropriate place(s).

SUMMARY: This Amendment applies to Clauses 4 and 6.

Published on 31 January 2006.

AMDT
No. 1
JAN
2006

Page 1 Clause 4(a), Items (i) and (ii)

Delete existing Items (i) and (ii) and *replace* with the following:

- (i) Plain tiles, not less than 25 000 mm².
- (ii) Other than plain tiles, not less than 50 000 mm².

Alternatively, a form as shown in Figure 1(b) may be used, in which the whole tile is sealed around its perimeter.

AMDT
No. 1
JAN
2006

Page 2 Clause 6, Item (d)

Delete existing text and *replace* with the following:

- (d) Maintain the level of the water for a period of 2 h and at the end of this period check whether any drops of water have formed on the underside of the tile.

This page has been left intentionally blank.