

STANDARDS AUSTRALIA

Amendment No. 1
to
AS 4264.1—2009
Coal and coke—Sampling
Part 1: Coal—Sampling procedures

CORRECTION

The 2009 edition of AS 4264.1 is amended as follows; the amendment should be inserted in the appropriate place.

SUMMARY: This Amendment applies to Table 2.6.

Published on 14 September 2011.

AMDT
No.1
SEP
2011

Table 2.6

Delete existing table including table title and the note and *replace* with the following:

TABLE 2.6
MINIMUM MASS OF GROSS SAMPLE/MINIMUM MASS
OF SAMPLE AFTER DIVISION

Nominal top size of coal mm	Common samples and general analysis samples kg
300	15 000
200	5 400
150	2 600
125	1 700
90	750
75	460
63	300
50	170
45	125
38	85
31.5	55
22.4	25
16	10
11.2	4
10	3
8	1.70
5.6	0.70
4	0.30
2.8	0.30
2	0.30
1	0.30

NOTE: The masses for the common and general analysis samples have been determined to correspond to a precision of approximately 0.2% ash.