

Australian Standard™

Cast iron—Designation of microstructure of graphite

This Australian Standard was prepared by Committee MT-001, Iron and Steel. It was approved on behalf of the Council of Standards Australia on 17 May 2002 and published on 24 June 2002.

The following are represented on Committee MT-001:

Australian Institute of Steel Construction
Australian Chamber of Commerce and Industry
Australian Industry Group
Australasian Railway Association
Australian Building Codes Board
Australian Foundry Institute
Bureau of Steel Manufacturers of Australia
Institute of Materials Engineering Australia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

This Standard was issued in draft form for comment as DR 02081.

Australian Standard™

Cast iron—Designation of microstructure of graphite

First published as AS 5049—2002.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 4550 4

PREFACE

This Standard was prepared by the Australian members of the Joint Standards Australia/Standards New Zealand Committee MT-001. After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian, rather than an Australian/New Zealand Standard.

This Standard is identical with and has been reproduced from ISO 945:1975, *Cast iron—Designation of microstructure of graphite*.

This Standard is one of a series of Standards covering the range of cast irons. The series comprises the following:

AS

1830 Grey cast iron

1831 Ductile cast iron

1832 Malleable cast iron

1833 Austenitic cast iron

2027 Wear resistant white cast iron

5049 Cast iron—Designation of microstructure of graphite

As this Standard is reproduced from an International Standard, the following applies:

- (a) Its number does not appear on each page of text and its identity is shown only on the cover and title page.
- (b) In the source text, 'this International Standard' should read 'this Australian Standard'.
- (c) A full point substitutes for a comma when referring to a decimal marker.

AUSTRALIAN STANDARD

Cast iron – Designation of microstructure of graphite**1 SCOPE AND FIELD OF APPLICATION**

This International Standard specifies a method of designating the microstructure of graphite in cast iron. It is not intended as a basis for acceptance specifications.

2 GENERAL

2.1 When iron-carbon alloys are examined under a microscope, the graphite occurring in these alloys can be classified by

- a) its form (designated by roman numerals, see figure 1);
- b) its distribution (designated by capital letters, see figure 2);
- c) its size (designated by arabic numerals, see figures 3 to 6).

2.2 The three series of reference diagrams included in this International Standard for evaluating the type of graphite form a basis for such a classification. The characteristic features of the graphite which occur are designated by letters and numerals. For this purpose, microstructures of graphite are arranged side by side in the series. Form, distribution and size of the graphite observed are determined by comparison with the diagrams and the allocation of the same classification as that of the diagrams that resemble them most closely. This method permits quick identification of the graphite, promotes mutual understanding between technicians in this field, permits clear representation of the findings, facilitates statistical analysis and saves a vast amount of photographic work.

2.3 The comparison of the graphite observed with the three series of reference diagrams in figures 1 to 6 does not give any information on the suitability of the iron-carbon alloys for any particular service.

3 SAMPLING AND PREPARATION OF SPECIMENS

3.1 When taking specimens from the casting, it is essential that attention be paid to the location, to the wall thickness, to the distance from the surface and to the presence of chills and the like. The location of the surface examined shall be carefully recorded in any report.

3.2 The area of polished surface shall be sufficient to give a true representation of the graphite distribution. Attention shall be paid to the careful grinding and polishing of the specimens in order that the graphite particles appear in their true form and size. The examination of the graphite under the microscope is usually carried out on the unetched polished section, though final etching is recommended in the case of some special alloy cast irons, for example those containing high silicon.

4 MICROSCOPIC EXAMINATION

4.1 The polished specimens shall be viewed under a microscope so that the entire polished area may be examined. A comparison shall first be made with the reference diagrams for the graphite form and distribution (see figures 1 and 2) and the microstructures observed shall then be identified from the corresponding reference diagrams. Following this, the size of the graphite particles shall be determined at a magnification of 100 diameters, by reference to figures 3 to 6 inclusive and/or the table.

4.2 Examination under the microscope can be carried out by direct observation or by projection on the ground glass of the microscope. The field of view shall have approximately the same size as the reference diagrams (about 80 mm diameter).

4.3 The measurement of the graphite particles can be facilitated by the use of suitable calibrated eye-pieces.

4.4 The method described above gives good results, but any other method of examination which gives good results may be used.

5 REFERENCE DIAGRAMS

A series of reference diagrams is provided for form, distribution and size of graphite. The reference diagrams show microstructures of an ideal character instead of actual photomicrographs, thus avoiding the minor effects which might interfere with the results of the observation.

5.1 Reference diagrams for graphite form

The reference diagrams for graphite form (figure 1) show six characteristic forms which are designated by the roman

numerals I to VI. These represent the principal types of graphite found in cast iron. However, other forms are also known to occur occasionally.

5.2 Reference diagrams for graphite distribution

The reference diagrams for the graphite distribution (figure 2) show five examples designated by the letters A to E.

The diagrams in figure 2 apply to form I graphite. The other forms generally occur in distribution A, but other distributions may sometimes be found.

5.3 Reference diagrams for graphite size

Figures 3 to 6 and the table serve to determine the graphite size. For the 100 diameter reproduction scale, sizes are indicated ranging from a maximum dimension of the particle of > 100 mm (size 1) down to < 1,5 mm (size 8). The size ranges covered by the size reference numbers 3 to 7 inclusive are based on an average particle size which is half that of the larger size range.

TABLE – Dimension of the graphite particles forms I to VI

Reference number	Dimension of the particles observed at X 100 magnification	True dimension
	mm	mm
1	> 100	> 1
2	50 to 100	0,5 to 1
3	25 to 50	0,25 to 0,5
4	12 to 25	0,12 to 0,25
5	6 to 12	0,06 to 0,12
6	3 to 6	0,03 to 0,06
7	1,5 to 3	0,015 to 0,03
8	< 1,5	< 0,015

6.2 If the graphite observed lies between two sizes, reference to both is possible (for example 3/4).

In a given case the predominating size may be emphasized by underlining (for example 3/4).

This method can be extended to cover structures where more than two sizes are present.

6.3 Mixed structures with different types of graphite may be defined by estimating the percentage proportion of the different types of graphite : for example,

$$60 \% \text{ I A } 4 + 40 \% \text{ I D } 7$$

means 60 % graphite of the form I, distribution A and size 4, and 40 % graphite of the form I, distribution D and size 7.

6 DESIGNATION OF GRAPHITE BY FORM, DISTRIBUTION AND SIZE

6.1 To characterize the graphite observed, indications are generally necessary on the form, distribution and size of the graphite particles. To this purpose, the roman numerals of figure 1 are used for the form, the capital letters of figure 2 for the distribution and the arabic numerals of figure 3 and the table for the size, in that order. Thus, for example, type I A 4 means that, with a 100 mm diameter magnification, graphite particles, form I, distribution A, having a maximum dimension of 12 to 25 mm, have been observed.