

SUPERSEDED

BY

SAA TR1, Part 6/2309-1982

Superseded

Amendment No. 1

November 1976.

Under Revision see DR 78044 of March 1978

K113-

1964

ALIAN STANDARD K113-1964

(UDC 667.633)

ENAMELISED PAINT

FOR EXTERIOR USE



Incorporated by
Royal Charter

STANDARDS ASSOCIATION OF AUSTRALIA



Documents

Document Sharing Hub

THE FOLLOWING SCIENTIFIC, INDUSTRIAL AND GOVERNMENTAL organizations and departments were officially represented on the committee entrusted with the preparation of this standard:

Associated Chambers of Manufactures
Australian and New Zealand Railways Conferences
Australian Paint Manufacturers' Federation
Commonwealth Paint Committee
Country Roads Board, Victoria
Defence Standards Laboratories
Department of Supply
Division of Building Research, CSIRO
Government Stores Department, NSW
Master Painters', Decorators' and Signwriters' Association
Oil and Colour Chemists' Association
Royal Australian Chemical Institute
Royal Australian Institute of Architects
State Electricity Commission of Victoria

This standard, prepared by Committee CH/3, Paints and Varnishes, was approved on behalf of the Council of the Standards Association of Australia on 25 May 1964.

In order to keep abreast of progress in the industries concerned, Australian standards are subject to periodical review. Suggestions for improvements, addressed to the Headquarters of the Association, will be welcomed.

The specification is intended to include the technical provisions necessary for the supply of the materials referred to but does not purport to comprise all the necessary provisions of a contract.

Amendment No 1
November 1976

STANDARDS ASSOCIATION OF AUSTRALIA

Incorporated by Royal Charter

AMENDMENT No 1

to

AS K113 – 1964

ENAMELISED PAINT FOR EXTERIOR USE

SUMMARY: The following sections of this standard are covered by this amendment:
Preface, Clause 1.2, Page 3 Footnote, Clause 2.3, Page 4 Footnote, Clauses 3.8, 3.9, 3.10,
3.15, Page 6 Footnotes, Clauses 4.1, 4.2, 4.3, Table 1, Clause 4.4, Page 7 Footnotes, Clauses
4.5, 4.6, 4.7.1, 4.7.2, 4.7.3, Page 8 Footnotes, Clause 4.7.4, Page 9 Footnote, Table 3.

STANDARDS ASSOCIATION OF AUSTRALIA

Incorporated by Royal Charter

Australian Standard Specification for ENAMELISED PAINT FOR EXTERIOR USE

AS K113 — 1964

First edition	1959
Revised	1964

PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
SCIENCE HOUSE, 157 GLOUCESTER STREET, SYDNEY (Copyright)



AVA Documents
Document Sharing Hub

1-3 JUL 1964

PREFACE

This revised edition of AS K113 is one of a series of Australian standards for prepared paints being developed by the Paint and Varnish Committee.

Experience since the former edition was published has indicated the need for changes to a number of clauses and to the panel testing schedule, and also the replacement of certain tests by those developed since the original publication.

Companion specifications for the supply of wood priming paint oil base, and undercoat oil base, have been issued as AS K109 and AS K110 respectively.

This standard requires reference to various Australian standards for priming and undercoating paints, and to—

- AS K8 ~~Mineral Turpentine and White Spirit~~
 - AS K41 ~~Standard Methods of Test for Paints, Varnishes, Lacquers and Related Materials~~
- SEE AMENDMENTS No. 1

STANDARDS ASSOCIATION OF AUSTRALIA

**Australian Standard Specification
for
ENAMELISED PAINT
FOR EXTERIOR USE**

SECTION 1. SCOPE AND DESCRIPTION

1.1 SCOPE. This specification applies to the supply, primarily on the basis of performance, of enamelled paint for general use.

The enamel is normally intended for use as a finishing paint in painting systems incorporating the following materials:

Wood priming paint, oil base—complying with AS K109

Undercoat, oil base—complying with AS K110.

It may, by agreement between the purchaser and vendor, be used with other materials.

NOTE: The enamelled paint is referred to in the specification as the "enamel".

1.2 CONDITION. The enamel shall be supplied in a condition suitable for application by brushing, either as supplied or when thinned as recommended by the vendor with not more than 5 per cent by volume of mineral turpentine complying with ~~AS K8~~ *AS 1700* **SEE AMENDMENTS No. 1.**

1.3 COLOUR. The colour in which the enamel is supplied shall be the subject of agreement between the purchaser and the vendor.

SECTION 2. GENERAL PROVISIONS

2.1 INFORMATION TO BE SUPPLIED WITH THE ENQUIRY AND ORDER. When enquiring for and ordering enamel to comply with this specification the purchaser shall supply the following particulars, as appropriate:

- (i) Colour (see Clause 1.3).
- (ii) The types of priming and undercoating paints with which the enamel will be used (see Clause 1.1).

The purchaser shall, in addition, supply details of any special requirements such as wet hiding power (see Clause 3.9).

NOTE: When ordering paint complying with this specification the purchaser should take into consideration any Statutory or other special requirements in regard to the restriction of lead content, e.g. the Queensland Health Act, and specify the paint accordingly.

¹ ~~AS K8, Mineral Turpentine and White Spirit.~~