

Australian/New Zealand Standard™

Methods of test for pulp and paper

**Method 444: Determination of edgewise
crush resistance (unwaxed edge
method)**



AS/NZS 1301.444:2016

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee PK-019, Methods of Test for Pulp and Paper. It was approved on behalf of the Council of Standards Australia on 6 December 2016 and by the New Zealand Standards Approval Board on 9 December 2016.
This Standard was published on 23 December 2016.

The following are represented on Committee PK-019:

Appita
Australian Forest Products Association
New Zealand Paper Forum
Scion

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at www.saiglobal.com or Standards New Zealand web site at www.standards.govt.nz and looking up the relevant Standard in the on-line catalogue.

For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of Standards Australia or the New Zealand Standards Executive at the address shown on the back cover.

This Standard was issued in draft form for comment as DR AS/NZS 1301.444:2015.

Australian/New Zealand Standard™

Methods of test for pulp and paper

Method 444: Determination of edgewise crush resistance (unwaxed edge method)

First published in Australia as AS 1301.P444rp—1978.
Revised and redesignated as AS 1301.444s—1988.
Second edition 1992.
First published in New Zealand as NZS 1301.444s—1992.
AS 1301.444s—1992 and NZS 1301.444s—1992 jointly revised,
amalgamated and designated as AS/NZS 1301.444s:2004.
Jointly revised and designated as AS/NZS 1301.444:2016.

COPYRIGHT

© ISO 2016 – All rights reserved

© Standards Australia Limited

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968.

Published by SAI Global Limited under licence from Standards Australia Limited, GPO Box 476, Sydney, NSW 2001, Australia

ISBN 978 1 76035 653 8

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee PK-019, Methods of Test for Pulp and Paper to supersede AS/NZS 1301.444s:2004, *Methods of test for pulp and paper—Corrugated fibreboard—Part 444s: Determination of edgewise crush resistance (unwaxed edge method) (ISO 3037:1994, MOD)*.

The objective of this Standard is to provide a method for determining the edgewise crush resistance of corrugated fibreboard.

This Standard is identical with, and has been reproduced from ISO 3037:2013, *Corrugated fibreboard—Determination of edgewise crush resistance (unwaxed edge method)*.

As this Standard is reproduced from an International Standard, the following applies:

- (a) In the source text ‘this International Standard’ should read ‘this Australian/New Zealand Standard’.
- (b) A full point substitutes for a comma when referring to a decimal marker.

References to International Standards should be replaced by references to Australian or Australian/New Zealand Standards, as follows:

<i>Reference to International Standard</i>		<i>Australian/New Zealand Standard</i>	
ISO		AS/NZS	
186	Paper and board—Sampling to determine average quality	1301	Method of test for pulp and paper
		1301.417s	Method 417s: Sampling to determine average quality

The normative references ISO 187 and ISO 13820 have not been adopted as Australian/New Zealand Standards. In Australia and New Zealand the following Standards are generally used:

- (i) AS/NZS 1301.414s:2006, *Methods of test for pulp and paper*, Method 414s: *Conditioning of paper for testing*.
- (ii) AS/NZS 1301.415s:2008, *Methods of test for pulp and paper*, Method 415s: *Standard atmosphere for testing paper and board and procedure for monitoring the atmosphere*.
- (iii) The AS/NZS Standards use different humidity ranges and allow different apparatus to ISO 187.
- (iv) AS/NZS 1301.449s:2013, *Methods of test for pulp and paper*, Method 449s: *Description of crush testing equipment*.
- (v) The above Standards describe the test instruments used to perform crush tests set out as in other parts of AS/NZS 1301.

Only normative references that have been adopted as Australian or Australian/New Zealand Standards have been listed.

The term ‘informative’ has been used in this Standard to define the application of the annexes to which it applies. An ‘informative’ annex is only for information and guidance.

CONTENTS

1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	1
5	Apparatus	1
6	Sampling	2
7	Conditioning	2
8	Preparation of test pieces	2
9	Procedure	3
10	Calculation	3
11	Test report	4
	Annex A (informative) Examples of suitable cutting devices	5
	Annex B (informative) Precision data	6
	Bibliography	8

INTRODUCTION

A variety of methods for the determination of edgewise crush resistance are in use in different parts of the world. These can be classified into three groups as follows:

- a) Those in which a carefully cut rectangular test piece is tested without any special treatment or modification (e.g. ISO 3037).
- b) Those in which the edges of the test piece to which the force is applied are waxed, to prevent the test result being influenced by “edge effects” (e.g. ISO 13821, *Corrugated fibreboard — Determination of edgewise crush resistance — Waxed edge method*).
- c) Those in which the test piece edges are not waxed but the shape of the test piece is such that the length is substantially reduced at a point midway between the loaded edges, in order to induce the failure to occur away from those edges (e.g. JIS Z 0403-2).

The dimensions of the test piece vary from one group to the other and, in group c), the methods vary in the shape and method of reducing the length, and in whether or not the test piece is held in a clamp during crushing.

The methods may not give the same numerical results, but it can be shown that most of them can be used to predict the top-to-bottom compression strength which will be achieved when the board is properly converted into a transport package.

This International Standard describes a method from group a). It is intended as a method for quality measurement and quality specification purposes and is selected because it correlates with the top-to-bottom compression strength of the final transport package and because it is the simplest and most operationally convenient method, an important factor when large numbers of tests need to be conducted. However, it does not measure the actual intrinsic compressive strength of the corrugated fibreboard, giving lower results than most of the methods in groups b) and c). This systematic difference is due to edge effects.

Other methods may be used for other purposes, particularly when the object of the test is to study fundamental structural characteristics of the package.

There are methods available for calculating the edgewise crush resistance from the compression strength of the component papers.