

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

RECONFIRMATION

OF

AS/NZS 1580.481.1.7:1998

Paints and related materials—Methods of test

Method 481.1.7: Coatings—Exposed to weathering—Degree of checking

RECONFIRMATION NOTICE

Technical Committee CH-003 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 30 May 2013.

Approved for reconfirmation in New Zealand on behalf of the Standards Council of New Zealand on 26 August 2013.

The following are represented on Technical Committee CH-003

Australasian Corrosion Association
Australian Paint Approval Scheme
Australian Paint Manufacturers' Federation
Australian Pipeline Industry Association
Institution of Professional Engineers New Zealand
Master Painters New Zealand Association
Water Corporation Western Australia

NOTES

Australian/New Zealand Standard™

Paints and related materials—Methods of test

Method 481.1.7: Coatings—Exposed to weathering—Degree of checking

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee CH/3, Paints and Related Materials, to supersede AS 1580.481.1.7—1991.

This Standard is essentially the same as the 1991 edition of AS 1580.481.1.7, but includes a new Figure 2 illustrating checking in one preferential direction.

METHOD

1 SCOPE This Standard sets out a method for determining the degree of checking in a paint film that has been exposed to weathering.

2 REFERENCED DOCUMENTS The following documents are referred to in this Standard:

AS

1580 Paints and related materials—Methods of test
1580.481.0 Part 481.0: Coatings—Guide to assessing paint systems exposed to weathering conditions

AS/NZS

1580 Paints and related materials—Methods of test
1580.457.1 Method 457.1: Resistance to natural weathering

ISO

4628 Paints and varnishes—Evaluation of degradation of paint coatings—Designation of intensity, quantity and size of common types of defect
4628.4 Part 4: Designation of degree of cracking

3 DEFINITIONS For the purpose of this Standard, the definitions in AS 1581.481.0 apply.

4 PRINCIPLE The test film is superficially cleaned with water and then visually evaluated for the degree of checking and, where appropriate, using a microscope or magnifying glass of 10× magnification, by comparison with diagrammatic reference standards showing rated stages of checking.

NOTE: The diagrammatic reference standards have been adopted from ISO 4628.4.