

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

Amendment No. 1
to
AS/NZS 1595:1998
Cold-rolled, unalloyed, steel sheet and strip

REVISED TEXT

The 1998 edition of AS/NZS 1595 is amended as follows; the amendments should be inserted in the appropriate places.

SUMMARY: This Amendment applies to Tables 2.2 and 3.2.

Published on 7 April 2014.

Approved for publication in New Zealand on behalf of the Standards Council of New Zealand on 21 February 2014.

Table 2.2

1 After row—

CA350†	0.11	1.60	0.025	0.020
--------	------	------	-------	-------

add the following two rows:

CA400†	0.20	1.60	0.03	0.03
CA450†	0.20	1.60	0.03	0.03

2 Add the following Note to the Table:

NOTE: Carbon equivalent based on $C+Mn/6$ shall be restricted to 0.43% maximum.

Table 3.2

After row—

CA350	350	430	23	22	0
-------	-----	-----	----	----	---

add the following two rows:

CA400	400	450	10	10	3a
CA450	450	500	10	10	4a

AMDT
No. 1
APR
2014

AMDT
No. 1
APR
2014

This page has been left intentionally blank.