

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

Amendment No. 2
to
AS/NZS 1660.2.5:1998
Test methods for electric cables, cords and conductors
Method 2.5: Insulation, extruded semi-conductive screens and non-metallic sheaths—
Methods specific to cables above 1 kV

REVISED TEXT

The 1998 edition of AS/NZS 1660.2.5 is amended as follows; the amendment should be inserted in the appropriate place.

SUMMARY: This Amendment applies to Clause 2.3(b).

Published on 24 July 2001.

Approved for publication in New Zealand on behalf of the Standards Council of New Zealand on 20 July 2001.

Page 6 Clause 2.3(b)

Delete Paragraph (b) and *substitute* the following:

- (b) Measure the tension required to pull the strip away from the cable at an approximately 90-degree angle such that the strip separates from the insulation at a speed of 12 ± 1 mm/s.

This Amendment forms part of the Standard on publication.

AMDT
No. 2
JULY
2001

This page has been left intentionally blank.