

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

Amendment No. 1
to
AS/NZS 2576:2005
Welding consumables for build-up and wear resistance

CORRECTION

The 2005 edition of AS/NZS 2576 is amended as follows; the amendment should be inserted in the appropriate place.

SUMMARY: This Amendment applies to Figure 1.1.


Published on 26 October 2006.

Approved for publication in New Zealand on behalf of the Standards Council of New Zealand on 15 September 2006.

AMDT
No. 1
OCT
2006

Section 1 Figure 1.1

Delete existing Figure and replace with the following:



Example: 2360-A1—an austenitic chromium carbide iron, with a mean hardness within the range of 60 HRC to 64 HRC used for manual arc welding, supplied in a tubular form, with the deposited weld metal receiving no alloy contribution from the flux coating

This page has been left intentionally blank.