

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

Amendment No. 2
to
AS/NZS 4266.9:2003
Reconstituted wood-based panels—Methods of test
Part 9: Thickness stability and glue bond quality

REVISED TEXT

The 2003 edition of AS/NZS 4266.9 is amended as follows; the amendments should be inserted in the appropriate places.

SUMMARY: This Amendment applies to Clauses 2, 3, 5(a), 6.1, 7.1, 7.2, 7.4 and 9.

Published on 3 February 2006.

Approved for publication in New Zealand on behalf of the Standards Council of New Zealand on 23 September 2005

Page 1, Clause 2

For AS/NZS 4266 series, *delete* ‘(Int)’ from all references.

Page 1, Clause 3

Delete ‘AS/NZS 4266.1(Int)’, and *replace* with ‘AS/NZS 4266.1’.

Page 2, Clause 5(a)

Delete ‘AS/NZS 4266.5(Int)’, and *replace* with ‘AS/NZS 4266.5’.

Page 2, Clause 6.1

Last line, *delete* ‘AS/NZS 4266.1(Int)’, and *replace* with ‘AS/NZS 4266.1’.

Page 2, Clause 7.1

Second line, *delete* ‘AS/NZS 4266.35(Int)’, and *replace* with ‘AS/NZS 4266.35’.

Page 2 Clause 7.2

Delete existing paragraph, and *replace* with the following:

Prior to the bending test, the test pieces shall be immersed in water at $20 \pm 2^\circ\text{C}$ and subjected to a negative pressure of 85 ± 5 kPa for a period of 30 min followed immediately by the application of a pressure of 400 ± 5 kPa for a period of 23 ± 1 h. The test pieces shall be immersed so that their length is either horizontal or vertical, depending on the dimensions of the bath. They shall have a minimum clearance of 15 mm from each other and the bottom and sides of the vessel.

Page 3, Clause 7.4

First line, *delete* ‘AS/NZS 4266.5(Int)’, and *replace* with ‘AS/NZS 4266.5’.

Page 3, Clause 9

1 Item (b), *delete* ‘AS/NZS 4266.1(Int)’, and *replace* with ‘AS/NZS 4266.1’.

2 Item (d), *delete* ‘AS/NZS 4266.9(Int)’, and *replace* with ‘AS/NZS 4266.9’.

ISBN 0 7337 7223 4

This page has been left intentionally blank.