

AS/NZS 60695.11.20:2001  
(Incorporating Amendment 1)

## Australian/New Zealand Standard™

Fire hazard testing –

Part 11.20: Test flames – 500 W  
flame test methods  
(IEC 60695-11-20:1999, IDT)



This Joint Australian/New Zealand Standard was prepared by Joint Technical EL-002- Safety of Household and Similar Electrical Appliances and Small Power Transformers. It was approved on behalf of the Council of Standards Australia on 21 May 2001 and on behalf of the Council of Standards New Zealand on 12 May 2001. It was published on 11 June 2001.

---

The following interests are represented on Committee EL-002

Association of Certification Bodies

Australian Chamber of Commerce and Industry

Australian Electrical and Electronic Manufacturers Association

Canterbury Manufacturers Association New Zealand

Consumer Electronic Suppliers Association, Australia

Electrical regulatory authorities, Australia

Electrical test laboratories

Electrical consultants

Electricity Supply Association of Australia

Institution of Engineers Australia

Metal trade Industries Association of Australia

Ministry of Consumer Affairs, New Zealand

---

### **Keeping Standards up-to-date**

Standards are living documents, which reflect progress in science, technology and systems.

To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Australia web site at [www.standards.org.au](http://www.standards.org.au) or Standards New Zealand web site at [www.standards.co.nz](http://www.standards.co.nz) and looking up the relevant Standard in the on-line catalogue. Alternatively, both organizations publish an annual printed Catalogue with full details of all current Standards. For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comment to the Chief Executive of either Standards Australia International or Standards New Zealand at the address shown on the back cover.

---

*This standard was issued in draft form for comment as draft DR 00925*

# AS/NZS 60695.11.20:2001 (Incorporating Amendment 1)

## Australian/New Zealand Standard™

---

### Fire hazard testing –

### Part 11.20: Test flames – 500 W flame test methods (IEC 60695-11-20:1999, IDT)

---

Originated in Australia and New Zealand as part of ASNZS 4695.707:1996

Jointly revised and redesignated AS/NZS 60695.11.20:2001

#### **COPYRIGHT**

© Standards Australia/ Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher

Published jointly by Standards Australia International Ltd  
GPO Box 5420, Sydney, NSW 2001 Australia, and  
Standards New Zealand  
Private Bag 2439, Wellington 6020, New Zealand

## PREFACE

This standard was prepared by the Joint Standards Australia/Standards New Zealand Committee EL-002- Safety of Household and Similar Electrical Appliances and Small Power Transformers, to supersede the LF test methods contained in AS/NZS 4695.707, two years from publication.

A1

This Standard incorporates Amendment No. 1 (May 2004). The changes introduced by the Amendment are indicated in the text by a marginal bar and amendment number against the clause, note, table, figure or part thereof affected.

The objective of this Standard is to provide a small-scale laboratory screening procedure that allows manufacturers and designers to pre-select materials based on the relative burning behaviour of specimens made from non-metallic materials using a flame ignition source of 500 W nominal power.

This Standard forms the first edition of AS/NZS 60695.11.20, *Fire hazard testing - Part 11.20: Test flames – 500 W flame test methods*.

A1

This Standard is identical to and is reproduced from IEC 60695-11-20:1999, *Fire hazard testing - Part 11-20: Test flames - 500 W flame test methods*, including its Corrigendum 1 (2000-02) and amendment 1 (2003-06).

Annex A is for information only.

Clause 2 has been reformatted to indicate the Australia/New Zealand standard that is equivalent to the IEC standard or ISO standard to which normative reference is made.

The bibliography has been reformatted to indicate the Australia/New Zealand standard that is equivalent to the IEC standard or ISO standard to which an informative reference is made.

As this Standard is reproduced from an International Standard, the following applies:

- a) Its number does not appear on each page of text and its identity is shown on the cover and title page only.
- b) In the source text "IEC 60695" should read "AS/NZS 60695".
- c) A full point substitutes for a comma when referring to a decimal marker.

# CONTENTS

|                                                          | Page |
|----------------------------------------------------------|------|
| INTRODUCTION.....                                        | 1    |
| Clause                                                   |      |
| 1 Scope .....                                            | 3    |
| 2 Normative references .....                             | 3    |
| 3 Definitions .....                                      | 4    |
| 4 Principle .....                                        | 5    |
| 5 Significance of test .....                             | 5    |
| 6 Apparatus .....                                        | 5    |
| 6.1 Laboratory fumehood/chamber .....                    | 5    |
| 6.2 Laboratory burner .....                              | 5    |
| 6.3 Ring stand .....                                     | 6    |
| 6.4 Timing device .....                                  | 6    |
| 6.5 Measuring scale .....                                | 6    |
| 6.6 Conditioning chamber .....                           | 6    |
| 6.7 Micrometer .....                                     | 6    |
| 6.8 Desiccator chamber .....                             | 6    |
| 6.9 Air-circulating oven .....                           | 6    |
| 6.10 Cotton pad .....                                    | 6    |
| 6.11 Burner mounting block or fixture .....              | 6    |
| 7 Specimens .....                                        | 6    |
| 7.1 End product testing .....                            | 6    |
| 7.2 Material testing .....                               | 7    |
| 7.3 Bar test specimens .....                             | 7    |
| 7.4 Plate test specimens .....                           | 7    |
| 8 Test method .....                                      | 7    |
| 8.1 Conditioning .....                                   | 7    |
| 8.2 Procedure – Bar test specimens .....                 | 8    |
| 8.3 Procedure – Plates .....                             | 9    |
| 8.4 Classification .....                                 | 9    |
| 8.5 Test report .....                                    | 10   |
| Annex A (informative) Precision of the test method ..... | 15   |
| Bibliography .....                                       | 16   |
| Figure 1 – Vertical burning test for bar specimens ..... | 11   |
| Figure 2 – Horizontal burning test for plates .....      | 12   |
| Figure 3 – Burner mounting block – Example .....         | 13   |
| Figure 4 – Test specimens .....                          | 14   |

|                                                                                                                            |    |
|----------------------------------------------------------------------------------------------------------------------------|----|
| Table 1 – 5V burning categories.....                                                                                       | 9  |
| Table A.1 – Precision data on the afterflame time $t_1$ after the fifth flame application.....                             | 15 |
| Table A.2 – Precision data on the afterflame time $t_1$ and/or afterglow time $t_2$ after the fifth flame application..... | 15 |

## INTRODUCTION

When considering the use of the tests in this International Standard, it is important to distinguish the term “end-product test”, meaning a fire hazard assessment test on a completed product, piece part, component or subassembly, from the term “pre-selection test”, meaning a combustion characteristic test made on a material (piece part, component or subassembly).

Pre-selection tests on materials normally use test pieces that have standardised shapes, such as a rectangular bar or sheet, and are frequently prepared using standardised moulding procedures.

It is emphasized that data using the pre-selection tests given in this standard need careful consideration to ensure their relevance to the intended application and to avoid misuse and erroneous interpretation. The actual fire performance of a part or product is affected by its surroundings, design variables such as shape and size, fabrication techniques, heat transfer effects, the type of potential ignition source and the length of exposure to it. It is important to bear in mind that these properties may also be affected by foreseeable use, abuse and environmental exposure.

The advantages of a pre-selection procedure are listed below.

- a) A material, which reacts more favourably than another when tested as a standard test specimen, will usually also react more favourably when used as a finished part in the product, provided that possible synergistic effects are avoided.
- b) Data concerning relevant combustion characteristics can aid the selection of materials, components and subassemblies during the design stage.
- c) The precision of pre-selection tests is usually higher, and their sensitivity may be superior when compared with end-product tests.
- d) Pre-selection tests may be used in a decision-making process directed to minimize fire hazards. Where applicable for the purpose of fire hazard assessment, they may lead to a reduction in the number of end-product tests, with a consequent reduction in the total testing effort.
- e) When fire hazard requirements need to be upgraded quickly, it may be possible to do this by upgrading the requirements of a pre-selection test before modifying the end-product test.
- f) The grading and classification obtained from the pre-selection test results may be used to specify a basic minimum performance of materials used in product specifications.

It should be noted that, when pre-selection testing is used to replace some of the end-product testing, it is necessary to fix an increased margin of safety in an attempt to ensure satisfactory performance of the end-product. End-product testing may avoid restrictions in innovative design and in economic material selection imposed by a pre-selection procedure. Consequently, following a pre-selection procedure, it may be necessary to implement a value analysis on the end-product, in order not to overspecify the product beyond what is strictly needed.

For electrotechnical products, IEC 60695-1-1 indicates that the risk of fire is present in any electrical circuit which is energized. With regard to this risk, the objective of component circuit and equipment design, and of the choice of materials is to reduce the likelihood of fire, even in the event of foreseeable abnormal use, malfunction or failure. The practical aim is to prevent ignition due to the electrically energized part but, if ignition and fire occur, to control the fire, preferably within the bounds of the enclosure of the electrotechnical product.

The best method for testing electrotechnical products with regard to fire hazards is to duplicate exactly the conditions occurring in practice. In most instances this is not possible. Accordingly, for practical reasons, the testing of electrotechnical products with regard to fire

hazard is best conducted by simulating as closely as possible the actual effects occurring in practice.

IEC 60695-1-3 provides that pre-selection may be made on the basis of specified tests and by the use of specifications of the necessary resistance to fire and related combustion characteristics. It also outlines guidance that is intended to relate the specific function of the electrotechnical product, its subassemblies and its parts to the tested properties of materials, and to demonstrate the significance and the limitations of such a pre-selection procedure.

ISO/TR 10840 summarises specific problems associated with the fire testing of plastics, which should be taken into account when assessing and interpreting test results.