

Australian/New Zealand Standard™

Electrical installations in ships

Part 350: General construction and test methods of power, control and instrumentation cables for shipboard and offshore applications



AS/NZS IEC 60092.350:2019

This Joint Australian/New Zealand Standard™ was prepared by Joint Technical Committee EL-003, Electric Wires And Cables. It was approved on behalf of the Council of Standards Australia on 5 November 2019 and by the New Zealand Standards Approval Board on 4 December 2019.

This Standard was published on 20 December 2019.

The following are represented on Committee EL-003:

- Australian Cablemakers Association
- Australian Industry Group
- Electrical Regulatory Authorities Council
- Engineers Australia
- Institute of Electrical Inspectors (Australia)
- Master Electricians (New Zealand)
- National Electrical and Communications Association (Australia)
- Queensland University of Technology
- WorkSafe New Zealand

This Standard was issued in draft form for comment as DR AS/NZS IEC 60092.350:2019.

Keeping Standards up-to-date

Ensure you have the latest versions of our publications and keep up-to-date about Amendments, Rulings, Withdrawals, and new projects by visiting:

www.standards.org.au

www.standards.govt.nz

ISBN 978 1 76072 674 4

Australian/New Zealand Standard™

Electrical installations in ships

Part 350: General construction and test methods of power, control and instrumentation cables for shipboard and offshore applications

Originated as AS 60092.350—2005.
Jointly revised and redesignated as AS/NZS IEC 60092.350:2019.

COPYRIGHT

© IEC 2019 — All rights reserved
© Standards Australia Limited/the Crown in right of New Zealand, administered by the New Zealand Standards Executive 2019

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Cth) or the Copyright Act 1994 (New Zealand).

Preface

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee EL-003, Electric Wires and Cables, to supersede AS 60092.350—2005, *Electrical installations in ships, Part 350: Shipboard power cables — General construction and test requirements*.

The objective of this Standard is to provide the general constructional requirements and test methods for use in the manufacture of electric power, control and instrumentation cables with copper conductors intended for fixed electrical systems at voltages up to and including 18/30(36) kV on board ships and offshore (mobile and fixed) units.

The following types of cables are not included:

- (a) Optical fibre.
- (b) Sub-sea and umbilical cables.
- (c) Data and communication cables.
- (d) Coaxial cables.

This Standard is identical with, and has been reproduced from, IEC 60092-350:2014, *Electrical installations in ships — Part 350: General construction and test methods of power, control and instrumentation cables for shipboard and offshore applications*.

As this document has been reproduced from an International Standard, the following applies:

- (i) In the source text “this part of IEC 60092” should read “this Australian/New Zealand Standard”.
- (ii) A full point substitutes for a comma when referring to a decimal marker.

Australian or Australian/New Zealand Standards that are identical adoptions of international normative references may be used interchangeably. Refer to the online catalogue for information on specific Standards.

The terms “normative” and “informative” are used in Standards to define the application of the appendices or annexes to which they apply. A “normative” appendix or annex is an integral part of a Standard, whereas an “informative” appendix or annex is only for information and guidance.

NOTES

CONTENTS

FOREWORD.....	7
1 Scope.....	9
2 Normative references	9
3 Terms and definitions	11
4 Construction requirements.....	16
4.1 General requirements	16
4.1.1 General	16
4.1.2 Voltage designation	16
4.1.3 Cable marking	16
4.1.4 Core identification.....	17
4.1.5 Halogen-free cables	17
4.2 Conductors	17
4.2.1 Material	17
4.2.2 Metal coating and separator	17
4.2.3 Class and form	18
4.2.4 Resistance	18
4.3 Insulation system.....	19
4.3.1 Material	19
4.3.2 Application.....	19
4.3.3 Insulation thickness	19
4.4 Screens	19
4.4.1 Conductor and insulation screens for high-voltage cables.....	19
4.4.2 Screens (shields) for low voltage cables	20
4.5 Cabling	20
4.5.1 Multi-core cables	20
4.5.2 Multi-unit cables	20
4.6 Inner coverings, fillers and binders	21
4.7 Inner sheath.....	21
4.7.1 Material	21
4.7.2 Application.....	21
4.7.3 Thickness of inner sheath.....	21
4.8 Metal braid armour.....	21
4.8.1 Material	21
4.8.2 Application.....	22
4.9 Outer sheath.....	22
4.9.1 Material	22
4.9.2 Application.....	22
4.9.3 Thickness of outer sheath.....	22
5 Test methods.....	23
5.1 Test conditions	23
5.1.1 Ambient temperature	23
5.1.2 Frequency, waveform and magnitude of power-frequency test voltages	23
5.2 Routine tests	23
5.2.1 General	23
5.2.2 Measurement of the electrical resistance of the conductors	23
5.2.3 Voltage test	24

5.2.4	Partial discharge test.....	25
6	Sample tests	26
6.1	General.....	26
6.2	Frequency of sample tests	26
6.3	Repetition of tests.....	26
6.4	Conductor examination	26
6.5	Measurement of thickness of insulation.....	27
6.5.1	General	27
6.5.2	Procedure.....	27
6.5.3	Requirements	27
6.6	Measurements of thickness of non-metallic sheaths.....	27
6.6.1	General	27
6.6.2	Procedure.....	27
6.6.3	Requirements	27
6.7	Measurement of external diameter	27
6.8	Hot-set test for insulations and sheaths	27
6.8.1	General procedure.....	27
6.8.2	Requirements	28
6.9	Insulation resistance test (volume resistivity determination)	28
7	Type tests, electrical	29
7.1	General.....	29
7.2	Insulation resistance measurement.....	29
7.2.1	Measurement at ambient temperature.....	29
7.2.2	Measurement at maximum rated temperature	29
7.3	Increase in a.c. capacitance after immersion in water	30
7.3.1	General	30
7.3.2	Preparation of test specimens	30
7.3.3	Apparatus.....	30
7.3.4	Procedure.....	30
7.3.5	Requirements	30
7.4	High-voltage test for 4 h up to 1,8/3 kV	31
7.4.1	General	31
7.4.2	Requirement.....	31
7.5	Mutual capacitance (control and instrumentation cables only).....	31
7.6	Inductance to resistance ratio (control and instrumentation cables only)	31
7.7	High voltage sequence test (cables having a voltage rating higher than 3,6/6 (7,2) kV)	31
7.7.1	General	31
7.7.2	Special provisions	31
7.7.3	Partial discharge test.....	32
7.7.4	Bending test	32
7.7.5	Tan δ measurement as a function of the voltage	32
7.7.6	Tan δ measurement as a function of the temperature.....	32
7.7.7	Heating cycle test plus partial discharge test	33
7.7.8	Impulse withstand test, followed by a power-frequency voltage test	33
7.7.9	High-voltage test for 4h	33
8	Type tests, non-electrical.....	33
8.1	General.....	33
8.2	Measurement of thickness of insulation.....	33

8.3	Measurement of thickness of non-metallic sheaths (excluding inner coverings)	33
8.4	Tests for determining the mechanical properties of insulation before and after ageing	34
8.4.1	Sampling	34
8.4.2	Ageing treatments	34
8.4.3	Conditioning and mechanical tests	34
8.4.4	Requirements	34
8.5	Tests for determining the mechanical properties of sheaths before and after ageing	34
8.5.1	Sampling	34
8.5.2	Ageing treatments	34
8.5.3	Conditioning and mechanical tests	34
8.5.4	Requirements	34
8.6	Additional ageing test on pieces of completed cables (compatibility test)	34
8.6.1	General	34
8.6.2	Sampling	35
8.6.3	Ageing treatment	35
8.6.4	Mechanical tests	35
8.6.5	Requirements	35
8.7	Loss of mass test on PVC ST2 sheath	35
8.7.1	Procedure	35
8.7.2	Requirements	35
8.8	Test for the behaviour of PVC ST2 and halogen-free SHF 1 sheaths at high temperature (hot pressure test)	35
8.8.1	Procedure	35
8.8.2	Requirements	35
8.9	Test for the behaviour of PVC sheath ST2 and halogen-free SHF 1 and SHF 2 sheaths at low temperature	35
8.9.1	Procedure	35
8.9.2	Requirements	36
8.10	Special test for low temperature behaviour (when required)	36
8.11	Test of the metal coating of copper wires	36
8.12	Galvanizing test	36
8.13	Test for resistance of PVC ST2 and halogen-free SHF1 sheaths to cracking (heat shock test)	36
8.13.1	Procedure	36
8.13.2	Requirements	36
8.14	Ozone resistance test for insulation and for sheaths	36
8.14.1	Procedure	36
8.14.2	Requirements	36
8.15	Hot oil immersion test and enhanced hot oil immersion test for sheaths	36
8.15.1	Hot oil immersion test	36
8.15.2	Enhanced hot oil immersion test (when required)	37
8.16	Mud drilling fluid test (when required)	37
8.17	Fire tests	37
8.17.1	Flame-spread test on single cables	37
8.17.2	Flame-spread test on bunched cables	37
8.17.3	Smoke emission test	37
8.17.4	Acid gas emission test	37

8.17.5	pH and conductivity test	37
8.17.6	Fluorine content test	37
8.17.7	Fire-resistance test (test for circuit integrity cables)	38
8.18	Determination of hardness for HEPR	38
8.19	Determination of elastic modulus for HEPR	38
8.20	Durability of print	38
Annex A (normative) Fictitious calculation method for determination of dimensions of protective coverings		39
A.1	Overview	39
A.2	General	39
A.3	Method	39
A.3.1	Conductors	39
A.3.2	Cores	40
A.3.3	Diameter over laid-up cores	41
A.3.4	Inner coverings	43
A.3.5	Sheath	43
A.3.6	Braid armour	43
Annex B (informative) Recommended minimum spark test voltage levels (according to IEC 62230)		45
B.1	General	45
B.2	Test voltages	45
B.2.1	General	45
B.2.2	Contact electrodes	45
B.2.3	Non-contact electrodes	46
Annex C (normative) Rounding of numbers		47
C.1	Rounding of numbers for the purpose of the fictitious calculation method	47
C.1.1	Rules	47
C.1.2	Illustrations	47
C.2	Rounding of numbers for other purposes	47
Annex D (normative) Calculation of the lower and upper limits for the outer dimensions of cables with circular copper conductors		49
D.1	General	49
D.2	Lower limit for the outer diameter	49
D.3	Upper limit for the outer diameter	49
D.4	Thickness of the mandatory or optional coverings other than the insulation and the sheath(s)	50
Annex E (normative) Cold bend test and impact test for low temperature behaviour		52
E.1	Cold bend test at any specified low temperature	52
E.1.1	Method No. 1	52
E.1.2	Method No. 2	52
E.1.3	Examination and Requirements	53
E.2	Impact test at any specified low temperature	53
E.2.1	Apparatus	53
E.2.2	Procedures	53
E.2.3	Requirements	53
Bibliography		54

Table 1 – Minimum size of conductors	18
--	----

Table 2 – Routine test voltage	20
--------------------------------------	----

Table 3 – Number of samples according to cable length	26
Table 4 – Tan δ versus voltage	32
Table 5 – Tan δ versus temperature	32
Table 6 – Impulse withstand voltages	33
Table 7 – Test methods and requirements for halogen-free components	38
Table A.1 – Fictitious diameter of conductor	40
Table A.2 – Increase of diameter for concentric conductors and metallic screens made of tape or wire.....	40
Table A.3 – Assembly coefficient k for laid-up	42
Table A.4 – Coefficient c_f	43
Table B.1 – Recommended minimum spark-test voltages for cables having rated voltage (U_0) between 150 V and 1 800 V	45
Table D.1 – Lower and upper limits of circular copper conductors for cables for fixed installations	51
Table E.1 – Details of low temperature bending test	52

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ELECTRICAL INSTALLATIONS IN SHIPS –

Part 350: General construction and test methods of power, control and instrumentation cables for shipboard and offshore applications

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60092-350 has been prepared by subcommittee 18A: Electric cables for ships and mobile and fixed offshore units, of IEC technical committee 18: Electrical installations of ships and of mobile and fixed offshore units.

This fourth edition cancels and replaces the third edition published in 2008 and constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) reference to IEC 60092-360 for both the insulating and sheathing compounds;
- b) partial discharge tests have been transferred from IEC 60092-354 to align it with IEC 60092-353;
- c) requirements for oil and drilling-fluid resistance (former Annexes F and G) have been transferred to IEC 60092-360;

- d) requirements for cold bending and shocks have been improved;
- e) the document reflects the changes of material types that have been introduced during the development of IEC 60092-353 and IEC 60092-360.

The text of this standard is based on the following documents:

FDIS	Report on voting
18A/374/FDIS	18A/378/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The list of all the parts of the IEC 60092 series, under the general title *Electrical installations in ships*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

The contents of the corrigendum of November 2018 have been included in this copy.

ELECTRICAL INSTALLATIONS IN SHIPS –

Part 350: General construction and test methods of power, control and instrumentation cables for shipboard and offshore applications

1 Scope

This part of IEC 60092 provides the general constructional requirements and test methods for use in the manufacture of electric power, control and instrumentation cables with copper conductors intended for fixed electrical systems at voltages up to and including 18/30(36) kV on board ships and offshore (mobile and fixed) units.

The reference to fixed systems includes those that are subjected to vibration (due to the movement of the ship or installation) or movement (due to motion of the ship or installation) and not to those that are intended for frequent flexing. Cables suitable for frequent or continual flexing use are detailed in other IEC standards, for example IEC 60227 and IEC 60245, and their uses are restricted to those situations which do not directly involve exposure to a marine environment, for example, portable tools and domestic appliances.

The following types of cables are not included:

- optical fibre;
- sub-sea and umbilical cables;
- data and communication cables;
- coaxial cables.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-461, *International Electrotechnical Vocabulary – Part 461: Electric cables*

IEC 60092-353, *Electrical installations in ships – Part 353: Power cables for rated voltages 1 kV and 3 kV*

IEC 60092-360:2014, *Electrical installations in ships – Part 360: Insulating and sheathing materials for shipboard and offshore units, power, control, instrumentation, telecommunication and data cables*

IEC 60228, *Conductors of insulated cables*

IEC 60230, *Impulse tests on cables and their accessories*

IEC 60331-1, *Tests for electric cables under fire conditions – Circuit integrity – Part 1: Test method for fire with shock at a temperature of at least 830 °C for cables of rated voltage up to and including 0,6/1,0 kV and with an overall diameter exceeding 20 mm*

IEC 60331-2, *Tests for electric cables under fire conditions – Circuit integrity – Part 2: Test method for fire with shock at a temperature of at least 830 °C for cables of rated voltage up to and including 0,6/1,0 kV and with an overall diameter not exceeding 20 mm*

IEC 60331-11, *Tests for electric cables under fire conditions – Circuit integrity – Part 11: Apparatus – Fire alone at a flame temperature of at least 750 °C*

IEC 60331-21, *Tests for electric cables under fire conditions – Circuit integrity – Part 21: Procedures and requirements – Cables of rated voltage up to and including 0,6/1,0 kV*

IEC 60332-1-2, *Tests on electric and optical fibre cables under fire conditions – Part 1-2: Test for vertical flame propagation for a single insulated wire or cable – Procedure for 1 kW pre-mixed flame*

IEC 60332-3-22, *Tests on electric cables under fire conditions – Part 3-22: Test for vertical flame spread of vertically-mounted bunched wires or cables – Category A*

IEC 60684-2, *Flexible insulating sleeving – Part 2: Methods of test*

IEC 60754-1, *Test on gases evolved during combustion of materials from cables – Part 1: Determination of the halogen acid gas content*

IEC 60754-2, *Test on gases evolved during combustion of materials from cables – Part 2: Determination of acidity (by pH measurement) and conductivity*

IEC 60811-201, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 201: General tests – Measurement of insulation thickness*

IEC 60811-202, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 202: General tests – Measurement of thickness of non-metallic sheath*

IEC 60811-203, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 203: General tests – Measurement of overall dimensions*

IEC 60811-401, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 401: Miscellaneous tests – Thermal ageing methods – Ageing in an air oven*

IEC 60811-403, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 403: Miscellaneous tests – Ozone resistance test on cross-linked compounds*

IEC 60811-404, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 404: Miscellaneous tests – Mineral oil immersion tests for sheaths*

IEC 60811-409, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 409: Miscellaneous tests – Loss of mass test for thermoplastic insulations and sheaths*

IEC 60811-501, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 501: Mechanical tests – Tests for determining the mechanical properties of insulating and sheathing compounds*

IEC 60811-504, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 505: Mechanical tests – Bending tests at low temperature for insulations and sheaths*

IEC 60811-505, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 505: Mechanical tests – Elongation at low temperature for insulations and sheaths*

IEC 60811-506, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 505: Mechanical tests – Impact test at low temperature for insulations and sheaths*

IEC 60811-507, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 507: Mechanical tests – Hot set test for cross-linked materials*

IEC 60811-508, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 508: Mechanical tests – Pressure test at high temperature for insulation and sheaths*

IEC 60811-509, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 509: Mechanical tests – Test for resistance of insulations and sheaths to cracking (heat shock test)*

IEC 60885-2, *Electrical test methods for electric cables. Part 2: Partial discharge tests*

IEC 61034-1, *Measurement of smoke density of cables burning under defined conditions – Part 1: Test apparatus*

IEC 61034-2, *Measurement of smoke density of cables burning under defined conditions – Part 2: Test procedure and requirements*

ISO 7989-2:2007, *Steel wire and wire products – Non-ferrous metallic coatings on steel wire – Part 2: Zinc or zinc-alloy coating*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60050-461 as well as the following terms and definitions apply.

3.1 approximate value

value which is neither guaranteed nor checked

Note 1 to entry: It is used, for example, for the calculation of other dimensional values.

3.2 braid

covering formed from braided metallic or non-metallic material

[SOURCE: IEC 60050-461:2008, 461-05-10, modified ("plaited" replaced by "braided")]

3.3 braid armour

covering formed from braided metal wires used to protect a cable from external mechanical effects

Note 1 to entry: Where the rules of the applicable national, regulatory or approval body permit the practice, it is also possible to use the braid armour as an earth conductor.

Note 2 to entry: Copper-wire braid armour may also provide a limited function of an electrostatic collective screen, provided it is effectively earthed.

3.4 compatibility test

test intended to check that the insulation and sheath are not liable to deteriorate in operation due to contact either with each other or with other components in the cable

3.5**conductor (of a cable)**

part of a cable which has the specific function of carrying current

[SOURCE: IEC 60050-461:2008, 461-01-01]

3.6**conductor screen**

non-metallic conducting layer applied between the conductor and insulation to equalise the electrical stress between these components

Note 1 to entry: It may also provide smooth surfaces at the boundaries of the insulation and assist in the elimination of spaces at these boundaries

3.7**core-insulated conductor (North America)**

assembly comprising a conductor and its own insulation (and screens, if any)

Note 1 to entry: In North American usage, the core of a cable has been defined as the assembly of components of a cable lying under a common covering such as the sheath (jacket).

3.8**drain wire**

un-insulated wire laid in contact with an electrical screen or an electrical shield which has the specific function of earthing an electrostatic screen by ensuring a low resistive path throughout the length of the cable

[SOURCE: IEC 60050-461:2008, 461-03-07, modified (addition of text from "... which has ...")]

3.9**electrostatic screen****electrostatic shield (North America)**

earthed metallic layer surrounding a cable which confines the electric field generated by the cable within the cable cores, pair(s), triples(s) or quad(s), and/or protects the core(s), pair(s), triple(s) or quad(s) from external influence

Note 1 to entry: Metallic sheaths, foils, braids, armours and earthed concentric conductors may also serve as an electrostatic screen, provided they are effectively grounded or earthed.

3.10**fictitious value**

value calculated according to the "fictitious method" described in Annex A

[SOURCE: IEC 60502-2:2005, definition 3.1.4]

3.11**filler**

material used to fill the interstices between the cores of a multi-conductor cable

[SOURCE: IEC 60050-461:2008, 461-04-05]

3.12**fire resistance (circuit integrity)**

ability to continue to operate in the designated manner whilst subject to a specified flame source for a specified period of time

[SOURCE: IEC 60331-11:2009, definition 3.1, modified (addition of "fire resistance")]

3.13**flexible cable**

cable which is required to be capable of being flexed while in service and of which the structure and materials are such as to fulfil this requirement

[SOURCE: IEC 60050-461:2008, 461-06-14]

3.14**individually screened cable****radial field cable**

cable in which each core is covered with an individual screen

[SOURCE: IEC 60050-461:2008, 461-06-12]

3.15**inner covering**

non-metallic covering which surrounds the assembly of the cores (and fillers, if any) of a multi-conductor cable and over which further layers are applied and which has no mechanical or electrical functions

Note 1 to entry: The inner covering can be either extruded or taped, and in either case forms a continuous layer, which has only an approximate value of thickness and no defined mechanical requirements.

Note 2 to entry: Taped inner coverings are also sometimes called lapped beddings.

[SOURCE: IEC 60050-461:2008, 461-05-02, modified (addition of "further layers ..." and Notes 1 and 2 to entry)]

3.16**inner sheath****inner jacket (North America)**

non-metallic sheath generally applied under a metallic sheath, reinforcement or armour. It should be extruded

Note 1 to entry: The inner sheath shall have the following properties:

It shall be extruded;

It may be used to fill the interstices;

It shall be of a material listed in IEC 60092-360;

It shall have a defined nominal thickness (value).

3.17**insulated cable**

assembly consisting of

- one or more cores;
- their individual covering(s) (if any);
- assembly protection (if any);
- protective covering(s) (if any).

Note 1 to entry: Additional un-insulated conductor(s) may be included in the cable.

Note 2 to entry: The assembly protection may consist of fillers, binders or inner coverings.

Note 3 to entry: The protective covering(s) consists of one or more "constituent elements" such as a metallic braid, wire or a metallic screen, thermosetting or thermoplastic sheaths, (impregnated) fibrous braid or woven tape, bedding for metal armour or paint for metal armour.

[SOURCE: IEC 60050-461:2008, 461-06-01, modified (addition of Notes 2 and 3 to entry)]

3.18**insulation screen
core screen**

electrical screen of non-metallic semi-conducting layer in combination with a metallic layer

[SOURCE: IEC 60050-461:2008, 461-03-03, modified definition]

3.19**length of lay**

axial length of one complete turn of the helix formed by one cable component in a twisted construction

[SOURCE: IEC 60050-461:2008, 461-04-01, modified (addition of "in a twisted construction")]

3.20**median value**

middle value, when several results have been obtained and ordered in increasing (or decreasing) succession, if the number of available values is odd, and the mean of the two middle values if the number is even

[SOURCE: IEC 60502-2:2005, 3.1.3]

3.21**multi-unit cable**

cable consisting of more than one pair, triple or quad unit either unscreened or with an individual electrostatic screen around each unit or having an electrostatic screen applied around the assembly of units (a collective screen) in a twisted construction

3.22**nominal value**

value by which quantity is designated, and which is often used in tables

Note 1 to entry: Usually, in this standard, nominal values refer to values which are to be checked by measurements, taking into account specified tolerances.

3.23**oversheath****outer sheath****protective (overall) jacket** (North America)

non metallic sheath applied over a covering, generally metallic, ensuring the protection of the cable from the outside

Note 1 to entry: The outer sheath shall have the following properties:

- It shall be extruded;
- It may be used to fill the interstices;
- It shall be of a material listed in IEC 60092-360;
- It shall have a defined nominal thickness (value).

Note 2 to entry: In North-America, the term sheath is generally used for metallic coverings, whereas the term jacket is used only for non-metallic coverings.

3.24**pair unit**

two cores laid up with or without interstitial fillers or binder tape(s)

3.25**quad unit**

four cores laid up with or without interstitial fillers or binder tape(s)