

AS/NZS IEC 60754.1:2017
IEC 60754-1 ED. 3.0 (2011)
IEC 60754-1:2011/Amd 1:2019
(Incorporating Amendment No. 1)



Australian/New Zealand Standard™

Test on gases evolved during combustion of materials from cables

Part 1: Determination of the halogen acid gas content



AS/NZS IEC 60754.1:2017

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee EL-003, Electric Wires And Cables. It was approved on behalf of the Council of Standards Australia on 30 April 2017 and by the New Zealand Standards Approval Board on 7 June 2017.

This Standard was published on 30 June 2017.

The following are represented on Committee EL-003:

- Australian Cablemakers Association
- Australian Industry Group
- Electrical Compliance Testing Association
- Electrical Contractors Association of New Zealand
- Electrical Regulatory Authorities Council
- Institute of Electrical Inspectors
- National Electrical and Communications Association
- Queensland University of Technology
- WorkSafe New Zealand

This Standard was issued in draft form for comment as DR AS/NZS IEC 60754.1:2017.

Keeping Standards up-to-date

Ensure you have the latest versions of our publications and keep up-to-date about Amendments, Rulings, Withdrawals, and new projects by visiting:

www.standards.org.au

www.standards.govt.nz

ISBN 978 1 76035 835 8

Australian/New Zealand Standard™

Test on gases evolved during combustion of materials from cables

Part 1: Determination of the halogen acid gas content

Originated in Australia as AS 1660.5.3—1988.
Jointly revised and designated as AS/NZS 1660.5.3:1998.
AS/NZS 1660.5.3:1998 revised and redesignated as AS/NZS IEC 60754.1:2017.
Reissued incorporating Amendment No 1 (October 2021).



Standards Australia Limited/Standards New Zealand 2017

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Cth) or the Copyright Act 1994 (New Zealand).

Preface

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee, EL-003 Electric Wires and Cables, to supersede, in part, AS/NZS 1660.5.3:1998, *Test methods for electric cables, cords and conductors*, Method 5.3: *Fire tests—Determination of the amount of halogen acid gas evolved during the combustion of polymeric materials taken from cables*.

A1 Amendment No. 1 (October 2021) to this Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee EL-003, *Electric Cables and Wires*. **A1**

The objective of this Standard is to specify the apparatus and procedure for the determination of the amount of halogen acid gas, other than hydrofluoric acid, evolved during the combustion of compounds based on halogenated polymers and compounds containing halogenated additives taken from electric or optical fibre cable constructions.

A1 This Standard is identical with, and has been reproduced from IEC 60754-1:2011 (ED. 3.0), *Test on gases evolved during combustion of materials from cables, Part 1: Determination of the halogen acid gas content* and its Amendment No. 1 (2019) which has been added at the end of the source text. **A1**

As this Standard is reproduced from an International Standard, the following applies:

- (a) In the source text 'this part of IEC 60754' should read 'this Australian/New Zealand Standard'.
- (b) A full point substitutes for a comma when referring to a decimal marker.

None of the normative references in the source document have been adopted as Australian or Australian/New Zealand Standards.

NOTES

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references	7
3 Terms and definitions	7
4 Test method principle	8
5 Test apparatus	8
5.1 General	8
5.2 Tube furnace	8
5.3 Quartz glass tube	8
5.4 Combustion boats	8
5.5 Bubbling devices for gases	9
5.6 Air supply system	9
5.7 Analytical balance	10
5.8 Laboratory glassware	10
5.9 Reagents.....	10
6 Test specimen	10
6.1 General	10
6.2 Conditioning of specimen	10
6.3 Mass of specimen	11
7 Test procedure	11
7.1 General	11
7.2 Test apparatus and arrangement.....	11
7.3 Heating procedure	11
7.3.1 Determination of heating regime	11
7.3.2 Test specimen heating procedure	11
7.4 Washing procedure	12
7.5 Determination of halogen acid content.....	12
7.5.1 Blank test	12
7.5.2 Material test	12
7.5.3 Halogen acid content calculation	13
8 Evaluation of the test results	13
9 Performance requirement	13
10 Test report.....	13
Annex A (informative) Determination of the halogen acid gas content of a sample representative of a cable construction.....	20
Bibliography.....	21
Figure 1 – Device for inserting combustion boat and test specimen	15
Figure 2 – Example of a gas washing bottle	16
Figure 3 – Test apparatus: method 1 – Use of synthetic or compressed air from a bottle	17
Figure 4 – Test apparatus: method 2 – Use of laboratory compressed air supply	18

Figure 5 – Test apparatus: method 3 – Use of ambient air sucked by means of a suction pump	19
--	----

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**TEST ON GASES EVOLVED DURING
COMBUSTION OF MATERIALS FROM CABLES –****Part 1: Determination of the halogen acid gas content**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60754-1 has been prepared by IEC technical committee 20: Electric cables.

It has the status of a group safety publication in accordance with IEC Guide 104.

This third edition cancels and replaces the second edition, published in 1994, and constitutes a technical revision.

The significant technical changes with respect to the previous edition are as follows:

- improved definition of safety requirements relating to capture of gases and use of reagents;
- introduction of guidance on preparation of test specimens for a more even combustion;
- improvements to the procedure for establishing the heating regime;
- improved expression of tolerances and precision;

- definition of the procedure for the blank test;
- introduction of an informative annex giving details of a methodology for the determination of the halogen acid gas content of a sample representative of a cable construction.

The text of this standard is based on the following documents:

FDIS	Report on voting
20/1266/FDIS	20/1276/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60754 series, published under the general title *Test on gases evolved during combustion of materials from cables*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

The contents of the corrigendum of November 2013 have been included in this copy.

INTRODUCTION

IEC 60754 consists of the following parts, under the general title *Test on gases evolved during combustion of materials from cables*:

- *Part 1: Determination of the halogen acid gas content*
- *Part 2: Determination of acidity (by pH measurement) and conductivity*

IEC 60754-1 was developed due to concerns expressed by cable users over the amount of acid gas which is evolved when some cable insulating, sheathing and other materials are burned, as this acid can cause extensive damage to electrical and electronic equipment not involved in the fire itself.

This standard provides a method for determining the amount of acid gases evolved by burning cable components so that limits can be agreed for cable specifications. As the test is not carried out on a complete cable test piece, for a hazard assessment the actual material volumes of the cable components should be taken into consideration.

TEST ON GASES EVOLVED DURING COMBUSTION OF MATERIALS FROM CABLES –

Part 1: Determination of the halogen acid gas content

1 Scope

This part of IEC 60754 specifies the apparatus and procedure for the determination of the amount of halogen acid gas, other than hydrofluoric acid, evolved during the combustion of compounds based on halogenated polymers and compounds containing halogenated additives taken from electric or optical fibre cable constructions.

NOTE 1 This test method is not able to determine hydrofluoric acid. A suitable method may be found in IEC 60684-2.

NOTE 2 This test method may be used to test materials to be used in cable manufacture, but a declaration of cable performance should not be made based on such a test.

NOTE 3 The relevant cable standard should indicate which components of the cable should be tested.

NOTE 4 For the purposes of this standard, the term “electric cable” covers all insulated metallic conductor cables used for the conveyance of energy or signals.

The method specified in this standard is intended for the testing of individual components used in a cable construction. The use of this method will enable the verification of requirements which are stated in the appropriate cable specification for individual components of a cable construction.

NOTE 5 By agreement between the producer and purchaser, the methodology given in this standard may be used to test combinations of materials representing a cable construction, but a declaration of cable performance to this standard should not be made based on such a test. Information on such a method is given in Annex A.

For reasons of precision this method is not recommended for reporting values of halogen acid evolved less than 5 mg/g of the sample taken.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385, *Laboratory glassware – Burettes*

ISO 1042, *Laboratory glassware – One-mark volumetric flasks*

ISO 3696, *Water for analytical laboratory use – Specification and test methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

halogen acid gas content

amount of halogen acid gas evolved, except hydrofluoric acid, expressed as milligrams of hydrochloric acid per gram of total test specimen