

AS/NZS ISO 11798:2023
ISO 11798:2023



Australian/New Zealand Standard™

Information and documentation — Permanence and durability of writing, printing and copying on paper — Requirements and test methods



AS/NZS ISO 11798:2023

This Joint Australian/New Zealand Standard™ was prepared by Joint Technical Committee IT-019, Information and Documentation, Information Technology — Learning, Education, Training and Research. It was approved on behalf of the Council of Standards Australia on 29 September 2023 and by the New Zealand Standards Approval Board on 04 October 2023.

This Standard was published on 20 October 2023.

The following are represented on Committee IT-019:

- Australasian Society for Computers in Learning in Tertiary Education
- Australian Computer Society
- Australian Library and Information Association
- Australian Research Data Commons
- Caval
- Charles Darwin University
- Council of Australian University Librarians
- CSIRO
- Education Services Australia
- Flinders University
- Library & Archives NT
- Lincoln University
- Macquarie University
- National Library of New Zealand
- NSW Department of Education
- Professional Scientists Australia
- University of Otago, NZ
- Victoria University of Wellington, NZ

This Standard was issued in draft form for comment as DR AS/NZS ISO 11798:2023.

Keeping Standards up-to-date

Ensure you have the latest versions of our publications and keep up-to-date about Amendments, Rulings, Withdrawals, and new projects by visiting:

www.standards.org.au

www.standards.govt.nz

ISBN 978 1 76139 372 3

Australian/New Zealand Standard™

Information and documentation — Permanence and durability of writing, printing and copying on paper — Requirements and test methods

First published as AS/NZS ISO 11798:2004.
Second edition 2023.

COPYRIGHT

© ISO 2023 — All rights reserved

© Standards Australia Limited/the Crown in right of New Zealand, administered by the New Zealand Standards Executive 2023

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Cth) or the Copyright Act 1994 (New Zealand).

Preface

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee IT-019 Information and Documentation, Information Technology — Learning, Education, Training and Research, to supersede AS/NZS ISO 11798:2004.

The objective of this document is to specify requirements and test methods for evaluation of the permanence and durability of writing, printing, and copying on paper stored in libraries, archives, and other protected environments for long periods of time, in which the information recorded on paper must be retained but not necessarily the full artistic quality.

This document is identical with, and has been reproduced from, ISO 11798:2023, *Information and documentation — Permanence and durability of writing, printing, and copying on paper — Requirements and test methods*.

As this document has been reproduced from an International document, a full point substitutes for a comma when referring to a decimal marker.

Australian or Australian/New Zealand Standards that are identical adoptions of international normative references may be used interchangeably. Refer to the online catalogue for information on specific Standards.

The terms “normative” and “informative” are used in Standards to define the application of the appendices or annexes to which they apply. A “normative” appendix or annex is an integral part of a Standard, whereas an “informative” appendix or annex is only for information and guidance.

Contents

Preface	ii
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Preparation of specimens	4
4.1 Performance testing paper	4
4.2 Conditioning of document substrates and recording atmosphere	4
4.3 Guidance for sample preparation	4
4.4 Conditioning of specimens	4
4.5 Reference material used for testing of mechanical properties	5
5 Required characteristics	5
5.1 General	5
5.2 Colour fastness	5
5.3 Visual appearance	6
5.4 Lightfastness	6
5.5 Water resistance	6
5.6 Transfer of recording	6
5.7 Abrasion resistance	7
5.8 Resistance to heat	7
5.9 Effects of recording on the mechanical strength of the paper	7
5.9.1 General	7
5.9.2 Tensile energy absorption	7
5.9.3 Folding endurance	7
6 Test method and procedure	7
6.1 General	7
6.2 Colour fastness	8
6.3 Visual appearance	8
6.4 Lightfastness	9
6.5 Water resistance	9
6.6 Transfer of recording	9
6.7 Abrasion resistance	10
6.8 Resistance to heat	11
6.9 Effects of recording on the mechanical strength of the paper	11
6.9.1 General	11
6.9.2 Tensile energy absorption	12
6.9.3 Folding endurance	12
7 Test report	13
Annex A (normative) Performance testing paper	14
Annex B (normative) Specimen preparation	15
Annex C (normative) Printout templates for sample preparation of printers and copying machines	17
Annex D (informative) Reporting forms	22
Bibliography	25

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 46, *Information and documentation*, Subcommittee SC 10, *Requirements for document storage and conditions for preservation*.

This second edition cancels and replaces the first edition (ISO 11798:1999), which has been technically revised.

The main changes are as follows.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

It is of great importance that recording of images on paper which, during long-term storage in libraries, archives, and other protected environments, undergo little or no change in properties that affects its use. The documents must preserve their information content and, thus, enable information storage and information supply for the future. Accordingly, it is important to study the permanence and durability of recording on paper.

Writing materials and printing equipment meeting the requirements given in this document can be used in the preparation of paper documents intended for long-term storage and recurrent use. Such documents contain permanent and durable images, i.e. images likely to be stable and thus undergo little or no change in properties that influence legibility and the possibility of copying or converting the paper documents to other data carriers.

Permanent paper and archival paper, used in the preparation of documents, may differ widely in properties of importance for the quality and permanence of the image. Some properties of an image, such as abrasion resistance, depend on the combination of the image and the paper. The testing conditions of this document are chosen so that results, representative of most papers on the market to be used for a particular imaging process, shall be obtained.

In this document, the requirements are given in the following attributes:

Experience has shown that images written with carbon black ink as well as printed images using commercial printing inks have proved to be consistently reliable. There are, however, many documents where acidic inks have affected the paper to such an extent that the paper has degraded. Images produced from dry or liquid toner are also susceptible to ageing problems.

Images printed with modern material and machinery are often completely different from old images with respect to composition and properties. The rapid development of new printing techniques makes this testing very important. One printing technology may be replaced by a newer technology within a few years on the market. Therefore, conclusions based on studies of old documents in libraries and archives are of limited use when discussing the permanence of modern documents.

Strictly speaking, the only way to test the permanence and durability of documents is to handle them and to store them under the relevant conditions for long periods of time. In practice, one can only rely on the observations made on documents kept for a few decades and evaluate the effect of factors known to influence the permanence and durability of the image. Therefore, the testing according to this document does not correlate to lifetime of documents, but rather the documents that satisfy the requirements can be stored for a long time in the future in archives and protected environments, probably for several hundred years.

NOTES

Australian/New Zealand Standard

Information and documentation — Permanence and durability of writing, printing and copying on paper — Requirements and test methods

1 Scope

This document specifies requirements and test methods for evaluation of the permanence and durability of writing, printing and copying on paper stored in libraries, archives, and other protected environments for long periods of time, in which the information recorded on paper must be retained but not necessarily the full artistic quality.

It is applicable to:

It does not apply to:

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 536, *Paper and board — Determination of grammage*

ISO 1924-2, *Paper and board — Determination of tensile properties — Part 2: Constant rate of elongation method (20 mm/min)*

ISO 2470-1, *Paper, board and pulps — Measurement of diffuse blue reflectance factor — Part 1: Indoor daylight conditions (ISO brightness)*

ISO 4892-2, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps*

ISO 5626, *Paper — Determination of folding endurance*

ISO 9352, *Plastics — Determination of resistance to wear by abrasive wheels*

ISO 9706, *Information and documentation — Paper for documents — Requirements for permanence*

ISO 11108, *Information and documentation — Archival paper — Requirements for permanence and durability*

ISO 12757-1, *Ball point pens and refills — Part 1: General use*

ISO 13655, *Graphic technology — Spectral measurement and colorimetric computation for graphic arts images*

ISO 14145-1, *Roller ball pens and refills — Part 1: General use*

ISO 27668-1, *Gel ink ball pens and refills — Part 1: General use*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

3.1 abrasion resistance rub resistance

characteristic of a document with *recording* (3.14) against losses of image or text from the action of abrasion (i.e. the ability of materials and structures to withstand mechanical wear or rubbing by means of friction)

Note 1 to entry: Abrasion resistance is measured in this standard as the *degree of abrasion resistance*, R_a (3.4).

3.2 archival paper

paper of high *permanence* (3.11) and high *durability* (3.6)

[SOURCE: ISO 11108:1996, 3.1]

3.3 CIELAB colour shift

lightness and colour change (ΔL^* , Δa^* , Δb^* and ΔE_{ab}^*) measured between two coordinates in the CIELAB colour space

Note 1 to entry: CIELAB colour space is a three-dimensional, approximately uniform colour space, produced by plotting, in rectangular coordinates L^* , a^* , b^* . It was defined by the International Commission on Illumination (CIE) in 1976 (Synonymously referred to as CIE 1976 $L^*a^*b^*$, CIELAB colour space or CIELAB values.).

Note 2 to entry: The quantity L^* is a measure of the lightness, where $L^* = 0$ corresponds to black and $L^* = 100$ corresponds to the perfect reflecting diffuser. Visually, the quantities a^* and b^* represent respectively the red-green and yellow-blue axes in colour space, such that:

If both a^* and b^* are equal to zero, the test piece is grey

Note 3 to entry: Synonymously referred to as CIE 1976 $L^*a^*b^*$, CIELAB colour space or CIELAB values.

Note 4 to entry: Adapted from ISO/TS 21331:2020, 3.3.5.

3.4 degree of abrasion resistance R_a

measure of the magnitude of retain of recorded image (or text) on paper because of abrasion (or wear, or rubbing)

Note 1 to entry: Degree of abrasion resistance is evaluated by measuring the % of changes in L^* of a printed image or text prior to and after the abrasion test, according to ISO 13655, and is calculated according to [Formula \(5\)](#) in [6.7](#).

3.5 document

recorded information which can be treated as a unit in a documentation process

[SOURCE: ISO 5127:2017, 3.1.1.38, modified — "material object" and Notes to entry have been deleted from the definition.]

3.6 durability

ability to resist the effect of physical stress, such as wear and tear, pressure, or damage during recurrent use

3.7 image

visual representation with colourants (such as dyes or pigments) distributed on paper as text characters, lines, colour patches or other visually identifiable patterns

3.8**monochromatic image**

image (3.7) with *recording* (3.14) uniformly in one colour

Note 1 to entry: Images produced in one colour from a black and white printer, or any colour from a printer that can produce other colours, such as black, cyan, magenta and yellow.

3.9**multicoloured image**

image (3.7) composed of *recording* (3.14) in more than one colour, where the colours constitute part of the information contents

Note 1 to entry: It can be separated into different base colours (e.g. black, cyan magenta and yellow).

Note 2 to entry: Not to be confused with a coloured image. A coloured image is in this standard referred to as an image recorded in any colour as a *monochromatic image* (3.8).

3.10**performance testing paper**

permanent paper (3.13) or *archival paper* (3.2) used for sample preparation

Note 1 to entry: The performance testing paper shall be handled according to [clause 4.1](#) and meet the requirements of [Annex A](#).

3.11**permanence**

ability to remain chemically and physically stable over long periods of time

3.12**permanent image**

image (3.7) which, during long-term storage in libraries, archives and other protected environments will undergo little or no change in properties that affect its use

3.13**permanent paper**

paper of high *permanence* (3.11) in accordance with ISO 9706

3.14**recording**

process of performing writing, printing and copying on paper

3.15**spot colour image**

specialized ink mixes to create a specific predetermined uniform colour in commercial printing

3.16**sample**

aggregate of all the *specimens* (3.17) taken to be representative of a lot

[SOURCE: ISO 4046-5:2016, 5.100]

3.17**specimen**

portion of a paper or board sample (in this context performance testing paper with recording from the tested writing, printing, or copying material) sufficient in size so that *test pieces* (3.18) can be obtained from it

[SOURCE: ISO 4046-5:2016, 5.106, modified — text in brackets has been added.]