

Australian/New Zealand Standard™

**Welding consumables—Tubular cored
electrodes and rods for gas shielded
and non-gas shielded metal arc welding
of stainless and heat-resisting steels—
Classification (ISO 17633:2004, MOD)**



AS/NZS ISO 17633:2006

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee WD-002, Welding Consumables. It was approved on behalf of the Council of Standards Australia on 9 May 2006 and on behalf of the Council of Standards New Zealand on 19 May 2006.
This Standard was published on 6 June 2006.

The following are represented on Committee WD-002:

Australian Chamber of Commerce and Industry
Bureau of Steel Manufacturers of Australia
Business New Zealand
CSIRO Manufacturing and Infrastructure Technology
Welding Technology Institute of Australia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at www.standards.com.au or Standards New Zealand web site at www.standards.co.nz and looking up the relevant Standard in the on-line catalogue.

Alternatively, both organizations publish an annual printed Catalogue with full details of all current Standards. For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of either Standards Australia or Standards New Zealand at the address shown on the back cover.

This Standard was issued in draft form for comment as DR 06067.

Australian/New Zealand Standard™

Welding consumables—Tubular cored electrodes and rods for gas shielded and non-gas shielded metal arc welding of stainless and heat-resisting steels—Classification (ISO 17633:2004, MOD)

First published as AS/NZS ISO 17633:2006.

COPYRIGHT

© Standards Australia/Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Jointly published by Standards Australia, GPO Box 476, Sydney, NSW 2001 and Standards New Zealand, Private Bag 2439, Wellington 6020

ISBN 0 7337 7483 0

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee WD-002, Welding Consumables.

The objective of this Standard is to specify requirements for classification of tubular flux and metal cored electrodes and rods, based on the all-weld metal chemical composition, the type of electrode core, shielding gas, welding position and the all-weld metal mechanical properties, in the as welded or heat treated conditions, for gas shielded and non-gas shielded metal arc welding of stainless and heat-resisting steels.

This Standard is an adoption with national modifications, to take account of Australian/New Zealand conditions, and has been reproduced from ISO 17633:2004 *Welding consumables — Tubular cored electrodes and rods for gas shielded and non-gas shielded metal arc welding of stainless and heat-resisting steels — Classification*.

Variations to ISO 17633:2004 are indicated at the appropriate places throughout this standard. Strikethrough (~~example~~) identifies ISO text, tables and figures which, for the purposes of this Australian/New Zealand Standard, are deleted. Where text, tables or figures are added, each is set in its proper place and identified by shading (~~example~~). Added figures are not themselves shaded, but are identified by a shaded border.

As this Standard is reproduced from an International Standard, the following applies:

- (a) Its number does not appear on each page of text and its identity is shown only on the cover and title page.
- (b) In the source text 'ISO 17633' should read 'AS/NZS ISO 17633'.
- (c) A full point should be substituted for a comma when referring to a decimal marker.
- (d) Any French text on figures should be ignored.

The term 'informative' is used in this Standard to define the application of the annex to which it applies. An informative annex is for information and guidance.

CONTENTS

	<i>Page</i>
1 Scope	1
2 Normative references	1
3 Classification	2
4 Symbols and requirements	3
4.1 Symbol for the product/process	3
4.2 Symbol for the chemical composition of all-weld metal	4
4.3 Symbol for type of electrode core	14
4.4 Symbol for Shielding gases	14
4.5 Symbol for welding position	15
5 Mechanical tests	16
5.1 Preheating and interpass temperatures	16
5.2 Pass sequence	17
6 Chemical analysis	17
7 Fillet weld test	17
8 Retests	18
9 Technical delivery conditions	18
10 Examples of designation	19
Annex A (informative) Comparison charts of alloy designation according to nominal composition and alloy type	20
Annex B (informative) Description of types of electrode core — classification according to nominal composition	21
Annex C (informative) Description of types of tubular cored electrodes and rods — classification according to alloy type	22
Annex D (informative) Considerations on weld metal ferrite contents [2]	23
Annex ZA (informative) Health and safety	26
Bibliography	28

INTRODUCTION

This International Standard provides a classification system for tubular cored electrodes and rods for welding stainless steels. It recognizes that there are two somewhat different approaches in the global market, to classifying a given tubular stainless steel welding consumable, and allows for either or both to be used, to suit a particular market need. Application of either type of classification designation (or of both where suitable) identifies a product as classified according to this International Standard.

The classification according to system A is mainly based on EN 12073:1999, Welding consumables — Tubular cored electrodes for metal arc welding with or without a gas shield of stainless and heat-resisting steels — Classification. The classification according to system B is mainly based upon standards used around the Pacific Rim.

Requests for official interpretations of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 3, via your national standards body, a complete listing of which can be found at www.iso.org.

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

Australian/New Zealand Standard**Welding consumables—Tubular cored electrodes and rods for gas shielded and non-gas shielded metal arc welding of stainless and heat-resisting steels—Classification (ISO 17633:2004, MOD)**

Any table, figure or text of the international standard that is struck through is not part of this standard. Any Australian/New Zealand table, figure or text that is added is part of this standard and is identified by shading.

1 Scope

This International Standard specifies requirements for classification of tubular flux and metal cored electrodes and rods, based on the all-weld metal chemical composition, the type of electrode core, shielding gas, welding position and the all-weld metal mechanical properties, in the as welded or heat treated conditions, for gas shielded and non-gas shielded metal arc welding of stainless and heat-resisting steels.

This International Standard is a combined standard providing for classification utilizing a system based upon classification according to nominal composition, or utilizing a system based upon classification according to alloy type.

- 1) Paragraphs and tables which carry the label “classification according to nominal composition” are applicable only to products classified to that system.
- 2) Paragraphs and tables which carry the label “classification according to alloy type” are applicable only to products classified to that system.
- 3) Paragraphs and tables which carry neither label are applicable to products classified according to either or both systems.

It is recognized that the operating characteristics of tubular cored electrodes can be modified by the use of pulsed current, but for the purposes of this International Standard, pulsed current is not permitted for determining the electrode classification.

NOTE – General information on health and safety in welding is given in Annex ZA.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

References to international standards that are struck through in this clause are replaced by references to Australian or Australian/New Zealand Standards that are listed immediately thereafter and identified by shading. Any Australian or Australian/New Zealand Standard that is identical to the International Standard it replaces is identified as such.

ISO 31-0:1992, *Quantities and units — Part 0: General principles*

~~ISO 544, *Welding consumables — Technical delivery conditions for welding filler materials — Type of product, dimensions, tolerances and marking*~~

AS/NZS ISO 544, *Welding consumables—Technical delivery conditions for welding filler materials—Type of product, dimensions, tolerances and marking.*

~~ISO 3690, Welding and allied processes — Determination of hydrogen content in ferritic steel arc weld metal~~

ISO 6847, Welding consumables — Deposition of a weld metal pad for chemical analysis

~~ISO 6947:1990, Welds — Working positions — Definitions of angles of slope and rotation~~

AS 3545, Welding positions

~~ISO 13916, Welding — Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature~~

AS/NZS ISO 13916, Welding—Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature.

~~ISO 14175:1997, Welding consumables — Shielding gases for arc welding and cutting~~

AS 4882, Shielding gases for welding

~~ISO 14344, Welding and allied processes — Flux and gas shielded electrical welding processes — Procurement guidelines for consumables~~

AS/NZS ISO 14344, Welding and allied processes—Flux and gas shielded electrical welding processes—Procurement guidelines for consumables.

ISO 15792-1:2000, Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys

ISO 15792-3, Welding Consumables — Test methods — Part 3: Classification testing of positional capacity and root penetration of welding consumables in a fillet weld

3 Classification

Classification designations are based upon two approaches to indicating the chemical composition of the all-weld metal deposit obtained with a given electrode or rod.

The “nominal composition” approach uses designation components indicating directly the nominal levels of certain alloying elements, given in a particular order, and some symbols for low but significant levels of other elements, whose levels are not conveniently expressed as integers. The “alloy type” approach uses tradition-based three or four-digit designations for alloy families, and an occasional additional character or characters for compositional modifications of each original alloy within the family. The two designation approaches include additional designators for all other classification requirements, but not entirely the same classification requirements, as will be clear from the following.

In most cases, a given commercial product can be classified in both systems. Then either or both classification designations can be used for the product.

3A Classification according to nominal composition

The classification is divided into five parts:

- 1) The first part gives a symbol indicating the product/process to be identified (see 4.1A);
- 2) The second part gives a symbol indicating the chemical composition of the all-weld metal (see Table 1A);
- 3) The third part gives a symbol indicating the type of electrode core (see Table 3A);
- 4) The fourth part gives a symbol indicating the shielding gas (see 4.4);
- 5) The fifth part gives a symbol indicating the welding position (see Table 4A).

In order to promote the use of this International Standard, the classification is split into two sections:

b) Compulsory section

This section includes the symbols for the type of product, the chemical composition of all-weld metal, the type of electrode core and the shielding gas, viz, the symbols defined in Clause 4.

a) Optional section

This section includes the symbol for the welding position for which the electrode is suitable, viz, the symbols defined in Table 4A.

The full identification (see Clause 10) shall be used on packages and in the manufacturer's literature and data sheets.

4 Symbols and requirements

4.1 Symbol for the product/process

4.1A Classification according to nominal composition

The symbol for the tubular cored electrode used in the metal arc welding process shall be the letter "T".

3B Classification according to alloy type

The classification is divided into five parts:

- 6) The first part gives a symbol indicating the tubular cored electrode and rod (see 4.1B);
- 7) The second part gives a symbol indicating the chemical composition of the all-weld metal (see Table 1B);
- 8) The third part gives a symbol indicating the type of tubular cored electrode or rod (see Table 3B);
- 9) The fourth part gives a symbol indicating the shielding gas (see 4.4);
- 10) The fifth part gives a symbol indicating the welding position (see Table 4B).

This section includes the symbols for the type of product, the chemical composition of all-weld metal, the type of electrode core, the shielding gas and the welding position, viz, the symbols defined in Clause 4.

4.1B Classification according to alloy type

The symbol for the tubular cored electrode or rod used in the metal arc welding process shall be the letters "TS". The initial letter, "T", indicates tubular cored electrode or rod as distinguished from covered electrodes and from solid electrodes and rods. The second letter, "S", indicates that the alloy system is stainless or heat-resisting steel.

4.2 Symbol for the chemical composition of all-weld metal

4.2A Classification according to nominal composition

The symbol in Table 1A identifies the chemical composition of all-weld metal determined in accordance with Clause 6. The all-weld metal obtained with the tubular cored electrodes in Table 1A under conditions given in Clause 5 shall also fulfil the requirements given in Table 2A. (See Annex A.)

4.2B Classification according to alloy type

The symbol in Table 1B identifies the chemical composition of all-weld metal determined in accordance with Clause 6. The all-weld metal obtained with the tubular cored electrodes and rods in Table 1B under conditions given in Clause 5 shall also fulfil the requirements given in Table 2B. (See Annex A.)

Table 1A — Symbol for chemical composition requirements for all-weld metal (classification according to nominal composition)

Alloy designation according to nominal composition	Chemical composition (percentage mass fraction) ^{a, b, c}												
	Shielding gas- ^d	C	Mn	Si	P ^e	S ^e	Cr	Ni	Mo	Nb + Ta ^f	Cu	N	Ti
13	M ₁ -C ₁ -N	0,12	1,5	1,0	0,030	0,025	11,0 to 14,0	0,3	0,3	—	0,3	—	—
13 Ti	M ₁ -C ₁ -N	0,10	0,80	1,0	0,030	0,030	10,5 to 13,0	0,3	0,3	—	0,3	—	10 × C to 1,5
13 4	M ₁ -C ₁ -N	0,06	1,5	1,0	0,030	0,025	11,0 to 14,5	3,0 to 5,0	0,4 to 1,0	—	0,3	—	—
17	M ₁ -C ₁ -N	0,12	1,5	1,0	0,030	0,025	16,0 to 18,0	0,3	0,3	—	0,3	—	—
19 9 L	M ₁ -C ₁ -N	0,04	2,0	1,2	0,030	0,025	18,0 to 21,0	9,0 to 11,0	0,3	—	0,3	—	—
19 9 Nb	M ₁ -C ₁ -N	0,08	2,0	1,2	0,030	0,025	18,0 to 21,0	9,0 to 11,0	0,3	8 × C to 1,1	0,3	—	—
19 12 3 L	M ₁ -C ₁ -N	0,04	2,0	1,2	0,030	0,025	17,0 to 20,0	10,0 to 13,0	2,5 to 3,0	—	0,3	—	—
19 12 3 Nb	M ₁ -C ₁ -N	0,08	2,0	1,2	0,030	0,025	17,0 to 20,0	10,0 to 13,0	2,5 to 3,0	8 × C to 1,1	0,3	—	—
19 13 4 N L	M ₁ -C ₁ -N	0,04	1,0 to 5,0	1,2	0,030	0,025	17,0 to 20,0	12,0 to 15,0	3,0 to 4,5	—	0,3	0,08 to 0,20	—
22 9 3 N L	M ₁ -C ₁ -N	0,04	2,5	1,2	0,030	0,025	21,0 to 24,0	7,5 to 10,5	2,5 to 4,0	—	0,3	0,08 to 0,20	—
18 16 5 N L	M ₁ -C ₁ -N	0,04	1,0 to 4,0	1,2	0,035	0,025	17,0 to 20,0	15,5 to 19,0	3,5 to 5,0	—	0,3	0,08 to 0,20	—
18 8 Mn	M ₁ -C ₁ -N	0,20	4,5 to 7,5	1,2	0,035	0,025	17,0 to 20,0	7,0 to 10,0	0,3	—	0,3	—	—
20 10 3	M ₁ -C ₁ -N	0,08	2,5	1,2	0,035	0,025	19,5 to 22,0	9,0 to 11,0	2,0 to 4,0	—	0,3	—	—
23 12 L	M ₁ -C ₁ -N	0,04	2,5	1,2	0,030	0,025	22,0 to 25,0	11,0 to 14,0	0,3	—	0,3	—	—
23 12 2 L	M ₁ -C ₁ -N	0,04	2,5	1,2	0,030	0,025	22,0 to 25,0	11,0 to 14,0	2,0 to 3,0	—	0,3	—	—
29 9	M ₁ -C ₁ -N	0,15	2,5	1,2	0,035	0,025	27,0 to 31,0	8,0 to 12,0	0,3	—	0,3	—	—
22 12 H	M ₁ -C ₁ -N	0,15	2,5	1,2	0,030	0,025	20,0 to 23,0	10,0 to 13,0	0,3	—	0,3	—	—
25 20	M ₁ -C ₁ -N	0,06 to 0,20	1,0 to 5,0	1,2	0,030	0,025	23,0 to 27,0	18,0 to 22,0	0,3	—	0,3	—	—

^a Single values shown in the table are maximum values.

^b Tubular cored electrodes not listed in the table shall be symbolized similarly and prefixed by the letter "Z".

^c The results shall be rounded to the same number of significant figures as in the specified value using the rules in accordance with Annex B, Rule A of ISO 31-0:1992.

^d The symbol N shall be used for tubular cored electrodes without a gas shield.

^e The sum of P and S shall not exceed 0,050 %, except for 18 16 5 L, 18 8 Mn and 29 9.

^f Up to 20 % of the amount of Nb can be replaced by Ta.

**Table 1B-1 — Symbol for chemical composition requirements for all-weld metal of gas shielded flux cored electrodes
(classification according to alloy type)**

Alloy designation according to alloy type	Chemical composition (percentage mass fraction) a, b, c												
	Shielding gas (see 4.4)	C	Mn	Si	P	S	Cr	Ni	Mo	Nb + Ta	Cu	N	Ti
307	M ₁ , B ₁ , C ₁ , G	0,13	3,30 to 4,75	1,0	0,04	0,03	18,0 to 20,5	9,0 to 10,5	0,5 to 1,5	–	0,5	–	–
308	M ₁ , B ₁ , C ₁ , G	0,08	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	9,0 to 11,0	0,5	–	0,5	–	–
308L	M ₁ , B ₁ , C ₁ , G	0,04	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	9,0 to 12,0	0,5	–	0,5	–	–
308H	M ₁ , B ₁ , C ₁ , G	0,04 to 0,08	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	9,0 to 11,0	0,5	–	0,5	–	–
308Mo	M ₁ , B ₁ , C ₁ , G	0,08	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	9,0 to 11,0	2,0 to 3,0	–	0,5	–	–
308LMo	M ₁ , B ₁ , C ₁ , G	0,04	0,5 to 2,5	1,0	0,04	0,03	18,0 to 21,0	9,0 to 12,0	2,0 to 3,0	–	0,5	–	–
309	M ₁ , B ₁ , C ₁ , G	0,10	0,5 to 2,5	1,0	0,04	0,03	22,0 to 25,0	12,0 to 14,0	0,5	–	0,5	–	–
309L	M ₁ , B ₁ , C ₁ , G	0,04	0,5 to 2,5	1,0	0,04	0,03	22,0 to 25,0	12,0 to 14,0	0,5	–	0,5	–	–
309Mo	M ₁ , B ₁ , C ₁ , G	0,12	0,5 to 2,5	1,0	0,04	0,03	21,0 to 25,0	12,0 to 16,0	2,0 to 3,0	–	0,5	–	–
309LMo	M ₁ , B ₁ , C ₁ , G	0,04	0,5 to 2,5	1,0	0,04	0,03	21,0 to 25,0	12,0 to 16,0	2,0 to 3,0	–	0,5	–	–
309LNb	M ₁ , B ₁ , C ₁ , G	0,04	0,5 to 2,5	1,0	0,04	0,03	22,0 to 25,0	12,0 to 14,0	0,5	0,7 to 1,0	0,5	–	–
310	M ₁ , B ₁ , C ₁ , G	0,20	1,0 to 2,5	1,0	0,03	0,03	25,0 to 28,0	20,0 to 22,5	0,5	–	0,5	–	–
312	M ₁ , B ₁ , C ₁ , G	0,15	0,5 to 2,5	1,0	0,04	0,03	28,0 to 32,0	8,0 to 10,5	0,5	–	0,5	–	–
316	M ₁ , B ₁ , C ₁ , G	0,08	0,5 to 2,5	1,0	0,04	0,03	17,0 to 20,0	11,0 to 14,0	2,0 to 3,0	–	0,5	–	–
316L	M ₁ , B ₁ , C ₁ , G	0,04	0,5 to 2,5	1,0	0,04	0,03	17,0 to 20,0	11,0 to 14,0	2,0 to 3,0	–	0,5	–	–
316H	M ₁ , B ₁ , C ₁ , G	0,04 to 0,08	0,5 to 2,5	1,0	0,04	0,03	17,0 to 20,0	11,0 to 14,0	2,0 to 3,0	–	0,5	–	–
316LCu	M ₁ , B ₁ , C ₁ , G	0,04	0,5 to 2,5	1,0	0,04	0,03	17,0 to 20,0	11,0 to 16,0	1,25 to 2,75	–	1,0 to 2,5	–	–