

AS/NZS ISO 18274:2023
ISO 18274:2023



Australian/New Zealand Standard™

Welding consumables — Solid wire electrodes, solid strip electrodes, solid wires and solid rods for fusion welding of nickel and nickel alloys — Classification



AS/NZS ISO 18274:2023

This Joint Australian/New Zealand Standard™ was prepared by Joint Technical Committee WD-002, Welding Consumables. It was approved on behalf of the Council of Standards Australia on 13 September 2023 and by the New Zealand Standards Approval Board on 06 September 2023.

This Standard was published on 20 October 2023.

The following are represented on Committee WD-002:

Australian Chamber of Commerce and Industry
Bureau of Steel Manufacturers of Australia
New Zealand Heavy Engineering Research Association
University of Auckland (New Zealand)
Weld Australia

This Standard was issued in draft form for comment as DR AS/NZS ISO 18274:2023.

Keeping Standards up-to-date

Ensure you have the latest versions of our publications and keep up-to-date about Amendments, Rulings, Withdrawals, and new projects by visiting:

www.standards.org.au

www.standards.govt.nz

ISBN 978 1 76139 341 9

Australian/New Zealand Standard™

Welding consumables — Solid wire electrodes, solid strip electrodes, solid wires and solid rods for fusion welding of nickel and nickel alloys — Classification

Originated in Australia as AS B29—1932.
Jointly revised and redesignated as AS/NZS 1167.2:1999.
Jointly revised and redesignated as AS/NZS ISO 18274:2023.

COPYRIGHT

© ISO — All rights reserved

© Standards Australia Limited/the Crown in right of New Zealand, administered by the New Zealand Standards Executive 2023

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Cth) or the Copyright Act 1994 (New Zealand).

Preface

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee WD-002, Welding Consumables, to supersede AS/NZS 1167.2:1999, *Welding and brazing — Filler metals, Part 2: Filler metal for welding*.

The objective of this document is to specify requirements for classification of solid wire electrodes, solid strip electrodes, solid wires and solid rods for fusion welding of nickel and nickel alloys. The classification of the solid wire electrodes, solid strip electrodes, solid wires and solid rods is based on their chemical composition. It includes those compositions in which the nickel content exceeds that of any other element.

The principles of this document can be applied to metal powders for cladding, hard facing and additive manufacturing.

This document is identical with, and has been reproduced from, ISO 18274:2023, *Welding consumables — Solid wire electrodes, solid strip electrodes, solid wires and solid rods for fusion welding of nickel and nickel alloys — Classification*.

As this document has been reproduced from an International document, a full point substitutes for a comma when referring to a decimal marker.

Australian or Australian/New Zealand Standards that are identical adoptions of international normative references may be used interchangeably. Refer to the online catalogue for information on specific Standards.

The terms “normative” and “informative” are used in Standards to define the application of the appendices or annexes to which they apply. A “normative” appendix or annex is an integral part of a Standard, whereas an “informative” appendix or annex is only for information and guidance.

Contents

Preface	ii
Foreword	iv
Introduction	v
Section 1 Scope	1
Section 2 Normative references	1
Section 3 Terms and definitions	1
Section 4 Classification	1
Section 5 Symbols and requirements	1
5.1 Symbols for the product form	1
5.2 Symbol for the chemical composition	2
Section 6 Chemical analysis	10
Section 7 Mechanical properties of the weld metal	10
Section 8 Rounding procedure	10
Section 9 Retests	10
Section 10 Technical delivery conditions	10
Section 11 Designation	10
Annex A (informative) System for designation of welding consumables	12
Annex B (informative) Description and uses of welding consumables	13
Annex C (informative) Corresponding national classifications and typical weld metal tensile strengths	21
Bibliography	25

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 18274:2010), which has been technically revised.

The main changes are as follows:

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html. Official interpretations of ISO/TC 44 documents, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

Introduction

For nickel welding consumables, there is no unique relationship between the product form, for example: and the welding process used, for example:

Consequently, solid wire electrodes, solid strip electrodes, solid wires or solid rods can be classified on the basis of any of these product forms and can be used, as appropriate, for more than one of these processes (see also [Annex B](#)).

The International Organization for Standardization (ISO) draws attention to the fact that it is claimed that compliance with this document may involve the use of a patent.

ISO takes no position concerning the evidence, validity and scope of this patent right.

The holder of this patent right has assured ISO that they are willing to negotiate licences under reasonable and non-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holder of this patent right is registered with ISO. Information may be obtained from the patent database available at www.iso.org/patents.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those in the patent database. ISO shall not be held responsible for identifying any or all such patent rights.

NOTES

Australian/New Zealand Standard

Welding consumables — Solid wire electrodes, solid strip electrodes, solid wires and solid rods for fusion welding of nickel and nickel alloys — Classification

Section 1 Scope

This document specifies requirements for classification of solid wire electrodes, solid strip electrodes, solid wires and solid rods for fusion welding of nickel and nickel alloys. The classification of the solid wire electrodes, solid strip electrodes, solid wires and solid rods is based on their chemical composition. It includes those compositions in which the nickel content exceeds that of any other element.

The principles of this document can be applied to metal powders for cladding, hard facing and additive manufacturing.

Section 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 80000-1:2022, *Quantities and units — Part 1: General*

Section 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

Section 4 Classification

The symbol for the classification is divided into two parts:

- a) the first part indicates the product form, being solid wire electrode, solid strip electrode, solid wire or solid rod, see [5.1](#);
- b) the second part gives a numerical symbol indicating the chemical composition of the solid wire electrode, solid strip electrode, solid wire or solid rod, see [Table 1](#).

Section 5 Symbols and requirements

5.1 Symbols for the product form

The symbol for the solid wire electrode, solid wire or solid rod shall be “S”.

The symbol for the solid strip electrode shall be “B”.

NOTE One product form can be used for more than one welding process.

5.2 Symbol for the chemical composition

The initial symbol “Ni” in [Table 1](#) identifies the welding consumable as a nickel base alloy. The following four digits indicate the chemical composition of the solid wire electrode, solid strip electrode, solid wire or solid rod, determined under conditions given in [Clause 6](#). The first digit is an indicator of the alloy group as follows:

The remaining digits indicate the alloy composition of the welding consumable. The basis of the system of designation is described in [Annex A](#). A description of common uses of each welding consumable alloy is given in [Annex B](#).

NOTE 1 In addition, the chemical symbol can be used.

NOTE 2 Corresponding national classifications are shown in [Annex C, Table C.1](#).

Table 1 — Symbols and chemical composition requirements for solid wire electrodes, solid strip electrodes, solid wires and solid rods

Alloy symbols		Chemical composition, % (mass fraction) ^a													
Numerical ^b	Chemical	C	Mn	Fe	Si	Cu	Ni ^c	Co	Al	Ti	Cr	Nb ^d	Mo	W	Other ^{e, f}
Nickel															
Ni 2061	NiTi3	0,15	1,0	1,0	0,7	0,25	≥ 92,0	—	1,5	2,0 to 3,5	—	—	—	—	P 0,03
Ni 2061B	(NiTi3)	0,15	1,0	1,0	0,7	0,25	≥ 93,0	—	1,5	2,0 to 3,5	—	—	—	—	P 0,03
Nickel-copper															
Ni 4060	NiCu30Mn3Ti	0,15	4,0	2,5	1,2	28,0 to 32,0	62,0 to 69,0	—	1,2	1,5 to 3,0	—	0,3	—	—	—
Ni 4061	NiCu30Mn3Nb	0,15	4,0	2,5	1,25	28,0 to 32,0	≥ 60,0	—	1,0	1,0	—	3,0	—	—	—
Ni 5504	NiCu25Al3Ti	0,25	1,5	2,0	1,0	≥ 20,0	63,0 to 70,0	—	2,0 to 4,0	0,3 to 1,0	—	—	—	—	P 0,03
Nickel-chromium															
Ni 6072	NiCr44Ti	0,01 to 0,10	0,20	0,50	0,20	0,50	≥ 52,0	—	—	0,3 to 1,0	42,0 to 46,0	—	—	—	—
Ni 6073	NiCr38AlNbTi	0,03	0,50	1,0	0,30	0,30	≥ 63,0	1,0	0,75 to 1,20	0,25 to 0,75	36,0 to 39,0	0,25 to 1,00	0,50	—	P 0,02 B 0,003 Zr 0,02
Ni 6076	NiCr20	0,08 to 0,15	1,0	2,00	0,30	0,50	≥ 75,0	—	0,4	0,15 to 0,50	19,0 to 21,0	—	—	—	P 0,03
Ni 6082	NiCr20Mn3Nb	0,10	2,5 to 3,5	3,0	0,5	0,5	≥ 67,0	—	—	0,7	18,0 to 22,0	2,0 to 3,0	—	—	P 0,03
Ni 6699	NiCr29Al	0,005 to 0,10	0,5	2,5	0,50	0,50	≥ 60	—	1,9 to 3,0	0,60	26,0 to 30,0	0,50	—	—	Zr 0,10 N 0,05 S 0,01 B 0,008
Nickel-chromium-iron															
Ni 6002	NiCr21Fe18Mo9	0,05 to 0,15	1,0	17,0 to 20,0	1,0	0,5	≥ 44,0	0,5 to 2,5	—	—	20,5 to 23,0	—	8,0 to 10,0	0,2 to 1,0	P 0,04 S 0,03
Ni 6025	NiCr25Fe10AlY	0,15 to 0,25	0,5	8,0 to 11,0	0,5	0,1	≥ 59,0	1,0	1,8 to 2,4	0,1 to 0,2	24,0 to 26,0	—	—	—	Y 0,05 to 0,12 Zr 0,01 to 0,10