

Australian/New Zealand Standard™

**Welding consumables—Tubular cored
electrodes for gas shielded and non-gas
shielded metal arc welding of high-
strength steels—Classification
(ISO 18276:2005, MOD)**



AS/NZS ISO 18276:2006

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee WD-002, Welding Consumables. It was approved on behalf of the Council of Standards Australia on 4 September 2006 and on behalf of the Council of Standards New Zealand on 15 September 2006.
This Standard was published on 19 October 2006.

The following are represented on Committee WD-002:

Australian Chamber of Commerce and Industry
Bureau of Steel Manufacturers of Australia
Business New Zealand
CSIRO Manufacturing & Infrastructure Technology
Welding Technology Institute of Australia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at www.standards.com.au or Standards New Zealand web site at www.standards.co.nz and looking up the relevant Standard in the on-line catalogue.

Alternatively, both organizations publish an annual printed Catalogue with full details of all current Standards. For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of either Standards Australia or Standards New Zealand at the address shown on the back cover.

This Standard was issued in draft form for comment as DR 06415.

Australian/New Zealand Standard™

**Welding consumables—Tubular cored
electrodes for gas shielded and non-gas
shielded metal arc welding of high-
strength steels—Classification
(ISO 18276:2005, MOD)**

Originated as AS 2203—1981.

Revised and redesignated AS 2203.1—1990.

Revised (in part) and redesignated AS/NZS ISO 18276:2006.

COPYRIGHT

© Standards Australia/Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Jointly published by Standards Australia, GPO Box 476, Sydney, NSW 2001 and Standards New Zealand, Private Bag 2439, Wellington 6020

ISBN 0 7337 7779 1

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee WD-002, Welding Consumables, to supersede (in part) AS 2203.1:1990, *Covered electrodes for arc-welding*, Part 1: *Ferritic steel electrodes*.

The objective of this Standard is to provide requirements for classification of tubular cored electrodes with or without a gas shield for metal arc welding of high-strength steels.

This Standard is an adoption with national modifications and has been reproduced from ISO 18276:2005, *Welding consumables—Tubular cored electrodes for gas shielded and non-gas shielded metal arc welding of high-strength steels—Classification*, and has been varied as indicated to take account of Australian/New Zealand conditions.

As this Standard is reproduced from an International Standard, the following applies:

- (a) Its number does not appear on each page of text and its identity is shown only on the cover and title page.
- (b) In the source text ‘ISO number’ should read ‘AS or AS/NZS number’.
- (c) A full point should be substituted for a comma when referring to a decimal marker.
- (d) Any French text on figures should be ignored.

The terms ‘normative’ and ‘informative’ are used to define the application of the annex to which they apply. A normative annex is an integral part of a standard, whereas an informative annex is only for information and guidance.

For the purpose of this standard, the ISO text is modified as set out in Annex ZA.

References to International Standards should be replaced by references to Australian or Australian/New Zealand Standards, as follows:

<i>Reference to International Standard</i>		<i>Australian or Australian/New Zealand</i>	
ISO		AS	
31-0	Quantities and units— Part 0: General principles	2900.0	Quantities and units—General principles
		AS/NZS	
544	Welding consumables—Technical delivery conditions for welding filler metals—Type of product, dimensions, tolerances and marking	544	Welding consumables—Technical delivery conditions for welding filler metals—Type of product, dimensions, tolerances and marking
3690	Welding and allied processes—Determination of hydrogen content in ferritic steel arc weld metal	3752	Welding and allied processes—Determination of hydrogen content in ferritic steel arc weld metal
		AS	
6947	Welds—Working positions—Definitions of angles of slope and rotation	3545	Welding positions

ISO		AS/NZS	
13916	Welding—Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature	13916	Welding—Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature
		AS	
14175	Welding Consumables — Shielding gases for arc welding and cutting	4882	Shielding gases for welding
		AS/NZS	
14344	Welding and allied processes—Flux and gas shielded electrical welding processes—Procurement guidelines for consumables	14344	Welding and allied processes—Flux and gas shielded electrical welding processes—Procurement guidelines for consumables

CONTENTS

	<i>Page</i>
Introduction	v
1 Scope	1
2 Normative references	1
3 Classification	2
4 Symbols and requirements	4
4.1 Symbol for the product/process	4
4.2 Symbol for tensile properties of all-weld metal	4
4.3 Symbol for impact properties of all-weld metal	5
4.4 Symbol for chemical composition of all-weld metal	5
4.5 Symbol for type of electrode core or the usability characteristics of the electrodes	8
4.6 Symbol for shielding gas	9
4.7 Symbol for welding position	9
4.8 Symbol for hydrogen content of deposited metal	10
4.9 Symbol for conditions of post-weld heat treatment	10
4.10 Rounding-off procedure	10
5 Mechanical tests	11
5.1 Preheating and interpass temperatures	11
5.2 Pass sequence	12
5.3 Post-weld heat treatment (PWHT) condition	12
6 Chemical analysis	13
7 Fillet weld test	13
8 Retest	14
9 Technical delivery conditions	14
10 Examples of designations	14
Annex A	16
Annex B	19
Annex C	20
Annex D	21
Annex E	23
Annex ZA	24
Annex ZB	25

INTRODUCTION

This International Standard proposes a classification system for tubular cored electrodes in terms of the tensile properties, impact properties, chemical composition of the all-weld metal, type of electrode core, shielding gas and welding position. The ratio of yield strength to tensile strength of the weld metal is generally higher than that of the parent metal. Users should note that matching weld metal yield strength to parent metal yield strength will not necessarily ensure that the weld metal tensile strength matches that of the parent metal. Where the application requires matching tensile strength, therefore, selection of the consumable should be made by reference to column 3 of Table 1A or Table 1B.

It should be noted that the mechanical properties of all-weld metal test specimens used to classify tubular cored electrodes will differ from those obtained with production joints because of differences in welding procedure such as electrode size, width of weave, welding position and parent metal composition.

The classification in accordance with system A is mainly based on EN 12535:2000, *Welding consumables — Tubular cored electrodes for gas shielded metal arc welding of high strength steels — Classification*. The classification in accordance with system B is mainly based upon standards used around the Pacific Rim.

Requests for official interpretation of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 3 via the user's national standardization body. A complete listing of these bodies can be found at <<http://www.iso.org>>.

NOTES

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

**Welding consumables—Tubular cored electrodes for gas shielded and non-gas shielded metal arc welding of high-strength steels—
Classification (ISO 18276:2005, MOD)**

1 Scope

This International Standard specifies requirements for classification of tubular cored electrodes with or without a gas shield for metal arc welding of high-strength steels in the as-welded condition or in the post-weld heat-treated condition with a minimum yield strength higher than 550 MPa or a minimum tensile strength higher than 590 MPa. One tubular cored electrode can be tested and classified with different shielding gases, if used with more than one.

This document is a combined specification providing classification utilizing a system based upon the yield strength and an average impact energy of 47 J of the all-weld metal, or utilizing a system based upon the tensile strength and an average impact energy of 27 J of the all-weld metal.

- 1) Subclauses and tables which carry the suffix letter "A" are applicable only to tubular cored electrodes classified under the system based upon the yield strength and an average impact energy of 47 J of the all-weld metal given in this International Standard.
- 2) Subclauses and tables which carry the suffix letter "B" are applicable only to tubular cored electrodes classified under the system based upon the tensile strength and an average impact energy of 27 J of the all-weld metal given in this International Standard.
- 3) Subclauses and tables which do not have either the suffix letter "A" or the suffix letter "B" are applicable to all tubular cored electrodes classified under this International Standard.

It is recognized that the operating characteristics of tubular cored electrodes can be modified by the use of pulsed current but, for the purposes of this International Standard, pulsed current is not used for determining the electrode classification.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 31-0:1992, *Quantities and units — Part 0: General principles*

ISO 544, *Welding consumables — Technical delivery conditions for welding filler materials — Type of product, dimensions, tolerances and markings*

ISO 3690, *Welding and allied processes — Determination of hydrogen content in ferritic steel arc weld metal*

ISO 6847, *Welding consumables — Deposition of a weld metal pad for chemical analysis*

ISO 6947:1990, *Welds — Working positions — Definitions of angles of slope and rotation*

ISO 13916, *Welding — Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature*

ISO 14175:1997, *Welding consumables — Shielding gases for arc welding and cutting*

ISO 14344, *Welding and allied processes — Flux and gas shielded electrical welding processes — Procurement guidelines for consumables*

ISO 15792-1:2000, *Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys*

ISO 15792-3, *Welding consumables — Test methods — Part 3: Classification testing of positional capacity and root penetration of welding consumables in a fillet weld*

3 Classification

Classification designations are based upon two approaches to indicate the tensile properties and the impact properties of the all-weld metal obtained with a given electrode. The two designation approaches include additional designators for some other classification requirements, but not all, as will be clear from the following subclauses. In most cases, a given commercial product can be classified under both systems. Then either or both classification designations can be used for the product.

The classification includes all-weld metal properties obtained with a tubular cored electrode and appropriate shielding gas combination as given below. With the exception of the symbol for welding position, which is based on ISO 15792-3, the classification of gas-shielded tubular cored electrodes is based on an electrode size of 1,2 mm or, if this size is not manufactured, the next larger diameter manufactured, and the classification of self-shielded tubular cored electrodes is based on a diameter of 2,4 mm or the largest diameter manufactured if less than 2,4 mm.

3.1A Classification by yield strength and 47 J impact energy

The classification designation is divided into nine parts:

- 1) the first part (T) indicates a tubular cored electrode;
- 2) the second part gives a symbol indicating the strength and elongation of the all-weld metal in the as-welded or post-weld heat-treated condition (see Table 1A);
- 3) the third part gives a symbol indicating the impact properties of the all-weld metal (see Table 2);

3.1B Classification by tensile strength and 27 J impact energy

The classification designation is divided into nine parts:

- 1) the first part (T) indicates a tubular cored electrode;
- 2) the second part gives a symbol indicating the strength and elongation of the all-weld metal in either the as-welded or the post-weld heat-treated condition (see Table 1B);
- 3) the third part gives a symbol indicating the impact properties of the all-weld metal (see Table 2). The symbol “U”, added as an optional supplemental designator at or near the end of the complete tubular cored electrode designation, indicates that the deposit meets an average optional requirement of 47 J at the designated Charpy test temperature;

- | | |
|---|---|
| <p>4) the fourth part gives a symbol indicating the chemical composition of the all-weld metal (see Table 3A);</p> <p>5) the fifth part gives a symbol indicating the type of electrode core (see Table 4A);</p> <p>6) the sixth part gives a symbol indicating the shielding gas (see 4.6 and 4.6A);</p> <p>7) the seventh part gives a symbol indicating the welding position (see Table 5A);</p> <p>8) the eighth part gives a symbol indicating the hydrogen content of the deposited metal (see Table 6);</p> <p>9) the ninth part gives a symbol indicating the post-weld heat treatment if this is applied (see 4.9A).</p> | <p>4) the fourth part gives a symbol indicating the usability characteristics of the electrode (see Table 4B);</p> <p>5) the fifth part gives a symbol indicating the welding position (see Table 5B);</p> <p>6) the sixth part gives a symbol indicating the shielding gas (see 4.6 and 4.6B);</p> <p>7) the seventh part gives a symbol indicating whether the classification tests were conducted in the as-welded condition (A) or the post-weld heat-treated condition (P);</p> <p>8) the eighth part gives a symbol indicating the chemical composition of the all-weld metal (see Table 3B);</p> <p>9) the ninth part gives a symbol indicating the hydrogen content of the deposited metal (see Table 6).</p> |
|---|---|

Electrodes may be classified under any number of classifications for either or both the as-welded and post-weld heat-treated condition.

In both systems, the electrode classification shall include all the compulsory section and may include the optional section, as outlined below.

3.2A Compulsory and optional sections in the classification by yield strength and 47 J impact energy

a) Compulsory section

This section includes the symbols for the type of product, the strength and elongation, the impact properties, the chemical composition, the type of electrode core, the shielding gas and the post-weld heat treatment, i.e. the symbols defined in 4.1, 4.2, 4.3A, 4.4, 4.5A, 4.6 and 4.9A.

b) Optional section

This section includes the symbols for the welding positions for which the electrode is suitable and the symbol for hydrogen content, i.e. the symbols defined in 4.7 and 4.8.

3.2B Compulsory and optional sections in the classification by tensile strength and 27 J impact energy

a) Compulsory section

This section includes the symbols for the type of product, the strength and elongation in the as-welded condition or post-weld heat-treated condition, the welding positions for which the electrode is suitable, the usability characteristics, the shielding gas, the impact properties and the chemical composition, i.e. the symbols defined in 4.1, 4.2, 4.3B, 4.4, 4.5B, 4.6, 4.7 and 4.9B.

b) Optional section

This section includes the symbol "U" to indicate that the weld metal will have an average of 47 J impact energy at the classification test temperature and the symbol for hydrogen content, i.e. the symbol "U" defined in 4.3B and the symbols defined in 4.8.

The full designation (see Clause 10) shall be used on packages and in the manufacturer's literature and data sheets.

4 Symbols and requirements

4.1 Symbol for the product/process

The symbol for the tubular cored electrodes used in the metal arc welding process is the letter T.

4.2 Symbol for tensile properties of all-weld metal

The symbol in Table 1A or 1B indicates the yield strength, tensile strength and elongation of the all-weld metal, determined in accordance with Clause 5.

Table 1A — Symbol for tensile properties of all-weld metal (classification by yield strength and 47 J impact energy)

Symbol	Minimum yield strength ^a MPa	Tensile strength MPa	Minimum elongation ^b %
55	550	640 to 820	18
62	620	700 to 890	18
69	690	770 to 940	17
79	790	880 to 1 080	16
89	890	940 to 1 180	15
^a For yield strength, the lower yield (R_{eL}) is used when yielding occurs, otherwise the 0,2 % proof strength ($R_{p0,2}$) is used. ^b Gauge length is equal to five times the test specimen diameter.			

Table 1B — Symbol for tensile properties of all-weld metal (classification by tensile strength and 27 J impact energy)

Symbol	Minimum yield strength ^a MPa	Tensile strength MPa	Minimum elongation ^b %
59	490	590 to 790	16
62	530	620 to 820	15
69	600	690 to 890	14
76	680	760 to 960	13
78	680	780 to 980	13
83	745	830 to 1 030	12
^a For yield strength, the lower yield (R_{eL}) is used when yielding occurs, otherwise the 0,2 % proof strength ($R_{p0,2}$) is used. ^b Gauge length is equal to five times the test specimen diameter.			

4.3 Symbol for impact properties of all-weld metal

4.3A Classification by yield strength and 47 J impact energy

The symbols in Table 2 indicate the temperature at which an impact energy of 47 J is achieved under the conditions given in Clause 5. Three test specimens shall be tested. Only one individual value may be lower than 47 J but not lower than 32 J.

4.3B Classification by tensile strength and 27 J impact energy

The symbols in Table 2 indicate the temperature at which an impact energy of 27 J is achieved in the as-welded condition or in the post-weld heat-treated condition under the conditions given in Clause 5. Five test specimens shall be tested. The lowest and highest values obtained shall be disregarded. Two of the three remaining values shall be greater than the specified 27 J level, one of the three may be lower but shall not be less than 20 J. The average of the three remaining values shall be at least 27 J. Three test specimens shall be tested when the optional symbol “U” is used to indicate that the weld deposit will meet a minimum impact energy of 47 J at the test temperature. The impact value shall be determined by the average of the three test specimens. The average of the three values shall be 47 J or greater.

When an all-weld metal has been classified for a certain temperature, it automatically covers any higher temperature in Table 2.

Table 2 — Symbol for impact properties of all-weld metal

Symbol	Temperature for minimum average impact energy of 47 J ^a or 27 J ^b °C
Z	No requirements
A ^a or Y ^b	+ 20
0	0
2	– 20
3	– 30
4	– 40
5	– 50
6	– 60
7	– 70
8	– 80
^a Classification by yield strength and 47 J impact energy (see 4.3A).	
^b Classification by tensile strength and 27 J impact energy (see 4.3B).	

4.4 Symbol for chemical composition of all-weld metal

The symbols in Table 3A or Table 3B indicate the chemical composition of the all-weld metal, determined in accordance with Clause 6.