

Australian/New Zealand Standard™

**Ophthalmic optics—Uncut finished
spectacle lenses**

**Part 3: Transmittance specifications
and test methods**



AS/NZS ISO 8980.3:2015

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee MS-024, Spectacles. It was approved on behalf of the Council of Standards Australia on 20 January 2015 and on behalf of the Council of Standards New Zealand on 20 January 2015.

This Standard was published on 12 February 2015.

The following are represented on Committee MS-024:

Australian Dispensing Opticians Association
New Zealand Association of Optometrists
Optical Distributors and Manufacturers Association of Australia
Optometrists Association Australia
Queensland University of Technology
University of Auckland (New Zealand)
University of Melbourne
University of New South Wales

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at www.saiglobal.com.au or Standards New Zealand web site at www.standards.co.nz and looking up the relevant Standard in the on-line catalogue.

For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of either Standards Australia or Standards New Zealand at the address shown on the back cover.

This Standard was issued in draft form for comment as DR AS/NZS ISO 8980.3:2014.

Australian/New Zealand Standard™

Ophthalmic optics—Uncut finished spectacle lenses

Part 3: Transmittance specifications and test methods

Originated as AS/NZS ISO 8980.3:2011.
Second edition 2015.

COPYRIGHT

© Standards Australia Limited/Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Australia) or the Copyright Act 1994 (New Zealand).

Jointly published by SAI Global Limited under licence from Standards Australia Limited, GPO Box 476, Sydney, NSW 2001 and by Standards New Zealand, Private Bag 2439, Wellington 6140.

ISBN 978 1 74342 977 8

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee MS-024, Spectacles, to supersede AS/NZS ISO 8980.3:2011.

The objective of this Standard is to specify the requirements for the transmittance properties of uncut finished spectacle lenses.

This Standard is identical with, and has been reproduced from, ISO 8980-3:2013, *Ophthalmic optics—Uncut finished spectacle lenses, Part 3: Transmittance specifications and test methods*.

As this Standard is reproduced from an International Standard, the following applies:

- (a) In the source text ‘this part of ISO 8980’ should read ‘this Australian/New Zealand Standard’.
- (b) A full point substitutes for a comma when referring to a decimal marker.

References to International Standards should be replaced by references to Australian or Australian/New Zealand Standards, as follows:

<i>Reference to International Standard</i>		<i>Australia/New Zealand Standard</i>	
ISO		AS/NZS ISO	
13666	Ophthalmic optics—Spectacle lenses—Vocabulary	13666	Ophthalmic optics—Spectacle lenses—Vocabulary
14889	Ophthalmic optics—Spectacle lenses—Fundamental requirements for uncut finished lenses	14889	Ophthalmic optics—Spectacle lenses—Fundamental requirements for uncut finished lenses

Only normative references that have been adopted as Australian or Australian/New Zealand Standard have been listed.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the annexes to which they apply. A ‘normative’ annex is an integral part of a Standard, whereas an ‘informative’ annex is only for information and guidance.

CONTENTS

1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Symbols	4
5	Classification	4
6	Requirements	4
6.1	General	4
6.2	General transmittance requirements	5
6.3	Spectral transmittance requirements of spectacle lenses intended for road use and driving	6
6.4	Additional transmittance requirements for special types of spectacle lenses	6
6.5	Resistance to radiation	7
7	Test methods	8
7.1	General	8
7.2	Spectral transmittance	8
7.3	Luminous transmittance and relative visual attenuation coefficient (quotient)	8
7.4	Ultraviolet transmittance	8
7.5	Transmittance properties of photochromic spectacle lenses and photochromic specimens	9
7.6	Test methods for polarizing spectacle lenses	11
7.7	Determination of resistance to radiation	13
8	Identification	14
Annex A	(normative) Spectral data for calculating relative visual attenuation quotients for incandescent signal lights	15
Annex B	(normative) Calculation of solar UV transmittance values	20
Annex C	(normative) Cut-on filter for UV filtering	22
Annex D	(informative) Spectral data for calculating relative visual attenuation quotients for LED signal lights	25
Annex E	(informative) Spectral radiation risks	28
Annex F	(informative) Example of the calculation of luminous transmittance, τ_v	29
	Bibliography	31

NOTES

AUSTRALIA/NEW ZEALAND STANDARD

Ophthalmic optics—Uncut finished spectacle lenses**Part 3:****Transmittance specifications and test methods****1 Scope**

This part of ISO 8980 specifies requirements for the transmittance properties of uncut finished spectacle lenses and mounted pairs, including attenuation of solar radiation.

This part of ISO 8980 is not applicable to

- spectacle lenses having particular transmittance or absorption characteristics prescribed for medical reasons;
- products where specific personal protective equipment transmittance standards apply;
- products intended for direct observation of the sun, such as for solar-eclipse viewing.

NOTE Optical and geometric requirements for uncut finished spectacle lenses are specified in ISO 8980-1 and ISO 8980-2, and for mounted lenses, in ISO 21987.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11664-1, *Colorimetry — Part 1: CIE standard colorimetric observers*

ISO 11664-2, *Colorimetry — Part 2: CIE standard illuminants*

ISO 13666, *Ophthalmic optics — Spectacle lenses — Vocabulary*

ISO 14889, *Ophthalmic optics — Spectacle lenses — Fundamental requirements for uncut finished lenses*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 13666 apply.

NOTE 1 For the convenience of the reader, the following definitions have been reproduced from ISO 13666.

NOTE 2 Absorptance, reflectance and transmittance are usually expressed as percentages. The equations in this clause are written in this form. Although the definitions use integrals, in practice summation, typically at 1 nm, 5 nm or 10 nm intervals, is performed to calculate the various transmittances.

3.1**mean UV-A transmittance**

τ_{UVA}

mean transmittance between 315 nm and 380 nm

$$\tau_{\text{UVA}} = 100 \times \frac{1}{65 \text{ nm}} \int_{315 \text{ nm}}^{380 \text{ nm}} \tau(\lambda) \cdot d\lambda \%$$

[ISO 13666:2012, definition 15.3.1]

3.2

solar UV-A transmittance

τ_{SUVA}

mean of the spectral transmittance between 315 nm and 380 nm weighted by the solar radiation distribution $E_s(\lambda)$ at sea level, for air mass 2, and the relative spectral effectiveness function for UV radiation $S(\lambda)$

$$\tau_{\text{SUVA}} = 100 \times \frac{\int_{315 \text{ nm}}^{380 \text{ nm}} \tau(\lambda) \cdot E_s(\lambda) \cdot S(\lambda) \cdot d\lambda}{\int_{315 \text{ nm}}^{380 \text{ nm}} E_s(\lambda) \cdot S(\lambda) \cdot d\lambda} \%$$

Note 1 to entry: The complete weighting function $W(\lambda)$ is the product of $E_s(\lambda)$ and $S(\lambda)$ and is given in [Table B.1](#).

[SOURCE: ISO 13666:2012, definition 15.3.2]

3.3

solar UV-B transmittance

τ_{SUVB}

mean of the spectral transmittance between 280 nm and 315 nm weighted by the solar radiation distribution $E_s(\lambda)$ at sea level, for air mass 2, and the relative spectral effectiveness function for UV radiation $S(\lambda)$

$$\tau_{\text{SUVB}} = 100 \times \frac{\int_{280 \text{ nm}}^{315 \text{ nm}} \tau(\lambda) \cdot E_s(\lambda) \cdot S(\lambda) \cdot d\lambda}{\int_{280 \text{ nm}}^{315 \text{ nm}} E_s(\lambda) \cdot S(\lambda) \cdot d\lambda} \%$$

Note 1 to entry: The complete weighting function $W(\lambda)$ is the product of $E_s(\lambda)$ and $S(\lambda)$ and is given in [Table B.1](#).

[SOURCE: ISO 13666:2012, definition 15.3.3]

3.4

luminous transmittance

τ_V

ratio of the luminous flux transmitted by the lens or filter to the incident luminous flux

$$\tau_V = 100 \times \frac{\int_{380 \text{ nm}}^{780 \text{ nm}} \tau(\lambda) \cdot V(\lambda) \cdot S_{\text{D65}}(\lambda) \cdot d\lambda}{\int_{380 \text{ nm}}^{780 \text{ nm}} V(\lambda) \cdot S_{\text{D65}}(\lambda) \cdot d\lambda} \%$$

where

$\tau(\lambda)$ is the spectral transmittance of the spectacle lens;

$V(\lambda)$ is the spectral luminous efficiency function for daylight (see ISO 11664-1);

$S_{\text{D65}}(\lambda)$ is the spectral distribution of radiation of CIE standard illuminant D65 (see ISO 11664-2).

Note 1 to entry: The spectral values of the product of the spectral radiation distributions $S_{\text{D65}}(\lambda)$ of the CIE standard illuminant D65 and the eye's spectral luminous efficiency function $V(\lambda)$ are given in [Table A.2](#).

[SOURCE: ISO 13666:2012, definition 15.4]

3.5

relative visual attenuation coefficient (quotient) for incandescent traffic signal light recognition/detection

Q-value

ratio of the luminous transmittance of a tinted lens for the spectral radiant power distribution of the light emitted by a traffic signal τ_{signal} to the luminous transmittance of the same lens for CIE standard illuminant D65 (τ_V)

$$Q = \frac{\tau_{\text{signal}}}{\tau_V}$$

where

τ_{signal} is the luminous transmittance of the lens for the spectral radiant power distribution of the traffic signal light.

Note 1 to entry: *Q*-values can be determined for each of blue, green, amber (yellow) and red signal lights. τ_{signal} is given by the equation:

$$\tau_{\text{signal}} = 100 \times \frac{\int_{380 \text{ nm}}^{780 \text{ nm}} \tau(\lambda) \cdot \tau_S(\lambda) \cdot V(\lambda) \cdot S_A(\lambda) \cdot d\lambda}{\int_{380 \text{ nm}}^{780 \text{ nm}} \tau_S(\lambda) \cdot V(\lambda) \cdot S_A(\lambda) \cdot d\lambda} \%$$

where

$\tau_S(\lambda)$ is the spectral transmittance of the traffic signal lens;

$S_A(\lambda)$ is the spectral distribution of radiation of CIE standard illuminant A (or 3 200 K light source for blue signal light) (see ISO 11664-2);

Note 2 to entry: The spectral values of the products of the spectral distributions $S_A(\lambda)$ of the illuminant A, the spectral luminous efficiency function $V(\lambda)$ of the eye and the spectral transmittance $\tau_S(\lambda)$ of the traffic signal lens are given in [Table A.1](#), where $E_{\text{Signal}}(\lambda) = S_A(\lambda) \times \tau_S(\lambda)$.

Note 3 to entry: Calculations are currently based on the measured values of $E(\lambda)$ for traffic signal lights using incandescent quartz-halogen lamps. They previously used the product $\tau_S(\lambda) \cdot S_A(\lambda)$ of the spectral transmittance of the traffic signal filter and the spectral distribution of radiation of CIE standard illuminant A. Calculations using the values for quartz-halogen lamps and LED signals will give different results

Note 4 to entry: Adapted from ISO 13666:2012, definition 15.5.

3.6

polarizing efficiency

property of a polarizing lens, describing the percentage of the transmitted light that is polarised, defined by the equation

$$P = 100 \times \frac{\tau_{p,\text{max}} - \tau_{p,\text{min}}}{\tau_{p,\text{max}} + \tau_{p,\text{min}}} \%$$

where

- $\tau_{p,max}$ is the maximum value of **luminous transmittance** as determined with 100% linearly polarised radiation;
- $\tau_{p,min}$ is the minimum value of **luminous transmittance** as determined with 100% linearly polarised radiation.

Note 1 to entry: Adapted from ISO 13666:2012, definition 8.1.12.3.

4 Symbols

The symbols for the characteristic luminous transmittances of photochromic lenses are given in [Table 1](#).

Table 1 — Symbols for the characteristic luminous transmittances of photochromic lenses

Symbols	Characteristic luminous transmittances
τ_{V0}	Luminous transmittance in the faded state as reached at $(23 \pm 2)^\circ\text{C}$ after specified conditioning.
τ_{V1}	Luminous transmittance in the darkened state as reached at $(23 \pm 2)^\circ\text{C}$ after specified irradiation simulating mean outdoor conditions.
τ_{VW}	Luminous transmittance in the darkened state as reached at $(5 \pm 2)^\circ\text{C}$ after specified irradiation simulating outdoor conditions at low temperatures.
τ_{VS}	Luminous transmittance in the darkened state as reached at $(35 \pm 2)^\circ\text{C}$ after specified irradiation simulating outdoor conditions at high temperatures.
τ_{VA}	Luminous transmittance in the darkened state as reached at $(23 \pm 2)^\circ\text{C}$ after specified irradiation simulating reduced light conditions.

5 Classification

Spectacle lenses are classified with respect to transmittance as follows:

- clear spectacle lenses, having no intended colour (including grey) in transmission;
- uniformly tinted spectacle lenses;
- gradient-tinted spectacle lenses;
- photochromic spectacle lenses;
- polarizing spectacle lenses.

NOTE Two or more of the above classifications may be combined.

6 Requirements

6.1 General

The fundamental requirements for uncut finished lenses, including reference to [6.3](#) in this part of ISO 8980, are in ISO 14889. The requirements shall apply at a temperature of $(23 \pm 5)^\circ\text{C}$, and shall apply at the design reference point, unless specified otherwise.

6.2 General transmittance requirements

6.2.1 Tint descriptions, categories, and UV transmittance requirements

Spectacle lenses shall be attributed to one of five tint descriptions or luminous transmittance categories as specified in [Table 2](#), and shall be tested as described in [Clause 7](#).

A spectacle lens intended to have a luminous transmittance τ_V that is in categories 0, 1, 2 and 3 shall have a luminous transmittance at its design reference point that shall not lie outside the limits of the stated category by more than 2 % absolute. For example, a lens intended to have a luminous transmittance of 40 % but actually having a transmittance of 45 % shall comply with the UV requirements of a category 2 lens.

A spectacle lens intended to have a luminous transmittance τ_V that is in category 4 shall have a luminous transmittance τ_V at its design reference point that shall not lie outside the limits of that category by more than 20 % relative to the stated luminous transmittance.

All lenses shall meet the specified UV requirements corresponding to their intended luminous transmittance τ_V in [Table 2](#), but those clear glass spectacle lenses of category 0 for which no specific claim is made as to UV transmittance performance are excluded from the UV requirements of [Table 2](#).

NOTE This exclusion applies because some clear crown glass lenses cannot meet the UV-B requirement.

6.2.2 Tolerances on luminous transmittance of tinted lenses

It is recommended that a tint should be ordered by reference to a manufacturer's sample. Such a tint shall not be obviously dissimilar from the tint of the sample and its assessment is not restricted by its luminous transmittance τ_V measured by spectrophotometer.

For a lens ordered by a specific luminous transmittance τ_V shall have a measured τ_V at the design reference point within ± 8 % absolute of that ordered. The tint of the two lenses of a pair should not be obviously dissimilar.

Table 2 — Categories for luminous transmittance and the related permissible transmittance in the ultraviolet solar spectral range

		Visible spectral range		Ultraviolet spectral range	
		Range of luminous transmittance τ_V		Maximum value of solar UV-A transmittance τ_{SUVA}	Maximum value of solar UV-B transmittance τ_{SUVB}
Tint description	Luminous transmittance category	from over %	to %	> 315 nm to 380 nm UV-A	> 280 nm to 315 nm UV-B
Clear or very light tint	0	80,0	100	τ_V	0,05 τ_V
Light tint	1	43,0	80,0	τ_V	0,05 τ_V
Medium tint	2	18,0	43,0	0,5 τ_V	1,0 % absolute or 0,05 τ_V , whichever is greater
Dark tint	3	8,0	18,0	0,5 τ_V	1,0 % absolute
Very dark tint	4	3,0	8,0	1,0 % absolute or 0,25 τ_V , whichever is greater	1,0 % absolute

6.3 Spectral transmittance requirements of spectacle lenses intended for road use and driving

6.3.1 General

Spectacle lenses having a luminous transmittance τ_V less than or equal to 8 % are not intended for road use and driving. This clause therefore does not contain requirements for such lenses.

6.3.2 Spectral transmittance

The spectral transmittance $\tau(\lambda)$ at any wavelength in the range 475 nm to 650 nm shall be not less than 0,2 τ_V .

For a period of three years from the date of publication of this part of ISO 8980, products that are existing at the date of publication of this part of ISO 8980 that satisfy the requirement that the spectral transmittance, $\tau(\lambda)$ at any wavelength in the range 500 nm to 650 nm shall be not less than 0,2 τ_V will be deemed to pass the requirement of this part of ISO 8980.

6.3.3 Daylight use

When using illuminant D65, the luminous transmittance τ_V of spectacle lenses for road use and driving during daylight shall be more than 8 % at the design reference point.

6.3.4 Driving in twilight or at night

Spectacle lenses with a luminous transmittance τ_V less than 75 % shall not be used for road use and driving in twilight or at night. In the case of photochromic spectacle lenses, this requirement applies when tested in accordance with [7.5.3.5](#).

6.3.5 Relative visual attenuation coefficient (quotient) for recognition/detection of incandescent signal lights

Spectacle lenses shall have a relative visual attenuation coefficient (quotient) Q not less than:

- a) 0,8 for Q_{red} ;
- b) 0,6 for Q_{yellow} ;
- c) 0,6 for Q_{green} ;
- d) 0,4 for Q_{blue} .

The relative visual attenuation coefficient (quotient) Q shall be calculated according to [3.5](#), in accordance with [Table A.1](#).

6.4 Additional transmittance requirements for special types of spectacle lenses

6.4.1 Photochromic spectacle lenses

6.4.1.1 General

Photochromic spectacle lenses are usually attributed to two categories, corresponding to the faded state and to the darkened state. The faded and darkened state transmittances shall be determined according to the method in [7.5](#). The UV transmittance in both the faded and darkened states shall conform to the values specified for both categories in [Table 2](#).

NOTE It is not required to claim the category of the lens in its darkened state.

6.4.1.2 Photochromic response

When tested by the methods described in [7.5.3.1](#) to [7.5.3.3](#), the ratio of the luminous transmittance of a photochromic specimen (see [7.5.1](#)) in its faded state τ_{V0} and, after 15 min irradiation, in its darkened state τ_{V1} shall be at least 1,25, i.e.

$$\frac{\tau_{V0}}{\tau_{V1}} \geq 1,25$$

6.4.1.3 Photochromic response at various temperatures

If photochromic temperature influence is stated, it shall be determined by measuring the luminous transmittance of the specimen (see [7.5.1](#)) in the darkened state using the procedure described in [7.5.3.6](#) at 5 °C (τ_{VW}), 23 °C (τ_{V1}) and 35 °C (τ_{VS}).

NOTE The manufacturer may use additional temperatures, provided this information is made available.

6.4.1.4 Photochromic response at moderate light levels

If the photochromic response at moderate light levels is stated, it shall be determined by measuring the luminous transmittance of the specimen (see [7.5.1](#)) in the darkened state τ_{VA} using the procedure described in [7.5.3.4](#) after exposure to the illumination specified in [7.5.2.1](#) attenuated to an intensity of 30 %.

6.4.2 Polarizing spectacle lenses

6.4.2.1 Individual uncut polarizing lenses

When tested according to the method in [7.6](#), the polarizing efficiency as calculated in [3.6](#) shall be > 78 % for luminous transmittance categories 2, 3, 4 and > 60 % for luminous transmittance category 1.

If there is a marking on the spectacle lens indicating the intended direction of horizontal orientation, then the actual plane of transmittance shall be at $(90 \pm 3)^\circ$ from this marking.

6.4.2.2 Mounted pairs of polarizing lenses

If the lenses mounted in spectacles are claimed to be polarizing for sun glare attenuation, the lenses shall be fitted in the frame so that their planes of transmission do not deviate from the vertical by more than $\pm 5^\circ$ when tested according to the method in [7.6](#).

6.4.3 Gradient-tinted spectacle lenses

The requirements for gradient-tinted spectacle lenses shall be determined at the design reference point of the spectacle lens. It is recommended that gradient tints be ordered by reference to a manufacturer's sample lens, identification code, name or reference number.

6.5 Resistance to radiation

Following irradiation as specified in [7.7](#), the absolute change in the luminous transmittance ($\tau_V' - \tau_V$) of the lenses shall be less than or equal to 5 % absolute where τ_V' is the luminous transmittance after irradiation. In addition, the following shall be met:

- for photochromic filters $\frac{\tau_{V0}}{\tau_{V1}}$ shall be $\geq 1,25$;
- the UV requirements for the initial τ_V shall continue to be satisfied;
- if originally intended for road use and driving, the requirements of [6.3](#) shall continue to be satisfied;