

ANSI/ASAE S459 MAR1992 (R2017)
Shear and Three-Point Bending Test of Animal Bone



STANDARD

American Society of Agricultural and Biological Engineers

ASABE is a professional and technical organization, of members worldwide, who are dedicated to advancement of engineering applicable to agricultural, food, and biological systems. ASABE Standards are consensus documents developed and adopted by the American Society of Agricultural and Biological Engineers to meet standardization needs within the scope of the Society; principally agricultural field equipment, farmstead equipment, structures, soil and water resource management, turf and landscape equipment, forest engineering, food and process engineering, electric power applications, plant and animal environment, and waste management.

NOTE: ASABE Standards, Engineering Practices, and Data are informational and advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. The ASABE assumes no responsibility for results attributable to the application of ASABE Standards, Engineering Practices, and Data. Conformity does not ensure compliance with applicable ordinances, laws and regulations. Prospective users are responsible for protecting themselves against liability for infringement of patents.

ASABE Standards, Engineering Practices, and Data initially approved prior to the society name change in July of 2005 are designated as "ASAE", regardless of the revision approval date. Newly developed Standards, Engineering Practices and Data approved after July of 2005 are designated as "ASABE".

Standards designated as "ANSI" are American National Standards as are all ISO adoptions published by ASABE. Adoption as an American National Standard requires verification by ANSI that the requirements for due process, consensus, and other criteria for approval have been met by ASABE.

Consensus is established when, in the judgment of the ANSI Board of Standards Review, substantial agreement has been reached by directly and materially affected interests. Substantial agreement means much more than a simple majority, but not necessarily unanimity. Consensus requires that all views and objections be considered, and that a concerted effort be made toward their resolution.

CAUTION NOTICE: ASABE and ANSI standards may be revised or withdrawn at any time. Additionally, procedures of ASABE require that action be taken periodically to reaffirm, revise, or withdraw each standard.

Copyright American Society of Agricultural and Biological Engineers. All rights reserved.

ASABE, 2950 Niles Road, St. Joseph, MI 49085-9659, USA, phone 269-429-0300, fax 269-429-3852, hq@asabe.org

ANSI/ASAE S459 MAR1992 (R2017)

Approved February 1993; reaffirmed January 2017 as an American National Standard

Shear and Three-Point Bending Test of Animal Bone

Developed by the ASAE Physical Properties of Agricultural Products Committee; approved by the ASAE Food and Process Engineering Institute Standards Committee; adopted by ASAE March 1992; approved as an American National Standard February 1993; revised editorially and reaffirmed by ASAE December 1996; reaffirmed by ANSI March 1998; reaffirmed by ASAE December 2001, January 2007; reaffirmed by ANSI January 2007; reaffirmed by ASABE January 2012; reaffirmed by ANSI February 2012; reaffirmed by ASABE January 2017.

Keywords: Animal, Bone, Test

1 Purpose

1.1 This Standard is designed for use in determining the mechanical properties of animal bones such as the ultimate shear strength, ultimate bending strength, apparent modulus of elasticity, and fracture energy.

2 Scope

2.1 Shear and bending tests of intact animal bones provide an objective method for evaluating the effects of age, sex, nutrition, contaminants, and environment on the physical condition of the animal.

2.2 Understanding the problems encountered in evaluating the mechanical properties of animal bones and attempting to compare the results of previous investigators, has led to the need for a standard procedure for testing, data interpretation, and reporting of results.

2.3 The type of test selected, shear or three-point bending, will be dependent on the size and shape of the bone. The three-point bending tests should be used only when the bone is straight, has a symmetrical cross section, and has a support length to diameter ratio greater than 10. The shear test is good for any size or shape of bone.

2.4 Determination of the shear or bending properties of animal bone requires the development of a force-deformation curve. From a shear force-deformation curve, ultimate shear force, ultimate shear strength (stress), and fracture energy can be obtained. From a bending force-deformation curve, ultimate bending force, deformation to fracture, ultimate bending strength (stress), apparent modulus of elasticity, and fracture energy can be obtained. Any of these mechanical properties can be used for the purpose of evaluation, and it is recommended that more than one property be used.

3 Definitions

3.1 Force: Fracture load applied to the test specimen.

3.2 Deformation: Amount specimen deflects under load.

3.3 Force-deformation curve: A graph (see Figure 1) with values of deformation on the abscissa and values of force on the ordinate.




Figure 1 – Force deformative curve

3.4 Ultimate shear strength: Maximum shear stress that can be sustained by a material before rupture caused by a shear load.

3.5 Ultimate bending strength: Maximum bending stress developed in a material before rupture caused by a flexural load.

3.6 Fracture energy: The energy required to deform a material to the point of fracture. It is the area under the force-deformation curve up to the point of fracture (see Figure 1).

3.7 Stress-strain diagram: Graph of stress as a function of strain which is constructed from data taken from the force-deformation curve.

3.8 Modulus of elasticity: The slope of the straight line portion of a stress-strain diagram.

3.9 Apparent modulus of elasticity: When a material is inelastic (bone), loading and unloading the material several times within the linear limit may produce loading and unloading curves that may give different values for the modulus of elasticity. The apparent modulus of elasticity is the value of the modulus calculated from the first loading cycle (see ASAE Standard S368, Compression Test of Food Materials of Convex Shape).

4 Apparatus

4.1 Testing machine. Any testing machine capable of applying a constant rate of crosshead movement with the following:

4.1.1 A driving device for the crosshead with a reproducible speed with and accuracy of $\pm 1.0\%$.

4.1.2 A force-deformation indicating mechanism (x-y plotter, chart recorder, data acquisition unit, etc.). The mechanism must be calibrated before testing. The testing machine should be periodically verified following ASTM Standard E-4, Practices for Load Verification of Testing Machines.