NOTICE: This standard has either been superseded and replaced by a new version or withdrawn.
Contact ASTM International (www.astm.org) for the latest information

Designation: A428/A428M – 10

StandardTest Method for Weight [Mass] of Coating on Aluminum-Coated Iron or Steel Articles[1]

This standard is issued under the fixed designation A428/A428M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This test method covers procedures for determining the weight [mass] of coating on aluminum-coated iron or steel sheets and wire, and on other aluminum-coated iron and steel articles.

1.2 The final results determined by this test method shall be expressed in inch-pound units or SI units, depending on the units used in the material specification to which the results are to be compared. Certain portions of the procedure involving determination of specimen weight [mass] have traditionally been performed in SI units, and corresponding inch-pound units are not included.

1.3 For sheet products, the final results are expressed as either coating weight [mass] total both sides, or coating weight [mass] separately on each side, depending on the specified requirements.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*For a specific precautionary statement, see Note 1.

2. Referenced Documents

2.1 *ASTM Standards:*[2]

D1193 Specification for Reagent Water

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

3. Significance and Use

3.1 This test method provides a standard method of determining the weight [mass] of coating for comparison with specification requirements. A coating of aluminum on iron or steel articles provides protection against corrosion by forming a relatively inert barrier. Specifications for aluminum-coated articles occasionally provide for different classes (weights) [masses] of coating so that the purchaser can select the coating weight [mass] most suited to his needs. The heavier coating will provide greater protection against mechanical damage which may break the coating.

4. Reagents

4.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.[3] Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

4.2 *Purity of Water*—Water used in preparation of reagent solutions shall conform to Specification D1193, Type IV or better.

4.3 *Antimony Trichloride Solution*—Dissolve 200 g of antimony trichloride ($SbCl_3$) in 1000 mL of concentrated hydrochloric acid (HCl, sp gr 1.18 to 1.19) without heating.

4.4 *Hydrochloric Acid (sp gr 1.18 to 1.19)*—Concentrated hydrochloric acid (HCl).

[1] This test method is under the jurisdiction of ASTM Committee A05 on Metallic-Coated Iron and Steel Products and is the direct responsibility of Subcommittee A05.07 on Methods of Testing.

Current edition approved May 1, 2010. Published June 2010. Originally approved in 1958. Last previous edition approved in 2006 as A428/A428M - 06. DOI: 10.1520/A0428_A0428M-10.

[2] For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[3] *Reagent Chemicals, American Chemical Society Specifications* , American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmaceutical Convention, Inc. (USPC), Rockville, MD.

*A Summary of Changes section appears at the end of this standard

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States

Documents
Document Sharing Hub
Full document details: ASTM A428/A428M-10

4.5 *Sodium Hydroxide Solution (20 %)* —Dissolve 20 parts by weight [mass] of sodium hydroxide (NaOH) in 80 parts of water.

4.6 *Stannous Chloride Solution*—Dissolve 100 g of stannous chloride ($SnCl_2 \cdot 2H_2O$ in 1000 mL of concentrated hydrochloric acid (HCl, sp gr 1.18 to 1.19) without heating. Add a few granules of reagent grade tin.

4.7 *Hydrochloric Acid (1 +1)*—Mix 500 mL of HCl (sp. gr. 1.18 to 1.19) with 500 mL of reagent water and cool to room temperature.

NOTE 1—**Warning:** Small amounts of the poisonous gas stibine (SbH_3) may be evolved during the stripping process using the hydrochloric acid-antimony trichloride-stannous chloride method. Hydrochloric acid fumes are present, and hydrogen gas is evolved in the stripping process. Therefore, the test should be performed under conditions of adequate ventilation. A fume hood is recommended for large numbers of samples or where the test is to be carried out frequently over extended periods of time.

5. Sampling

5.1 *Aluminum-Coated Sheets*—Samples for weight-of-coating [mass-of-coating] determination shall be secured as designated in the appropriate specification. Test specimens shall have a minimum area of 3 in.^{2} [2000 mm^2] of sheet, but preferably approximately 5 in.^{2} [3300 mm^2] of sheet.

NOTE 2—For convenience in calculating test results in inch-pound units, the specimen should have an area of 5.08 in.^{2} of sheet (2.25 ± 0.01 in. square or 2.54 ± 0.01 in. in diameter). The weight [mass] of coating in grams on a specimen of that area is numerically equal to the weight [mass] of coating in ounces per square foot of sheet. For results to be reported in SI units, the specimen should have an area of 3330 mm^2 of sheet (57.7 ± 0.1 mm square or 65.1 ± 0.1 mm in diameter).

5.2 *Aluminum-Coated Wire*—Samples shall be secured as designated in the appropriate specification. The specimen of aluminum-coated wire may be of any length over 12 in. (approximately 300 mm), but preferably about 24 in. (approximately 600 mm). Where a continuous length is not available, shorter lengths totaling over 12 in., but preferably about 24 in., shall be used. Since the density of the steel is known (0.283 lb/in.^{3} or 7830 kg/m^3), it is not necessary to use a specific length of specimen.

5.3 *Aluminum-Coated Articles Other Than Sheet or Wire*—Samples for weight [mass] of coating determination shall be secured as designated in the appropriate specification. Except as otherwise provided, the specimens should have a minimum area of 3 in.^{2} [1935 mm^2] of aluminum-coated surface. For very small items, several pieces may have to be stripped to obtain the minimum area.

5.3.1 In the case of threaded articles, such as bolts and screws, the determination shall be made on a portion of the article that does not include any thread.

6. Procedure

6.1 Strip the aluminum coating from the specimens by using one of the following methods— the sodium hydroxide-hydrochloric acid method (method A), the hydrochloric acid-antimony trichloride-stannous chloride method (method B) or dilute hydrochloric acid method (method C).

NOTE 3—Methods A and B are the most common methods used for sheets.

6.2 Clean the specimens immediately before determining the weight [mass] by washing in petroleum ether or other suitable solvent, and dry thoroughly.

6.3 Determine the weight [mass] of the specimens individually to the nearest 0.01 g.

6.4 *Sodium Hydroxide-Hydrochloric Acid Method (method A)*—Heat the NaOH solution to approximately 195°F [90°C] (Note 4) and immerse each specimen in the hot solution until the strong reaction ceases. With silicon-free coatings, evolution of gas for considerable time is likely, but do not leave the specimens in the solution for more than a few minutes. Longer immersion inhibits the removal of coating during subsequent dips. Immersion of several specimens simultaneously is permitted provided all surfaces are freely exposed to the solution. Remove specimens from solution and scrub all surfaces under running tap water with a clean cellulose sponge to remove the loose deposit formed in the NaOH solution. Use vigorous scrubbing as necessary for some types of coating, but do not use abrasive materials to remove the deposit. Blot with a towel to remove most of the water (Note 5) and immerse each specimen singly for not more than 3 s in HCl (sp gr 1.18 to 1.19) at room temperature. Remove, scrub again under running tap water with a sponge, and re-immerse in the hot NaOH solution for not more than a few minutes or until action again ceases. Repeat this cycle until immersion in HCl shows no visible reaction (Note 6). Use one to three or more cycles as required, depending on the type and weight of coating. After the final immersion in the NaOH and HCl solutions, scrub as before, dry thoroughly, and determine the weight [mass] of each specimen to the nearest 0.01 g.

NOTE 4—This temperature is not critical, but the solution should be held several degrees below the boiling point (approximately 105°C) to prevent excessive foaming during the first immersion. The beaker used for heating the solution and immersing the specimens should be less than half full of solution to avoid the danger of foaming over when the specimens are immersed.

NOTE 5—Most of the water should be removed to prevent dilution of the HCl, as dilute HCl will attack the base metal to a greater extent than concentrated HCl.

NOTE 6—It is sometimes difficult to determine the point at which all of the alloy layer has been removed, when stripping silicon-free coatings. If in doubt, determine the weight [mass] of the specimen (after scrubbing and drying) and then put it through one additional stripping cycle. Loss in weight [mass] due to the additional cycle will be of the order of 0.005 g on a 2.25-in. [57.2-mm] square sheet specimen, if all the coating had been removed before the extra cycle.

6.5 *Hydrochloric Acid-Antimony Trichloride-Stannous Chloride Method (method B)*—After determining the weight [mass], immerse each specimen singly in a solution made by mixing 100 mL of antimony trichloride solution and 100 mL of stannous chloride solution (Note 7). Allow the specimen to remain immersed until the evolution of hydrogen has ceased. Action will stop after 1 to 4 min, or somewhat longer, depending on the thickness and silicon content of the coating. Use fresh solution for each test (Note 8). The temperature of the stripping solution shall not exceed 100°F [38°C]. After stripping, wash the specimen and scrub thoroughly under running

AVA Documents
Document Sharing Hub

Full document details: ASTM A428/A428M-10