



Designation: A 856/A 856M – 98

Standard Specification for Zinc-5 % Aluminum-Mischmetal Alloy-Coated Carbon Steel Wire¹

This standard is issued under the fixed designation A 856/A 856M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers soft, medium, and hard temper zinc-5 % aluminum-mischmetal (Zn-5 Al-MM) alloy-coated carbon steel wire in coils for general use. The product is intended for applications requiring corrosion resistance, drawability, and formability.

1.2 This specification is applicable to orders in either inch-pound units (as A 856) or acceptable SI units [as A 856M]. Inch-pound units and SI units are not necessarily equivalent; therefore, each system shall be used independently of the other, without combining values in any way.

1.3 This specification references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of this specification.

2. Referenced Documents

2.1 ASTM Standards:

- A 90/A 90M Test Method for Weight [Mass] of Coating on Iron and Steel Articles with Zinc-Alloy Coatings²
- A 700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Domestic Shipment³
- A 902 Terminology Relating to Metallic Coated Steel Products²
- B 117 Test Method of Salt Spray (Fog) Testing²
- B 750 Specification of Zinc-5 % Aluminum-Mischmetal Alloy (UNS Z38510) in Ingot Form for Hot-Dip Coatings⁴
- E 8 Test Methods of Tension Testing of Metallic Materials⁵
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specification⁶
- E 47 Test Methods for Chemical Analysis of Zinc Die-Casting Alloys⁷

¹ This specification is under the jurisdiction of ASTM Committee A-5 on Metallic Coated Iron and Steel Products and is the direct responsibility of Subcommittee A05.12 on Wire Specifications.

Current edition approved April 10, 1998. Published November 1998. Originally published as A 856/A 856M – 86. Last previous edition A 856/A 856M – 97.

² Annual Book of ASTM Standards, Vol 01.06

³ Annual Book of ASTM Standards, Vol 01.05.

⁴ Annual Book of ASTM Standards, Vol 02.04.

⁵ Annual Book of ASTM Standards, Vol 03.01.

⁶ Annual Book of ASTM Standards, Vol 14.02.

⁷ Annual Book of ASTM Standards, Vol 03.05.

E 1277 Test Method for Chemical Analysis of Zinc-5 % Aluminum-Mischmetal Alloy by the ICP Argon Plasma Spectrometric Method⁸

2.2 Military Standards:

MIL-STD-129 Marking for Shipment and Storage⁹

MIL-STD-163 Steel Mill Products Preparation⁹

2.3 Federal Standards:

Fed Std. No. 123 Marking for Shipment (Civil Agencies)⁹

2.4 Other Standards:

GF-1 Standard Practice for Determination of Cerium and Lanthanum Compositions in Galfan Alloy (5–Al-0.04 % La-0.04 % Ce-Ba1 SHG Zn)¹⁰

3. Terminology

3.1 *Definitions*—See Terminology A 902 for definitions of general terminology relating to metallic coated steel products.

4. Classification

4.1 *Temper*—The wire is classified with regard to mechanical properties by temper, which is related to tensile strength and stiffness. The temper designations are soft, medium, and hard.

4.2 *Coating Classes*—Zn-5AL-MM alloy coating on the wire is classified in a number of classes (Class 20, Class 40, Class 60, Class 80, Class 100, and Class 120) (see Table 1).

5. Ordering Information

5.1 Orders for material under this specification shall include the following information:

5.1.1 Quantity (weight),

5.1.2 Coated wire diameter,

5.1.3 Class of coating (see 4.2)

5.1.4 Temper (soft, medium, or hard) (see Table 2),

5.1.5 Packaging requirements, and

5.1.6 ASTM designation and year of issue, as A 856-____ for inch-pound units or A 856M-____ for SI units.

⁸ Annual Book of ASTM Standards, Vol 03.06.

⁹ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111–5094, Attn: NPODS

¹⁰ Available from International Lead Zinc Research Organization 2525 Meridian Parkway, P.O. Box 12036, Research Triangle Park, NC 27709-2036.

TABLE 1 Minimum Weight of Zn-5 Al-MM Alloy Coating per Unit Area of Uncoated Wire Surface, oz/ft² [g/m²]

Coating Class	Coating Weight	
	oz/ft ²	[g/m ²]
20	0.20	[61]
40	0.40	[122]
60	0.60	[183]
80	0.80	[244]
100	1.00	[305]
120	1.20	[366]

NOTE 1—A typical ordering description is as follows: 50 000 lb, 0.120-in. diameter Zn-5 Al-MM alloy-coated wire, Coating Class 60, Soft Temper in 600-lb coils on tubular carriers to ASTM A 856-____ or [50 000 kg, 3.00-mm diameter Zn-5 Al-MM alloy-coated wire, Coating Class 20, Soft Temper in 1000-kg coils on tubular carriers to ASTM A 856M-____].

6. Materials and Manufacture

6.1 The steel from which the wire is produced shall be made by any commercially accepted steelmaking process.

6.2 *Coating Bath Analysis*—The bath metal used in continuous hot-dip Zn-5 Al-MM alloy-coated wire shall meet the chemical composition limits specified in Specification B 750.

6.2.1 For a two-step coating operation where the first coating is zinc (hot-dip galvanizing or electrogalvanizing) the final bath shall be permitted to have an aluminum content of up to 7.2 % to prevent depletion of the aluminum content of the bath.

6.2.2 *Method of Analysis*—The determination of chemical composition shall be made in accordance with suitable chemical (see Test Method E 47 for tin), ICP Argon Plasma Spectrometric (see Test Methods E 1277), or other methods. In case of dispute, the results secured by Text Methods E 1277 shall be the basis of acceptance.

6.2.3 A standard practice for X-ray fluorescence spectrometry for determination of cerium and lanthanum in a zinc-5 % aluminum-mischmetal alloy has been established by the International Lead Zinc Research Organization (Standard Practice GF-1). In case of dispute, the results secured by Test Methods E 1277 shall be the basis of acceptance.

7. Mechanical Properties

7.1 The Zn-5 Al-MM alloy coated wire as represented by the test specimens tested in accordance with Test Methods E 8 shall conform to the tensile strength requirements prescribed in Table 2.

7.2 Test specimens found to contain a weld or obvious imperfections shall be discarded and another test specimen obtained to very conformance to the tensile strength requirements.

8. Permissible Variations

8.1 The permissible variation in diameter of the Zn-5 Al-MM alloy-coated wire as represented by the test specimens shall meet the requirements shown in Table 3.

9. Coating Tests

9.1 *Weight of Coating*—The Zn-5 Al-MM alloy-coated wire when tested in accordance with Test Method A 90/A 90M shall

conform to the requirements of Table 1 for minimum weight of coating for the class required.

NOTE 2—A typical ratio of 0.20 oz/ft² (61 g/m²) equals 200 to 240 h as salt spray test in accordance with Test Method B 117 may be used.

9.2 *Adherence of Coating*—The Zn-5 Al-MM alloy-coated wire as represented by the test specimens shall be capable of being wrapped in a close helix at a rate not exceeding 15 turns/min around a cylindrical steel mandrel having a diameter as prescribed in Table 4 without cracking or flaking the coating to such an extent that any coating is removed when rubbed with the bare fingers.

NOTE 3—Loosening or detachment during the adhesion test of superficial, small particles of Zn-5 Al-MM alloy formed by mechanical polishing of the surface of the coated wire shall not be considered cause for rejection.

10. Workmanship, Finish, and Appearance

10.1 The Zn-5 Al-MM alloy-coated wire shall be free of slivers, scale, and other imperfections not consistent with good commercial practice. The coating shall be continuous and reasonably uniform. To ensure large continuous length coils, welds are permitted in the finished wire.

11. Number of Tests and Retests

11.1 The number of test specimens taken from the ends of coils during production to ensure compliance with Sections 7, 8, and 9 vary with the quality control procedures and the manufacturing facilities of each manufacturer but is generally not less than 10 % of the coils produced. For the purpose of final product testing, one specimen from every ten coils or fraction thereof in a lot shall be selected at random or a total of seven specimens, whichever is less.

11.2 A wire sample of sufficient length, approximately 4 ft [1.2 m], shall be cut from either end of each coil selected for tests described in Sections 7, 8, and 9.

11.3 If one or more of the wire specimens fail any requirement, the lot shall be subjected to retest. For retest purposes, the original lot shall be regrouped into 50 coil lots or fractions thereof. Each lot shall be 10 % tested for the property in which the original sample failed to comply. The number of samples thus selected shall be at least twice the number of the original sampling. Any lot that exhibits a failure shall be rejected.

11.3.1 The manufacturer has the option of testing each coil in the failed lot for the property in which the failure occurred, rejecting the nonconforming coils. The coils which conform for the property tested shall be accepted.

12. Inspection

12.1 Unless otherwise specified in the purchase order or contract, the manufacturer is responsible for the performance of all inspection and test requirements specified in this specification. Except as otherwise specified in the purchase order or contract, the manufacturer shall use his own or any other suitable facilities for the performance of the inspection and test requirements, at his option, unless disapproved by the purchaser at the time the order is placed. The purchaser shall have the right to perform any of the inspections and tests specified in