



Designation: A 947M – 95 (Reapproved 2000)

METRIC

Standard Specification for Textured Stainless Steel Sheet [Metric]¹

This standard is issued under the fixed designation A 947M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers stainless steel, textured sheets, especially for use in electronic packaging applications, for example, cabinet, rack, enclosure, and shelf constructions for telecommunication, computer, and data-processing equipment.

1.2 This specification applies to all finished flat-rolled stainless products specified by standards organizations such as International Standards Organization (ISO), American Society for Testing and Materials (ASTM), European Committee for Standardization (CEN), German Institute for Standardization (DIN), and others participating in a global standards harmonization effort.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

2. Referenced Documents

2.1 ASTM Standards:

- A 176 Specification for Stainless and Heat-Resisting Chromium Steel Plate, Sheet, and Strip²
- A 370 Test Methods and Definitions for Mechanical Testing of Steel Products²
- A 480/A480M Specification for General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip²
- A 700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Domestic Shipment³
- A 751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products²
- B 117 Practice for Operating Salt Spray (Fog) Apparatus⁴
- B 193 Test Method for Resistivity of Electrical Conductor Material⁵

D 257 Test Methods for D-C Resistance or Conductance of Insulating Materials⁶

D 523 Test Method for Specular Gloss⁷

2.2 ISO Standards:

ISO 1462 Accelerated Corrosion Tests and Evaluation of Results⁸

ISO 6892 Metallic Materials Tensile Testing⁸

2.3 IEC Standard:

IEC 68 Environmental Testing⁹

2.4 CEN Standard:

EN 10002/1 Metallic Materials Tensile Testing¹⁰

2.5 DIN Standards:

DIN 17441 Stainless Steel Technical Delivery Conditions for Stainless Cold Rolled Steel¹¹

DIN 50021-SS Spray Test with Different Sodium Chloride Solutions¹¹

DIN 50980 Evaluation of Corrosion Tests¹¹

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *textured*—a three-dimensional design pattern, regardless of the specific production-process approach.

4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Such requirements may include, but are not limited to the following:

4.1.1 *Quantity*—Number of sheets or weight.

⁶ Annual Book of ASTM Standards, Vol 10.01.

⁷ Annual Book of ASTM Standards, Vol 06.01.

⁸ Available from International Organization for Standards (ISO), 1 Rue de Varembe, Case Postale 56, 20 Geneve, Suisse 1211.

⁹ Available from International Electrotechnical Commission (IEC), 3 Rue de Varembe, 20 Geneve, Suisse 1211.

¹⁰ Available from European Committee for Standardization (CEN), Rue Brederoode 2, B 1000 Bruxelles.

¹¹ Available from German Institute for Standardization (DIN), Burggrafstrasse 6, 1000 Berlin 30.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.17 on Wrought Stainless Products.

Current edition approved Sept. 10, 1995. Published November 1995.

² Annual Book of ASTM Standards, Vol 01.03.

³ Annual Book of ASTM Standards, Vol 01.05.

⁴ Annual Book of ASTM Standards, Vol 03.02.

⁵ Annual Book of ASTM Standards, Vol 02.03.



4.1.2 Dimensions of sheet (thickness (texture included), width, and length). See Tables 1-5 and Section 9 for preferred sizes and tolerances.

4.1.3 ASTM designation and date of issue.

4.1.4 Name and type of material.

4.1.5 Surface condition of the nontextured surface. See Specification A 480/A 480M or DIN 17441 Table 8.

4.1.6 Textured identification reference number. See Table 6.

4.1.7 Type and thickness of protective liner, if required by the purchaser.

4.1.8 Marking requirements. Reference: Practices A 700.

NOTE 1—A typical ordering description is as follows: 500 sheets, 1.00 by 1200 by 2500 mm; ASTM Specification 176, Type 430; Surface Finish Texture ID: S-F-O, 6-1, 3-6-170-3; 100 sheet maximum/skid, textured side up. Each skid marked with purchase order number, applicable ASTM standard, and date of shipment.

5. Materials and Manufacture

5.1 The textured side or sides of the sheet shall be produced in such a manner that guarantees repeatability of the pattern over time. See 6.2.

5.2 Manufacture process of textured material under this specification shall follow industry practices.

6. Texture of Sheet

6.1 The texture of any sheet delivered under this specification shall meet the provisions outlined in Table 6 and Section 13.

6.2 The customer shall either provide a control-sample (300 mm by 400 mm) or designate a control-sample from a chosen textured material to ensure accurate repetition in appearance of like products. See Section 13.

7. Chemical Composition

7.1 The heat chemical composition shall be reported to the purchaser, or his representative, and shall conform to the requirements specified in the applicable ASTM standard of the steel type selected for texturing.

7.2 Methods and practices relating to chemical analysis required by this specification shall be in accordance with Test Methods, Practices, and Terminology A 751.

TABLE 1 Permissible Deviations in Thickness^A

Preferred Nominal Thickness	Applicable Thickness		Permissible Thickness Variations for Nominal Sheet Widths $\geq 10 \leq 1600$
	$\geq$	$\leq$	
0.40	0.4	0.5	0.04
0.50; 0.60	0.5	0.7	0.05
0.70; 0.80; 0.90; 1.00	0.7	1.1	0.06
1.20	1.1	1.5	0.08
1.50; 2.00	1.5	2.5	0.1
2.50; 3.00	2.5	3.5	0.12
3.50; 4.00	3.5	4.5	0.14
4.50; 5.00; 6.00	4.5	6.0	0.15

^A In reference to preferred sheet thicknesses. Dimensions stated are in millimetres.

TABLE 2 Permissible Deviations for Nominal Widths^A

Nominal Thickness		Permissible Deviation at Nominal Width			
≥	≤	≤100	≥100 to ≤300	≥300 to ≤700	≥700 to ≤1600
0.40	1.00	0.5	0.8	1.0	1.5
1.00	1.75	0.7	1.0	1.5	1.5
1.75	3.00	1.0	1.5	1.5	2.0
3.00	6.00	...	...	2.0	2.0

^A Dimensions stated are in millimetres.

TABLE 3 Permissible Deviations for Nominal Length^A

Nominal "L"	Permissible Deviation for Nominal Length
≤ 2000	5
> 2000	$0.0025 \times \text{Length}$

^A Dimensions stated are in millimetres.

TABLE 4 Permissible Deviations on Flatness^A

Nominal Thickness	Total Deviation, %	
	Relating to Length D/L	Relating to Width D/W
0.40	2.00	0.4
2.00	4.00	0.3
4.00	6.00	0.1

^A Dimensions stated are in millimetres.

TABLE 5 Permissible Deviations on Squareness^A

Nominal Length	Squareness Tolerances at Nominal Width Ratio of AA/BB Dimension	
	$\geq$	$\leq$
...	2000	6
2000	3000	7
3000	3500	7
3500	5000	8
5000	6000	12

^A Dimensions stated are in millimetres.

8. Other Requirements

8.1 If requested by the purchaser, physical (electrical and optical) and mechanical (tensile, yield, and elongation) property requirements shall be reported to the purchaser based on a lot size as specified in 8.2.

8.2 A lot shall consist of all sheets of the same thickness made from the same coil. In case the material cannot be identified by coil, a lot shall consist of no more than 5000 kg (approximately 5 tons) of sheets of the same thickness.

8.3 Electrical Requirements:

8.3.1 The specific resistivity of the material measured at 20°C to be reported in: ohms·mm²/m ($\mu\Omega\cdot\text{cm}$).

8.3.2 The surface resistivity of the material measured at 20°C to be reported in: milliohms. Refer to Test Methods D 257.

8.4 *Optical Requirements*—The textured surface of the material selected under this specification shall meet the inspection requirements (see 13.2) based on a visual sample comparison or a 6:1 art master pattern comparison, or both.

8.5 *Mechanical Requirements*—The mechanical properties, tensile strength, yield strength, and elongation of the material