



Designation: B286 – 20

Standard Specification for Copper Conductors for Use in Hookup Wire for Electronic Equipment¹

This standard is issued under the fixed designation B286; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers uninsulated metallic-coated copper conductors for use in hookup wire for electronic equipment.

1.2 The SI values for density are to be regarded as standard. For all other properties, the inch-pound values are to be regarded as the standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards:*²

B33 Specification for Tin-Coated Soft or Annealed Copper Wire for Electrical Purposes

B189 Specification for Lead-Coated and Lead-Alloy-Coated Soft Copper Wire for Electrical Purposes

B193 Test Method for Resistivity of Electrical Conductor Materials

B258 Specification for Standard Nominal Diameters and Cross-Sectional Areas of AWG Sizes of Solid Round Wires Used as Electrical Conductors

B298 Specification for Silver-Coated Soft or Annealed Copper Wire

B355 Specification for Nickel-Coated Soft or Annealed Copper Wire

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

3.1.1 Quantity of each size, designation (**Table 1**) and type,

3.1.2 Conductor size, designation, construction, and type (**Table 1**).

3.1.3 Whether tin, lead alloy, silver-coated, or nickel-coated (see **4.1**).

3.1.4 For silver-coated conductors and nickel-coated conductors, class of coating (see **4.1**), and when required, unannealed (see **4.2**),

3.1.5 Desired constructions where alternates are given (**Table 1**, Type II and, **5.1**, **6.1**, and **6.2**),

3.1.6 Package size (Section **12**).

3.1.7 Special package marking if required (Section **11**), and

3.1.8 Place of inspection (Section **10**).

4. General Requirements

4.1 *Coating of Wires*—The coating of the solid conductors and the wires composing stranded conductors (before stranding) shall conform to the coating requirements of ASTM Specifications **B33**, **B189**, **B298**, and **B355**, as indicated on the purchase order.

4.2 *Temper*—Unless otherwise specified, all coated conductors shall be furnished in the annealed temper. When so specified, silver-coated conductors or nickel-coated conductors shall be furnished unannealed (Explanatory **Note 1**).

NOTE 1—The term unannealed as used in this specification means cold-worked conductor as produced on commercial wire-drawing machines.

4.3 *Elongation*—The elongation of annealed Type I conductors shall be as specified in Specifications **B33**, **B189**, **B298**, and **B355** as applicable. The elongation of stranded conductors shall be permitted to vary from the requirements of the applicable Specifications: **B33**, **B189**, **B298**, and **B355** by the following amounts:

4.3.1 For stranded conductors 22 AWG and smaller, the test shall be performed on the whole conductor and the elongation

¹ This specification is under the jurisdiction of ASTM Committee **B01** on Electrical Conductors and is the direct responsibility of Subcommittee **B01.04** on Conductors of Copper and Copper Alloys.

Current edition approved Nov. 1, 2020. Published November 2020. Originally approved in 1954. Last previous edition approved in 2017 as B286 – 07 (2017). DOI: 10.1520/B0286-20.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



TABLE 1 Details of Conductor Construction

Type I (Solid Conductors)										
Size Designation, AWG	Nominal Area, cmils	Nominal Diameter, in.	D-C Resistance at 20°C, Ω/1000 ft, max (Explanatory Note 2)							
			Annealed Tin or Lead-Alloy Coated	Annealed Silver Coated	Class 2 Nickel ^A	Class 10 Nickel	Class 27 Nickel	Class 10 Nickel	Class 27 Nickel	Class 27 Nickel
10	10380	0.1019	1.06	1.02	1.05	1.17	1.44	1.17	1.44	1.44
12	6530	0.0808	1.69	1.62	1.68	1.84	2.28	1.84	2.28	2.28
14	4110	0.0641	2.68	2.58	2.67	2.93	3.63	2.93	3.63	3.63
16	2580	0.0508	4.26	4.10	4.27	4.65	5.77	4.65	5.77	5.77
18	1620	0.0403	6.78	6.52	6.79	7.39	9.17	7.39	9.17	9.17
20	1020	0.0320	10.7	10.3	10.8	11.8	14.6	11.8	14.6	14.6
22	640	0.0253	17.2	16.5	17.3	18.8	23.3	18.8	23.3	23.3
24	404	0.0201	27.2	26.2	27.3	29.8	36.9	29.8	36.9	36.9
26	253	0.0159	44.5	41.9	43.8	47.5	58.9	47.5	58.9	58.9
28	159	0.0126	70.8	66.8	69.4	75.4	107.0	75.4	107.0	107.0
30	100	0.0100	114.0	106.0	110.0	120.0	149.0	120.0	149.0	149.0

Type II (Stranded Conductors)										
Size Designation ^B	Conductor Construction			D-C Resistance at 20°C, Ω/1000 ft, max (Explanatory Note 2)						
	Number of Wires ^C	Nominal Diameter of Each Wire, in.	Calculated Cross-Sectional Area, cmils	Maximum Allowable Diameter, in. ^D	Length of Lay, in. (Explanatory Note 3)	Annealed Tin or Lead-Alloy Coated	Annealed Silver Coated	50 to 100 μin. of Nickel ^E	Class 10 Nickel	Class 27 Nickel
0000-2109	2109 ^F	0.0100	210 900	0.635	...	0.0576	0.0537	0.0559(2)	0.0610	0.0756
000-1672	1672 ^F	0.0100	167 200	0.545	...	0.0727	0.0677	0.0705(2)	0.0770	0.0954
00-1330	1330 ^F	0.0100	133 000	0.486	...	0.0914	0.0851	0.0887(2)	0.0967	0.120
0-1064	1064 ^F	0.0100	106 400	0.435	...	0.114	0.106	0.111(2)	0.121	0.150
0-1045	1045 ^F	0.0100	104 500	0.431	...	0.116	0.108	0.113(2)	0.123	0.153
1-836	836 ^F	0.0100	83 600	0.386	...	0.145	0.135	0.141(2)	0.154	0.191
1-817 ^E	817 ^F	0.0100	81 700 ^E	0.382	...	0.149	0.139	0.144(2)	0.158	0.195
2-665	665 ^F	0.0100	66 500	0.342	...	0.183	0.170	0.177(2)	0.194	0.240
4-133 ^E	133 ^F	0.0179	42 615 ^E	0.274	...	0.280	0.263	0.274(2)	0.299	0.371
4-420	420 ^G	0.0100	42 000	0.275	...	0.289	0.270	0.281(2)	0.306	0.380
6-133 ^E	133 ^F	0.0142	26 818 ^E	0.217	...	0.444	0.418	0.436(2)	0.475	0.589
6-266	266 ^G	0.0100	26 600	0.220	...	0.457	0.426	0.443(2)	0.600	0.800
8-133 ^E	133 ^F	0.0113	16 983 ^E	0.173	...	0.701	0.661	0.688(2)	0.751	0.930
8-168	168 ^G	0.0100	16 800	0.177	...	0.724	0.674	0.702(2)	0.766	0.949
10-105	105 ^G	0.0100	10 500	0.130	1.2 to 1.8	1.15	1.07	1.11(2)	1.21	1.50
10-104	104 ^H	0.0100	10 400	0.130	1.7 to 2.1	1.16	1.08	1.12(2)	1.23	1.52
10-49 ^E	49 ^G	0.0142	9 880 ^G	0.132	...	1.21	1.14	1.18(2)	1.29	1.60
10-37 ^E	37 ^E	0.0159	9 354 ^E	0.115	1.10 to 1.75	1.26	1.19	1.24(2)	1.35	1.67
12-65	65 ^H	0.0100	6 500	0.099	1.3 to 1.7	1.85	1.73	1.80(2)	1.96	2.43

Type II (Stranded Conductors)										
Size Designation ^B	Conductor Construction			D-C Resistance at 20°C, Ω/1000 ft, max (Explanatory Note 2)						
	Number of Wires ^C	Nominal Diameter of Each Wire, in.	Calculated Cross-Sectional Area, cmils	Maximum Allowable Diameter, in. ^D	Length of Lay, in. (Explanatory Note 2)	Annealed Tin or Lead-Alloy Coated	Annealed Silver Coated	50 to 100 μin. of Nickel ^E	Class 10 Nickel	Class 27 Nickel
2-37 ^E	37 ^E	0.0126	5 874 ^E	0.091	0.90 to 1.45	2.01	1.89	1.97(2)	2.15	2.66
2-19 ^E	19 ^J	0.0179	6 088 ^E	0.093	0.90 to 1.45	1.92	1.81	1.88(2)	2.05	2.55
4-41	41 ^H	0.0100	4 100	0.081	0.80 to 1.35	2.94	2.74	2.85(2)	3.11	3.85
4-19 ^E	19 ^J	0.0142	3 831 ^E	0.073	0.80 to 1.15	3.05	2.87	2.99(2)	3.26	4.05
6-26	26 ^H	0.0100	2 600	0.062	0.60 to 0.90	4.59	4.27	4.45(2)	4.86	6.02
6-19 ^E	19 ^J	0.0113	2 426 ^E	0.059	0.60 to 0.90	4.82	4.54	4.73(2)	5.15	6.39
8-26 ^E	26 ^H	0.0080	1 664 ^E	0.050	0.50 to 0.70	7.20	6.71	7.14(4)	7.63	9.45
18-19 ^E	19 ^J	0.0100	1 900 ^E	0.052	0.50 to 0.70	6.22	5.79	6.03(2)	6.58	8.16