



Designation: B 85 – 96

Standard Specification for Aluminum-Alloy Die Castings¹

This standard is issued under the fixed designation B 85; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense. Consult the DoD Index of Specifications and Standards for the specific year of issue which has been adopted by the Department of Defense.

1. Scope

1.1 This specification covers aluminum-alloy die castings. Ten alloy compositions are specified, designated as shown in Table 1.

1.2 For acceptance criteria for inclusion of new aluminum and aluminum alloys in this specification, see Annex A1.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

2. Referenced Documents

2.1 The following documents of the issue in effect on date of order acceptance form a part of this specification to the extent referenced herein:

2.2 ASTM Standards:

B 179 Specification for Aluminum Alloys in Ingot Form for Castings from all Casting Processes²

B 275 Practice for Codification of Certain Nonferrous Metals and Alloys, Cast and Wrought²

B 660 Practices for Packaging/Packing of Aluminum and Magnesium Products²

E 8 Test Methods for Tension Testing of Metallic Materials³

E 23 Test Methods for Notched Bar Impact Testing of Metallic Materials³

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁴

E 34 Test Methods for Chemical Analysis of Aluminum and Aluminum-Base Alloys⁵

E 88 Practice for Sampling Nonferrous Metals and Alloys in Cast Form for Determination of Chemical Composition⁵

E 101 Test Method for Spectrographic Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique⁵

E 227 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique⁵

E 505 Reference Radiographs for Inspection of Aluminum and Magnesium Die Castings⁶

E 527 Practice for Numbering Metals and Alloys (UNS)⁷

E 607 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique, Nitrogen Atmosphere⁸

E 716 Practices for Sampling Aluminum and Aluminum Alloys for Spectrochemical Analysis⁸

E 1251 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Argon Atmosphere, Point-to-Plane, Unipolar Self-Initiating Capacitor Discharge⁸

2.3 ANSI Standard:

H35.1 Alloy and Temper Designation Systems for Aluminum²

2.4 American Die Casting Institute Standards:

“E” Series Product Standards for Die Castings²

2.5 Federal Standards:

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)⁹

Fed. Std. No. 184 Identification Marking of Aluminum, Magnesium and Titanium⁹

2.6 Military Standard:

MIL-STD-129 Marking for Shipment and Storage (Military Agencies)⁹

3. Terminology

3.1 Definition:

3.1.1 *die casting*—a metal object produced by the introduction of molten metal under substantial pressure into a metal die and characterized by a high degree of fidelity to the die cavity.

4. Ordering Information

4.1 Orders for material under this specification shall include the following information:

4.1.1 This specification designation (which includes the number, the year, and the revision letter, if applicable),

4.1.2 The quantity in either pieces or pounds,

4.1.3 Part name and number,

4.1.4 Alloy (Table 1), and

4.1.5 Drawing of die casting, when required, giving all necessary dimensions and showing latest revisions and allowances for machining, if any. Location of ejector pin marks or

¹ This specification is under the jurisdiction of ASTM Committee B-7 on Light Metals and Alloys, and is the direct responsibility of Subcommittee B07.01 on Aluminum Alloy Ingots and Castings.

Current edition approved Aug. 10, 1996. Published September 1996. Originally published as B 85 – 31 T. Last previous edition B 85 – 95.

² *Annual Book of ASTM Standards*, Vol 02.02.

³ *Annual Book of ASTM Standards*, Vol 03.01.

⁴ *Annual Book of ASTM Standards*, Vol 14.02.

⁵ *Annual Book of ASTM Standards*, Vol 03.05.

⁶ *Annual Book of ASTM Standards*, Vol 03.03.

⁷ *Annual Book of ASTM Standards*, Vol 01.01.

⁸ *Annual Book of ASTM Standards*, Vol 03.06.

⁹ Available from Standardization Documents Order Desk, Bldg 4, Section 9, 700 Robbins Ave., Philadelphia, PA 19104, Attn: NPODS.

TABLE 1 Chemical Requirements^{A, B, C}

Alloy ^D			Composition %										
ANSI	ASTM	UNS	Silicon	Iron	Copper	Man- ganese	Magne- sium	Nickel	Zinc	Tin	Tita- nium	Other Consti- tuents, Except Aluminum (Total)	Aluminum
360.0	SG100B	A03600	9.0–10.0	2.0	0.6	0.35	0.40–0.6	0.50	0.50	0.15	...	0.25	remainder
A360.0	SG100A	A13600	9.0–10.0	1.3	0.6	0.35	0.40–0.6	0.50	0.50	0.15	...	0.25	remainder
380.0	SC84B	A03800	7.5–9.5	2.0	3.0–4.0	0.50	0.10	0.50	3.0	0.35	...	0.50	remainder
A380.0 ^E	SC84A	A13800	7.5–9.5	1.3	3.0–4.0	0.50	0.10	0.50	3.0	0.35	...	0.50	remainder
383.0 ^E	SC102A	A03830	9.5–11.5	1.3	2.0–3.0	0.50	0.10	0.30	3.0	0.15	...	0.50	remainder
384.0 ^E	SC114A	A03840	10.5–12.0	1.3	3.0–4.5	0.50	0.10	0.50	3.0	0.35	...	0.50	remainder
390.0	SC174A	A03900	16.0–18.0	1.3	4.0–5.0	0.10	0.45–0.65	...	0.10	...	0.20	0.20	remainder
B390.0	SC174B	A23900	16.0–18.0	1.3	4.0–5.0	0.50	0.45–0.65	0.10	1.5	...	0.10	0.20	remainder
392.0	S19	A03920	18.0–20.0	1.5	0.40–0.80	0.20–0.60	0.80–1.20	0.50	0.50	0.30	0.20	0.50	remainder
413.0	S12B	A04130	11.0–13.0	2.0	1.0	0.35	0.10	0.50	0.50	0.15	...	0.25	remainder
A413.0	S12A	A14130	11.0–13.0	1.3	1.0	0.35	0.10	0.50	0.50	0.15	...	0.25	remainder
C433.0	S5C	A34430	4.5–6.0	2.0	0.6	0.35	0.10	0.50	0.50	0.15	...	0.25	remainder
518.0	G8A	A05180	0.35	1.8	0.25	0.35	7.5–8.5	0.15	0.15	0.15	...	0.25	remainder

^A Analysis shall ordinarily be made only for the elements mentioned in this table. If, however, the presence of other elements is suspected, or indicated in the course of routine analysis, further analysis shall be made to determine that the total of these other elements are not present in excess of specified limits.

^B For purposes of acceptance and rejection, the observed value or calculated value obtained from analysis should be rounded off to the nearest unit in the last right-hand place of figures, used in expressing the specified limit, in accordance with the rounding procedure prescribed in Section 3 of Practice E 29.

^C Limits are in percent maximum unless shown otherwise.

^D Alloys 360.0, 380.0, 413.0, C443.0 and 518.0 are suitable for the production of die casting by either the hot-chamber or the cold-chamber process. Die castings of alloys A360.0, A380.0, 383.0, 384.0 and A413.0 may be made only in cold-chamber machines.

ASTM designations were established in accordance with Practice B 275. ANSI designations were established in accordance with ANSI H35.1. UNS designations were established in accordance with Practice E 527.

^E With respect to mechanical properties, alloys A380.0, 383.0 and 384.0 are substantially interchangeable.

parting lines shall be at the option of the producer; unless specifically designated on the drawing.

4.2 Additional tests, options and special inspection requirements as provided below should be justified only on the basis of need. These shall be specified in the contract or purchase order, as additional procedures and extended delivery time may be involved.

4.2.1 Chemical analysis (7.1.1),

4.2.2 Quality assurance (Section 6),

4.2.3 Special proof tests or mechanical properties (Section 8),

4.2.4 General quality options for internal soundness or for finish (Section 10),

4.2.5 Source inspection (Section 11),

4.2.6 Certification (Section 12),

4.2.7 Marking for identification (Section 14), and

4.2.8 Special packaging (Section 15).

5. Materials

5.1 Unless otherwise specified, only aluminum alloy conforming to the requirements of Specification B 179 or producer's foundry scrap (identified as being made from alloy conforming to Specification B 179) shall be used in the remelting furnace from which molten metal is taken for pouring directly into castings. Additions of small amounts of modifiers and grain refining elements or alloys are permitted.

5.1.1 Pure materials, recycled materials, and master alloys and material not conforming to Specification B 179 may be used to make alloys conforming to this specification, provided chemical analysis can be taken and adjusted to conform to Table 1 prior to pouring any castings.

6. Quality Assurance

6.1 *Responsibility for Inspection*—When specified in the contract or purchase order, the producer or supplier is responsible for the performance of all inspection and test

requirements specified herein. Except as otherwise specified in the contract or order, the producer or supplier may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless disapproved by the purchaser. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification. Quality assurance standards shall be agreed upon between the producer or supplier and purchaser at the time a contract or order is placed.

6.2 *Lot Definition*—An inspection lot shall be defined as follows:

6.2.1 An inspection lot shall consist of the production from each die or compound die on each machine for each 24 h during the first week of normal operation and the production for each 48 h thereafter of normal operation. Any significant change in the machine, composition, die or continuity of operation shall be considered as the start of a new lot. Die castings inspected by this method shall be so marked or handled during the finishing operations as not to lose their identity.

6.2.2 Each die casting of a randomly selected sample shall be examined to determine conformance to the requirements with respect to general quality, dimensions, and identification marking. The producer or supplier may use a system of statistical quality control for such examinations.

7. Chemical Composition

7.1 *Limits*—The die castings shall conform to the requirements as to chemical composition prescribed in Table 1. Conformance shall be determined by the producer by analyzing samples taken at the time castings are made. If the producer has determined the chemical composition of the metal during the course of manufacture, he shall not be required to sample and analyze the finished product.

7.1.1 When a detailed chemical analysis is required with a