



Designation: C 321 – 00

Standard Test Method for Bond Strength of Chemical-Resistant Mortars¹

This standard is issued under the fixed designation C 321; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers the determination of the bond strength between chemical-resistant mortars and chemical-resistant brick.

1.2 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

C 279 Specification for Chemical-Resistant Masonry Units²

C 287 Specification for Chemical-Resistant Sulfur Mortar²

C 904 Terminology Relating to Chemical-Resistant Non-metallic Materials²

E 4 Practices for Force Verification of Testing Machines³

3. Terminology

3.1 *Definitions*—For definitions of terms used in this test method, see Terminology C 904.

4. Significance and Use

4.1 This test offers a method of determining the bond strength between chemical-resistant mortars and chemical-resistant brick. The results obtained by this test method should be used as a guide in, but not as the sole basis for, selection of a chemical-resistant material for a particular application. If failure is within the brick, then the result reported shall be stated as a minimum bond strength and it shall be noted that the brick broke.

5. Apparatus

5.1 *Equipment*, capable of weighing materials or specimens to ± 0.3 % accuracy.

¹ This test method is under the jurisdiction of ASTM Committee C03 on Chemical-Resistant Nonmetallic Materials and is the direct responsibility of Subcommittee C03.01 on Test Methods.

Current edition approved Sept. 10, 2000. Published November 2000. Originally published as C 321–54T. Last previous edition C 321–94.

² *Annual Book of ASTM Standards*, Vol 04.05.

³ *Annual Book of ASTM Standards*, Vol 03.01.

5.2 *Equipment for Mixing Materials*, consisting of a container of suitable size, preferably made of corrosion-resistant metal, or a porcelain enameled pan, and a strong, sturdy spatula or trowel.

5.3 *Equipment for Melting Sulfur*, consisting of a container of suitable size, preferably made of corrosion-resistant metal, and a heater for melting the sulfur mortar. Also required is a laboratory mixer capable of operating at a speed sufficient to lift the aggregate but without beating air into the melt.

5.4 *Testing Machine*, of the universal type, in which the load is applied hydraulically, mechanically, or electromechanically at a constant but adjustable rate of crosshead movement. The machine shall conform to Practices E 4.

5.5 *Guide for Marking Brick*, of the type shown in Fig. 1.

5.6 *Special Test Fixture*, consisting of two units of the type shown in Fig. 2.

5.7 *Apparatus for Preparation of Mortar Joint by Casting*, of the type shown in Fig. 3.

5.8 *Brick*, as defined in 1.1. See Specification C 279.

6. Temperature

6.1 The standard temperature of the laboratory equipment and materials shall be $73 \pm 4^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$).

7. Number of Specimens

7.1 A minimum of six crossed-brick test specimens shall be prepared.

8. Preparation of Crossed-Brick Test Specimens

8.1 With mortars designed for a trowel-type application, apply the mortar over the area on the brick that is marked for the joint. The amount of mortar applied shall be 25 to 50 % in excess of the required amount to ensure a full joint. Place one of the brick, mortared side up, on a flat level surface. Then place two blocks on each side of the joint area of the bottom brick. The height of the blocks must be uniform and is dependent on the thickness of the mortar joint desired and the height of the brick; for example, if a $\frac{1}{8}$ -in. (3.2-mm) thick joint is desired and the height of the brick laying flat is $3\frac{3}{8}$ in. (85.7 mm), then the blocks should be $3\frac{1}{2}$ in. (88.9 mm) in height in order to provide the desired joint thickness. It is suggested that the blocks be made of wood or rigid plastic. Mortar shall be




FIG. 1 Guide for Marking Brick




FIG. 2 Special Test Fixture

trowelled onto the marked area of the second brick. The amount of mortar applied shall be 10 to 25 % in excess of the required amount to ensure a full joint. Place the second brick

on top of the bottom brick as shown in Fig. 3. Compress the top brick until its ends are firmly against the side blocks. At the same time, align the two brick-mortar