



Designation: D1448 – 05

Standard Test Method for Micronaire Reading of Cotton Fibers¹

This standard is issued under the fixed designation D1448; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers the determination of the micronaire reading of loose cotton fibers by measuring the resistance of a plug of cotton fibers to air flow under prescribed conditions.

NOTE 1—For other methods for determining the fineness of fibers based on the air-flow principle, refer to Test Method [D1449](#), Test Method for Specific Area and Immaturity Ratio of Cotton Fibers (Arealometer Method),² and to Test Method [D1282](#), Test Method for Resistance to Air Flow as an Indication of Average Fiber Diameter of Wool Top, Card Sliver, and Scoured Wool.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

[D123](#) Terminology Relating to Textiles

[D1282](#) Test Method for Resistance to Airflow as an Indication of Average Fiber Diameter of Wool Top, Card Sliver, and Scoured Wool

[D1441](#) Practice for Sampling Cotton Fibers for Testing

[D1449](#) Discontinued 1978; Method of Test for Specific Area and Immaturity Ratio of Cotton Fibers (Arealometer Method)³

[D1776](#) Practice for Conditioning and Testing Textiles

[D7139](#) Terminology for Cotton Fibers

¹ This test method is under the jurisdiction of ASTM Committee [D13](#) on Textiles and is the direct responsibility of Subcommittee [D13.11](#) on Cotton Fibers.

Current edition approved March 1, 2005. Published April 2005. Originally approved in 1954 to replace portions of D414. Last previous edition approved in 1997 as D1448–97. DOI: 10.1520/D1448-05.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn. The last approved version of this historical standard is referenced on www.astm.org.

3. Terminology

3.1 For all terminology related to D13.11, refer to Terminology [D7139](#).

3.1.1 The following terms are relevant to this standard: calibration cotton standards, fineness, micronaire reading.,

3.2 For all other terminology related to textiles, refer to Terminology [D123](#).

4. Summary of Test Method

4.1 The resistance a plug of cotton fibers offers to the flow of air is measured as an approximate indication of the fineness of fiber. A predetermined mass of loose cotton fibers is placed in the specimen holder and compressed to a fixed volume. The resistance to air flow is measured and expressed as micronaire reading. Instruments available to measure resistance to air flow use compressed air or vacuum and are constructed to measure air flow under constant pressure drop across the plug, to measure pressure drop when a constant flow of air is maintained, or to indicate resistance to air flow from both a balanced and unbalanced wheatstone bridge.

5. Significance and Use

5.1 This test method for determining micronaire reading of cotton fibers is considered satisfactory for acceptance testing of commercial shipments when the levels are controlled by use of a full range of calibration cotton standards.

5.1.1 In case of a dispute arising from differences in reported test results when using this test method for acceptance testing of commercial shipments, the purchaser and the supplier should conduct comparative tests to determine if there is a statistical bias between their laboratories. Competent statistical assistance is recommended for the investigation of bias. As a minimum, the two parties should take a group of test specimens that are as homogeneous as possible and that are from a lot of material of the type in question. The test specimens should then be randomly assigned in equal numbers to each laboratory for testing. The average results from the two laboratories should be compared using Student's *t*-test for unpaired data and an acceptable probability level chosen by the two parties before the testing is begun. If a bias is found, either

its cause must be found and corrected or the purchaser and the supplier must agree to interpret future test results in the light of the known bias.

5.2 The micronaire reading of cotton fibers is a function of both fineness and maturity and is related to mill processing performance and to the quality of the end products. Factors correlated with micronaire reading include cleaning efficiency, neppiness, and the strength and uniformity of the yarn.

NOTE 2—A modification of this test method is used in commercial trading to select bales which will conform to contract guarantees for specified micronaire readings. For this purpose, it is usual practice to test only one specimen per sample.

6. Apparatus and Materials

6.1 *Air-Flow Instrument*, calibrated in micronaire readings or yielding numerical readings from which micronaire readings can be computed.⁴

6.2 *Micronaire Scale*, appropriate for instrument.

NOTE 3—The air instrument scale is calibrated for a specific air regulator and tube. The model number on the scale should correspond to the model number of the instrument. If a regulator or tube is replaced, and the same scale is to be used, the new parts must be of the same make and model as those originally furnished with the instrument (1).⁵

6.3 *Balance*, having a capacity suitable for mass of the specimen to be used and a sensitivity of at least 0.2 % of the mass.

6.4 *Air Supply*, to furnish the required pressure or vacuum to operate the instrument in accordance with the manufacturer's instructions.

6.5 *Calibration Cotton Standards*, with assigned micronaire readings.

7. Sampling and Selection of Specimens

7.1 Take the test specimen by random sampling from the laboratory sample prepared as directed in Practice D1441.

NOTE 4—In commercial testing consider the classer's sample that represents both sides of the bale as the laboratory sample. Take portions for each specimen from the end of the classer's sample, to be representative of all layers, or take two test specimens, one from each side of the bale.

8. Conditioning

8.1 Bring the laboratory sample from the prevailing atmosphere to moisture equilibrium for testing and check the equilibrium as directed in Practice D1776. Preconditioning is not necessary.

NOTE 5—The effect of conditioning is small for cottons having micronaire readings below 3.5 but is appreciable for readings of 5.0 and above (2, 3).

9. Procedure

9.1 Set up and adjust the instrument as directed in the manufacturer's instructions. Adjust the instrument if necessary to secure values which check the values assigned to the

International Calibration Cotton Standards at the beginning of each testing period. Make two tests with each standard cotton. If the average of the two results is not within ± 0.1 unit of the established micronaire reading, recheck the instrument and the technique used by the operator. Check the instrument against the standards again at the end of each testing period. If incorrect readings on the standards are obtained at the end of a testing period, discard the results, recheck the instrument, and repeat the tests.

NOTE 6—Built-in calibration devices and calibration plugs alone give only approximate results.

9.2 Test the conditioned specimens in the atmosphere for testing textiles.

9.3 Remove obvious, large pieces of nonfibrous materials. Weigh out a test specimen having the mass specified for the instrument. Place the weighed specimen in the fiber compression cylinder, fluffing it with the fingers as it is packed into the cylinder to eliminate knotty balls, and being careful to place all the fibers inside the cylinder. Insert or activate the fiber compression plunger. Turn on or activate the air, and read the value to the nearest 0.1 unit reading.

9.4 Test two specimens.

10. Calculation

10.1 If the instrument readings are not in micronaire readings, compute micronaire readings from instrument readings in accordance with manufacturer's instructions.

10.2 Calculate the average for the two specimens tested to the nearest 0.1 micronaire reading.

11. Report

11.1 State that the test was carried out as directed in ASTM Test Method D1448.

11.2 Report the following information:

11.2.1 Type of material used and identification of the samples by shipment, mark, lot numbers or bale numbers, whichever is applicable.

11.2.2 Average readings to the nearest 0.1 micronaire reading.

11.2.3 Make, type, and model of the instrument used.

12. Precision and Bias

12.1 *Interlaboratory Test Data*⁶—An interlaboratory test is carried out semi-annually in connection with the International Calibration Cotton Standards Program (4). The data obtained by the five laboratories designated to establish standard values for check test numbers 29, 30, and 31 in 1971 and 1972 were used as the basis for the precision and accuracy statements. One operator at each of the five laboratories tested three specimens from each of six subsamples representing six different cottons. The subsamples for these tests were extracted from cotton which had been hand blended and processed into picker laps to obtain uniform material. The components of variance calculated from the results of these tests and expressed as standard deviations of micronaire reading are

⁴ Instruments commercially available.

⁵ The boldface numbers in parentheses refer to the list of references appended to this test method.

⁶ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report No. RR D14-1074.