NOTICE: This standard has either been superseded and replaced by a new version or withdrawn.
Contact ASTM International (www.astm.org) for the latest information

Designation: D 1566 – 04a

Standard Terminology Relating to Rubber[1]

This standard is issued under the fixed designation D 1566; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This terminology covers definitions of technical terms used in the rubber industry. Terms that are generally understood or adequately defined in other readily available sources are not included.

1.2 Definitions for terms that have been established by other bodies recognized as expert in the field will, after ballot approval, be inserted in this terminology without change, and the source of the definition will be identified. Exceptions to this rule will be where the meaning of the term as used in the rubber industry is different from the common meaning of the term.

1.3 Users of this standard who require mathematical expressions for the time and temperature dependent physical properties of some terms found in this standard should refer to Guide D 5992 and other standards listed under referenced documents. Selected terms from Guide D 5992 may be found in the Annex

1.4 Although this terminology standard avoids the inclusion of jargon and archaic terms as much as possible, some terms have been retained for historical reasons.

2. Referenced Documents

2.1 *ASTM Standards:* [2]

D 412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension

D 925 Test Methods for Rubber Property—Staining of Surfaces (Contact, Migration, and Diffusion)

D 1076 Specification for Rubber—Concentrated, Ammonia Preserved, Creamed, and Centrifuged Natural Latex

D 1148 Test Method for Rubber Deterioration—Heat and Ultraviolet Light Discoloration of Light-Colored Surfaces

D 1415 Test Method for Rubber Property—International Hardness

D 1646 Test Methods for Rubber—Viscosity, Stress Relaxation, and Pre-Vulcanization Characteristics (Mooney Viscometer)

D 1765 Classification System for Carbon Blacks Used in Rubber Products

D 3053 Terminology Relating to Carbon Black

D 5992 Guide for Dynamic Testing of Vulcanized Rubber and Rubber-Like Materials Using Vibratory Methods

D 6085 Practice for Sampling in Rubber Testing—Terminology and Basic Concepts

E 6 Terminology Relating to Methods of Mechanical Testing

E 20 Practice for Particle Size Analysis of Particulate Substances in the Range of 0.2 to 75 µm by Optimal Microscopy[3]

E 28 Test Methods for Softening Point of Resins Derived from Naval Stores by Ring-and-Ball Apparatus

E 111 Test Method for Young's Modulus, Tangent Modulus, and Chord Modulus

E 126 Test Method for Inspection and Verification of Hydrometers

2.2 *ISO Standards:*[4]

1382-82 Rubber-Vocabulary Second Edition (Addendum 16-18-1998)

3. Terminology

abrasion, *n*—the surface loss of a material due to frictional forces.

abrasion resistance index, *n*—a measure of the abrasion resistance of a rubber relative to that of a standard rubber under the same specified conditions, expressed as a percentage.

accelerated life test, *n*—a test method designed to approximate in a short time, the deteriorating effect of normal long-term service conditions.

accelerator (rubber), *n*—a compounding material used in small amounts with a vulcanizing agent to increase the speed of vulcanization.

DISCUSSION—Properties of a vulcanizate are changed by the type or amount of accelerator used.

accelerator, delayed action, *n*—an accelerator that, in conjunction with other curing agent(s), produces, at vulcanizing

[1] This terminology is under the jurisdiction of ASTM Committee D11 on Rubber and is the direct responsibility of Subcommittee D11.08 on Terminology.

Current edition approved July 1, 2004. Published July 2004. Originally approved in 1957. Last previous edition approved in 2004 as D 1566 - 04.

The boldface designations refer to the original source of the definition and the ASTM technical committee having jurisdiction.

[2] For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[3] Withdrawn.

[4] Available from International Organization for Standardization (ISO), 1 rue de Varembé, Case postale 56, CH-1211, Geneva 20, Switzerland.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

Documents
Document Sharing Hub
Full document details: ASTM D1566-04a

temperatures, a period of no significant cross-linking, followed by a period of rapid cross-link formation.

activator, *n*—compounding material used in small proportions to increase the effectiveness of an accelerator.

adhesion, *n*—condition in which surfaces are held together by chemical or physical forces or both.

adhesion failure, *n*—the loss of structural integrity due to the separation of two bonded surfaces at the bond interface.

adhesion value, *n*—force required to cause adhesion failure.

DISCUSSION—Any separation occurring at any other point, for example, inside either component under test, is a failure of the component material, and such separation should not be considered as indicating adhesion strength.

adhesive failure, *n*—a separation of two bonded surfaces that occurs within the bonding material.

DISCUSSION—Adhesive failure occurs when the adhesive strength of a bonding material is greater than its cohesive strength.

aftercure, *n*—a continuation of the process of vulcanization after the energy source has been removed.

age resistance, *n*—the ability of a material to resist deterioration caused by ageing.

agglomerate, compounding material, *n*—a cluster of particles of one or more compounding materials loosely held together.

agglomerate, latex, *n*—a cluster of rubber particles in a colloidal aqueous suspension of such particles.

agglomerates, *n*—clusters of particles of compounding materials contained in a continuous rubber phase.

agglomeration (latex), *n*—reversible or irreversible joining together of latex particles.

ageing (act of), *n*—exposure of materials to a deteriorating environment for a specified time interval.

ageing (rubber), *n*—the irreversible change of material properties during exposure to a deteriorating environment, for a specified time interval.

ageing, accelerated, *n*—exposure of rubber to a test environment with the intent of producing, in a shorter time period, effects similar to normal ageing.

ageing, air bomb, *n*—the process of exposing materials to the action of air at an elevated temperature and pressure.

ageing, air oven, *n*—The process of exposing materials to the action of air at an elevated temperature at atmospheric pressure.

ageing, natural, *n*—ageing under normal service conditions.

ageing, oxygen bomb, *n*—the process of exposing materials to the action of oxygen at an elevated temperature and pressure.

ageing, shelf, *n*—ageing during storage.

alloy, *n*—a unique composition of two or more polymers that has one or more of the polymers treated or processed in a special way to confer enhanced performance characteristics on the resulting material.

anticoagulant (natural rubber latex), *n*—a substance added to field latex to retard bacterial action which would otherwise cause rapid coagulation of the latex.

DISCUSSION—The word "stabilizer" is often used in place of "anticoagulant" in latex terminology.

antidegradant, *n*—compounding material used to retard deterioration caused by oxidation, ozone, light, and combinations of these.

DISCUSSION—"Antidegradant" is a generic term for such additives as antioxidants, antiozonants, and waxes.

antiflex cracking agent, *n*—a compounding material used to retard cracking caused by cyclic deformations.

antifoaming agent, *n*—an agent that inhibits bubble formation in an agitated liquid, usually by reducing the surface tension.

antioxidant, *n*—compounding material used to retard deterioration caused by oxidation.

antiozonant, *n*—compounding material used to retard deterioration caused by ozone.

antistatic agent, *n*—a material which reduces the tendency for accumulation of electric charge on the surface of an article.

apparent density, *n*—See **density, bulk,** the preferred term.

aromatic oil, *n*—a hydrocarbon process oil containing at least 35 %, by mass, of aromatic hydrocarbons.

ash, *n*—the residue from incineration of a material under specified conditions.

autoclave (rubber), *n*—a pressure vessel used for vulcanizing rubber products by means of steam under pressure.

backrinding, *n*—a molding defect in which the rubber adjacent to the spew line shrinks below the surface of the molded product, with the spew line often being ragged and torn.

bag cure, *n*—a method of vulcanization in which an inflated flexible bag is used to impart positive internal pressure on the article being vulcanized.

balata, *n*—a hard thermoplastic consisting of approximately equal proportions of trans-polyisoprene and resin, obtained from trees of the *Sapotaceae* family.

bale coating, *n*—a coating applied to surfaces of rubber bales that inhibits adhesion to other surfaces.

ball mill, *n*—a closed rotating cylinder containing hard balls (or other shaped members) that serves to grind coarse materials to a finer particle size.

bank (mill, calender, or spreader), *n*— a reservoir of material at the opening between rolls (mill or calender), or at the spreader bar.

batch, *n*—the product of one mixing operation.

bench marks, *n*—two marks of known separation applied to a specimen to measure the strain of the specimen during extension.

blank, *n*—a portion of a rubber compound of suitable volume to fill the cavity of a mold.

bleeding, *n*—the exuding of a liquid compounding material from the surface of a vulcanized or unvulcanized rubber.

blister(s), *n*—surface or internal imperfection(s), produced by entrapped gases or other volatiles, during the manufacture of rubber articles.

bloom (rubber), *n*—a liquid or solid material that has migrated to the surface of a rubber and generally changes the surface appearance.

blow, *n*—the volume expansion that occurs during the production of cellular or sponge rubber.

AVA Documents
Document Sharing Hub

Full document details: ASTM D1566-04a

blowing agent, *n*—a compounding material used to produce gas by chemical or physical action, or both, in the manufacture of hollow or cellular articles.

booster, *n*— synonym for **secondary accelerator**, which is the preferred term.

bound monomer, *n*—monomer that is combined or reacted with itself or other types of monomers in a polymerization reaction to form a polymer.

DISCUSSION—This term is used in synthetic rubber production, and the bound monomer is normally expressed as a percentage of total polymer.

buffing rubber, *n*—particulate rubber produced as a byproduct of the buffing operation in the carcass preparation stage of a tire retreading; characterized by a wide range of particle sizes that are predominately elongated or acicular in shape. See **particulate rubber**.

DISCUSSION—The appearance of the unique shape of the particles of this material is only apparent in finished goods or products that contain particles having a dimension greater in size than 600 µm (30 mesh).

bumping, molding process, *n*—the application, release, and reapplication of pressure prior to the start of vulcanization to vent entrapped gases, thereby facilitating complete filling of the mold.

calender, *n*—a machine with two or more parallel, counter-rotating rolls with a controllable, roll-to-roll spacing, rotating at selected surface speeds and controlled temperatures, used for sheeting, laminating, skim coating (topping) and friction coating, to a controlled thickness and/or surface condition.

carbon black, *n*—a material consisting essentially of elemental carbon in the form of near-spherical colloidal particles and coalesced particle aggregates of colloidal size, obtained by partial combustion or thermal decomposition of hydrocarbons. **D 3053**

carbon black, thermal, *n*—a type of carbon black produced under controlled conditions by the thermal decomposition of hydrocarbons in the absence of air or flames.

DISCUSSION—These grades are designated with an "N" first character and a second character of "8 or 9" in Table 1 of Classification D 1765. **D 3053**

carbon black, thermal, acetylenic, *n*—a thermal black produced from acetylene gas **D 3053**

carbon gel (carbon-rubber-gel), *n*—the portion of rubber that is not leached by a solvent under specified conditions, from an intimate mixture of carbon black and unvulcanized rubber.

carcass, *n*—the fabric, cord, or metal reinforced section, or all three, of a rubber product as distinguished from the rubber tube, cover, or tread.

cell, *n*—a single small cavity surrounded partially or completely by walls.

cell, closed, *n*—a cell totally enclosed by its walls, hence not interconnecting with other cells.

cell, open, *n*—a cell not totally enclosed by its walls and hence interconnecting with other cells.

cellular material, *n*—a generic term for materials containing many cells (either open, closed, or both) dispersed throughout the mass.

cellular material, collapse, *n*—undesirable densification of a cellular material resulting from the breakdown of its cellular structure.

cellular material, cored, *n*—cellular material containing a multiplicity of holes (usually, but not necessarily, cylindrical in shape), molded or cut into the material in some pattern normally perpendicular to the largest surface, and extending part or all the way through the piece.

cellular material, flexible, *n*—a cellular organic polymeric material that will not rupture when a specimen 200 by 25 by 25 mm (8 by 1 by 1 in.) is bent around a 25-mm (1-in.) diameter mandrel at a uniform rate of one lap in 5 s at a temperature between 18 and 29°C.

cellular striation, *n*—a condition characterized by a layer within a cellular material that differs greatly from the characteristic cell structure.

cement, rubber, *n*—an adhesive that is either a liquid dispersion or solution of raw or compounded rubber, or both.

chalking (rubber), *n*—the formation of a powdery residue on the surface of a rubber, commonly resulting from surface degradation.

chatter marks, *n*—defect on calendered sheeting consisting of transverse narrow bands of alternately thicker and thinner material.

coagent, *n*—a compounding ingredient used in small amounts to increase the crosslinking efficiency of certain non-sulfur vulcanizing systems, or to modify the properties given by such systems.

DISCUSSION—The term is usually identified with additives used to modify vulcanization by organic peroxides.

coagulant dipping (latex), *n*—a dipping process in which the product form is first immersed in a coagulant solution, withdrawn, dried, and then immersed in the latex.

coagulation (rubber latex), *n*—irreversible agglomeration of particles originally dispersed in a rubber latex.

coagulum (latex), *n*—an undesirable, irreversible, agglomeration of rubber particles retained on a 180-µm mesh screen. **D 1076**

coated fabric, *n*—a flexible product composed of a textile fabric and an adherent polymeric material applied to one or both surfaces.

cohesive failure (bonded assembly), *n*—a rupture occurring entirely within any single uniform layer of the assembly.

cold checks, *n*—defect on calendered sheeting consisting of surface roughness.

cold flow (unvulcanized rubber), *n*—slow deformation, under gravitational force, at or below room temperature.

comonomer, *n*—one of two or more monomer species that polymerize to form a copolymer.

Documents
Document Sharing Hub

Full document details: ASTM D1566-04a

compound, *n*—an intimate admixture of a polymer(s) with all the materials necessary for the finished article.

compound, standard, *n*—a control or reference compound prepared according to a prescribed formula and mixing procedure.

compounding ingredient, *n*—See **compounding material**, the preferred term.

compounding material, *n*—a substance used as part of a rubber mix.

compression molding, *n*—molding process in which the material is placed directly in the mold cavity and compressed to shape by closure of the mold.

compression set, *n*—the residual deformation of a material after removal of the compressive stress.

conditioning (environmental), *n*—the storage of a rubber, under specified conditions (time, temperature, humidity) prior to testing.

conditioning (mechanical), *n*—the prescribed program of deformation of a specimen prior to testing.

conventional sulfur vulcanizing system, *n*—as applied to natural and isoprene rubbers and butadiene-based synthetic rubbers, a vulcanizing system using a relatively high proportion of sulfur in which the combined sulfur exists predominantly in the polysulfidic cross links chain modifications.

DISCUSSION—The amount of free sulfur and the ratio of free sulfur to accelerator will vary from rubber to rubber.

copolymer, *n*—a polymer formed from two different monomers.

cracker, *n*—heavy-duty mill having two deeply corrugated or pyramid-cut rolls for breaking down a rubber or a mix, or for cutting rubber or a mix into pieces.

cracks, *n*—fissure(s) originating in the surface of a rubber vulcanizate or product as a result of natural weathering.

cracks, flex, *n*—fissures originating in the surface of a rubber vulcanizate, resulting from cyclic deformation (usually bending).

crack(s), ozone, *n*—fissure(s) originating in the surface of a rubber vulcanizate, caused by exposure to an ozone-containing environment; these fissures are perpendicular to the direction of strain, and usually occur in rubbers having main chain unsaturation.

crazing, *n*—formation of a random pattern of shallow cracks on a rubber surface usually due to ageing by light.

DISCUSSION—Unlike ozone cracking, crazing does not depend on the presence of a tensile strain in the rubber.

creep, *n*—the time-dependent part of a strain resulting from stress.

crosslink, *n*—chemical bond bridging one polymer chain to another.

crosslinking (the act of), *n*—formation of chemical bonds between polymer chains to give a network structure.

crowsfeet, *n*—small flowmarks of V-shape on calendered sheeting.

crystallization, polymer, *n*—arrangement of previously disordered polymer segments of repeating patterns into geometric symmetry.

cure, *n*— See **vulcanization**, the preferred term.

cure meter, *n*—a testing device that measures the progress of vulcanization at a vulcanizing temperature.

DISCUSSION—The measured property, normally proportional to the complex dynamic modulus, is recorded at closely spaced time intervals to produce a quasi-continuous measured property versus time curve.

curing agent, *n*—synonym for **vulcanizing agent**, the preferred term.

density, *n*—the mass per unit volume of a material. **E 126, E 20**

density, bulk, *n*—the mass per unit volume of a material, including any voids present.

desiccant, *n*—compounding material used to irreversibly absorb moisture present (in a rubber mix) particularly for the purpose of minimizing risk of porosity during vulcanization.

devulcanization, *n*—destruction of the chemical crosslinks in a vulcanized rubber.

die swell, *n*—difference between the dimensions of the cross section of an extrudate and the corresponding dimensions of the die orifice by which the extrudate is formed.

DISCUSSION—It is usually quantified as the percentage increases in the cross-sectional area.

diene polymer, *n*—a polymer formed from one or more monomer species, at least one of which is a diolefin.

dipping (latex), *n*—a process in which a layer of rubber is deposited on a mold or form as a result of immersion in a bath of compounded latex.

dispersing agent (latex), *n*—a surface-active substance used to facilitate the suspension of solid compounding materials in a liquid medium and to stabilize the dispersion thereby produced.

dispersion (the act of), *n*—application of shearing forces to distribute one or more compounding materials uniformly throughout the mass of a continuum of material.

dough (rubber), *n*—a paste-like mass of smooth texture, consisting of a rubber mix and solvent; it is used for spreading.

dumbbell specimen (rubber), *n*—a flat specimen having a narrow straight central portion of essentially uniform cross section with enlarged ends. **D 412**

durometer, *n*—an instrument for measuring the indentation hardness of rubber.

dusting, *n*—the application of a powder to a rubber surface, generally to prevent adhesion to another surface.

dynamic vulcanizate, *n*— See **thermoplastic vulcanizate**, the preferred term.

dynamic vulcanization, *n*—the process of intimate melt mixing a thermoplastic polymer and a suitable reactive rubbery polymer to generate a thermoplastic elastomer with a chemically cross-linked rubbery phase resulting in properties close to those of a thermoset rubber when compared to the same cross-linked composition.

Documents
Document Sharing Hub

Full document details: ASTM D1566-04a

ebonite, *n*—a hard material made by sulfur vulcanization of rubber, in which the hardness is substantially obtained by the action of the sulfur.

efficient vulcanizing (EV) systems, *n*—as applied to natural rubber and isoprene- and butadiene-based synthetic rubbers, a vulcanizing system making efficient use of sulfur and producing at optimum cure a network containing a preponderance of thermally stable monosulfidic crosslinks.

DISCUSSION—EV systems are comprised of a sulfur donor or a combination of low concentration of free sulfur (for example, <0.5 parts per hundred parts of rubber), or both, at a comparatively high concentration of accelerator(s).

elastic, *adj*—of or pertaining to elasticity.

elastic limit, *n*—the greatest stress that a material is capable of sustaining, without any permanent strain remaining, upon complete release of the stress. **E 6, E 28**

elasticity, *n*—The rapid recovery of a material to its approximate initial shape and dimensions after substantial deformation by force and subsequent release of that force.

elastomer, *n*—an elastic polymer.

elongation, *n*—extension produced by a tensile stress.

elongation, percent, *n*—the extension of a uniform section of a specimen expressed as percent of the original length.

DISCUSSION—Elongation, % =

$$\frac{(\text{final length} - \text{original length})}{\text{original length}} \times 100$$

elongation, ultimate, *n*—the elongation at the time of rupture.

emulsifying agent (latex), *n*—a surface-active substance used to facilitate the dispersion of an immiscible liquid compounding material in another liquid and to stabilize the emulsion thereby produced.

extender, *n*—an organic material used to augment the polymer in a compound.

extensometer, *n*—a device for determining elongation of a specimen as it is strained.

extrudate, *n*—the material that issues from an extruder.

extruder, *n*—machine designed to force a rubber or rubber mix through an orifice, which is often shaped to the geometry of the desired product.

extrusion, *n*—the continuous shaping of a material during plastic passage through a die.

extrusion mark (score line), *n*—a mark formed on an extrudate during the extrusion process either by accident or intent.

fatigue breakdown, *n*—the deterioration of an elastomeric product during repeated deformation.

fatigue, dynamic, *n*—the deterioration of a material by repeated deformation. See **fatigue breakdown**.

fatigue life, *n*—the number of deformations required to produce a specified state of fatigue breakdown in a test specimen or product that is deformed under a prescribed set of conditions.

field latex, *n*—See **latex, field**

filler, *n*—a solid compounding material, usually in finely divided form, which may be added in relatively large proportions to a polymer for technical or economic reasons.

filler, inert, *n*—a filler having no reinforcing effect.

flash, *n*—the excess material protruding from the surface of a molded article at the mold junctions.

flat cure, *n*—a synonym for **plateau vulcanization**

flex life, *n*—the number of cycles required to produce a specified state of failure in a specimen that is flexed in a prescribed method.

flexometer, *n*—a machine that subjects a test specimen to repeated deformation by compression, tension, shear, bending, torsion, or any combination thereof.

flocculation, *n*—formation (sometimes reversible) of loosely coherent, partially agglomerated rubber, distributed in the liquid phase of a latex.

flow marks, *n*—marks or line on a molded product, caused by imperfect fusion of flowing fronts.

foam stabilizer (latex), *n*—a substance used in the preparation of latex foam, before gelation, drying, and vulcanization to help maintain the foam cell structure.

foaming agent (latex), *n*—a substance used to facilitate the formation of suspended gas in latex during the production of latex foam.

former (latex), *n*—a shaped object on which a rubber article is produced by dipping into a latex, from which the article is subsequently removed.

formula, *n*—a list of the materials and their amounts used in the preparation of a compound.

friction coat, calender, *n*—a layer of rubber compound applied to a fabric by shearing action so that it impregnates the fabric.

friction coating, *n*—applying a rubber coat (friction coat) on a textile by shearing action so that the coat impregnates the textile.

friction ratio, *n*—ratio of surface speeds of two adjacent rolls (mill, calender, or refiner).

frosting, *n*—formation of a matte, whitish appearance on a rubber surface exposed to air, resulting from the action of ozone; often confused with bloom.

furnace carbon black, *n*—type of carbon black produced by the decomposition reaction of hydrocarbons when injected into a high velocity stream of combustion gases under controlled conditions. **D 3053**

gage length, *n*—the known distance between bench marks.

gasket (mechanical), *n*—a deformable material clamped between essentially stationary faces to prevent the passage of matter through an opening or joint.

gate (injection or transfer mold), *n*—the orifice through which a shaped cavity in a mold is filled with material.

gel, dry rubber, *n*—the portion of unvulcanized rubber insoluble in a chosen solvent.

gel, latex, *n*—a semi-solid system consisting of a network of aggregates in which liquid is held.

gel time, *n*—the period of time from the initial mixing of the reactants of a plastic or rubber composition to the time when gelation occurs as defined by a specified test.

gelling (latex), *n*—the formation of a uniform coagulum from which the aqueous phase has not been separated.

AVA Documents
Document Sharing Hub

Full document details: ASTM D1566-04a