



Designation: D 2617 – 96 (Reapproved 2001)

Standard Test Method for Total Ash in Leather¹

This standard is issued under the fixed designation D 2617; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of total ash in leather.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 2807 Test Method for Chromic Oxide in Leather (Perchloric Acid Oxidation)²

D 2813 Practice for Sampling Leather for Physical and Chemical Tests²

3. Summary of Test Method

3.1 The sample is ignited in air at $600 \pm 25^\circ\text{C}$ until constant mass is attained. The weighed residual matter is termed “ash” and is calculated as a percentage of the original sample.

4. Significance and Use

4.1 This test method is useful in determining the approximate amount of nonvolatile inorganic material in leather. This may be in the form of salts or oxides of the elements. In a mixed chrome tannage, the approximate percentage of other elements in the leather may be determined by subtracting the chromic oxide that may be conveniently determined on the ash. (See Test Method D 2807.)

4.2 The temperature of 600°C specified is high enough to produce a reproducible result but it does not completely dehydrate such oxides as aluminum oxide, (Al_2O_3) and chromic oxide (Cr_2O_3). Likewise, such salts as sulfates and phosphates may be incompletely dehydrated, and if alkalies and chromium are present simultaneously, oxidation to chro-

mate may occur. Therefore, caution is advised in drawing conclusions based on quantitative relations of the elements.

5. Apparatus

5.1 *Crucible*, 30 to 50-mL, high-form, platinum or porcelain.

5.2 *Electric Muffle Furnace*, with controller or rheostat and pyrometer, capable of maintaining a temperature of $600 \pm 25^\circ\text{C}$.

6. Test Specimen

6.1 The specimen shall consist of 1 to 5 g of leather from the composite sample prepared in accordance with an accepted procedure.³

NOTE 1—In some leathers, silicones or other organometallic complexes that are solvent, soluble, and ash producing are used. It may be desirable to obtain ash on an extracted sample, and if so, it should be indicated on the report.

7. Procedure

7.1 Weigh accurately (to 1 mg) into a tared crucible 1 to 5 g of leather, prepared as described in 6.1, and preferably at sufficiently close equilibrium with the laboratory humidity that it does not gain or lose mass at a significant rate. Place the crucible and sample in the muffle furnace and maintain at $600 \pm 25^\circ\text{C}$ for at least 15 min, or longer if necessary to destroy carbonaceous matter (Note 2). Remove the crucible from the furnace, cool in a desiccator, and weigh (Note 3). Replace in the furnace and maintain at $600 \pm 25^\circ\text{C}$ for another 15 min. Repeat the weighing operation. Continue heating for 15 min and weighing as described above until a mass constant within 0.2 mg is obtained. Record the final mass.

NOTE 2—The above procedure is satisfactory with most leathers. With heavily oiled or stuffed leather, start with a cold muffle and raise temperature gradually to 600°C , or burn off the oil carefully over a gas burner before placing the crucible in the hot furnace.

NOTE 3—If it is difficult to burn off the carbon, as evidenced by inspection or failure to achieve constant mass, moisten the ash with a few drops of 1+1 nitric acid, dry carefully over a low flame, and then transfer to the muffle and heat as before. If this procedure is unsuccessful, digest

¹ This test method is under the jurisdiction of ASTM Committee D31 on Leather and is the direct responsibility of Subcommittee D31.06 on Chemical Analysis—General. This test method was developed in cooperation with the American Leather Chemists Assn. (Standard Method B 15 – 1969).

Current edition approved May 10, 1996. Published July 1996. Originally published as D 2617 – 69. Last previous edition D 2617 – 69 (1991)^{ε1}.

² *Annual Book of ASTM Standards*, Vol 15.04.

³ Acceptable procedures are published in the *Journal of the American Leather Chemists Association*, Vol 51, 1956, p. 497; see Practice D 2813.

the ash in the crucible with 15 to 20 mL of hot water for a few minutes, and filter the suspension through an ashless high-retention filter paper. Transfer the paper and insoluble residue to the crucible and ignite at $600 \pm 25^\circ\text{C}$ as described above. Cool, add the filtrate to the crucible, evaporate carefully to dryness, then ignite at $600 \pm 25^\circ\text{C}$ to constant mass as described above.

8. Calculations

8.1 Calculate the percentage of ash in the leather weighed as follows:

$$\text{Ash, \%} = [(A - B)/(C - B)] \times 100 \quad (1)$$

where:

A = mass of the ash and crucible,

B = mass of the crucible, and

C = mass of the sample and crucible.

8.2 If it is desired to convert the percentage obtained above to the dry basis, perform a moisture determination on a portion of the same sample weighed under the same conditions as in Section 7. If the percentage moisture found is D , then calculate the percentage of ash on a dry basis as follows:

$$\text{Ash, dry basis, \%} = [(A - B)/(C - B)] \times [100/(1 - D/100)] \quad (2)$$

where A , B , and C have the same meaning as in 8.1.

8.3 The ash may be determined on a sample conditioned as to temperature and relative humidity. In this case, weigh the

sample under identically controlled temperature and humidity, and report the results in such a manner as to indicate this fact, for example:

$$\text{Ash } (X^\circ\text{C}, Y\% \text{ relative humidity}) = Z\% \quad (3)$$

9. Precision and Bias ⁴

9.1 *Precision*—The precision of this test method is largely limited by the homogeneity of the sample in a complex natural material such as leather.

9.1.1 *Repeatability*—At the 95 % confidence level, duplicate determinations by the same operator should not differ by more than 0.14 % ash.

9.1.2 *Reproducibility*—At the 95 % confidence level, the average of duplicate determinations in each of two laboratories by different operators should not differ by more than 0.20 % ash.

9.2 *Bias*—Inasmuch as all leathers contain an unknown amount of natural or inherent ash, no meaningful statement can be made with respect to bias.

10. Keywords

10.1 aluminum oxide; ash; chromic oxide

⁴ The precision and bias statements are based on data filed at the ASTM Headquarters as RR 89: D-31.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).