



Designation: D2702 – 05 (Reapproved 2021)

Standard Practice for Rubber Chemicals—Determination of Infrared Absorption Characteristics¹

This standard is issued under the fixed designation D2702; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This practice covers a simple, rapid practice to prove the identity of a rubber chemical before incorporation into a rubber mix by comparison of its infrared absorption spectrum with that of a reference specimen.

1.2 This technique can also be used to detect gross contamination or large differences in rubber chemicals. Thus, it can provide a basis for producer-consumer agreement.

1.3 Wherever “infrared spectrophotometer” is used, “Fourier Transform Infrared Spectrometer (FTIR)” may also be understood.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E131 Terminology Relating to Molecular Spectroscopy

E168 Practices for General Techniques of Infrared Quantitative Analysis

E275 Practice for Describing and Measuring Performance of Ultraviolet and Visible Spectrophotometers

¹ This practice is under the jurisdiction of ASTM Committee D11 on Rubber and Rubber-like Materials and is the direct responsibility of Subcommittee D11.11 on Chemical Analysis.

Current edition approved Nov. 1, 2021. Published November 2021. Originally approved in 1968. Last previous edition approved in 2016 as D2702 – 05 (2016). DOI: 10.1520/D2702-05R21.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Terminology

3.1 *Definitions:* For definitions of terms used in this practice refer to Terminology E131.

4. Summary of Practice

4.1 A method of specimen preparation is selected that is compatible with the physical and chemical properties of the rubber chemical that will provide the desired spectral information.

4.2 The specimen is placed in the specimen beam of the spectrophotometer and scanned to obtain a spectrum over the region of interest under specified instrument parameters.

4.3 The spectrum is compared with that of a reference specimen. It is understood that the reference specimen was prepared and scanned in an identical manner and preferably on the same infrared spectrophotometer.

5. Significance and Use

5.1 This procedure can be used for a variety of applications, including identifying unlabeled material, process control, raw material acceptance, product evaluation, and compositional change during environmental testing.

5.2 Rubber chemicals vary widely in their chemical and physical properties. Infrared spectrophotometers vary in the presentation of a spectrum (some are linear with absorbance, others with transmittance, some use grating for energy dispersion, others use a sodium chloride prism, some obtain a spectrum through a mathematical Fourier Transform, and the like). For these reasons, a single universal method of specimen preparation and set of instrument parameters is not possible.

5.3 By using a specific sampling procedure and operating conditions, a given spectrophotometer will give an absorption curve that is characteristic of the rubber chemical or mixture under investigation.

5.4 The ability to superimpose the infrared spectrum of the test specimen upon that of a reference specimen, obtained under the same conditions, is evidence that the two are identical.

5.5 The presence of additional absorption bands in either the test specimen or the reference specimen indicates the presence of one or more additional components.

6. Apparatus

6.1 *Initial Specimen Preparation*—The diverse physical nature of rubber chemicals may require the use of one or more of the following:

6.1.1 *Agate Mortar and Pestle*, small.

6.1.2 *Wig-L-Bug Amalgameter*.³

6.1.3 *Mold and Press for KBr Pellets*—The die size will depend on the disk holder available with the user's infrared spectrophotometer. The hydraulic press should be capable of exerting 140-MPa (20 000-psi) pressure.

6.1.4 *Vacuum Pump*, operating at 250 Pa or less.

6.2 *Infrared Spectrophotometer*:

6.2.1 The spectral region from 2.5 to 15 μm (4000 to 667 cm^{-1}) is the region most often used for rubber chemical identification, although inorganic chemicals may have useful bands down to 250 cm^{-1} .

6.2.2 If the performance of the spectrophotometer must be evaluated, refer to Practice E275.

6.3 *Demountable Cells*—Liquid cells ranging from 0.025 to 1.0 mm in specimen path length and KBr pellet holder should be available. On occasion, a variable-path cell is useful.

6.4 *KBr or NaCl Plates*, of suitable size for spectrophotometer.

7. Reagents

7.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁴ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 Observe all health and safety recommendations for handling the chemicals in this practice.

7.3 Any of the following reagents may be required depending on the method chosen for sample preparation:

7.3.1 *Carbon Disulfide*, spectro quality.

7.3.2 *1,2-Dichlorobenzene*.

7.3.3 *Ether*, anhydrous.

7.3.4 *Hexachlorobutadiene*.

³ The sole source of supply of the apparatus known to the committee at this time is Crescent Dental and Manufacturing, 7750 W. 47th St., Lyons IL 60534. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

⁴ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Annual Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

7.3.5 *Refined Mineral Oil*.⁵

7.3.6 *Perfluorocarbon Oil*.

7.3.7 *Potassium Bromide* (KBr), infrared quality.

7.3.8 *Tetrahydrofuran*, (without inhibitor).

7.3.9 *Acetone*, infrared quality.

8. Sampling and Sample Preparation

8.1 Generally, the physical nature of the specimen will determine the specimen preparation procedure. In some cases, where alternative procedures could be used, agreement between the chemical producer and consumer would be required. In choosing a specimen preparation procedure, certain potential sources of error should be considered. These are listed in the preparation procedures 8.2 – 8.5. The techniques are also described in Practices E168.

8.2 *Liquids*—Fixed-thickness absorption cells of 0.025 to 0.5 mm are used for the analysis of low-viscosity liquids. Demountable cells are used with more viscous liquid specimens. Spacers can be used to adjust specimen thickness, but the usual practice is to spread a film of viscous liquid over one salt plate, overlay a second plate, and squeeze out the excess until the desired film thickness has been reached. Initially, the desired thickness may be obtained by trial and error. A specimen thickness of 0.02 to 0.1 mm usually gives a good spectrum. The experienced spectroscopist can usually judge an adequate film thickness with minimum effort.

8.3 *Solids*—Specimens that are solid (amorphous, polymeric, or crystalline) may be handled by one or more of several techniques:

8.3.1 *Mulling Techniques*:

8.3.1.1 Perhaps the most common method for infrared study of solid powders is to grind a few milligrams of powder in an agate mortar and add a suspending agent to make a mull (see Practices E168). Scan the resultant paste in a demountable cell.

8.3.1.2 *Mineral Oil*⁵ is a mulling agent, which in the thickness used, is quite transparent in the infrared, except for the CH absorption frequencies at 3.3, 6.9, 7.3, and 13.9 μm (3000, 1450, 1375, and 720 cm^{-1}). If information is desired in these regions, alternative mulling materials are hexachlorobutadiene or perfluorocarbon oil.

8.3.1.3 It is desirable to grind the specimen thoroughly with mortar and pestle before adding the mulling agent to minimize light scattering and reduce window scratching. A minimum of mulling agent should be used to wet the powder.

8.3.1.4 Polymeric specimens are usually better handled by other techniques because of the grinding difficulty. Freezing this type of specimen with dry ice or the use of a freezer mill may help, but it can also introduce water condensate contamination.

8.3.2 *Melted Film Technique*:

8.3.2.1 This method can be used for polymeric or highly viscous materials. It consists of melting the specimen and spreading a thin film across the face of a salt plate.

8.3.2.2 Advantages are that no solvent or mulling agent interference bands are introduced. Possible disadvantages are

⁵ Nujol has been found satisfactory for this purpose.