



Designation: D 3201 – 08a

Standard Test Method for Hygroscopic Properties of Fire-Retardant Wood and Wood- Based Products¹

This standard is issued under the fixed designation D 3201; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method prescribes the procedure for determining the moisture content of fire-retardant-treated wood and wood-based product samples after exposure to a standard high relative humidity condition of $92 \pm 2\%$ at $27 \pm 2^\circ\text{C}$ ($81 \pm 4^\circ\text{F}$).

1.2 The text of this test method references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of this test method.

1.3 The values stated in SI units are to be regarded as the standard. The inch-pound values given in parentheses are for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D 9 Terminology Relating to Wood and Wood-Based Products

E 176 Terminology of Fire Standards

3. Terminology

3.1 *Definitions*—Definitions used in this practice are in accordance with Terminologies **D 9** and **E 176**.

¹ This test method is under the jurisdiction of ASTM Committee D07 on Wood and is the direct responsibility of Subcommittee D07.07 on Fire Performance of Wood.

Current edition approved Nov. 1, 2008. Published December 2008. Originally approved in 1973. Last previous edition approved in 2008 as D 3201 – 08.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Significance and Use

4.1 The hygroscopic properties of wood and wood-based products treated with fire-retardant chemicals are often greater than for untreated products. This is particularly true at the higher relative humidity conditions. This higher hygroscopicity sometimes is the cause for staining, decay, poor paint adhesion, and migration and exuding of chemicals and moisture at the high humidities. Corrosion of metal fasteners sometimes also occurs.

4.2 The results obtained with this standard are important in identifying treatments with low hygroscopic properties.

4.3 Results can be useful in determining exposure limitations in service for specific treated products.

4.4 Building codes and other specifications for fire-retardant-treated wood for interior use include requirements based on this test method.

5. Apparatus

5.1 *Conditioning* chamber with air circulation and capable of being maintained at $27 \pm 2^\circ\text{C}$ ($81 \pm 4^\circ\text{F}$) and a relative humidity of $92 \pm 2\%$.

5.2 *Oven*, air-circulated and vented, capable of maintaining a temperature of $103 \pm 2^\circ\text{C}$ ($217 \pm 4^\circ\text{F}$).

5.3 *Weighing Scale*—A scale or balance that will weigh a specimen within an accuracy of $\pm 0.2\%$.

6. Test Specimens

6.1 A minimum of five specimens shall be selected that represent the lot. Unless otherwise specified, specimens shall be full cross sections, no less than 25.4 mm (1 in.) along the grain, but longer as needed to provide a minimum volume of $33\,000\text{ mm}^3$ (2 in.³).

6.2 The specimens shall be penetrated by the fire-retardant chemical to be representative for the treated product.

NOTE 1—The use of untreated specimens as control specimens is recommended to provide verification of the high-humidity conditions used.

7. Procedure

7.1 All measurements of the specimen weight shall be to an accuracy of $\pm 0.2\%$.

7.2 The specimens shall be in moisture equilibrium with a laboratory ambient condition of 30 to 65 % relative humidity or shall be exposed for at least 7 days at such a condition prior to high-humidity exposure.

7.3 If the specimens will support fungal or mold growth during the high humidity exposure, then the specimens shall be sprayed with a suitable biocide just prior to the above exposure and allowed to air-dry for the seven days.

7.4 Weigh each specimen to obtain weight prior to high humidity exposure.

7.5 Expose all specimens under constant humidity conditions of $92 \pm 2\%$ at $27 \pm 2^\circ\text{C}$ ($81 \pm 4^\circ\text{F}$) for 7 days. Specimens shall be suitably suspended so that all surfaces are exposed.

7.6 If the specimens exude moisture or chemicals or both under the exposure conditions, collect any drippings and include the weight with the specimen weight.

7.7 Weigh each specimen immediately, after its removal from the conditioning chamber to obtain the weight after high humidity exposure. Observe and record the general appearance of the specimens.

7.8 Dry each specimen in an oven at $103 \pm 2^\circ\text{C}$ ($217 \pm 4^\circ\text{F}$) until approximately constant weight is attained, and reweigh to obtain ovendry weight after high humidity exposure. Constant weight can be assumed when two consecutive readings taken 2 h apart agree within 0.2 %. Avoid drying for periods longer than necessary to achieve constant weight, since thermal decomposition of chemical or wood might occur reflecting a higher than actual moisture content.

8. Calculations

8.1 Calculate the moisture content of each specimen prior to high-humidity exposure (u_i) as follows:

$$u_i, \% = \frac{m_i - m_{od}}{m(od)} \times 100 \quad (1)$$

where:

m_i = weight of specimen prior to high-humidity exposure, and

m_{od} = ovendry weight of specimen after high-humidity exposure.

8.2 Calculate the moisture content of each specimen after high-humidity exposure (u_f) as follows:

$$u_f, \% = \frac{m_f - m_{od}}{m(od)} \times 100 \quad (2)$$

where:

m_f = weight of the specimen after high-humidity exposure, and

m_{od} = ovendry weight of specimen after high-humidity exposure.

NOTE 2—These methods of determining the moisture content do not correct for any volatilization of chemical during the ovendrying, which increases the calculated percent moisture content. Also, the calculation for percent moisture content is relative to the total specimen weight of wood and chemical. The percent moisture content relative to the wood weight alone is higher and this value can be estimated by reducing the m_{od} value in the divisor of the above equation by the known or assumed percentage of chemical in the treated specimen.

9. Report

9.1 Report the following information:

9.1.1 Complete identification of the fire-retardant product as to species of wood, wood product, and treatment.

9.1.2 Description of sampling procedure and number and dimensions of test specimens.

9.1.3 General description of humidity chamber and controls used for the test.

9.1.4 When data are available for untreated specimens exposed simultaneously with the treated specimens to the high-humidity condition, the report shall include the average moisture content of the untreated specimens at the end of the exposure.

9.1.5 The average of the moisture contents for the treated specimens before high-humidity exposure, as calculated by Eq 1, shall be reported.

9.1.6 The average of the moisture contents for the treated specimens after high-humidity exposure, as calculated by Eq 2, shall be reported.

9.1.7 Report any change in the appearance of the specimen during exposure, including surface wetness, chemical exudation, or crystals on surface.

10. Precision and Bias

10.1 There is insufficient data available to write a precision and bias statement.

11. Keywords

11.1 fire-retardant treated wood; hygroscopicity; moisture content

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).