



Designation: D 4233 – 01

Standard Performance Specification for Women's and Girls' Knitted and Woven Brassiere Fabrics¹

This standard is issued under the fixed designation D 4233; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This performance specification covers woven and knitted fabrics comprised of any fiber or mixture of fibers used in women's and girls' brassieres.

1.2 This performance specification is not applicable to knitted or woven brassiere fabrics containing elastomeric yarns, to knitted lace fabrics, and to fabrics used for interlinings.

1.3 These requirements apply to the length and width directions for those properties where each fabric direction is pertinent.

2. Referenced Documents

2.1 ASTM Standards:²

- D 123 Terminology Relating to Textiles
- D 434 Test Method for Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam
- D 1424 Test Method for Tearing Strength of Fabrics by Falling-Pendulum Type (Elmendorf) Apparatus
- D 1682 Test Methods for Breaking Load and Elongation of Textile Fabrics³
- D 2261 Test Method for Tearing Strength of Fabrics by the Tongue (Single Rip) Procedure (Constant-Rate-of-Extension Tensile Testing Machine)
- D 2262 Test Method for Tearing Strength of Woven Fabrics by the Tongue (Single Rip) Method (Constant-Rate-of-Traverse Tensile Testing Machine)⁴
- D 3786 Test Method for Hydraulic Bursting Strength of Knitted Goods and Nonwoven Fabrics: Diaphragm Bursting Strength Tester Method⁵
- D 3787 Test Method for Bursting Strength of Knitted Goods: Constant-Rate-of-Traverse (CRT) Ball Burst Test⁵

2.2 AATCC Methods:⁶

- 8 Colorfastness to Crocking: AATCC Crockmeter Method
- 15 Colorfastness to Perspiration
- 16 Colorfastness to Light
- 23 Colorfastness to Burnt Gas Fumes
- 61 Colorfastness to Washing, Domestic, and Laundering, Commercial: Accelerated
- 116 Colorfastness to Crocking: Rotary Vertical Crockmeter Method
- 124 Appearance of Durable Press Fabrics after Repeated Home Launderings
- 132 Colorfastness to Drycleaning
- 135 Dimensional Changes in Automatic Home Laundering of Durable Press Woven or Knit Fabrics
- 172 Colorfastness to Non-chlorine Bleach in Home Laundering
- 188 Colorfastness to Chlorine Bleach in Home Laundering Evaluation Procedure 1 Gray Scale for Color Change Evaluation Procedure 2 Gray Scale for Staining Evaluation Procedure 3 AATCC Chromatic Transference Scale

2.3 Federal Standard:⁷

- 16 CFR, Chapter II-Consumer Product Safety Commission Subchapter D-Flammable Fabrics Act Regulations

2.4 Military Standard:⁸

- MIL-STD-105D Sampling Procedures and Tables for Inspection by Attributes

NOTE 1—Reference to test methods in this standard give only the permanent part of the designation of ASTM, AATCC, or other test methods. The current editions of each test method cited shall prevail.

3. Terminology

3.1 Definitions:

3.1.1 For definitions of textile terms used in this specification refer to the individual ASTM and AATCC test methods and to Terminology D 123.

¹ This performance specification is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.61 on Apparel. Current edition approved May 10, 2001. Published July 2001. Originally published as D 4233 – 83. Last previous edition D 4233 – 95.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Discontinued; see 1990 *Annual Book of ASTM Standards*, Vols 07.01.

⁴ Discontinued; see 1994 *Annual Book of ASTM Standards*, Vols 07.01.

⁵ Discontinued; see 1994 *Annual Book of ASTM Standards*, Vol 07.02.

⁶ Available from the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709.

⁷ Available from Superintendent of Documents, Government Printing Office, Washington, DC 20402.

⁸ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

3.2 Definitions found in a dictionary of common terms are suitable for this specification.

4. Specification Requirements

4.1 The properties of knitted and woven fabrics for women's and girls' brassieres shall conform to the specification requirements in Table 1.

5. Significance and Use

5.1 Upon mutual agreement between the purchaser and the seller, fabrics intended for this end use should meet all the requirements listed in Table 1 of this specification.

5.2 It is recognized that for purposes of fashion or aesthetics the ultimate consumer of articles made from these fabrics may find acceptable fabrics that do not conform to all of the requirements in Table 1. Therefore, one or more of the requirements listed in Table 1 may be modified by mutual agreement between the purchaser and the seller.

5.2.1 In such cases, any references to the specification shall specify that: "This fabric meets ASTM Specification D 4233 except for the following characteristic(s)."

5.3 Where no prepurchase agreement has been reached between the purchaser and the seller, and in case of controversy, the requirements listed in Table 1 are intended to be used as a guide only. As noted in 5.2, ultimate consumer demands dictate varying performance parameters for any particular style of fabric.

5.4 The uses and significance of particular properties and test methods are discussed in the appropriate sections of the specified test methods.

6. Sampling

6.1 *Lot Sample*—As a lot sample for acceptance testing, take at random the number of rolls as directed in an applicable

specification or other agreement between the purchaser and the supplier, such as an agreement to use MIL-STD-105D.

6.2 *Laboratory Sample*—From each roll or piece in the lot sample, cut two laboratory samples the full width of the fabric and at least 375 mm (15 in.) along the selvage.

7. Test Methods (See Note 1)

7.1 *Breaking Strength* (load) (woven fabrics only)—Determine the dry-breaking strength (load) in the standard atmosphere for testing textiles, as directed in the grab test procedure of Test Methods D 1682 using a constant-rate-of-traverse (CRT) tensile testing machine with the speed of the pulling jaw at 12 ± 0.5 in. (305 ± 13 mm)/min.)

NOTE 2—If preferred a constant-rate-of-extension (CRE) tensile testing machine may be used. The crosshead speed should be as agreed between the purchaser and the seller. There may be no overall correlation between the results obtained with the CRT machine and the CRE machine. Consequently, these two breaking load testers cannot be used interchangeably. In case of controversy, the CRT method shall prevail.

7.2 *Bursting Strength* (knit fabrics only)—Determine the bursting strength of knit fabrics as directed in Test Method D 3786 or Test Method D 3787 as agreed between the purchaser and the seller.

NOTE 3—Care should be taken to subtract the tare diaphragm pressure from the gross pressure to obtain actual bursting strength of fabric when using the diaphragm bursting tester. Calibrate the equipment according to manufacturer's instruction before use. Since there is no overall correlation between the results obtained with the CRT machine equipped with a bursting attachment and the diaphragm bursting tester, these two bursting testers cannot be used interchangeably. In case of controversy, the CRT machine equipped with a bursting attachment method shall prevail.

NOTE 4—The precision of the ball burst method using the CRT machine equipped with a bursting attachment and the precision of the diaphragm bursting tester method are being established by Subcommittee D13.59.

TABLE 1 Specification Requirements^A

Characteristic	Requirements		Section
	Knit	Woven	
<i>Breaking strength</i> (load) (CRT) ^B	...	40 lbf (178 N), min	7.1
<i>Bursting strength</i> (ball burst) ^B	50 lbf (222N), min	...	7.2
<i>Tongue-tear strength</i> ^B	...	1.5 lbf (6.7 N), min	7.3
<i>Yarn slippage</i>	...	¼ in. (6 mm) separation at 30 lbf (133 N), min	7.4
<i>Dimensional Change:</i>			
<i>Laundrying</i>	5 % max	2 % max (no change)	7.5.1
<i>Colorfastness:</i>			
<i>Burnt gas fumes—2 cycles</i>			7.6.1
Shade change, original fabric	Class 4 ^C , min	Class 4 ^C , min	
Shade change, after one laundrying	Class 4 ^C , min	Class 4 ^C , min	
<i>Laundrying</i>			7.6.2
Shade change	Class 4 ^C , min	Class 4 ^C , min	
Staining	Class 3 ^D , min	Class 3 ^D , min	
<i>Crocking</i>			7.6.3
Dry	Class 4 ^E , min	Class 4 ^E , min	
Wet	Class 3 ^E , min	Class 3 ^E , min	
<i>Perspiration</i>			7.6.4
Shade change	Class 4 ^C , min	Class 4 ^C , min	
Staining	Class 3 ^D , min	Class 3 ^D , min	
<i>Light</i> (10AATCC FU) ^B (xenon-arc)	Step 4 ^C , min	Step 4 ^C , min	7.6.5
<i>Chlorine Bleach</i>	Class 4 ^C , min	Class 4 ^C , min	7.6.6
<i>Non-chlorine Bleach</i>	Class 4 ^C , min	Class 4 ^C , min	7.6.7
<i>Flammability</i>	pass	pass	7.7

^A Class in colorfastness is based on a numerical scale of 5 for negligible color change or color transfer to 1 for very severe color change or color transfer.

^B There is more than one standard that can be used to measure breaking.

^C AATCC Gray Scale for Color Change.

^D AATCC Gray Scale for Staining.

^E AATCC Chromatic Transference Scale.