



Designation: D6085 – 97 (Reapproved 2022)

Standard Practice for Sampling in Rubber Testing—Terminology and Basic Concepts¹

This standard is issued under the fixed designation D6085; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers a standardized terminology and some basic concepts for testing and sampling across the broad range of chemical and physical testing operations characteristic of the rubber and carbon black manufacturing industries.

1.2 In addition to the basic concepts and terminology, a model for the test measurement process is given in [Annex A1](#). This serves as a mathematical foundation for the terms and other testing concepts. It may also find use for further development of this practice to address more complex sampling operations.

1.3 This general topic requires a comprehensive treatment with a sequential or hierarchical development of terms with substantial background discussion. A number of ancillary terms are also given that make for a more self-contained document. This cannot be accommodated in Terminology [D1566](#).

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

[D1566 Terminology Relating to Rubber](#)

¹ This practice is under the jurisdiction of Committee [D11](#) on Rubber and Rubber-like Materials and is the direct responsibility of Subcommittee [D11.16](#) on Application of Statistical Methods.

Current edition approved June 1, 2022. Published July 2022. Originally approved in 1997. Last previous edition approved in 2016 as D6085 – 97 (2016). DOI: 10.1520/D6085-97R22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D4483 Practice for Evaluating Precision for Test Method Standards in the Rubber and Carbon Black Manufacturing Industries](#)

[D5406 Practice for Rubber—Calculation of Producer's Process Performance Indexes](#)

3. Terminology

3.1 Definitions:

3.2 Despite the adoption of standard test methods, test result variation influences the data generated in all testing programs. As outlined in [Annex A1](#), there are two main categories: (1) variation inherent in the production process for a material or class of objects, and (2) variation due to the measurement operation itself. Each of these two sources may be further divided into two types of variation: (1) systematic or bias variation, and (2) random error variation. Both types can exist simultaneously for either of the main categories.

3.3 Random variation can be reduced to a low level by appropriate replication and sampling procedures, but bias variation cannot be so reduced. However, bias variation can be reduced or eliminated by comprehensive programs to sort out the causes of such perturbations and eliminate these causes.

3.4 Elementary Testing Terms:

3.4.1 *lot, n*—a specified mass of material or number of objects, generated by an identifiable process, with a recognized composition or property range.

3.4.1.1 *Discussion*—A lot is frequently generated by a common production process in a restricted time period and usually consists of a finite size or number. A lot may be a fractional part of a population (Interpretation 2 of *population*).

3.4.2 *material, n*—a specific entity that exists in bulk form (solid, powder, liquid).

3.4.2.1 *Discussion*—A material may or may not be homogeneous. Typical materials are individual rubbers, compounds, accelerators, carbon blacks, etc.

3.4.3 *object, n*—a discrete item or piece with a specified shape and size.

3.4.3.1 *Discussion*—Usually an object is an entity that is ready for testing. A typical object is an o-ring, dumbbell, pellet, or hose assembly.

3.4.4 *object class (or class of objects)*, n —a number of objects, with a recognized property range, generated by a common process, the objects are usually characterized by the value(s) of a unique property.

3.4.4.1 *Discussion*—In any testing program the phrase “a recognized property range” implies that the tester is aware of the approximate value of this range. At one extreme, this recognized range may denote “essentially identical property values;” at the opposite extreme this recognized range may denote “widely varying property values.” The range applies to both materials and object classes, and testing programs will differ in regard to the extent of variation under consideration.

3.4.5 *population*, n —a generic term used in testing operations that may refer to any one of the following: (1) a single object or a very limited mass of material, (2) a finite (but large) number of objects or large mass of material, or (3) a hypothetical infinite number of objects or mass of material; all three interpretations imply that the objects or material are generated by some identifiable process and have recognized property range.

3.4.5.1 *Discussion*—Testing programs may vary from a very limited focus of attention (Interpretation 1) to an extreme or broad focus of attention (Interpretation 3). The focus of attention is determined by the testing and the sampling program.

3.4.6 *test (or testing)*, n —a technical procedure performed on a material or object class using specified equipment that produces data unique to the material or object class; the data are used to evaluate or model selected properties or characteristics.

3.4.6.1 *Discussion*—Testing can be conducted on a narrow or broad basis, depending on the decisions to be made for any program. Sampling and replication plans (see 3.5) need to be specified for a complete program description. Testing may be divided into two major categories:

3.4.6.2 *global testing*, n —testing that is conducted at two or more locations or laboratories for the purpose of comparing materials or object classes at each location for selected characteristic properties.

3.4.6.3 *Discussion*—Typical global testing applications are producer-user testing and interlaboratory comparisons such as precision evaluation. These may be conducted on a worldwide basis.

3.4.6.4 *local testing*, n —testing that is conducted at one location or laboratory for the purpose of comparing a number of materials or object classes for some selected characteristic properties.

3.4.6.5 *Discussion*—Quality control and internal development programs are typical local testing.

3.5 Sampling and Related Testing Terms:

3.5.1 *random sample*, n —one of a sequence of samples (or sub-samples) taken on a random basis from a lot or population.

3.5.2 *replicate*, n —a generic term used in testing operations that denotes one of a selected number of fractional parts or objects taken from a sample; each fractional part or object is tested.

3.5.3 *replication*, n —the act of selecting replicates.

3.5.3.1 *Discussion*—The primary purpose of replication is the reduction of random test measurement variation. See [Annex A1](#) for additional discussion on types of replication.

3.5.4 *sample*, n —a small fractional part of a material or a specified number of objects that are selected from a lot for testing, inspection, or specific observations of particular characteristics.

3.5.4.1 *Discussion*—A sample may be obtained from the combination of a series of incremental parts, each part obtained in one step of a particular sampling process (see *sub-sample*).

3.5.5 *sampling*, n —the act of selecting samples of any type.

3.5.5.1 *Discussion*—The goals of sampling are (1) an accurate or representative evaluation of the characteristic properties of the lot or population, and (2) an accurate estimate of the variation of properties within the lot or population.

3.5.6 *sub-sample*, n —one of a sequence of intermediate fractional parts or intermediate sets of objects taken from a lot or population that usually will be combined in a prescribed protocol to form a sample.

3.5.7 *systematic sample*, n —one of a sequence of samples (or sub-samples), each taken from a particular location or region of a lot or population according to a prescribed plan; the usual goal is to determine if the lot or population is homogeneous.

3.5.7.1 *Discussion*—Non-homogeneity may be of a random nature or it may be systematic (variation), which is frequently referred to as “stratification.”

3.5.8 *test piece*, n —see *test specimen*, the preferred term.

3.5.9 *test portion*, n —see *test sample*, the preferred term.

3.5.10 *test sample*, n —that part of a sample of any type taken (usually with a prescribed blending or other protocol) for chemical or other analytical testing.

3.5.10.1 *Discussion*—A test sample may be a replicate or it may be subdivided into n replicates; these n replicates are frequently called “laboratory samples.” Test samples are typically drawn to represent materials such as rubbers, pigments, chemicals, etc.

3.5.11 *test specimen*, n —an object (appropriately shaped and prepared) taken from a sample for physical or mechanical testing.

3.5.11.1 *Discussion*—A test specimen is usually a replicate. Test specimens are typically prepared by a rubber processing (and curing) operation to evaluate characteristic properties of development compounds and the compounds used in manufactured rubber products. They may also be manufactured rubber parts such as o-rings, motor mounts, etc.

3.6 *Testing Variation Terms*—[Annex A1](#) defines a number of test data variation terms (see [A1.4](#)). Some additional terms, as given below, apply to typical development testing as well as quality control and quality assurance.

3.6.1 *common cause variation*, n —that residual variation inherent in any process that (1) is operating in a state of statistical control, and (2) is operating at some recognized or ascertained level of technological competence (Practice [D5406](#)).

3.6.2 *special cause variation, n*—that variation attributable to certain specific or assignable sources that have been (or may be) discovered through an investigation of the process (Practice D5406).

3.6.2.1 *Discussion*—Both common and special cause variation may contain bias as well as random variation components. A synonym for common cause variation is *non-assignable variation*; a synonym for special cause variation is *assignable variation*.

3.6.3 *total process variation, n*—a range, along the measured property scale, defined as six times the standard deviation (determined under specified process conditions); the variation may contain either common or combined common and special cause sources (Practice D5406).

3.6.3.1 *Discussion*—Although this is defined in terms of quality control operations, it applies equally to general testing. For this general testing, the “process” and the “standard deviation” refer to the total (testing and sampling) operation.

4. Significance and Use

4.1 This practice provides a standardized terminology and a review of some basic concepts for elementary sampling and testing. These operations are important for: (1) local or intralaboratory testing that generally applies to internal quality control, process capability or performance evaluation, as well as development programs, and (2) global or interlaboratory testing that applies to producer-user and other testing programs that have industry-wide or worldwide scope. It is recognized that certain test methods may require more detailed and specialized sampling operations than the generic ones as described herein. These specialized sampling procedures should utilize, as far as possible, the basic concepts as given in this practice.

4.2 This practice provides a list of terms and concepts that may be used in numerous test methods used by Committees D11 and D24. It improves communication among those that conduct testing in the rubber and carbon black manufacturing industries and those that use such testing and test results for technical decisions.

5. Elementary Sampling Concepts

5.1 The purpose of testing is the production of test data to be used to make technical decisions. Test data are the end result of a three-step process: (1) test program organization, (2) sampling, and (3) testing. Test data quality depend on the organization and the sampling for any program.

5.2 Types of Sampling Plans:

5.2.1 *Intuitive Sampling*—This is a plan organized on the basis of the developed skill and judgment of the sampler. General information of the lot or population as well as past sampling and testing experience are used to make sampling decisions. The decisions made on the data generated by such a plan are based on a combination of the skill and experience of the tester buttressed by limited statistical conclusions. Strict probabilistic conclusions usually are not warranted.

5.2.2 *Statistical Sampling*—This is based on strict statistical sampling and such a plan provides the basis for authentic probabilistic conclusions. Hypothesis testing may be

conducted, inferences drawn, and predictions made about future system or process behavior. Usually a large number of samples are needed if the significance of small differences is of importance. Conclusions from this type of sampling usually are not controversial. The statistical model chosen is important. When the number of samples required is large and this imposes a testing burden, hybrid plans using some simplifying intuitive assumptions are frequently employed.

5.2.3 *Protocol Sampling*—These are specified plans used for decision purposes in a given situation. Regulations (of the protocol) usually specify the type, size, frequency, and period of sampling in addition to the test methods to be used and other important sampling issues. The protocol may be based on a combination of intuitive and statistical considerations. Testing for conformance with producer-user specifications for commercial transactions is typical for this approach.

5.3 Ensuring the Quality of Samples and Testing:

5.3.1 Only the most elementary sampling issues are addressed in this section. For more detailed information, standard texts on sampling and sampling theory should be consulted. Well defined sampling operations must be conducted to ensure that high quality samples are used for any testing program. Quality is ensured when the samples are drawn in accordance with a prescribed procedure. This ensures that they accurately represent the lot or population. Such issues as sample homogeneity (or unintended stratification) and sample stability (conditioning or storage changes in the sample prior to testing) must be addressed. The sampling procedures, holding time, and other handling operations should be well documented. The test methods used for any program should be stable or in a state of statistical control and have demonstrated sensitivity as well as good precision in regard to the measured parameter.

5.3.2 **Annex A1**, paragraph A1.4, addresses the issue of production process and measurement variation or variance and how to evaluate these components. **Table 1** illustrates four testing scenarios for sampling variance, S^2 (sampling), and measurement variance, S^2 (measurement). The importance or significance of either component is determined in large part by the magnitude of the expected difference, d , for a simple comparison of the measured parameter values for two different or potentially different lots or populations.

5.3.3 Type 1 is encountered when the expected difference, d , is large. For this situation the variance of neither component is critical. Type 2 is typical of a less precise test where sampling variation is low. If the test is in control, and the variance known, the number of measurements needed can be calculated for any desired level of confidence for d .

TABLE 1 Four Testing Variation Component Scenarios

Type of Scenario	Component ^a	
	S^2 (sampling)	S^2 (measurement)
1	Not significant	Not significant
2	Not significant	Significant
3	Significant	Not significant
4	Significant	Significant

^a Not Significant = no significant or large variation component. Significant = a significant or large variation component.