Designation: D7801 – 12

Standard Terminology for Paint Brush Application Tools[1]

This standard is issued under the fixed designation D7801; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This standard establishes the definitions for terminology used in testing and manufacturing of paint brushes.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*[2]

D5068 Practice for Preparation of Paint Brushes for Evaluation

D5301 Practice for Physical Characterization of Paint Brushes

D7073 Guide for Application and Evaluation of Brush and Roller Applied Paint Films

3. Terminology

3.1 *Definitions:*

brush ferrule, *n*—the fitting that houses the butt end of the filament and secures it to the handle.

brush filling material, *n*—a set of aligned filament (whether natural hair, plant fibers or synthetic) used to provide the brushing portion of a paint brush.

brush stiffness, *n*—force required to deflect the filaments to a particular displacement.

chisel trim, *n*—a brush making process in which the tip of the brush is mechanically (cut or sheared) shaped to a domed profile.

cut-in, *v*—to carefully paint an edge to avoid spreading paint onto an adjacent area.

feathering, *n—for painting*, to reduce the thickness of a wet, coated region (such as using the strokes of a relatively dry brush) so that the edge fades off or softens.

fishtail, *n*—a condition in which the center filaments of a brush wear down more than the filaments on the side of the brush.

formed chisel, *n*—a property of a brush produced by a brush making process in which the filaments are assembled, formed and bound at the butt end to produce a domed (beveled) profile at the tip end.

formulation, *n*—a specification that gives the ingredients and amounts or process.

heeling, *n—for paint brush filaments*, reduction of brush performance caused by paint hardening in the handle (heel) end of the filament bundle.

length clear, *n*—the length of the filament exposed from the ferrule edge to the tip of the brush filament.

snap, *n—for paint brush filaments*, the flexibility and resiliency of brush filaments when bent to one side and then released.

tipped, *n—for synthetic filaments*, ending in a fine point that is formed by mechanical or chemical processes.

wear, *n—for paint brush filaments*, loss in effectiveness of a paint brush caused by abrasion of the filaments.

4. Keywords

4.1 brushes; definitions; terminology

---

[1] This terminology is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.61 on Paint Application Tools.

Current edition approved June 1, 2012. Published June 1, 2102. DOI: 10.1520/D7801-12.

[2] For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States

Documents
Document Sharing Hub
Full document details: ASTM D7801-12

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).

AVA Documents
Document Sharing Hub

Full document details: ASTM D7801-12