



Designation: E2240 – 06

Standard Test Method for Assessing the Current-Voltage Cycling Stability at 90°C (194°F) of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units¹

This standard is issued under the fixed designation E2240; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the accelerated aging and monitoring of the time-dependent performance of electrochromic windows (ECW). Cross sections of typical electrochromic windows have three to five-layers of coatings that include one to three active layers sandwiched between two transparent conducting electrodes (TCEs, see Section 3). Examples of the cross-sectional arrangements can be found in “Evaluation Criteria and Test Methods for Electrochromic Windows.”² (For acronyms used in this standard, see [Appendix X1](#), section [X1.1](#)).

1.2 This test method is applicable only for layered (one or more active coatings between the TCEs) absorptive electrochromic coatings on sealed insulating glass (IG) units fabricated for vision glass (superstrate and substrate) areas for use in buildings, such as glass doors, windows, skylights, and exterior wall systems. The layers used for electrochromically changing the optical properties may be inorganic or organic materials between the superstrate and substrate.

1.3 The electrochromic coatings used in this test method will be subsequently exposed (see Test Methods [E2141](#)) to solar radiation and deployed to control the amount of radiation by absorption and reflection and thus, limit the solar heat gain and amount of solar radiation that is transmitted into the building.

1.4 This test method is not applicable to other chromogenic devices, for example, photochromic and thermochromic devices.

1.5 This test method is not applicable to electrochromic windows that are constructed from superstrate or substrate materials other than glass.

1.6 This test method referenced herein is a laboratory test conducted under specified conditions. This test is intended to simulate and, possibly, to also accelerate actual in-service use of the electrochromic windows. Results from this test cannot be used to predict the performance with time of in-service units unless actual corresponding in-service tests have been conducted and appropriate analyses have been conducted to show how performance can be predicted from the accelerated aging tests.

1.7 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.8 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:³

2.1.1 For additional useful standards related to this standard, see [Appendix X1](#), section [X1.2](#).

[C168 Terminology Relating to Thermal Insulation](#)

[C1048 Specification for Heat-Strengthened and Fully Tempered Flat Glass](#)

[C1199 Test Method for Measuring the Steady-State Thermal Transmittance of Fenestration Systems Using Hot Box Methods](#)

[E632 Practice for Developing Accelerated Tests to Aid Prediction of the Service Life of Building Components and Materials](#)

[E903 Test Method for Solar Absorptance, Reflectance, and Transmittance of Materials Using Integrating Spheres](#) (Withdrawn 2005)⁴

¹ This test method is under the jurisdiction of ASTM Committee [E06](#) on Performance of Buildings and is the direct responsibility of Subcommittee [E06.22](#) on Durability Performance of Building Constructions.

Current edition approved Sept. 1, 2006. Published September 2006. Originally approved in 2002. Last previous edition approved in 2002 as E2240 – 02. DOI: 10.1520/E2240-06.

² Czanderna, A. W., and Lampert, C. M., “Evaluation Criteria and Test Methods for Electrochromic Windows,” SERI/PR-255-3537, July 1990, Golden, CO; Solar Energy Research Institute.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

⁴ The last approved version of this historical standard is referenced on www.astm.org.

E1423 Practice for Determining Steady State Thermal Transmittance of Fenestration Systems

E2094 Practice for Evaluating the Service Life of Chromogenic Glazings (Withdrawn 2011)⁴

E2141 Test Methods for Assessing the Durability of Absorptive Electrochromic Coatings on Sealed Insulating Glass Units

E2188 Test Method for Insulating Glass Unit Performance

G113 Terminology Relating to Natural and Artificial Weathering Tests of Nonmetallic Materials

2.2 *Canadian Standard:*

CAN/CGSB 12.8 Insulating Glass Units

3. Terminology

3.1 *Definitions*—Refer to terminology in Terminology **C168**, Practice **E632**, and Terminology **G113** for descriptions of general terms.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *accelerated aging test*—an aging test in which the rate of degradation of building components or materials is intentionally accelerated from that expected in actual service.

3.2.2 *bleached state*—a descriptor for an ECW when no ions reside in the electrochromic layer or after ions have been removed (or inserted, depending on the type of material) from the electrochromic layer(s) and if applicable, the maximum number of ions have been returned to the counterelectrode layer to restore the photopic optical specular transmittance in the bleached state (τ_b) from that of the photopic optical specular transmittance in the colored state (τ_c).

3.2.3 *colored state*—a descriptor for an ECW after ions have been inserted (or removed, depending on the type of material) into the electrochromic layer and, if applicable, removed from the counterelectrode layer to reduce the photopic optical specular transmittance (of wavelengths from 400 to 730 nm) from that in the bleached state (τ_b).

3.2.4 *durability*—the capability of maintaining the serviceability of a product, component, assembly or construction over a specified time.

3.2.5 *electrochromic coating*—the multilayered materials that include the electrochromic layers, other layers, and transparent conducting oxide layers required for altering the optical properties of the coating.

3.2.6 *electrochromic layer(s)*—the material(s) in an ECW that alter its optical properties in response to the insertion or removal of ions, for example, Li^+ or H^+ .

3.2.7 *electrochromic window (ECW)*—a window consisting of several layers of electrochromic and attendant materials, which are able to alter their optical properties in response to a change in an applied electric field. The changeable optical properties include transmittance, reflectance, and absorptance.

3.2.8 *ion conducting layer*—the material in an ECW through which ions are transported between the electrochromic layer and the ion storage layer and electron transport is minimized.

3.2.9 *ion storage layer or counter electrode layer*—the material in an ECW that serves as a reservoir for ions that can be inserted into the electrochromic layer.

3.2.10 *performance parameters*—the photopic transmittance ratio (PTR), of at least 5:1 ($\text{PTR} = \tau_b/\tau_c$) between the bleached (for example, τ_b of 60 to 70 %) and colored (for example, τ_c of 12 to 14 %) states; coloring and bleaching times of a few minutes; switching with applied voltages from ~1 to 3 V; and open-circuit memory of a few hours, for example, contemporary ECWs typically have open circuit memories of 6 to 24 h.

3.2.11 *serviceability*—the capability of a building product, component, assembly or construction to perform the function(s) for which it was designed and constructed.

3.2.12 *service life*—of a building component or material, the period of time after installation during which all properties exceed minimum acceptable values when routinely maintained.

3.3 For additional useful definitions for terminology used in this standard, see **Appendix X1**, section **X1.3**.

4. Significance and Use

4.1 This test method is intended to provide a means for evaluating the current-voltage cycling stability at 90°C (194°F) of ECWs as described in **1.2**.^{2,5} (See **Appendix X1**, sections **X1.4-X1.7**.)

5. Background

5.1 Observations and measurements have shown that some of the performance parameters of ECWs have a tendency to deteriorate over time. In selecting the materials, device design, and glazing for any application, the ability of the glazing to perform over time is an indication of that glazing's durability. The ability of the product to perform over time, at or better than specified requirements, is an indication of the service life of the glazings (see Practice **E2094**). While these two indicators are related, the purpose of this standard test method is to assess the current-voltage cycling stability at 90°C (194°F) of ECWs.

5.2 ECWs perform a number of important functions in a building envelope including: minimizing the solar energy heat gain; providing for passive solar energy gain; controlling a variable visual connection with the outside world; enhancing human comfort (heat gain), security, ventilation, illumination, and glare control; providing for architectural expression, and (possibly) improving acoustical performance. Some of these functions may deteriorate in performance over time. Solar heat gain through an ECW is decreased because of two principal processes. Energy from the visible part of the spectrum is absorbed by an ECW in the colored state. In addition, infrared radiation is either absorbed by the ECW materials or is reflected by the transparent conducting oxide layers that are used for applying the coloring or bleaching potentials across the other layers in the ECW.

⁵ Czanderna, A. W., Benson, D. K., Jorgensen, G. J., Zhang, J.-G., Tracy, C. E., and Deb, S. K., "Durability Issues and Service Lifetime Prediction of Electrochromic Windows for Buildings Applications," NREL/TP-510-22702, May 1997, National Renewable Energy Laboratory, Golden, CO; Solar Energy Materials and Solar Cells, 56, 1999, pp. 419-436.

5.3 It is possible, but difficult, to predict the time-dependent performance of ECWs from accelerated aging tests because of the reasons listed below. Users of this document should be aware of these limitations when reviewing published performance results and their connection to durability.

5.3.1 The degradation mechanisms of ECW materials or glazings, or both, are complex. In some cases, however, these mechanisms may be determined and quantified.

5.3.2 The external factors that affect the performance of ECWs are numerous and may be difficult to quantify. However, in some cases, the use, the environmental factors, and other information that influence performance may be known.

5.3.3 Fenestration units with tested ECWs may be different from those planned for use in service. Some companies have a database of in-service performance that can be compared to laboratory results.

5.4 Degradation factors (or stresses) for ECWs include the ion insertion and removal processes; temperature; solar radiation (especially UV); water vapor; atmospheric gases and pollutants; thermal stresses such as shock from sudden rain, as well as during the diurnal and annual temperature cycles; electrochemically induced stresses in the multilayer thin-film device; hail, dust, and wind; condensation and evaporation of water; and thermal expansion mismatches.^{2,5} These factors may singularly or collectively limit the stability and durability of ECWs. Because the ECWs are expected to have the multilayer of coatings on one of the surfaces in the cavity of double-pane or triple-pane IG units with an inert gas fill in the sealed space, many factors such as high humidity, atmospheric gases and pollutants, condensation and evaporation of water, and dust should not affect the durability of electrochromic coatings in IG units.²

5.4.1 Establishing test procedures from which ECW durability can be predicted and validated for in-service use is an extremely crucial element for the commercialization of ECWs, even for niche markets. To reduce the number of accelerated test parameters that are required to predict the long-term performance of ECWs, accepted procedures or methods have not been established for testing ECWs.² Because no uniformly accepted procedures or methods have been established for the real-time testing of ECWs and because manufacturers and users cannot wait 20 or more years for the real-time evaluation of each window design, accelerated life testing (ALT) methods and procedures must be used for evaluating ECW stability.^{2,5} These include (a) rapid but realistic current-voltage (I-V) cyclic tests emphasizing the electrical properties, (b) ALT parameters that are typically used in durability tests by standards organizations, (c) ALT parameters that are realistic for the intended use of large-area ECWs, and (d) how the ALT results must be related to real-time testing.² The purpose of this test method is to assess the current-voltage cycling stability at 90°C (194°F) of ECWs at least 254 by 254 mm (10 by 10 in.).

NOTE 1—The seals in IGUs may fail at lower temperatures than those planned for testing, that is, 90°C (194°F). A seal failure will virtually guarantee failure of the ECW coating, so no assessment of the stability of the ECW coating will be made if a seal fails during the test.

NOTE 2—The test method may also be used for smaller ECWs to assess the current-voltage cycling stability at 90°C (194°F) of prototype devices. The testing parameters chosen may only provide modest acceleration

factors. However, the quantitative parameters discussed in (a)–(c) above are presented and include a detailed description of the procedures for using an accelerated weathering unit.⁵

6. Apparatus (see Figs. 1 and 2 and Section 8.3 for Descriptive Detail)

6.1 *Voltage Cycling Unit*, for imposing voltage cycles to alternately and repeatedly color and bleach the ECWs from a fully bleached state to the colored state and back to the bleached state.

6.2 *Computer Controlled Photodiode Array Spectrophotometer*, for example, for obtaining and storing data from the electro-optical characterization of the optical transmittance in the colored and bleached state and measuring the rate of coloring and bleaching.

6.3 *Oven*, that is large enough for the largest ECW to be tested and that can reach the ECW testing temperature. The oven must also be designed to permit using the equipment in 6.2 for optical measurements while the ECW is maintained at the temperature chosen for testing.

6.4 *Tungsten Lamp*, a spectrum from the source must be compatible with the fiber optic illumination of the photodiode array spectrophotometer described in 6.2.

6.5 *Digital Camera*.

6.6 *Video Camera and Recorder*.

6.7 *Calibrated Thermocouples*.

6.8 *Electrical Leads*, from the unit in 6.1 to each ECW in the oven described in 6.3.

7. Test Specimens

7.1 Test specimen size, design, and construction shall be established and specified by the user of this standard, except the specimens shall be at least 254 by 254 mm (10 by 10 in.).

NOTE 3—Consideration should be given to the ultimate requirement for testing specimens that are 355 ± 6 mm by 505 ± 6 mm ($14 \pm 1/4$ in. by $20 \pm 1/4$ in.), such as those used in Test Method E2188, and for using heat-strengthened or tempered glass (Specification C1048). Consult Section 5 in Test Method E2188 and Section 12.1 in CAN/CGSB 12.8 for a description of test specimens and their preparation.

7.2 Six test specimens that are represented to be “identical” shall be the minimum number used to assess the current-voltage cycling stability at 90°C (194°F) of a particular design and construction.⁵ (See Appendix X1, section X1.5.)

7.3 The manufacturer shall provide control parameters and other information that are needed by the testing laboratory for carrying out this test.

NOTE 4—Control parameters for an ECW are the time-dependent voltage or current profile that is supplied by the manufacturer of the ECW in which the voltage or current is applied to the ECC for the cyclic coloring to achieve the desired PTR and bleaching of the device.

7.4 The testing laboratory shall retain two of the supplied units as control specimens.